



ANNEX VIII: APPENDIX C

BULK METAL ANALYSIS RESULTS



Tables

Table C-1	Metal Contents of Solid Samples.....	1
Table C-2	Whole Rock Analysis of Solid Samples	250

Abbreviations

Abbreviation	Definition
Ag	silver
Al	aluminum
Al ₂ O ₃	aluminum oxide
As	arsenic
Au	gold
B	boron
Ba	barium
Be	beryllium
Bi	bismuth
Ca	calcium
CaO	calcium monoxide
Cd	cadmium
Ce	cerium
Co	cobalt
Cr	chromium
Cr ₂ O ₃	chromium oxide
Cs	cesium
Cu	copper
Fe	iron
Fe ₂ O ₃	iron oxide
Ga	gallium
Ge	germanium
Hf	hafnium
Hg	mercury
ICP	inductively coupled plasma
In	indium
K	potassium
K ₂ O	potassium oxide
La	lanthanum
Li	lithium
LOI	Loss on ignition
Mg	magnesium
MgO	magnesium oxide
Mn	manganese
MnO	manganese oxide
Mo	molybdenum
Na	sodium
Na ₂ O	sodium oxide
Nb	niobium
Ni	nickel

Abbreviation	Definition
No.	number
P	phosphorus
P ₂ O ₅	phosphorus pentoxide
Pb	lead
Rb	rubidium
Re	rhenium
S	sulphur
Sb	antimony
Sc	scandium
Se	selenium
SiO ₂	silicon dioxide (silica)
Sn	tin
Sr	strontium
Ta	tantalum
Te	tellurium
Th	thallium
Ti	titanium
TiO ₂	titanium dioxide
Tl	thallium
U	uranium
V	vanadium
W	tungsten
XRF	X-ray fluorescence
Y	yttrium
Zn	zinc
Zr	zirconium

Units of Measure

Unit	Definition
%	percent
>	greater than
pH	potential of hydrogen, provides measure of the acidity or alkalinity of a solution on a scale of 0 to 14.
ppm	parts per million

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Overburden																						
Koala Black Clay																						
KBC-405-1	-	-	-	Black Clay	7.7	0.25	4.0	5.0	-	-	2,330	1.5	1	6.2	0.50	-	35	657	-	51	3.9	-
KBC-405-2	-	-	-	Black Clay	7.8	0.25	3.5	2.5	-	-	1,940	1.5	1	6.7	2.0	-	33	591	-	44	3.6	-
KBC-405-3	-	-	-	Black Clay	7.7	0.25	4.2	5.0	-	-	2,310	1.5	1	6.2	1.5	-	34	601	-	56	3.7	-
KBC-405-4	-	-	-	Black Clay	7.7	0.25	4.4	5.0	-	-	2,910	1.5	1	7.2	1.0	-	30	471	-	53	3.6	-
KBC-405-5	-	-	-	Black Clay	7.7	0.25	3.7	5.0	-	-	2,210	1.5	1	4.8	0.25	-	41	833	-	45	4.0	-
KBC-405-6	-	-	-	Black Clay	7.7	0.25	3.9	2.5	-	-	2,460	1.5	1	5.6	0.50	-	37	658	-	49	3.9	-
KBC-405-7	-	-	-	Black Clay	7.8	0.25	4.1	5.0	-	-	2,790	1.5	1	6.0	1.5	-	33	504	-	58	3.6	-
KBC-405-8	-	-	-	Black Clay	7.9	0.25	3.9	30	-	-	2,080	1.5	1	6.2	1.0	-	35	646	-	43	3.6	-
KBC-405-46-1A	-	-	-	Black Clay	7.4	0.25	4.1	10	-	-	1,900	2.0	1	7.7	0.50	-	38	996	-	51	4.2	-
KBC-408	-	-	-	Black Clay	7.2	0.25	3.5	5.0	-	-	1,340	1.5	1	4.2	0.25	-	19	406	-	27	3.0	-
KBC-DUMP-1A	-	-	-	Black Clay	7.7	0.25	4.1	5.0	-	-	2,060	2.0	1	6.3	0.25	-	40	1,080	-	50	4.2	-
KBC-DUMP-2A	-	-	-	Black Clay	7.5	0.25	4.3	5.0	-	-	1,710	2.0	1	4.0	0.25	-	41	830	-	48	4.1	-
KBC-DUMP-3A	-	-	-	Black Clay	7.4	0.25	4.5	5.0	-	-	1,480	2.0	8	3.6	0.25	-	44	746	-	51	4.0	-
KBC-DUMP-4A	-	-	-	Black Clay	7.8	0.25	3.9	5.0	-	-	1,970	2.0	1	6.0	0.25	-	36	1,075	-	45	3.8	-
KBC-DUMP-5A	-	-	-	Black Clay	7.2	0.25	4.6	10	-	-	2,050	2.5	6	5.4	0.50	-	34	746	-	52	3.8	-
KBC-DUMP-6A	-	-	-	Black Clay	7.3	0.25	4.3	5.0	-	-	2,150	2.0	1	6.2	0.25	-	38	966	-	51	4.3	-
KBC-DUMP-7A	-	-	-	Black Clay	7.3	0.25	3.7	5.0	-	-	1,610	2.0	1	4.3	0.25	-	48	1,265	-	43	4.3	-
KBC-DUMP-8A	-	-	-	Black Clay	7.4	0.25	3.7	10	-	-	1,270	2.0	1	3.5	0.25	-	45	988	-	38	3.9	-
KBC-DUMP-9A	-	-	-	Black Clay	7.3	0.25	3.7	5.0	-	-	1,440	2.0	1	3.8	0.25	-	40	720	-	38	3.7	-
KBC-DUMP-10A	-	-	-	Black Clay	7.4	0.25	3.8	5.0	-	-	1,760	2.0	6	6.5	0.50	-	37	805	-	45	3.9	-
Median					7.6	0.25	4.0	5.0	-	-	2,010	2.0	1	6.0	0.38	-	37	746	-	49	3.9	-
Minimum					7.2	0.25	3.5	2.5	-	-	1,270	1.5	1	3.5	0.25	-	19	406	-	27	3.0	-
Maximum					7.9	0.25	4.6	30	-	-	2,910	2.5	8	7.7	2.0	-	48	1,265	-	58	4.3	-
Count					20	20	20	20	0	0	20	20	20	20	20	0	20	20	0	20	20	0
Koala Till																						
KT-420-47 1A	-	-	-	Till	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KT-420-47 2A	-	-	-	Till	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Median					8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Minimum					8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Maximum					8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Count					2	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	Price Crustal Abundances																		
		From	To		-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					Paste pH unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm	
Diabase																							
Beartooth																							
60	96-35	36.98	37.43	Diabase	9.6	0.1	1.3	5.0	-	-	200	0.25	2.5	1.1	0.5	-	14	204	-	4.0	2.1	-	
61	96-35	42.02	42.63	Diabase	9.7	0.1	1.7	2.5	-	-	360	0.25	2.5	0.86	0.5	-	18	239	-	31	2.7	-	
Median					9.6	0.1	1.5	3.8	-	-	280	0.25	2.5	1.0	0.5	-	16	222	-	18	2.4	-	
Minimum					9.6	0.1	1.3	2.5	-	-	200	0.25	2.5	0.86	0.5	-	14	204	-	4.0	2.1	-	
Maximum					9.7	0.1	1.7	5.0	-	-	360	0.25	2.5	1.1	0.5	-	18	239	-	31	2.7	-	
Count					2	2	2	2	0	0	2	2	2	2	2	0	2	2	0	2	2	0	
Fox																							
FUC 3-3 - 65	FUC 3-3	65	65.3	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 66	FUC 3-3	66	66.3	Diabase	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 67	FUC 3-3	67	67.3	Diabase	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 70	FUC 3-3	70	70.3	Diabase	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 75	FUC 3-3	75	75.3	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 80	FUC 3-3	80	80.3	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 85	FUC 3-3	85	85.3	Diabase	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 90	FUC 3-3	90	90.3	Diabase	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 95	FUC 3-3	95	95.3	Diabase	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 712	Decline	712	712.1	Diabase	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 1202.2	Decline	1202.2	1202.3	Diabase	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 1-2 - 87.78	FUC 1-2	87.78	93.72	Diabase	8.2	0.60	7.4	0.5	-	-	5	0.25	1	6.8	0.25	-	61	161	-	184	8.5	-	
FUC 1-2 - 93.72	FUC 1-2	93.72	99.61	Diabase	8.1	0.40	7.2	0.5	-	-	30	0.25	1	6.8	0.25	-	50	200	-	189	8.5	-	
FUC 1-2 - 99.61	FUC 1-2	99.61	108.66	Diabase	8.1	0.20	6.9	0.5	-	-	80	0.25	1	6.4	0.25	-	43	149	-	153	8.2	-	
FUC 1-2 - 108.66	FUC 1-2	108.66	113.03	Diabase	8.3	0.20	7.3	0.5	-	-	40	0.25	1	6.6	0.25	-	27	107	-	196	8.4	-	
FGT-05 - 11.4	FGT-05	11.4	14.3	Diabase	-	0.25	6.7	2.5	-	-	240	0.50	1	5.6	0.25	-	36	94	-	133	7.3	-	
FGT-05 - 134.9	FGT-05	134.9	142	Diabase	8.5	1.0	6.8	2.5	-	-	50	0.25	1	6.7	0.25	-	44	81	-	213	9.1	-	
FGT-05 - 142	FGT-05	142	149.5	Diabase	-	0.50	7.2	2.5	-	-	30	0.25	1	7.1	0.25	-	43	93	-	174	8.7	-	
FGT-05 - 149.5	FGT-05	149.5	157	Diabase	-	0.25	7.1	2.5	-	-	40	0.25	1	6.5	0.25	-	42	82	-	207	9.1	-	
FGT-05 - 157	FGT-05	157	164.5	Diabase	-	0.25	6.8	2.5	-	-	30	0.25	1	6.9	0.25	-	45	96	-	192	9.1	-	
FGT-05 - 164.5	FGT-05	164.5	172	Diabase	-	0.50	6.4	2.5	-	-	30	0.25	1	6.7	0.25	-	44	88	-	199	8.9	-	
FGT-05 - 172	FGT-05	172	175.36	Diabase	-	0.50	6.5	2.5	-	-	50	0.25	1	6.8	0.25	-	44	89	-	194	9.1	-	
Fox-250-Diabase 8-Oct-09	-	-	-	Diabase	9.0	0.25	7.6	10	-	-	70	0.25	1	7.0	0.25	-	43	91	-	210	9.2	20	
Median					8.6	0.33	7.0	2.5	-	-	40	0.25	1	6.8	0.25	-	44	94	-	193	8.8	20	
Minimum					8.1	0.20	6.4	0.5	-	-	5	0.25	1	5.6	0.25	-	27	81	-	133	7.3	20	
Maximum					9.3	1.0	7.6	10	-	-	240	0.50	1	7.1	0.25	-	61	200	-	213	9.2	20	
Count					17	12	12	12	0	0	12	12	12	12	12	0	12	12	0	12	12	1	
Misery																							
MDC-10 142.36	-	-	-	Diabase	9.4	0.25	6.4	5.0	-	-	210	0.25	2	5.1	0.25	-	42	104	-	291	9.9	-	
MDC-10 159.49	-	-	-	Diabase	9.3	0.25	6.3	5.0	-	-	180	0.25	2	5.1	0.25	-	41	137	-	223	8.9	-	
MDC-10 171.12	-	-	-	Diabase	9.2	0.25	6.5	10	-	-	190	0.25	1	4.9	0.25	-	42	94	-	301	10	-	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Diabase (continued)																						
Misery (continued)																						
MD 450-26 1A	-	-	-	Diabase	8.8	0.1	6.3	0.5	-	-	180	0.50	1	5.3	0.50	-	52	128	-	227	9.1	-
MD 430 21 1A	-	-	-	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD 430 21 2A	-	-	-	Diabase	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD 430 25 1A	-	-	-	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD 430 25 2A	-	-	-	Diabase	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD- 430-33-1A	-	-	-	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD- 430-34-2A	-	-	-	Diabase	8.8	0.25	6.0	5.0	-	-	200	0.25	14	5.0	0.25	-	47	113	-	254	9.8	-
MD-430-91-01	-	-	-	Diabase	8.7	0.11	7.2	3.3	-	-	240	0.83	0.05	5.2	0.09	-	46	87	-	261	11	21
MD-430-91-02	-	-	-	Diabase	9.5	0.05	8.1	11	-	-	360	1.2	0.3	1.1	0.08	-	19	148	-	22	4.5	23
MD- 420-04-1A	-	-	-	Diabase	8.3	0.25	6.3	5.0	-	-	210	0.25	12	4.4	0.25	-	47	154	-	290	9.9	-
MD- 420-04-2A	-	-	-	Diabase	8.3	0.25	6.3	5.0	-	-	190	0.25	8	4.5	0.25	-	48	157	-	282	9.6	-
MD-420-12-01	-	-	-	Diabase	9.1	0.15	7.0	3.0	-	-	250	0.78	0.04	6.4	0.15	-	52	84	-	309	12	21
MD-410-08-01	-	-	-	Diabase	8.8	0.12	6.7	3.8	-	-	240	1.1	0.09	5.3	0.11	-	46	82	-	232	10	21
MD-410-08-02	-	-	-	Diabase	8.9	0.11	6.6	2.6	-	-	290	0.99	0.1	5.1	0.08	-	44	70	-	234	9.9	20
MD-410-07-01	-	-	-	Diabase	9.4	0.23	6.4	1.2	-	-	300	0.59	0.05	5.9	0.18	-	47	91	-	284	11	19
MD-410-07-02	-	-	-	Diabase	9.1	0.18	6.5	2.5	-	-	220	0.62	0.06	6.0	0.12	-	46	77	-	289	11	19
MD 400-42-1a	-	-	-	Diabase	8.7	0.25	6.8	2.5	-	-	220	2.0	1	5.4	0.50	-	47	90	-	327	11	-
MD-400-49-2a	-	-	-	Diabase	8.7	0.25	6.7	2.5	-	-	190	2.0	6	5.2	2.0	-	48	106	-	269	11	-
MD-390-38-2A	-	-	-	Diabase	9.2	0.25	6.8	5.0	-	-	230	0.50	2	6.1	1.5	-	52	113	-	331	11	-
MD-380-32-1A	-	-	-	Diabase	8.8	0.25	6.6	2.5	-	-	210	0.50	2	5.7	1.5	-	50	159	-	285	11	-
MD-370-22-1	-	-	-	Diabase	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD-370-22-2	-	-	-	Diabase	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MDC-28 3.9-7	-	-	-	Diabase	9.0	0.05	1.8	0.8	5.4	10	50	-	0.05	1.0	0.05	-	22	53	-	213	4.8	9.0
MDC-28 7-10	-	-	-	Diabase	9.2	0.05	1.6	0.8	2.9	10	62	-	0.05	0.93	0.05	-	23	40	-	224	4.7	8.0
MDC-28 10-13	-	-	-	Diabase	9.4	0.05	1.6	1.1	7.7	10	43	-	0.05	0.76	0.05	-	20	41	-	232	4.5	7.0
MDC-28 13-16	-	-	-	Diabase	9.3	0.05	1.6	1.4	4.5	10	55	-	0.05	0.78	0.05	-	20	42	-	201	4.3	7.0
MDC-28 16-19	-	-	-	Diabase	9.2	0.05	1.7	1.6	3.6	10	63	-	0.05	0.84	0.05	-	24	64	-	214	4.6	8.0
MDC-28 19-22	-	-	-	Diabase	9.1	0.05	1.5	2.7	4.6	10	67	-	0.05	0.72	0.05	-	21	41	-	201	4.4	7.0
MDC-28 23-26.07	-	-	-	Diabase	9.1	0.1	1.6	1.1	4.1	10	74	-	0.1	0.87	0.10	-	21	66	-	233	4.2	7.0
MGT-57 28.7-32	-	-	-	Diabase	9.1	0.05	0.42	0.8	0.25	10	21	-	0.2	0.16	0.05	-	1.4	78	-	0.9	0.67	2.0
MGT-57 40-43	-	-	-	Diabase	9.2	0.05	1.6	1.7	2.2	10	48	-	0.05	0.75	0.05	-	22	38	-	204	4.6	7.0
MGT-57 51-54	-	-	-	Diabase	9.4	0.05	1.6	1.8	1.7	10	52	-	0.05	0.76	0.05	-	23	40	-	200	4.5	6.0
MGT-57 62-65	-	-	-	Diabase	9.4	0.05	1.5	1.8	1.7	10	41	-	0.05	0.73	0.10	-	23	56	-	198	4.6	7.0
MGT-57 74-77	-	-	-	Diabase	8.3	0.05	1.5	2.2	2.1	10	66	-	0.05	0.82	0.10	-	20	50	-	210	4.4	7.0
MGT-66 16-19	-	-	-	Diabase	9.8	0.1	0.71	2.5	0.50	10	36	-	0.5	0.16	0.05	-	3.8	85	-	3.6	1.1	3.0
MGT-43 286-289	-	-	-	Diabase	9.0	0.2	1.6	0.8	13	10	73	-	0.1	0.80	0.2	-	22	49	-	276	4.6	7.0
MGT-43 289-292	-	-	-	Diabase	8.9	0.2	1.6	2.1	8.7	10	76	-	0.2	0.81	0.4	-	26	36	-	307	4.9	7.0
MGT-43 292-295	-	-	-	Diabase	8.9	0.2	1.6	2.9	7.3	10	74	-	0.05	0.69	0.2	-	26	38	-	303	4.6	7.0

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH unit	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
						Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm	
Diabase (continued)																							
Misery (continued)																							
MGT-43 300-303	-	-	-	Diabase	8.9	0.2	1.9	1.4	5.7	10	46	-	0.1	0.71	0.5	-	27	61	-	290	4.9	9.0	
MGT-43 303-306	-	-	-	Diabase	8.8	0.1	1.6	1.6	3.8	10	59	-	0.05	0.72	0.2	-	23	61	-	194	4.1	8.0	
MGT-43 306-309	-	-	-	Diabase	9.1	0.1	1.7	1.2	4.2	10	78	-	0.05	0.83	0.2	-	22	42	-	246	4.4	7.0	
MGT-43 309-311.13	-	-	-	Diabase	9.0	0.2	1.8	1.0	4.8	10	60	-	0.05	0.85	0.2	-	25	49	-	280	4.7	9.0	
MGT-54 211-213.47	-	-	-	Diabase	9.2	0.1	1.7	2.4	4.3	10	81	-	0.05	0.80	0.3	-	24	44	-	250	4.6	7.0	
MGT-54 208-211	-	-	-	Diabase	9.1	0.1	1.6	3.1	3.1	10	92	-	0.05	0.82	0.2	-	26	57	-	247	4.6	7.0	
97-54	97-54	126.14	126.46	Diabase	9.1	0.1	1.8	2.5	-	-	120	0.25	2.5	1.3	0.5	-	30	92	-	329	6.9	-	
97-54	97-54	18.88	19.08	Diabase	9.1	0.1	1.6	2.5	-	-	60	0.25	2.5	1.3	0.5	-	32	77	-	294	6.9	-	
97-54	97-54	20.54	20.65	Diabase	8.2	0.1	2.8	10	-	-	180	0.25	2.5	1.3	0.5	-	55	61	-	370	8.4	-	
97-54	97-54	41.3	42.03	Diabase	8.6	0.1	1.6	2.5	-	-	230	0.25	2.5	0.89	0.5	-	36	53	-	248	5.6	-	
97-54	97-54	52.75	53.29	Diabase	9.5	0.1	1.6	2.5	-	-	150	0.25	2.5	1.1	1.0	-	29	83	-	227	5.4	-	
97-54	97-54	81.07	81.38	Diabase	9.4	0.1	1.6	2.5	-	-	70	0.25	2.5	1.2	0.5	-	30	89	-	291	6.8	-	
HC-Pdef-1	-	-	-	Diabase	8.7	0.1	7.2	0.3	-	-	40	0.51	0.01	7.5	0.15	16	51	118	0.54	229	9.7	22	
Median					9.0	0.1	1.8	2.5	4.2	10	81	0.50	0.1	1.1	0.20	16	29	77	0.54	248	5.4	7.0	
Minimum					8.2	0.05	0.42	0.3	0.25	10	21	0.25	0.01	0.16	0.05	16	1.4	36	0.54	0.9	0.67	2.0	
Maximum					9.8	0.25	8.1	11	13	10	360	2.0	14	7.5	2.0	16	55	159	0.54	370	11.8	23	
Count					54	47	47	47	22	22	47	25	47	47	47	1	47	47	1	47	47	30	
Sable																							
SDC-13	SDC-13	164.64	164.91	Diabase	8.9	0.1	1.7	2.5	-	-	50	0.25	2.5	1.3	0.5	-	33	80	-	290	7.2	-	
Median					8.9	0.1	1.7	2.5	-	-	50	0.25	2.5	1.3	0.5	-	33	80	-	290	7.2	-	
Minimum					8.9	0.1	1.7	2.5	-	-	50	0.25	2.5	1.3	0.5	-	33	80	-	290	7.2	-	
Maximum					8.9	0.1	1.7	2.5	-	-	50	0.25	2.5	1.3	0.5	-	33	80	-	290	7.2	-	
Count					1	1	1	1	0	0	1	1	1	1	1	0	1	1	0	1	1	0	
Jay																							
2014-DD-040	JGT-03	349.4	356.81	Diabase	9.10	0.08	2.34	0.5	-	20	31	0.05	0.01	1.39	0.08	13.5	21.5	99	1.81	209	4.33	7.6	
2014-DD-043	JGT-03	47.22	57.11	Diabase	9.05	0.06	1.68	0.5	-	10	65	0.1	0.05	1.06	0.07	13.5	18.5	99	1.97	158	3.82	6.6	
2014-DD-044	JGT-03	57.95	65.48	Diabase	9.05	0.07	1.9	0.5	-	20	47	0.1	0.02	1.17	0.07	13.6	20	70	1.8	197	4.22	6.8	
2014-DD-049	JGT-02	413.02	421.45	Diabase	9.02	0.07	2.14	0.5	-	20	30	0.05	0.03	1.2	0.09	13.9	19.5	90	2.17	197	4.2	7	
Median					9.1	0.07	2.0	0.5	-	20	39	0.075	0.025	1.2	0.075	13.55	20	95	1.89	197	4.2	6.9	
Minimum					9.0	0.06	1.7	0.5	0	10	30	0.05	0.01	1.1	0.07	13.5	19	70	1.8	158	3.8	6.6	
Maximum					9.1	0.08	2.3	0.5	0	20	65	0.1	0.05	1.4	0.09	13.9	22	99	2.17	209	4.3	7.6	
Count					4	4	4	4	0	4	4	4	4	4	4	4	4	4	4	4	4	4	
Granite																							
Beartooth																							
58	96-35	13.5	13.95	Granite	9.8	0.1	2.5	2.5	-	-	500	0.25	2.5	0.61	0.5	-	20	269	-	6.0	3.5	-	
59	96-35	30	30.62	Granite	9.8	0.1	2.0	2.5	-	-	480	0.25	2.5	0.37	0.5	-	17	177	-	5.0	3.2	-	
62	96-35	30.14	46.78	Granite	9.8	0.1	2.4	2.5	-	-	510	0.25	2.5	0.52	0.5	-	18	245	-	14	3.6	-	
63	96-35	221.27	221.83	Granite	9.1	0.1	2.1	2.5	-	-	500	0.25	2.5	0.56	0.5	-	18	225	-	6.0	3.5	-	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
						unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm
Granite (continued)																							
Beartooth (continued)																							
12	BDC-05	40.2	40.53	Granite	9.8	0.1	2.0	2.5	-	-	400	0.25	2.5	0.33	0.5	-	17	221	-	68	3.1	-	
14	BDC-05	63.74	64.07	Granite	9.5	0.1	2.3	5.0	-	-	490	0.25	2.5	0.60	0.5	-	19	200	-	1.0	3.4	-	
15	BDC-07	224.63	225.02	Granite	9.9	0.1	2.2	2.5	-	-	500	0.25	2.5	0.52	0.5	-	19	198	-	9.0	3.5	-	
BDC 4-54.64	BDC 4	54.64	60.21	Granite	-	0.25	9.7	2.5	-	-	580	0.50	1	3.1	0.25	-	18	142	-	31	3.4	-	
BGT 01-108	BGT 01	108	112.35	Granite	-	0.25	8.0	2.5	-	-	630	0.50	1	2.5	0.25	-	18	179	-	86	3.1	-	
BGT 01-125.34	BGT 01	125.34	129.61	Granite	-	0.25	8.4	2.5	-	-	530	0.50	1	2.6	0.25	-	16	125	-	24	3.0	-	
BGT 02-60.12	BGT 02	60.12	64.52	Granite	-	0.25	7.9	2.5	-	-	560	0.50	1	2.3	0.25	-	17	184	-	24	3.0	-	
BGT 03-18.28	BGT 03	18.28	22.62	Granite	-	0.25	8.7	2.5	-	-	540	0.50	1	3.0	0.25	-	18	137	-	32	3.0	-	
BGT 03-64.95	BGT 03	64.95	69.2	Granite	-	0.25	8.8	2.5	-	-	560	0.50	1	3.2	0.25	-	20	176	-	62	3.3	-	
BGT 03-107.6	BGT 03	107.6	111.82	Granite	-	0.25	8.2	2.5	-	-	550	0.50	1	3.1	0.25	-	18	138	-	44	3.2	-	
BGT 04-70.03	BGT 04	70.03	74.32	Granite	-	0.25	8.7	5.0	-	-	560	0.50	1	3.2	0.25	-	18	130	-	26	3.2	-	
BGT 05-104.77	BGT 05	104.77	109.66	Granite	-	0.25	9.2	2.5	-	-	600	0.50	1	3.2	0.25	-	17	163	-	13	3.2	-	
BGT 05-135.31	BGT 05	135.31	139.58	Granite	-	0.5	8.7	2.5	-	-	540	0.50	2	3.3	0.25	-	18	175	-	42	3.1	-	
DDH 96-35-64.19	DDH 96-35	64.19	70.65	Granite	-	0.25	8.8	2.5	-	-	680	0.50	2	2.2	0.25	-	26	219	-	77	4.2	-	
BDC 2-88.19	BDC 2	88.19	90.86	Granite	-	0.25	10	2.5	-	-	670	1.5	1	1.1	0.25	-	33	280	-	48	5.8	-	
BDC 3-38	BDC 3	38	42	Granite	-	0.25	8.2	2.5	-	-	630	0.50	10	3.7	0.25	-	27	149	-	92	4.1	-	
BGT 01-99.36	BGT 01	99.36	103.64	Granite	-	0.25	7.6	2.5	-	-	560	0.50	1	2.2	0.25	-	17	209	-	126	2.7	-	
BGT 04-48.38	BGT 04	48.38	52.7	Granite	-	0.25	9.1	2.5	-	-	640	0.50	2	3.1	0.25	-	24	190	-	68	4.1	-	
BGT 05-78.58	BGT 05	78.58	81.93	Granite	-	0.25	8.1	2.5	-	-	680	0.50	1	2.4	0.25	-	24	283	-	84	4.1	-	
BDC 5-17	BDC 5	17	18	Granite	-	0.25	4.2	2.5	-	-	250	0.50	1	12	0.25	-	8.0	81	-	6.0	4.2	-	
BDC 3-42	BDC 3	42	57	Granite	-	0.25	7.5	5.0	-	-	340	0.25	6	4.2	0.25	-	38	644	-	35	4.4	-	
BDC 4-38.7	BDC 4	38.7	42	Granite	-	0.25	9.5	2.5	-	-	610	0.50	1	2.8	0.25	-	21	192	-	58	3.8	-	
BDC 5-20.96	BDC 5	20.96	26.65	Granite	-	0.25	8.4	5.0	-	-	520	0.50	2	3.1	0.25	-	18	127	-	15	3.1	-	
BDC 7-20.28	BDC 7	20.28	26.93	Granite	-	0.25	7.8	2.5	-	-	640	0.50	2	2.3	0.25	-	26	294	-	62	4.2	-	
BDC 7-32.42	BDC 7	32.42	36.9	Granite	-	0.25	8.7	2.5	-	-	560	1.0	1	3.1	0.25	-	17	131	-	13	3.1	-	
BDC 7-36.9	BDC 7	36.9	42	Granite	-	0.25	8.9	5.0	-	-	620	0.50	1	2.0	0.25	-	24	228	-	61	4.2	-	
BDC 7-53.95	BDC 7	53.95	58.98	Granite	-	0.25	8.4	5.0	-	-	540	0.50	1	2.3	0.25	-	17	145	-	26	3.0	-	
BDC 7-64.09	BDC 7	64.09	69.29	Granite	-	0.25	8.2	2.5	-	-	600	5.0	1	1.9	0.25	-	24	268	-	59	4.0	-	
BGT 01-65.18	BGT 01	65.18	69.43	Granite	-	0.25	9.3	2.5	-	-	640	0.50	1	3.0	0.25	-	19	154	-	153	3.5	-	
BGT 01-82.23	BGT 01	82.23	86.35	Granite	-	0.25	8.2	2.5	-	-	600	0.50	1	2.4	0.25	-	18	158	-	73	3.0	-	
BGT 02-107.4	BGT 02	107.4	111.73	Granite	-	0.25	8.9	2.5	-	-	510	0.50	1	3.2	0.25	-	17	175	-	8.0	3.0	-	
BGT 02-146.12	BGT 02	146.12	150.45	Granite	-	0.25	8.5	2.5	-	-	670	0.50	1	2.5	0.25	-	23	220	-	60	3.8	-	
BGT 03-39.31	BGT 03	39.31	43.66	Granite	-	0.25	7.7	2.5	-	-	580	0.50	2	2.6	0.25	-	18	178	-	67	3.2	-	
BGT 04-35.95	BGT 04	35.95	41	Granite	-	0.25	6.9	5.0	-	-	300	2.0	1	5.6	0.25	-	33	303	-	0.5	4.9	-	
BGT 04-91.65	BGT 04	91.65	95.95	Granite	-	0.25	8.9	2.5	-	-	540	0.50	2	3.4	0.25	-	18	170	-	36	3.4	-	
BGT 04-130.5	BGT 04	130.5	134.87	Granite	-	0.25	8.6	2.5	-	-	570	0.50	2	3.2	0.25	-	21	175	-	66	3.4	-	
BGT 05-25.9	BGT 05	25.9	30.95	Granite	-	0.25	9.1	5.0	-	-	740	0.50	4	2.8	0.25	-	27	282	-	60	4.5	-	
BGT 05-56.78	BGT 05	56.78	61.17	Granite	-	0.25	8.9	2.5	-	-	660	0.50	1	2.9	0.25	-	18	149	-	20	3.3	-	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Beartooth (continued)																						
BGT 05-165.49	BGT 05	165.49	169.74	Granite	-	0.25	7.4	2.5	-	-	450	0.50	1	2.9	0.25	-	15	100	-	24	2.7	-
BTG-460-25-01	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-460-25-02	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-04-02	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-03-01	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-03-02	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-2	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-3	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-4	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-5	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-6	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-7	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-8	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTGS-440-09-1	-	-	-	Granite	9.5	0.25	8.8	5.0	-	-	620	1.3	1	3.3	0.25	-	16	150	-	30	3.3	-
BTGS-440-09-2	-	-	-	Granite	9.7	0.25	8.6	2.5	-	-	670	1.4	1	3.4	0.25	-	20	168	-	67	3.8	-
BTGS-440-09-3	-	-	-	Granite	9.3	0.25	8.4	6.0	-	-	530	1.4	1	3.0	0.25	-	15	105	-	14	3.0	-
BTGS-440-09-4	-	-	-	Granite	9.8	0.25	8.5	7.0	-	-	570	1.3	1	3.2	0.25	-	15	138	-	28	3.2	-
BG-440-11-1	-	-	-	Granite	9.0	0.25	8.0	5.0	-	-	740	1.1	1	2.5	0.25	-	17	167	-	16	3.7	-
BG-440-11-2	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-11-3	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-11-4	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-12-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-12-2	-	-	-	Granite	8.8	0.25	7.4	2.5	-	-	700	1.0	1	2.6	0.25	-	15	155	-	19	3.1	-
BG-440-12-3	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-12-4	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-13-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-13-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-15-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-15-2	-	-	-	Granite	8.8	0.25	8.3	5.0	-	-	610	1.5	1	3.1	0.25	-	17	151	-	21	3.3	-
BG-440-20-04	-	-	-	Granite	9.7	0.25	8.6	2.5	-	-	570	1.5	1	3.0	0.25	-	16	106	-	5.0	3.2	-
BG-440-20-03	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-20-02	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-20-01	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-22-04	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-22-03	-	-	-	Granite	9.6	0.25	8.6	6.0	-	-	570	1.5	1	3.0	0.25	-	15	136	-	21	3.3	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Beartooth (continued)																						
BG-440-22-02	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-22-01	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-440-26-1	-	-	-	Granite	9.2	0.25	8.4	8.0	-	-	680	1.3	1	2.8	0.25	-	20	199	-	48	3.8	-
BTG-440-26-2	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-440-26-3	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-440-26-4	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-21-02	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-21-01	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-19-04	-	-	-	Granite	7.9	0.25	8.6	2.5	-	-	790	4.3	1	2.1	0.25	-	24	198	-	57	4.4	-
BG-430-19-03	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-19-02	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-19-01	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-18-04	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-18-03	-	-	-	Granite	9.6	0.25	8.1	6.0	-	-	650	1.5	1	3.0	0.25	-	15	59	-	6.0	3.3	-
BG-430-18-02	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-18-01	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-17-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-17-03	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-17-02	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-17-01	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-05-02	-	-	-	Granite	9.6	0.25	7.9	2.5	-	-	670	1.3	1	2.9	0.25	-	14	96	-	18	3.2	-
BG-430-05-01	-	-	-	Granite	9.6	0.25	7.8	2.5	-	-	630	1.2	1	2.7	0.25	-	16	102	-	31	3.1	-
BG-430-04-01	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-02-02	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-02-01	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-04	-	-	-	Granite	8.2	0.25	8.1	11	-	-	620	2.1	1	1.6	0.25	-	19	159	-	45	3.7	-
BG-420-04-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-03	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-03	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-02	-	-	-	Granite	8.8	0.25	8.9	7.0	-	-	620	1.7	1	2.1	0.25	-	23	200	-	56	4.6	-
BG-420-04-02	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-01	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-01	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-410-05-01	-	-	-	Granite	9.9	0.25	8.2	2.5	-	-	580	1.4	1	3.1	0.25	-	14	94	-	24	3.3	-
BTG-410-05-02	-	-	-	Granite	9.5	0.25	9.1	2.5	-	-	670	1.3	1	3.2	0.25	-	14	64	-	22	3.4	-
BT-310-Granite-3	-	-	-	Granite	9.5	0.25	8.3	7.0	-	-	620	3.1	2	3.2	0.25	-	16	64	-	25	3.4	20
BT-310-Granite-2	-	-	-	Granite	9.7	0.25	7.6	10	-	-	640	1.5	2	3.4	0.25	-	22	118	-	57	3.9	20
BT-310-Granite-1	-	-	-	Granite	9.8	0.25	7.6	2.5	-	-	620	1.5	2	3.1	0.25	-	15	65	-	62	3.2	20

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm	
Granite (continued)																							
Beartooth (continued)																							
BT-300-Granite-3	-	-	-	Granite	8.9	0.25	7.4	2.5	-	-	730	1.1	2	3.5	0.25	-	33	269	-	22	4.0	10	
BT-300-Granite-2	-	-	-	Granite	9.1	0.25	6.6	2.5	-	-	730	1.1	3	3.1	0.25	-	35	352	-	41	3.9	10	
BT-300-Granite-1	-	-	-	Granite	10.1	0.25	7.6	7.0	-	-	640	1.4	2	3.4	0.25	-	16	68	-	28	3.3	20	
BT-290-Granite-2	-	-	-	Granite	10.1	0.25	7.4	2.5	-	-	620	1.4	4	3.6	0.25	-	16	67	-	31	3.3	20	
BT-290-Granite-1	-	-	-	Granite	9.2	0.25	7.4	2.5	-	-	1,060	1.3	1	3.2	0.25	-	21	145	-	17	3.6	20	
BT-290-Granite-3	-	-	-	Granite	9.8	0.25	7.6	5.0	-	-	620	1.5	1	3.4	0.25	-	17	66	-	67	3.4	20	
BT-280-Granite-2	-	-	-	Granite	10.0	0.25	7.6	2.5	-	-	620	1.3	1	3.5	0.25	-	15	63	-	18	3.2	20	
BT-280-Granite-1	-	-	-	Granite	9.9	0.25	7.7	2.5	-	-	570	1.3	2	3.6	0.25	-	16	67	-	28	3.3	20	
Median					9.3	0.25	8.2	2.5	-	-	605	0.50	1	3.0	0.25	-	18	161	-	31	3.3	20	
Minimum					7.8	0.1	2.0	2.5	-	-	250	0.25	1	0.33	0.25	-	8.0	59	-	0.5	2.7	10	
Maximum					10.1	0.5	10	11	-	-	1,060	5.0	10	12	0.5	-	38	644	-	153	5.8	20	
Count					90	72	72	72	0	0	72	72	72	72	72	0	72	72	0	72	72	11	
Fox																							
FUC-2B - 56	FUC-2B	56	56.3	Granite	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 45	FUC 3-3	45	45.3	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 50	FUC 3-3	50	50.3	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 55	FUC 3-3	55	55.3	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 60	FUC 3-3	60	60.3	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 4-3 - 144	FUC 4-3	144	144.3	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 4-4 - 144	FUC 4-4	144	144.3	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 4-5 - 128	FUC 4-5	128	128.3	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FX 4-1 - 188	FX 4-1	188	188.3	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - -	Decline	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - -	Decline	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 69	Decline	69	69.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 200	Decline	200	200.1	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 245	Decline	245	245.1	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 296	Decline	296	296.1	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 365	Decline	365	365.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 372	Decline	372	372.1	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 377	Decline	377	377.1	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 447	Decline	447	447.1	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 500	Decline	500	500.1	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 552	Decline	552	552.1	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 610	Decline	610	610.1	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 660	Decline	660	660.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 764	Decline	764	764.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					unit	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																							
Fox (continued)																							
Decline - 809	Decline	809	809.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 822	Decline	822	822.1	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 851	Decline	851	851.1	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 901	Decline	901	901.1	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 951	Decline	951	951.1	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 1001	Decline	1,001	1,001.1	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 1055.9	Decline	1,055.9	1,056	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 1106.2	Decline	1,106.2	1,106.3	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 1168.8	Decline	1,168.8	1,168.9	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 1276.1	Decline	1,276.1	1,276.2	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 1326.1	Decline	1,326.1	1,326.2	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 1-2 - 70.15	FUC 1-2	70.15	76.02	Granite	8.2	0.2	9.4	0.5	-	-	640	1.5	1	3.2	0.25	-	23	144	-	45	3.1	-	
FUC 1-2 - 76.02	FUC 1-2	76.02	80.38	Granite	8.6	0.2	8.4	0.5	-	-	670	1.0	1	2.8	0.25	-	21	136	-	15	2.9	-	
FUC 1-2 - 80.38	FUC 1-2	80.38	87.78	Granite	8.4	0.2	7.0	0.5	-	-	50	0.25	1	6.9	0.25	-	60	168	-	187	8.4	-	
FUC 1-2 - 113.03	FUC 1-2	113.03	116.91	Granite	8.5	0.1	9.3	0.5	-	-	620	1.5	1	3.0	0.25	-	18	144	-	60	3.2	-	
FUC 1-2 - 116.91	FUC 1-2	116.91	122.67	Granite	8.6	0.6	9.4	0.5	-	-	720	1.5	1	3.0	0.25	-	19	132	-	44	3.3	-	
FUC 4-3 - 146.96	FUC 4-3	146.96	151.5	Granite	8.8	0.4	9.5	0.5	-	-	630	1.0	1	3.2	0.25	-	17	162	-	13	2.9	-	
FUC 4-3 - 155.2	FUC 4-3	155.2	163.4	Granite	8.3	0.6	9.5	0.5	-	-	710	1.5	1	3.2	0.25	-	16	166	-	35	3.0	-	
FDC 11 - 108.25	FDC 11	108.25	118.8	Granite	8.5	0.2	7.8	0.5	-	-	620	1.5	1	2.3	0.25	-	14	162	-	14	2.8	-	
FDC 11 - 118.8	FDC 11	118.8	123	Granite	8.6	0.2	8.1	0.5	-	-	640	1.5	1	2.9	0.25	-	11	187	-	18	2.5	-	
FDC 11 - 122.5	FDC 11	122.5	128.02	Granite	8.2	0.2	9.4	0.5	-	-	740	2.5	1	1.4	0.25	-	16	164	-	1.0	3.0	-	
FGT-03 - 1.52	FGT-03	1.52	10.82	Granite	9.1	0.5	7.8	15	-	-	690	1.5	1	3.0	0.25	-	18	70	-	42	3.7	-	
FGT-03 - 10.82	FGT-03	10.82	18.32	Granite	-	0.25	7.7	5.0	-	-	600	1.5	1	3.3	0.25	-	20	76	-	51	3.7	-	
FGT-03 - 18.32	FGT-03	18.32	25.82	Granite	-	0.25	7.6	5.0	-	-	580	1.5	1	2.6	0.25	-	17	61	-	20	3.5	-	
FGT-03 - 25.82	FGT-03	25.82	30.24	Granite	-	0.25	7.1	10.0	-	-	620	1.5	1	2.8	0.25	-	16	53	-	13	3.0	-	
FGT-03 - 30.24	FGT-03	30.24	37.74	Granite	-	0.25	7.8	5.0	-	-	640	1.5	1	3.0	0.25	-	18	60	-	13	3.5	-	
FGT-03 - 37.74	FGT-03	37.74	45.24	Granite	-	0.25	7.3	5.0	-	-	660	1.5	1	3.1	0.25	-	17	60	-	60	3.3	-	
FGT-03 - 45.24	FGT-03	45.24	52.74	Granite	-	0.25	7.4	10	-	-	620	1.5	1	3.1	0.25	-	20	79	-	92	3.6	-	
FGT-03 - 52.74	FGT-03	52.74	58.29	Granite	-	0.5	7.6	10	-	-	710	1.5	1	2.9	0.25	-	17	67	-	30	3.4	-	
FGT-03 - 58.29	FGT-03	58.29	65.79	Granite	-	0.25	7.7	10	-	-	660	1.5	1	3.1	0.25	-	17	62	-	64	3.4	-	
FGT-03 - 65.79	FGT-03	65.79	73.29	Granite	-	0.25	7.7	5.0	-	-	760	1.5	1	3.1	0.25	-	18	69	-	62	3.4	-	
FGT-03 - 73.29	FGT-03	73.29	80.79	Granite	9.6	0.25	7.9	5.0	-	-	740	1.5	1	3.3	0.25	-	19	72	-	59	3.7	-	
FGT-03 - 80.79	FGT-03	80.79	83.82	Granite	-	0.25	7.7	10	-	-	730	1.5	1	3.1	0.25	-	17	59	-	31	3.3	-	
FGT-03 - 83.82	FGT-03	83.82	90.22	Granite	-	0.25	7.8	5.0	-	-	680	1.5	1	3.1	0.25	-	17	64	-	21	3.5	-	
FGT-03 - 90.22	FGT-03	90.22	97.72	Granite	-	0.25	8.2	10	-	-	760	1.5	1	3.4	0.25	-	18	73	-	31	3.6	-	
FGT-03 - 97.72	FGT-03	97.72	105.22	Granite	-	0.25	6.8	5.0	-	-	610	1.5	1	3.0	0.25	-	16	64	-	24	3.3	-	
FGT-03 - 105.22	FGT-03	105.22	112.72	Granite	-	0.25	7.9	5.0	-	-	690	1.5	1	3.3	0.25	-	19	67	-	31	3.6	-	
FGT-03 - 112.72	FGT-03	112.72	115.5	Granite	-	0.25	7.9	5.0	-	-	710	1.5	1	3.2	0.25	-	18	65	-	20	3.6	-	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm	
Granite (continued)																							
Fox (continued)																							
FGT-03 - 115.5	FGT-03	115.5	123	Granite	-	0.25	7.7	5.0	-	-	710	1.5	1	3.4	0.25	-	21	103	-	17	3.7	-	
FGT-03 - 123	FGT-03	123	130.5	Granite	-	0.25	7.9	5.0	-	-	700	1.5	1	2.9	0.25	-	18	63	-	26	3.5	-	
FGT-03 - 130.5	FGT-03	130.5	138	Granite	-	0.5	8.0	5.0	-	-	660	1.5	1	2.9	0.25	-	19	62	-	20	3.4	-	
FGT-03 - 138	FGT-03	138	148.68	Granite	8.9	0.25	8.1	5.0	-	-	660	1.5	1	2.4	0.25	-	18	62	-	38	3.6	-	
FGT-03 - 148.68	FGT-03	148.68	153.11	Granite	-	0.25	8.3	5.0	-	-	720	1.5	1	3.1	0.25	-	18	68	-	35	3.6	-	
FGT-03 - 153.11	FGT-03	153.11	160.61	Granite	-	0.25	7.1	5.0	-	-	630	1.5	1	2.3	0.25	-	16	54	-	19	3.1	-	
FGT-03 - 160.61	FGT-03	160.61	168.11	Granite	-	0.25	8.1	5.0	-	-	650	1.5	1	3.4	0.25	-	19	54	-	39	3.5	-	
FGT-03 - 168.11	FGT-03	168.11	172.05	Granite	-	0.25	7.9	5.0	-	-	700	1.5	1	3.1	0.25	-	18	68	-	31	3.6	-	
FGT-03 - 172.05	FGT-03	172.05	179.55	Granite	-	0.25	8.1	5.0	-	-	700	1.5	1	3.2	0.25	-	19	64	-	35	3.5	-	
FGT-03 - 179.55	FGT-03	179.55	187.05	Granite	-	0.25	7.9	10	-	-	710	1.5	1	3.3	0.25	-	18	65	-	50	3.6	-	
FGT-03 - 187.05	FGT-03	187.05	193.21	Granite	-	0.25	8.4	5.0	-	-	810	1.5	1	3.5	0.25	-	20	72	-	33	3.8	-	
FGT-03 - 193.21	FGT-03	193.21	198.77	Granite	-	0.25	8.1	5.0	-	-	680	1.5	1	3.4	0.25	-	19	74	-	29	3.7	-	
FGT-03 - 198.77	FGT-03	198.77	206.27	Granite	-	0.25	8.0	15	-	-	750	1.5	1	3.4	0.25	-	19	66	-	24	3.6	-	
FGT-03 - 206.27	FGT-03	206.27	213.77	Granite	9.6	0.25	7.7	5.0	-	-	580	1.5	1	3.4	0.25	-	19	74	-	57	3.7	-	
FGT-03 - 213.77	FGT-03	213.77	221.27	Granite	-	0.25	7.7	5.0	-	-	660	1.5	1	3.2	0.25	-	17	63	-	31	3.5	-	
FGT-03 - 221.27	FGT-03	221.27	228.77	Granite	-	0.25	8.1	5.0	-	-	690	1.5	1	3.3	0.25	-	19	64	-	32	3.6	-	
FGT-03 - 228.77	FGT-03	228.77	235.73	Granite	-	0.25	8.0	5.0	-	-	720	1.5	1	3.3	0.25	-	19	66	-	23	3.6	-	
FGT-03 - 235.73	FGT-03	235.73	243.23	Granite	-	0.25	7.5	5.0	-	-	630	1.5	1	3.0	0.25	-	18	63	-	26	3.3	-	
FGT-03 - 243.23	FGT-03	243.23	251.46	Granite	-	0.25	8.0	2.5	-	-	660	1.5	1	3.2	0.25	-	18	64	-	34	3.4	-	
FGT-05 - 1.1	FGT-05	1.1	5.5	Granite	8.9	0.25	7.4	2.5	-	-	660	1.5	1	3.0	0.25	-	16	58	-	41	3.3	-	
FGT-05 - 5.5	FGT-05	5.5	11.4	Granite	-	0.25	7.0	2.5	-	-	630	1.0	1	2.6	0.25	-	14	54	-	53	3.3	-	
FGT-05 - 14.3	FGT-05	14.3	20.34	Granite	-	0.25	7.1	2.5	-	-	680	1.0	1	3.0	0.25	-	15	59	-	11	3.4	-	
FGT-05 - 20.34	FGT-05	20.34	26	Granite	-	0.25	7.0	5.0	-	-	690	1.0	1	3.0	0.25	-	16	57	-	14	3.4	-	
FGT-05 - 26	FGT-05	26	30.8	Granite	-	0.25	7.5	2.5	-	-	640	1.5	1	2.7	0.25	-	14	54	-	21	3.4	-	
FGT-05 - 30.8	FGT-05	30.8	37.7	Granite	-	0.25	7.8	2.5	-	-	690	1.5	1	2.1	0.25	-	16	53	-	31	3.2	-	
FGT-05 - 37.7	FGT-05	37.7	45	Granite	-	0.5	7.3	2.5	-	-	650	1.5	1	3.1	0.25	-	17	60	-	56	3.4	-	
FGT-05 - 45	FGT-05	45	52.5	Granite	-	0.25	7.3	2.5	-	-	630	1.5	1	3.0	0.25	-	15	60	-	26	3.2	-	
FGT-05 - 52.5	FGT-05	52.5	60	Granite	-	0.25	7.3	2.5	-	-	640	1.5	1	3.1	0.25	-	16	56	-	10	3.3	-	
FGT-05 - 60	FGT-05	60	67.5	Granite	9.5	0.5	7.3	2.5	-	-	640	1.5	1	3.2	0.25	-	17	55	-	59	3.4	-	
FGT-05 - 67.5	FGT-05	67.5	75	Granite	-	0.25	7.0	10	-	-	600	1.5	1	3.2	0.25	-	15	54	-	7.0	3.2	-	
FGT-05 - 75	FGT-05	75	82.5	Granite	-	0.25	6.8	2.5	-	-	590	1.0	1	3.3	0.25	-	17	72	-	19	3.5	-	
FGT-05 - 82.5	FGT-05	82.5	90	Granite	-	0.25	7.2	2.5	-	-	640	1.0	1	3.2	0.25	-	15	51	-	17	3.2	-	
FGT-05 - 90	FGT-05	90	97.5	Granite	-	1	7.3	2.5	-	-	670	1.5	1	3.2	0.25	-	15	54	-	24	3.3	-	
FGT-05 - 97.5	FGT-05	97.5	105	Granite	-	0.25	6.5	5.0	-	-	590	1.0	1	3.3	0.25	-	16	52	-	20	3.4	-	
FGT-05 - 105	FGT-05	105	112.5	Granite	-	0.25	7.6	2.5	-	-	720	1.0	1	3.0	0.25	-	16	60	-	50	3.4	-	
FGT-05 - 112.5	FGT-05	112.5	120	Granite	-	0.25	7.5	2.5	-	-	740	1.0	1	3.0	0.25	-	17	68	-	75	3.5	-	
FGT-05 - 120	FGT-05	120	128	Granite	-	0.25	7.1	2.5	-	-	640	1.5	1	2.8	0.25	-	16	50	-	6.0	3.4	-	
FGT-05 - 128	FGT-05	128	134.9	Granite	-	0.25	7.0	2.5	-	-	620	1.0	1	2.6	0.25	-	15	50	-	8.0	3.3	-	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	Price Crustal Abundances																		
		From	To		-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					Paste pH unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm	
Granite (continued)																							
Fox (continued)																							
FGT-05 - 175.36	FGT-05	175.36	183	Granite	-	0.25	7.3	2.5	-	-	610	1.0	1	3.2	0.25	-	17	62	-	4.0	3.6	-	
FGT-05 - 183	FGT-05	183	190.5	Granite	-	0.25	7.7	5.0	-	-	740	1.5	1	3.2	0.25	-	16	61	-	61	3.6	-	
FGT-05 - 190.5	FGT-05	190.5	198	Granite	-	0.25	7.4	2.5	-	-	690	1.5	1	3.4	0.25	-	16	55	-	13	3.6	-	
FGT-05 - 198	FGT-05	198	205.5	Granite	-	0.25	7.5	5.0	-	-	670	1.0	1	2.9	0.25	-	16	56	-	6.0	3.5	-	
FGT-05 - 205.5	FGT-05	205.5	213	Granite	9.4	0.5	7.0	2.5	-	-	600	1.5	1	3.2	0.25	-	17	61	-	82	3.5	-	
FGT-05 - 213	FGT-05	213	220.5	Granite	-	0.25	7.0	2.5	-	-	650	1.5	1	3.1	0.25	-	16	58	-	13	3.4	-	
FGT-05 - 220.5	FGT-05	220.5	228	Granite	-	0.25	7.1	2.5	-	-	640	1.5	1	3.1	0.25	-	15	56	-	10	3.3	-	
FGT-05 - 228	FGT-05	228	235.5	Granite	-	0.5	6.7	2.5	-	-	620	1.0	1	3.0	0.25	-	16	49	-	33	3.2	-	
FGT-05 - 235.5	FGT-05	235.5	243	Granite	-	0.5	7.2	2.5	-	-	660	1.5	1	3.2	0.25	-	15	51	-	18	3.3	-	
FGT-05 - 243	FGT-05	243	250.5	Granite	-	0.25	7.0	2.5	-	-	630	1.5	1	3.1	0.25	-	15	51	-	14	3.3	-	
FGT-05 - 250.5	FGT-05	250.5	258	Granite	-	0.25	7.3	2.5	-	-	630	1.0	1	3.1	0.25	-	16	46	-	11	3.3	-	
FGT-05 - 258	FGT-05	258	265.5	Granite	-	0.25	7.2	2.5	-	-	640	1.5	1	3.3	0.25	-	16	70	-	15	3.5	-	
FGT-05 - 265.5	FGT-05	265.5	273	Granite	-	0.5	7.0	2.5	-	-	620	1.0	1	3.2	0.25	-	16	50	-	18	3.3	-	
FGT-05 - 273	FGT-05	273	280.5	Granite	-	0.25	7.3	2.5	-	-	620	1.0	1	3.5	0.25	-	17	59	-	34	3.6	-	
FGT-05 - 280.5	FGT-05	280.5	288	Granite	9.3	0.25	7.3	2.5	-	-	630	1.0	1	3.4	0.25	-	16	52	-	15	3.4	-	
FGT-05 - 288	FGT-05	288	295	Granite	-	0.5	7.6	2.5	-	-	610	1.0	1	3.2	0.25	-	16	52	-	31	3.4	-	
FGT-05 - 295	FGT-05	295	EOH	Granite	-	0.5	7.4	2.5	-	-	620	1.5	1	3.4	0.25	-	17	54	-	8.0	3.4	-	
FGT-07 - 4	FGT-07	4	14.21	Granite	9.1	0.25	8.3	2.5	-	-	650	1.5	1	2.2	0.25	-	11	32	-	8.0	2.2	-	
FGT-07 - 14.21	FGT-07	14.21	20.12	Granite	-	0.25	8.3	2.5	-	-	600	1.5	1	2.1	0.25	-	10	27	-	1.0	2.0	-	
FGT-07 - 20.12	FGT-07	20.12	31.45	Granite	-	0.25	8.1	2.5	-	-	620	0.50	1	2.3	0.25	-	11	29	-	5.0	2.4	-	
FGT-07 - 31.45	FGT-07	31.45	39	Granite	-	0.25	7.8	2.5	-	-	630	1.5	1	2.1	0.25	-	12	37	-	6.0	2.2	-	
FGT-07 - 39	FGT-07	39	46.5	Granite	-	0.25	8.1	2.5	-	-	660	1.5	1	2.2	0.25	-	12	37	-	6.0	2.5	-	
FGT-07 - 46.5	FGT-07	46.5	54	Granite	-	0.25	8.0	2.5	-	-	630	1.5	1	1.9	0.25	-	12	30	-	4.0	2.2	-	
FGT-07 - 54	FGT-07	54	61.5	Granite	-	0.25	7.5	2.5	-	-	660	1.5	1	1.5	0.25	-	11	27	-	3.0	2.1	-	
FGT-07 - 61.5	FGT-07	61.5	69	Granite	-	0.25	7.7	2.5	-	-	630	1.0	1	1.3	0.25	-	9.0	21	-	23	1.9	-	
FGT-07 - 69	FGT-07	69	76.5	Granite	-	0.25	8.2	2.5	-	-	570	0.50	1	2.0	0.25	-	12	34	-	46	2.5	-	
FGT-07 - 76.5	FGT-07	76.5	86.23	Granite	-	0.25	8.7	2.5	-	-	620	0.50	1	2.8	0.25	-	17	52	-	17	3.0	-	
FGT-07 - 86.23	FGT-07	86.23	94	Granite	9.3	0.25	8.2	2.5	-	-	550	0.50	1	3.0	0.25	-	18	62	-	15	3.2	-	
FGT-07 - 94	FGT-07	94	101.5	Granite	-	0.25	8.1	2.5	-	-	550	0.50	1	3.0	0.25	-	18	60	-	31	3.1	-	
FGT-07 - 101.5	FGT-07	101.5	109	Granite	-	0.25	8.2	2.5	-	-	600	0.50	1	3.1	0.25	-	18	62	-	21	3.2	-	
FGT-07 - 109	FGT-07	109	116.5	Granite	-	0.25	8.9	2.5	-	-	630	0.50	1	3.1	0.25	-	20	66	-	68	3.4	-	
FGT-07 - 116.5	FGT-07	116.5	124	Granite	-	0.25	8.5	2.5	-	-	650	0.50	1	3.1	0.25	-	20	56	-	34	3.4	-	
FGT-07 - 124	FGT-07	124	131.78	Granite	-	0.25	8.1	2.5	-	-	590	0.50	1	3.0	0.25	-	19	56	-	23	3.2	-	
FGT-07 - 131.78	FGT-07	131.78	135.64	Granite	-	0.25	8.7	2.5	-	-	680	0.50	1	3.0	0.25	-	20	56	-	55	3.3	-	
FGT-07 - 135.64	FGT-07	135.64	143	Granite	-	0.25	8.6	2.5	-	-	640	0.50	1	3.1	0.25	-	19	53	-	36	3.3	-	
FGT-07 - 143	FGT-07	143	149	Granite	-	0.25	0.85	2.5	-	-	60	0.25	1	0.26	0.25	-	2.0	7.0	-	3.0	0.32	-	
FGT-07 - 149	FGT-07	149	156.5	Granite	-	0.25	1.4	2.5	-	-	90	0.25	1	0.37	0.25	-	3.0	10	-	7.0	0.43	-	
FGT-07 - 156.5	FGT-07	156.5	162.63	Granite	9.1	0.25	8.4	2.5	-	-	580	0.50	1	2.9	0.25	-	18	59	-	28	3.2	-	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm	
Granite (continued)																							
Fox (continued)																							
FGT-07 - 162.63	FGT-07	162.63	170	Granite	-	0.25	8.2	2.5	-	-	580	0.50	1	2.7	0.25	-	18	58	-	37	2.9	-	
FGT-07 - 170	FGT-07	170	177.5	Granite	-	0.25	8.2	2.5	-	-	620	0.50	1	2.9	0.25	-	20	77	-	37	3.3	-	
FGT-07 - 177.5	FGT-07	177.5	188.55	Granite	-	0.25	8.6	2.5	-	-	630	0.50	1	3.1	0.25	-	20	69	-	30	3.3	-	
FGT-07 - 188.55	FGT-07	188.55	193.27	Granite	-	0.25	8.1	2.5	-	-	550	0.50	1	2.9	0.25	-	19	67	-	21	3.2	-	
FGT-07 - 193.27	FGT-07	193.27	199.62	Granite	-	0.25	8.5	2.5	-	-	770	0.50	1	3.0	0.25	-	18	64	-	17	3.0	-	
FGT-07 - 199.62	FGT-07	199.62	204.78	Granite	-	0.25	8.5	2.5	-	-	590	0.50	1	3.4	0.25	-	20	65	-	37	3.7	-	
FGT-07 - 204.78	FGT-07	204.78	212.28	Granite	-	0.25	9.3	2.5	-	-	590	0.50	1	3.2	0.25	-	19	59	-	14	3.2	-	
FGT-07 - 212.28	FGT-07	212.28	219.78	Granite	-	0.25	8.4	2.5	-	-	640	0.50	1	3.1	0.25	-	19	61	-	24	3.3	-	
FGT-07 - 219.78	FGT-07	219.78	227.28	Granite	-	0.25	8.1	2.5	-	-	610	0.50	1	3.1	0.25	-	18	59	-	46	3.0	-	
FGT-07 - 227.28	FGT-07	227.28	234.78	Granite	9.3	0.25	7.4	2.5	-	-	620	0.50	1	2.8	0.25	-	18	62	-	37	3.0	-	
FGT-07 - 234.78	FGT-07	234.78	242.28	Granite	-	0.25	8.1	2.5	-	-	670	0.50	2	2.9	0.25	-	19	61	-	40	3.1	-	
FGT-07 - 242.28	FGT-07	242.28	249.78	Granite	-	0.25	8.4	2.5	-	-	620	0.50	1	3.0	0.25	-	17	59	-	24	3.1	-	
FGT-07 - 249.78	FGT-07	249.78	257.28	Granite	-	0.25	8.2	2.5	-	-	630	0.50	1	3.0	0.25	-	19	66	-	50	3.1	-	
FGT-07 - 257.28	FGT-07	257.28	267.52	Granite	-	0.25	8.2	2.5	-	-	680	1.0	1	3.1	0.25	-	19	68	-	35	3.2	-	
FG-470-01-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-470-01-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-450-23-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-450-23-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-447-24-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-447-24-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-447-25-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-447-25-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-447-26-1	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-447-26-2	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-447-31-1	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-447-31-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-03-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-03-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-03-1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-03-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-04-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-04-2	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-06-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-06-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-07-1	-	-	-	Granite	9.5	0.25	9.9	2.5	-	-	700	1.7	1	3.3	0.50	-	17	106	-	29	3.4	-	
FG-435-07-2	-	-	-	Granite	9.6	0.25	9.6	2.5	-	-	630	1.8	4	3.4	0.50	-	17	100	-	27	3.4	-	
FG-435-08-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-08-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Fox (continued)																						
FG-435-13-1	-	-	-	Granite	9.4	0.25	9.9	2.5	-	-	660	1.8	1	3.3	0.50	-	17	76	-	27	3.3	-
FG-435-13-2	-	-	-	Granite	9.5	0.25	9.7	2.5	-	-	820	1.6	1	3.3	0.50	-	16	91	-	19	3.2	-
FG-435-18-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-18-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-27-1a	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-27-1b	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-34-1a	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-34-1b	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-30-1a	-	-	-	Granite	9.3	0.25	9.7	13	-	-	620	1.6	1	3.3	0.50	-	14	64	-	33	3.2	-
FG-435-30-2a	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-31-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-31-2	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-38-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-38-2	-	-	-	Granite	9.1	0.25	9.8	2.5	-	-	750	1.6	1	3.2	0.50	-	14	69	-	35	3.0	-
FG-435-44-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-44-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-48-1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-48-1b	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-06-1	-	-	-	Granite	9.4	0.25	9.8	2.5	-	-	660	1.7	1	3.0	0.50	-	16	76	-	31	3.2	-
FG-420-06-2	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-14-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-14-2	-	-	-	Granite	9.4	0.25	9.4	2.5	-	-	620	1.6	1	2.9	0.50	-	14	65	-	20	3.0	-
FG-420-21-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-21-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-25-1	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-25-2	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-27-1	-	-	-	Granite	9.4	0.25	9.8	2.5	-	-	700	1.5	1	3.3	0.50	-	13	53	-	18	3.1	-
FG-420-27-2	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-36-1	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-36-2	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-38-1	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-38-2	-	-	-	Granite	9.3	0.25	9.4	2.5	-	-	710	1.4	1	2.3	0.50	-	15	49	-	43	3.1	-
F420	-	-	-	Granite	9.3	0.25	9.4	2.5	-	-	710	1.4	1	2.3	0.25	-	15	49	-	43	3.1	-
F420	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
F420	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
F420	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-25-1	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-25-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Fox (continued)																						
FG-420-27-1	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-27-2	-	-	-	Granite	9.4	0.25	9.8	2.5	-	-	700	1.5	1	3.3	0.25	-	13	53	-	18	3.1	-
FG-420-51-A	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-51-B	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-05-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-05-2	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-05-1	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-05-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-09-A	-	-	-	Granite	9.3	0.25	9.0	2.5	-	-	590	1.4	1	3.2	0.25	-	15	125	-	26	3.2	-
FG-405-09-B	-	-	-	Granite	9.4	0.25	8.3	5.0	-	-	620	1.4	1	3.2	0.25	-	14	112	-	42	3.0	-
FG-405-48-1	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-48-2	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-53-1	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-53-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
F-390-25-1A	-	-	-	Granite	9.6	0.25	8.5	11	-	-	640	1.5	1	3.1	0.25	-	17	174	-	30	3.1	-
F-390-25-1B	-	-	-	Granite	9.4	0.25	7.9	2.5	-	-	600	1.4	1	2.9	0.25	-	15	156	-	34	2.8	-
FG-390-20-1	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-20-2	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-25-1A	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-25-1B	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-37-1	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-37-2	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-38-1	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-38-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-42-1	-	-	-	Granite	9.6	0.25	8.7	7.0	-	-	670	1.4	1	3.2	0.25	-	16	146	-	51	3.1	-
FG-390-42-2	-	-	-	Granite	9.6	0.25	8.3	6.0	-	-	630	1.4	1	3.1	0.25	-	14	161	-	13	2.8	-
FG-390-43-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-43-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-43-3	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-43-4	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-44-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-44-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-45-1	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-45-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-45-3	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-45-4	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-46-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-46-2	-	-	-	Granite	8.9	0.25	8.0	2.5	-	-	720	1.4	1	3.2	0.25	-	16	109	-	23	2.9	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Fox (continued)																						
FG-390-46-3	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-46-4	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-48-1	-	-	-	Granite	9.1	0.25	7.5	2.5	-	-	620	1.3	1	2.7	0.25	-	14	104	-	15	2.7	-
FG-390-48-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-48-3	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-48-4	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-49-1	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-49-2	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-50-1	-	-	-	Granite	9.2	0.25	7.7	6.0	-	-	590	1.4	1	3.3	0.25	-	14	129	-	33	3.0	-
FG-390-50-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-50-3	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-50-4	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-08-1	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-08-1	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-08-2	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-08-2	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-09R1-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-09R1-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-12-01	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-12-02	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-18-1	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-18-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-18-3	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-18-4	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-22-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-22-2	-	-	-	Granite	8.6	0.25	8.4	2.5	-	-	640	1.4	1	2.8	0.25	-	18	125	-	32	3.1	-
FG-375-24-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-24-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-24-3	-	-	-	Granite	9.5	0.25	7.1	2.5	-	-	570	1.3	1	3.0	0.25	-	15	161	-	32	2.8	-
FG-375-24-4	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-28-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-28-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-28-3	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-28-4	-	-	-	Granite	9.4	0.25	8.4	14	-	-	680	1.4	1	3.4	0.25	-	16	148	-	33	3.1	-
FG-375-30-1	-	-	-	Granite	9.3	0.25	8.6	12	-	-	630	1.4	1	3.3	0.25	-	16	135	-	21	3.2	-
FG-375-30-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-30-3	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-30-4	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Fox (continued)																						
FG-375-31-1	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-31-2	-	-	-	Granite	8.5	0.25	7.5	2.5	-	-	860	1.4	1	3.5	0.25	-	20	224	-	37	3.3	-
FG-375-31-3	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-31-4	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-37-1	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-37-2	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-37-3	-	-	-	Granite	8.3	0.25	8.3	2.5	-	-	690	1.4	1	2.6	0.25	-	13	180	-	26	2.8	-
FG-375-37-4	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-1	-	-	-	Granite	9.8	0.25	8.8	2.5	-	-	730	1.5	1	3.1	0.25	-	16	145	-	42	3.1	-
FG-375-40-2	-	-	-	Granite	9.6	0.25	8.3	2.5	-	-	680	1.4	1	2.7	0.25	-	13	208	-	32	2.9	-
FOX-375-07-1A	-	-	-	Granite	9.8	0.25	8.7	6.0	-	-	810	1.5	1	3.6	0.25	-	16	200	-	15	3.1	-
FOX-375-07-1B	-	-	-	Granite	9.7	0.25	8.3	9.0	-	-	640	1.5	1	3.5	0.25	-	17	170	-	18	3.2	-
FG-375-52-02 22-NOV-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-52-01 22-NOV-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-45-04 29-OCT-04	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-45-03 29-OCT-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-45-02 29-OCT-04	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-45-01 29-OCT-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-04 24-OCT-04	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-04 20-OCT-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-03 24-OCT-04	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-03 20-OCT-04	-	-	-	Granite	9.3	0.25	7.9	2.5	-	-	770	1.4	1	3.3	0.25	-	17	214	-	30	3.2	-
FG-375-42-02 24-OCT-04	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-02 20-OCT-04	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-01 24-OCT-04	-	-	-	Granite	8.6	0.25	7.9	2.5	-	-	670	1.4	1	2.9	0.25	-	17	194	-	28	3.1	-
FG-375-42-01 20-OCT-04	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-41-04 13-OCT-04	-	-	-	Granite	8.8	0.25	8.5	2.5	-	-	590	1.4	1	2.7	0.25	-	16	166	-	23	2.9	-
FG-375-41-03 13-OCT-04	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-41-02 13-OCT-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-41-01 13-OCT-04	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-04 12-OCT-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-03 12-OCT-04	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-02 12-OCT-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-01 12-OCT-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-39-04 6-SEP-04	-	-	-	Granite	8.1	0.25	8.2	9.0	-	-	630	1.4	1	3.1	0.25	-	16	224	-	28	3.5	-
FG-375-39-03 6-SEP-04	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-39-02 6-SEP-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-39-01 6-SEP-04	-	-	-	Granite	7.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Fox (continued)																						
FG-375-33-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-33-03	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-33-02	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-33-01	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-370-06-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-01-01	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-01-02	-	-	-	Granite	9.6	0.25	7.8	6.0	-	-	710	1.4	1	3.1	0.25	-	16	112	-	34	2.9	-
FG-360-01-03	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-01-04	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-52-04	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-52-03	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-52-02	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-52-01	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-06	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-05	-	-	-	Granite	8.3	0.25	7.4	14	-	-	780	1.4	2	3.1	0.25	-	19	130	-	38	3.3	-
FG-360-51-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-03	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-02	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-01	-	-	-	Granite	9.3	0.25	7.4	7.0	-	-	740	1.5	1	3.0	0.25	-	16	81	-	35	3.0	-
FG-360-47-06	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-47-05	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-47-04	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-47-03	-	-	-	Granite	9.6	0.25	7.6	15	-	-	660	1.4	1	3.2	0.25	-	16	74	-	31	3.1	-
FG-360-47-02	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-47-01	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-46-04	-	-	-	Granite	9.5	0.25	6.8	2.5	-	-	620	1.4	1	3.0	0.25	-	14	104	-	23	2.8	-
FG-360-46-03	-	-	-	Granite	9.5	0.25	7.1	2.5	-	-	680	1.4	1	3.2	0.25	-	15	104	-	28	2.9	-
FG-360-46-02	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-46-01	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-44-04	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-44-03	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-44-02	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-44-01	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-42-06	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-42-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-42-04	-	-	-	Granite	8.9	0.25	7.4	2.5	-	-	680	1.3	1	2.7	0.25	-	16	123	-	40	3.0	-
FG-360-42-03	-	-	-	Granite	8.8	0.25	8.1	2.5	-	-	710	1.4	1	2.6	0.25	-	16	130	-	38	3.0	-
FG-360-42-02	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Fox (continued)																						
FG-360-42-01 28-JAN-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-41-04 1-FEB-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-41-03 1-FEB-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-41-02 24-JAN-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-41-01 24-JAN-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-40-04 4-FEB-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-40-03 4-FEB-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-40-02 4-FEB-05	-	-	-	Granite	9.7	0.25	8.2	8.0	-	-	660	1.4	1	3.3	0.25	-	16	106	-	29	3.1	-
FG-360-40-01 4-FEB-05	-	-	-	Granite	9.6	0.25	7.3	10	-	-	600	1.3	1	3.4	0.25	-	16	114	-	28	3.1	-
FG-360-39-06 1-FEB-05	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-05 1-FEB-05	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-04 23-JAN-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-04 18-JAN-05	-	-	-	Granite	9.5	0.25	8.7	2.5	-	-	640	1.4	1	2.8	0.25	-	14	90	-	17	2.9	-
FG-360-39-03 23-JAN-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-03 18-JAN-05	-	-	-	Granite	9.2	0.25	7.4	6.0	-	-	470	1.2	1	1.9	0.25	-	14	68	-	12	2.9	-
FG-360-39-02 22-JAN-05	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-02 18-JAN-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-01 22-JAN-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-01 18-JAN-05	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-38-04 23-JAN-05	-	-	-	Granite	9.8	0.25	7.7	2.5	-	-	600	1.4	1	3.0	0.25	-	14	106	-	32	3.1	-
FG-360-38-03 23-JAN-05	-	-	-	Granite	9.0	0.25	7.7	2.5	-	-	740	1.3	1	3.5	0.25	-	18	101	-	23	3.3	-
FG-360-38-02 22-JAN-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-38-01 22-JAN-05	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-36-02 30-JAN-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-36-01 30-JAN-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-35-04 14-JAN-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-35-03 14-JAN-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-35-02 14-JAN-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-35-01 14-JAN-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-04 23-JAN-05	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-03 23-JAN-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-02 20-JAN-05	-	-	-	Granite	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-02 11-JAN-05	-	-	-	Granite	9.3	0.25	8.7	2.5	-	-	590	1.3	1	3.1	0.25	-	14	106	-	23	2.7	-
FG-360-30-01 20-JAN-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-01 11-JAN-05	-	-	-	Granite	9.4	0.25	7.9	2.5	-	-	640	1.2	1	3.0	0.25	-	16	100	-	30	3.0	-
FG-360-29-04 26-DEC-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-29-03 26-DEC-04	-	-	-	Granite	8.0	0.25	6.7	2.5	-	-	1,160	1.1	1	3.6	0.25	-	32	388	-	44	3.5	-
FG-360-29-02 1-JAN-05	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm	
Granite (continued)																							
Fox (continued)																							
FG-360-29-01	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-28-02	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-28-01	-	-	-	Granite	8.1	0.25	8.9	2.5	-	-	310	0.70	1	5.9	0.25	-	37	122	-	186	7.8		
FG-360-25-02	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-25-01	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-22-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-22-03	-	-	-	Granite	8.8	0.25	8.3	2.5	-	-	630	1.4	1	3.1	0.25	-	17	128	-	23	3.2		
FG-360-22-02	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-22-01	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-18-02	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-18-01	-	-	-	Granite	8.5	0.25	7.7	2.5	-	-	790	1.3	1	3.1	0.25	-	16	198	-	40	3.3		
FG-360-11-04	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-11-03	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-11-02	-	-	-	Granite	8.2	0.25	7.8	2.5	-	-	560	1.4	1	2.1	0.25	-	18	160	-	30	3.3		
FG-360-11-02	-	-	-	Granite	8.9	0.25	7.5	2.5	-	-	610	1.1	1	3.7	0.25	-	22	132	-	64	4.4		
FG-360-11-01	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-11-01	-	-	-	Granite	9.2	0.25	8.1	2.5	-	-	690	1.1	1	4.5	0.25	-	26	114	-	88	5.2		
FG-360-03-04	-	-	-	Granite	8.3	0.25	8.0	2.5	-	-	730	1.4	1	3.2	0.25	-	16	110	-	33	3.1		
FG-360-03-03	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-03-02	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-03-01	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-02-04	-	-	-	Granite	8.2	0.25	8.2	6.0	-	-	600	1.4	1	2.9	0.25	-	16	84	-	14	3.1		
FG-360-02-03	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-02-02	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-360-02-01	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-42-4	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-42-3	-	-	-	Granite	9.1	0.25	8.7	2.5	-	-	330	0.90	1	6.2	0.25	-	39	124	-	158	7.1		
FG-345-42-2	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-42-1	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-42-08	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-42-07	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-42-06	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-42-05	-	-	-	Granite	8.9	0.25	8.5	5.0	-	-	170	0.60	1	7.1	0.25	-	45	121	-	202	8.4		
FG-345-42-04	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-42-03	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-42-02	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-42-01	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-41-04	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Fox (continued)																						
FG-345-41-03	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-41-02	-	-	-	Granite	9.2	0.25	8.3	2.5	-	-	540	1.3	1	2.7	0.25	-	16	74	-	43	2.9	-
FG-345-41-01	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-40-04	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-40-03	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-40-02	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-40-01	-	-	-	Granite	9.3	0.25	7.7	2.5	-	-	580	1.4	3	3.1	0.25	-	21	69	-	333	3.7	-
FG-345-38-06	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-04	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-03	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-02	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-01	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-37-04	-	-	-	Granite	9.3	0.25	8.2	2.5	-	-	600	1.4	1	3.0	0.25	-	15	77	-	28	2.9	-
FG-345-37-03	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-37-02	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-37-01	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-36-04	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-36-03	-	-	-	Granite	9.2	0.25	7.4	6.0	-	-	610	1.4	1	3.2	0.25	-	18	88	-	23	3.2	-
FG-345-36-02	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-36-01	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-35-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-35-03	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-35-02	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-35-01	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-34-04	-	-	-	Granite	9.8	0.25	7.5	2.5	-	-	690	1.2	2	2.8	0.25	-	15	79	-	39	2.8	-
FG-345-34-03	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-34-02	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-34-01	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-06	-	-	-	Granite	9.3	0.25	8.3	10	-	-	540	1.5	3	2.5	0.25	-	17	76	-	19	3.1	-
FG-345-27-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-04	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-03	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-02	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-01	-	-	-	Granite	9.4	0.25	7.4	2.5	-	-	610	1.4	1	2.9	0.25	-	16	75	-	32	3.3	-
FG-345-21-04	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-21-03	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-21-02	-	-	-	Granite	9.4	0.25	7.5	7.0	-	-	580	1.4	1	3.1	0.25	-	17	80	-	52	3.0	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Fox (continued)																						
FG-345-21-01 24-Mar-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-16-04 28-FEB-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-16-03 28-FEB-05	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-16-02 28-FEB-05	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-16-01 28-FEB-05	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-14-02 16-FEB-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-14-01 16-FEB-05	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-12-06 26-Mar-05	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-12-05 26-Mar-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-12-04 26-Mar-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-12-03 26-Mar-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-12-02 26-Mar-05	-	-	-	Granite	8.3	0.25	7.6	14	-	-	610	1.5	2	2.2	0.25	-	20	106	-	39	3.2	-
FG-345-12-01 26-Mar-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-10-04 15-FEB-05	-	-	-	Granite	9.9	0.25	8.1	6.0	-	-	670	1.3	1	3.6	0.25	-	16	116	-	42	3.3	-
FG-345-10-03 15-FEB-05	-	-	-	Granite	9.7	0.25	7.6	6.0	-	-	730	1.2	1	3.3	0.25	-	26	172	-	255	3.6	-
FG-345-10-02 15-FEB-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-10-01 15-FEB-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-09-04 7-FEB-05	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-09-03 7-FEB-05	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-09-02 7-FEB-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-09-01 7-FEB-05	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-07-04 16-FEB-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-07-03 16-FEB-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-07-02 4-FEB-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-07-01 4-FEB-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-25-04 24-Jun-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-25-03 24-Jun-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-25-02 24-Jun-05	-	-	-	Granite	9.6	0.25	8.2	6.0	-	-	630	1.4	1	3.4	0.25	-	15	64	-	47	3.1	-
FG-330-25-01 24-Jun-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-24-04 24-Jun-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-24-03 24-Jun-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-24-02 24-Jun-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-24-01 24-Jun-05	-	-	-	Granite	9.8	0.25	8.5	7.0	-	-	580	1.5	1	3.3	0.25	-	16	59	-	41	3.4	-
FG-330-23-04 15-Jun-05	-	-	-	Granite	9.0	0.25	7.9	6.0	-	-	590	1.6	1	2.3	0.25	-	13	102	-	15	3.1	-
FG-330-23-03 15-Jun-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-23-02 15-Jun-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-23-01 15-Jun-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-22-08 20-Jun-05	-	-	-	Granite	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Fox (continued)																						
FG-330-22-07	20-Jun-05	-	-	Granite	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-22-06	20-Jun-05	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-22-05	20-Jun-05	-	-	Granite	9.7	0.25	8.2	2.5	-	-	640	1.4	1	3.5	0.25	-	18	62	-	25	3.2	-
FG-330-22-04	20-Jun-05	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-22-03	20-Jun-05	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-22-02	20-Jun-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-22-01	20-Jun-05	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-20-04	10-Jun-05	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-20-03	10-Jun-05	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-20-02	10-Jun-05	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-20-01	10-Jun-05	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-18-02	11-Jun-05	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-18-01	11-Jun-05	-	-	Granite	8.9	0.25	8.2	2.5	-	-	790	1.4	1	3.0	0.25	-	17	126	-	27	3.3	-
FG-330-15-04	4-Jun-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-15-03	4-Jun-05	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-15-02	4-Jun-05	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-15-01	4-Jun-05	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-13-04	1-Jun-05	-	-	Granite	9.3	0.25	8.5	7.0	-	-	910	1.5	1	2.9	0.25	-	13	100	-	52	3.0	-
FG-330-13-03	1-Jun-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-13-02	1-Jun-05	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-13-01	1-Jun-05	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-08	18-May-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-07	18-May-05	-	-	Granite	9.6	0.25	8.4	2.5	-	-	630	1.4	1	3.2	0.25	-	15	62	-	25	3.2	-
FG-330-09-06	18-May-05	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-05	18-May-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-04	17-May-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-03	17-May-05	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-02	17-May-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-01	17-May-05	-	-	Granite	9.4	0.25	8.5	6.0	-	-	590	1.3	1	3.7	0.25	-	19	124	-	50	3.8	-
FG-315-13-02	14-07-05	-	-	Granite	8.9	0.25	7.5	8.0	-	-	600	1.3	1	3.1	0.25	-	15	71	-	35	3.0	-
FG-315-13-03	14-07-05	-	-	Granite	9.4	0.25	9.2	6.0	-	-	710	1.5	1	3.4	0.25	-	18	68	-	17	3.4	-
FG-315-13-04	14-07-05	-	-	Granite	9.2	0.25	8.3	5.0	-	-	650	1.4	1	3.4	0.25	-	17	72	-	29	3.3	-
FG-315-16-01	24-07-05	-	-	Granite	9.7	0.25	7.4	6.0	-	-	600	1.4	1	3.5	0.25	-	16	59	-	39	3.0	-
FG-315-16-02	24-07-05	-	-	Granite	9.5	0.25	8.4	2.5	-	-	650	1.3	1	3.3	0.25	-	14	84	-	28	3.1	-
FG-315-16-03	24-07-05	-	-	Granite	9.6	0.25	7.9	2.5	-	-	560	1.3	1	3.2	0.25	-	15	63	-	19	3.1	-
FG-315-16-04	24-07-05	-	-	Granite	9.5	0.25	8.3	2.5	-	-	630	1.4	2	3.2	0.25	-	14	80	-	50	3.1	-
FG-275-20-1		-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-275-20-2		-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Fox (continued)																						
FG-275-20-3	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-275-20-4	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-270-16-01	-	-	-	Granite	9.8	0.25	8.4	2.5	-	-	610	1.4	1	2.8	0.25	-	14	67	-	15	3.3	-
Fox-260-Granite-2 31-Mar-09	-	-	-	Granite	9.3	0.25	7.2	2.5	-	-	430	1.7	1	0.50	0.25	-	3.0	22	-	3.0	0.93	20
Fox-260-Granite-1 31-Mar-09	-	-	-	Granite	9.4	0.25	7.7	2.5	-	-	560	1.4	1	2.3	0.25	-	12	62	-	32	2.9	20
Fox-250-Granite-2 26-Jan-09	-	-	-	Granite	9.4	0.25	7.5	2.5	-	-	700	1.4	1	3.3	0.25	-	16	80	-	28	3.1	20
Fox-250-Granite-1 26-Jan-09	-	-	-	Granite	9.9	0.25	7.8	2.5	-	-	660	1.4	1	3.2	0.25	-	15	67	-	17	3.2	20
Fox-250-Gr.Xenolith 8-Oct-09	-	-	-	Granite	9.9	0.25	8.1	11	-	-	640	1.4	1	3.4	0.25	-	17	71	-	25	3.3	20
Fox-250-Granite-3 8-Oct-09	-	-	-	Granite	9.7	0.25	7.7	9.0	-	-	580	1.3	1	3.3	0.25	-	18	81	-	45	3.6	20
Fox-250-Granite-4 8-Oct-09	-	-	-	Granite	9.6	0.25	7.7	6.0	-	-	610	1.4	1	3.5	0.25	-	19	83	-	24	3.3	20
Fox-240-Granite-3a 26-Jan-09	-	-	-	Granite	9.8	0.25	7.5	2.5	-	-	560	1.3	1	3.4	0.25	-	15	73	-	88	3.2	20
Fox-240-Granite-2a 26-Jan-09	-	-	-	Granite	9.9	0.25	7.6	2.5	-	-	620	1.3	1	3.4	0.25	-	15	74	-	20	3.2	20
Fox-240-Granite-1a 26-Jan-09	-	-	-	Granite	9.6	0.25	7.6	2.5	-	-	620	1.4	1	3.2	0.25	-	14	64	-	48	3.0	20
Fox-240-Granite-2 31-Mar-09	-	-	-	Granite	9.5	0.25	8.0	2.5	-	-	610	1.4	1	2.9	0.25	-	14	68	-	25	3.1	20
Fox-240-Granite-1 31-Mar-09	-	-	-	Granite	9.8	0.25	7.7	2.5	-	-	540	1.4	1	3.5	0.25	-	18	90	-	95	3.5	20
Median					9.3	0.25	7.9	2.5	-	-	640	1.4	1	3.1	0.25	-	16	68	-	29	3.2	20
Minimum					7.5	0.1	0.85	0.5	-	-	50	0.25	1	0.26	0.25	-	2.0	7.0	-	1.0	0.32	20
Maximum					10.0	1	9.9	15	-	-	1,160	2.5	4	7.1	0.50	-	60	388	-	333	8.4	20
Count					475	218	218	218	0	0	218	218	218	218	218	0	218	218	0	218	218	12
Koala																						
KG-345-27-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-27-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-28-1	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-28-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-30-1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-30-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-33-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-33-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-36-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-36-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-28-1	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-28-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-13-2	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-05-1A	-	-	-	Granite	9.0	0.25	9.2	2.5	-	-	610	1.5	1	2.7	0.25	-	20	122	-	25	3.3	-
KG-330-05-2A	-	-	-	Granite	8.6	0.25	8.8	5.0	-	-	650	1.3	1	2.3	0.25	-	25	192	-	41	3.5	-
KG-330-15-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-15-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-13-1	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Koala (continued)																						
KG-330-13-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-26-1	-	-	-	Granite	8.8	0.25	11	2.5	-	-	160	1.5	2	2.1	0.25	-	18	65	-	6.0	3.5	-
KG-330-26-2	-	-	-	Granite	9.2	0.25	11	2.5	-	-	100	1.3	1	0.60	0.25	-	7.0	40	-	2.0	1.4	-
KG-330-17-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-17-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-10-1	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-10-2	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-21-1	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-21-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-12-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-12-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-27-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-27-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-05-1A	-	-	-	Granite	9.5	0.25	9.7	2.5	-	-	550	1.7	1	3.5	0.25	-	16	71	-	19	3.1	-
KG-315-05-2A	-	-	-	Granite	9.3	0.25	9.5	2.5	-	-	600	1.5	2	2.9	0.25	-	15	73	-	36	3.0	-
KG-315-28-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-28-2	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-17-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-17-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-20-1	-	-	-	Granite	9.0	0.25	9.6	2.5	-	-	760	1.4	1	3.2	0.25	-	14	73	-	12	2.9	-
KSG-300-20-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-20-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-20-2	-	-	-	Granite	9.0	0.25	9.6	2.5	-	-	760	1.4	1	3.2	0.25	-	14	73	-	12	2.9	-
KSG-290-01-1	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-01-2	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-06-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-06-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-06-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-06-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-290-11-A	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-290-11-B	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-16-1	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-16-2	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-1	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-1	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-1	-	-	-	Granite	9.7	0.25	8.3	2.5	-	-	560	1.7	1	3.2	0.25	-	18	150	-	21	3.0	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Koala (continued)																						
KG-280-18-2	-	-	-	Granite	9.2	0.25	8.4	6.0	-	-	580	1.4	1	2.3	0.25	-	14	136	-	16	2.9	-
KG-270-08-1	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-270-08-2	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-270-08-01	-	-	-	Granite	9.1	0.25	7.8	6.0	-	-	380	1.4	1	0.94	0.25	-	10	115	-	7.0	2.1	-
KG-270-08-02	-	-	-	Granite	9.2	0.25	8.5	7.0	-	-	460	1.3	1	1.5	0.25	-	11	110	-	8.0	2.0	-
KG-270-17-02	-	-	-	Granite	8.1	0.25	8.1	2.5	-	-	560	1.3	1	2.5	0.25	-	14	172	-	22	3.1	-
KG-270-17-01	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-290-13-1A	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-290-13-1B	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-280-16-1A	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-280-16-1B	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Koala-UG-Granite	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
			Median		9.1	0.25	9.2	2.5	-	-	560	1.4	1	2.5	0.25	-	14	110	-	16	3.0	-
			Minimum		7.8	0.25	7.8	2.5	-	-	100	1.3	1	0.60	0.25	-	7.0	40	-	2.0	1.4	-
			Maximum		9.9	0.25	11	7.0	-	-	760	1.7	2	3.5	0.25	-	25	192	-	41	3.5	-
			Count		68	13	13	13	0	0	13	13	13	13	13	0	13	13	0	13	13	0
Misery																						
MDC-1 31.7	-	-	-	Granite	8.8	0.25	8.0	5.0	-	-	600	1.5	1	1.2	0.25	-	2.0	7.0	-	2.0	0.95	-
MDC-1 61.21	-	-	-	Granite	9.2	0.25	8.4	5.0	-	-	840	1.0	1	1.4	0.25	-	2.0	5.0	-	3.0	1.0	-
MDC-1 90.8	-	-	-	Granite	9.4	0.25	7.9	2.5	-	-	580	1.5	1	1.3	0.25	-	1.0	6.0	-	2.0	0.98	-
MDC-6 218.2	-	-	-	Granite	9.7	0.25	7.2	5.0	-	-	610	1.5	1	0.87	0.25	-	1.0	6.0	-	2.0	0.98	-
MDC-4 23.6	-	-	-	Granite	8.7	0.25	8.3	5.0	-	-	950	1.5	1	0.55	0.25	-	3.0	10	-	2.0	1.1	-
MDC-4 56	-	-	-	Granite	9.5	0.25	9.7	2.5	-	-	1,120	2.0	1	0.79	0.25	-	3.0	15	-	5.0	1.3	-
MDC-6 161.4	-	-	-	Granite	9.5	0.25	7.5	20	-	-	600	2.5	2	0.47	0.25	-	2.0	20	-	6.0	1.1	-
MDC-8 82	-	-	-	Granite	9.7	0.25	7.2	5.0	-	-	620	0.50	1	0.48	0.25	-	2.0	10	-	6.0	1.2	-
MDC-4 41.14	-	-	-	Granite	8.9	0.25	7.7	5.0	-	-	950	1.5	1	0.50	0.25	-	1.0	8.0	-	3.0	0.95	-
MDC-4 45.8	-	-	-	Granite	9.4	0.25	11	5.0	-	-	930	3.0	1	0.84	0.25	-	5.0	38	-	8.0	1.9	-
MDC-6 54.5	-	-	-	Granite	9.4	0.25	7.9	135	-	-	390	1.0	1	1.2	0.25	-	15	85	-	34	3.2	-
MDC-8 106.45	-	-	-	Granite	9.5	0.25	7.9	15	-	-	570	1.5	2	0.51	0.25	-	12	90	-	35	2.6	-
MPG 450- A	-	-	-	Granite	9.5	0.1	8.2	0.5	-	-	540	1.5	1	1.4	0.50	-	3.0	187	-	14	0.90	-
MPG 450- AA	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPG 450-AAA	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-26 2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-27 1A	-	-	-	Granite	9.3	0.1	8.4	0.5	-	-	650	2.0	1	1.4	0.50	-	4.0	136	-	1.0	0.76	-
MG 450-27 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-31 1A	-	-	-	Granite	8.1	0.1	7.9	3.0	-	-	590	1.5	1	1.7	0.25	-	12	174	-	30	2.0	-
MG 450-34 1A	-	-	-	Granite	9.2	0.2	8.5	0.5	-	-	540	2.0	1	1.4	0.25	-	3.0	124	-	14	0.86	-
MG 450-39-1A	-	-	-	Granite	8.6	0.1	8.5	0.5	-	-	800	1.5	1	1.4	0.25	-	1.0	123	-	8.0	0.97	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Misery (continued)																						
MG 450-39-1AA	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-39-1AAA	-	-	-	Granite	8.3	0.1	7.1	1.0	-	-	290	0.50	2	4.8	0.25	-	39	145	-	188	8.7	-
MG 450-39-2A	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-39-2AA	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-39-2AAA	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-41-1A	-	-	-	Granite	8.9	0.1	8.8	0.5	-	-	640	2.0	1	1.5	0.25	-	0.5	125	-	2.0	0.88	-
MG 450-41-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-45-1A	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-45-2A	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-46-1A	-	-	-	Granite	7.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-46-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-48-1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-48-2A	-	-	-	Granite	8.9	0.2	8.9	0.5	-	-	640	2.0	1	1.6	0.25	-	3.0	89	-	2.0	0.93	-
MG- 450-49-1A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-49-2A	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-50-1A	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-50-2A	-	-	-	Granite	7.2	0.1	9.1	0.5	-	-	950	1.5	1	1.4	0.25	-	3.0	137	-	6.0	1.0	-
MG-440-SE-01	-	-	-	Granite	9.9	0.25	7.6	2.5	-	-	590	2.3	1	1.3	0.25	-	2.0	11	-	2.0	0.87	20
MG-440-SE-02	-	-	-	Granite	9.6	0.25	7.7	2.5	-	-	640	1.9	2	1.5	0.25	-	2.0	10	-	2.0	0.83	20
MG-440-SE-03	-	-	-	Granite	9.7	0.25	7.9	2.5	-	-	700	1.9	1	1.6	0.25	-	2.0	8.0	-	1.0	0.86	20
MG 440-01 1A	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-37-1A	-	-	-	Granite	9.2	0.25	7.7	5.0	-	-	720	1.5	1	1.2	0.25	-	3.0	69	-	3.0	0.89	-
MG- 440-37-2A	-	-	-	Granite	7.7	0.25	7.0	15	-	-	530	0.50	1	1.2	0.25	-	11	145	-	23	2.0	-
MG 440-39-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440-39-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-40-1A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-40-2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-44-1A	-	-	-	Granite	8.7	0.1	8.9	0.5	-	-	820	1.5	1	1.5	0.25	-	4.0	114	-	13	1.2	-
MG- 440-44-1A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-44-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-44-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-46-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-46-2A	-	-	-	Granite	8.7	0.1	9.1	0.5	-	-	910	1.5	1	1.2	0.25	-	3.0	130	-	7.0	1.1	-
MG- 440-53-1A	-	-	-	Granite	7.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-53-2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-54-1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-54-2A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-55-1A	-	-	-	Granite	7.6	0.1	9.5	3.0	-	-	630	3.0	1	1.7	0.25	-	4.0	171	-	7.0	1.2	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Misery (continued)																						
MG- 440-55-2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 57 1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 57 1B	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 59 1A	-	-	-	Granite	9.4	0.25	8.5	25	-	-	640	1.5	1	1.6	0.25	-	9.0	103	-	13	1.6	-
MG 440 59 2A	-	-	-	Granite	9.6	0.25	8.1	20	-	-	670	1.5	1	1.4	0.25	-	8.0	73	-	7.0	1.5	-
MG 440 60 1A	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 60 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 61 1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 61 2A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 62 1A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 62 2A	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 65 1A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 65 2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 66 1A	-	-	-	Granite	8.5	0.25	8.5	5.0	-	-	700	1.5	1	1.3	0.25	-	6.0	123	-	4.0	1.0	-
MG 440 66 2A	-	-	-	Granite	7.9	0.25	8.0	5.0	-	-	610	1.5	1	1.7	0.25	-	10	172	-	23	1.7	-
MG- 440-67-1A	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-67-2A	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-68-1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-68-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-440-70-1A	-	-	-	Granite	8.9	0.25	6.9	2.5	-	-	320	1.5	1	3.9	0.50	-	31	98	-	172	7.5	-
MG-440-70-2A	-	-	-	Granite	8.4	0.25	7.8	10	-	-	380	1.5	1	2.4	0.25	-	27	163	-	128	6.1	-
MG-430-W-01	-	-	-	Granite	9.7	0.25	7.6	2.5	-	-	660	2.2	1	1.5	0.25	-	1.0	10	-	2.0	0.84	20
MG-430-W-02	-	-	-	Granite	9.9	0.25	7.7	2.5	-	-	600	1.9	1	1.5	0.25	-	2.0	10	-	2.0	0.87	20
MG-430-W-03	-	-	-	Granite	9.6	0.25	7.3	2.5	-	-	660	1.7	1	1.3	0.25	-	2.0	10	-	2.0	0.79	20
MG- 430-11-1A	-	-	-	Granite	8.7	0.1	8.4	15	-	-	550	2.0	1	0.84	0.25	-	22	267	-	45	3.9	-
MG- 430-13-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-13-2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-13-3A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 18 1A	-	-	-	Granite	9.3	0.25	7.9	5.0	-	-	580	2.0	2	0.97	0.25	-	4.0	66	-	6.0	0.93	-
MG 430 18 2A	-	-	-	Granite	9.6	0.25	7.9	5.0	-	-	770	1.5	1	0.99	0.25	-	3.0	68	-	2.0	0.74	-
MG 430 19 1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 19 2A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 20 1A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 20 2A	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 27 2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 28 1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 28 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 29 1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm	
Granite (continued)																							
Misery (continued)																							
MG 430 29 2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG 430 30 1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG 430 30 2A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG 430 31 1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG 430 31 2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 430-33-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 430-34-1A	-	-	-	Granite	9.1	0.25	7.8	5.0	-	-	670	1.0	1	1.4	0.25	-	2.0	64	-	2.0	0.79		
MG- 430-35-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 430-35-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 430-36-1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 430-36-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 430-41-1B	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 430-41-2B	-	-	-	Granite	6.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG 430 47 1A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG 430 47 1B	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG 430 27 1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG/S-430-44-2A	-	-	-	Granite	9.1	0.25	8.1	2.5	-	-	670	2.5	4	1.3	0.50	-	1.0	66	-	8.0	0.87		
MG-430-42-1A	-	-	-	Granite	8.6	0.25	8.0	2.5	-	-	640	1.5	1	1.4	0.25	-	7.0	96	-	12	1.7		
MG-430-42-2A	-	-	-	Granite	7.8	0.5	8.0	2.5	-	-	730	1.5	2	1.3	0.25	-	4.0	81	-	12	1.2		
MG-430-58 1A	-	-	-	Granite	9.0	0.25	7.7	2.5	-	-	680	3.0	1	1.4	0.25	-	4.0	37	-	12	1.3		
MG-430-58 2A	-	-	-	Granite	8.9	0.25	7.7	2.5	-	-	520	3.5	1	2.6	0.25	-	16	64	-	89	4.1		
MG-420-SW-01	-	-	-	Granite	9.8	0.25	7.6	2.5	-	-	760	1.5	1	1.6	0.25	-	2.0	9	-	1.0	0.83		
MG-420-SW-02	-	-	-	Granite	10.0	0.25	7.7	2.5	-	-	660	1.7	1	1.6	0.25	-	2.0	10	-	1.0	0.85		
MG-420-SW-03	-	-	-	Granite	9.9	0.25	7.5	2.5	-	-	750	1.7	1	1.5	0.25	-	1.0	8	-	1.0	0.81		
MG- 420-07-1A	-	-	-	Granite	9.0	0.25	7.9	5.0	-	-	590	2.0	1	1.3	0.25	-	3.0	70	-	4.0	0.85		
MG- 420-07-2A	-	-	-	Granite	9.0	0.25	8.0	2.5	-	-	680	1.5	1	1.4	0.25	-	3.0	69	-	3.0	0.82		
MG- 420-10-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 420-10-2A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 420-13-1A	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 420-13-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 420-14-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 420-14-2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 420-15-1B	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG- 420-15-2B	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
MG 420 20 1A	-	-	-	Granite	8.4	0.25	7.9	2.5	-	-	610	1.0	1	1.1	0.25	-	4.0	85	-	7.0	1.1		
MG 420 20 1B	-	-	-	Granite	8.4	0.25	8.3	2.5	-	-	660	1.5	1	1.1	0.25	-	4.0	83	-	6.0	1.0		
MG/S-420-30-1A	-	-	-	Granite	9.3	0.25	7.3	2.5	-	-	900	1.5	1	1.4	0.25	-	1.0	52	-	7.0	0.81		
MG/S-420-30-2A	-	-	-	Granite	9.4	0.25	7.5	2.5	-	-	630	2.0	2	1.5	0.25	-	1.0	61	-	7.0	0.84		

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Misery (continued)																						
MG-420-18-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-18-2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-24-1A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-24-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-25/26-1A	-	-	-	Granite	9.2	0.25	9.4	20	-	-	480	2.0	1	1.7	0.25	-	13	148	-	42	2.6	-
MG-420-25/26-2A	-	-	-	Granite	8.9	0.25	6.6	205	-	-	460	1.5	2	0.89	0.25	-	16	176	-	38	3.1	-
MG-420-26-1A	-	-	-	Granite	9.1	0.25	7.7	2.5	-	-	610	1.5	1	1.0	0.25	-	9.0	110	-	18	1.7	-
MG-420-26-2A	-	-	-	Granite	9.2	0.25	12	2.5	-	-	860	3.0	1	4.8	0.25	-	30	170	-	170	7.9	-
MG-420-27-1A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-27-2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-28-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-28-2A	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-30-1A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-30-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-31-1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-31-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-36-1A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-36-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-02-01	-	-	-	Granite	9.6	0.04	7.3	0.2	-	-	890	1.5	0.11	1.0	0.02	-	2.4	11	-	4.9	1.0	21
MG-410-03-01	-	-	-	Granite	9.5	0.06	7.9	0.9	-	-	610	2.1	0.17	1.4	0.04	-	3.3	21	-	5.9	1.1	20
MG-410-07-01	-	-	-	Granite	8.8	0.03	7.1	0.6	-	-	600	1.8	0.11	1.0	0.04	-	2.5	10	-	4.1	0.86	20
MG 410 04 1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 04 1B	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 05 1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 05 2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 06 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 06 1B	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 07 1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 07 1B	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 09 1A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 09 1B	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 10 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 10 1B	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-12-1A	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-12-2A	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-16-1A	-	-	-	Granite	9.1	0.25	6.8	2.5	-	-	620	1.5	1	1.2	0.25	-	1.0	47	-	7.0	0.71	-
MG-410-16-2A	-	-	-	Granite	8.7	0.25	7.5	2.5	-	-	760	1.5	2	1.2	0.50	-	1.0	60	-	7.0	0.83	-
MG-410-17-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Misery (continued)																						
MG-410-17-2A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-19-1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-19-2A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-20 1A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-20 2A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-24 1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-24 2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-26 1A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-26 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-28 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-28 2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-31 1A	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-31 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-32 1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-32 2A	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-36 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-36 2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-38 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-38 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-40 1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-40 2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG/D-410-41 -1A	-	-	-	Granite	9.1	0.25	7.2	5.0	-	-	670	2.0	1	0.72	0.25	-	1.0	50	-	4.0	1.0	-
MG/D-410-41 -2A	-	-	-	Granite	9.4	0.25	7.6	2.5	-	-	490	2.5	1	0.80	0.25	-	4.0	60	-	7.0	1.1	-
MG 400-34 1a	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 400-34 2a	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 400-41 1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-01-1A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-01-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-02 1A	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-02 2A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-03 1A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-03 2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-05 1A	-	-	-	Granite	9.3	0.25	7.7	2.5	-	-	690	2.0	2	1.1	0.25	-	1.0	45	-	6.0	1.0	-
MG-400-05 2A	-	-	-	Granite	8.9	0.25	7.7	2.5	-	-	660	2.0	1	1.1	0.25	-	3.0	65	-	4.0	1.1	-
MG-400-07 1A	-	-	-	Granite	9.5	0.25	7.7	2.5	-	-	560	2.5	1	1.2	0.25	-	2.0	47	-	6.0	0.86	-
MG-400-07 2A	-	-	-	Granite	9.6	0.25	8.1	2.5	-	-	860	2.0	1	1.4	0.25	-	1.0	56	-	4.0	0.82	-
MG-400-08-1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-08-2A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Misery (continued)																						
MG-400-09-1A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-09-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-11-1A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-11-2A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-15-1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-15-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-21-1A	-	-	-	Granite	9.4	0.25	8.3	2.5	-	-	810	2.0	4	1.3	0.25	-	3.0	32	-	8.0	0.88	-
MG-400-21-2A	-	-	-	Granite	9.3	0.25	7.7	2.5	-	-	740	2.0	4	1.1	0.50	-	3.0	78	-	5.0	0.89	-
MG-400-24-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-24-2A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-25-1A	-	-	-	Granite	8.8	0.25	8.5	2.5	-	-	570	2.0	1	0.98	0.25	-	23	116	-	80	3.7	-
MG-400-25-2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-31-1A	-	-	-	Granite	8.9	0.25	8.9	15	-	-	580	1.5	1	1.3	0.25	-	24	132	-	70	4.0	-
MG-400-31-2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-32-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-32-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-36-1A	-	-	-	Granite	8.9	0.25	8.0	2.5	-	-	620	2.5	1	1.3	0.25	-	1.0	65	-	9.0	0.84	-
MG-400-36-2A	-	-	-	Granite	9.2	0.25	8.3	2.5	-	-	710	2.0	1	1.3	0.25	-	1.0	74	-	5.0	0.90	-
MG-400-37-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-37-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-05 1a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-05 2a	-	-	-	Granite	9.9	0.25	8.8	2.5	-	-	750	2.0	1	1.5	0.25	-	3.0	45	-	5.0	1.0	-
MG 390-06 1a	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-06 2a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-09 1a	-	-	-	Granite	9.7	0.25	8.5	5.0	-	-	1,240	1.5	1	1.0	0.25	-	1.0	37	-	7.0	1.0	-
MG 390-09 1a	-	-	-	Granite	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-09 2a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-09 2a	-	-	-	Granite	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-10 1a	-	-	-	Granite	9.5	0.25	8.3	2.5	-	-	720	2.0	1	1.4	0.25	-	1.0	45	-	3.0	0.85	-
MG 390-10 2a	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-11G 1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-11G 2a	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-13 1a	-	-	-	Granite	9.6	0.25	8.7	5.0	-	-	760	2.0	1	1.4	0.25	-	2.0	51	-	19	1.1	-
MG 390-13 2a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-14T 1a	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-14T 2a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-02-1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-02-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Misery (continued)																						
MG-390-03-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-03-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-04-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-04-2A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-17-1a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-17-1a	-	-	-	Granite	8.8	0.25	7.9	2.5	-	-	690	1.5	1	0.34	0.25	-	2.0	58	-	3.0	0.85	-
MG-390-17-2a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-17-2a	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-20-1a	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-20-2a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-21-1a	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-21-2a	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-22-1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-22-1a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-22-2a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-22-2a	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-23T-1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-23T-2a	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 380-10 1a	-	-	-	Granite	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 380-10 2a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 380-14 1a	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 380-14 2a	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-16-1a	-	-	-	Granite	9.8	0.25	8.2	5.0	-	-	750	2.0	1	1.4	0.25	-	1.0	55	-	1.0	0.82	-
MG-380-16-2a	-	-	-	Granite	9.9	0.25	8.3	2.5	-	-	510	2.5	1	1.4	0.25	-	1.0	64	-	2.0	0.76	-
MG-380-18-1a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-18-2a	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-19-1a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-19-2a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-23-1A	-	-	-	Granite	8.7	0.5	8.0	5.0	-	-	700	2.0	1	0.97	0.25	-	1.0	29	-	4.0	0.73	-
MG-380-23-2A	-	-	-	Granite	9.1	0.5	7.9	2.5	-	-	650	2.0	1	1.3	0.25	-	1.0	40	-	5.0	0.83	-
MG-380-26-1A	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-26-2A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-27-1A	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-27-2A	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-29T-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-29T-2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-31T-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-31T-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price	Crustal Abundances																		
		From	To	General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga	
unit	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm		
Granite (continued)																							
Misery (continued)																							
MG-370-06-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-370-06-2	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-370-24-B	-	-	-	Granite	6.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-360-28-1	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-360-28-2	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-360-31-1	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-360-31-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MGS-360-18-01	-	-	-	Granite	9.2	0.25	7.8	41	-	-	450	1.5	1	0.88	0.25	-	20	181	-	49	3.6	-	
MGS-360-18-02	-	-	-	Granite	9.3	0.25	7.2	33	-	-	400	1.3	1	0.79	0.25	-	18	213	-	42	3.3	-	
MG-350-35-1	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-350-35-2	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-340-23-02 10-DEC-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-340-23-01 10-DEC-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-330-19-02 27-DEC-04	-	-	-	Granite	7.8	0.25	8.0	2.5	-	-	890	1.6	1	1.2	0.25	-	2.0	44	-	3.0	0.88	-	
MG-330-19-01 27-DEC-04	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-330-18-02 26-DEC-04	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-330-18-01 26-DEC-04	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-320-31-02 15-JAN-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-320-31-01 15-JAN-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-320-30-02 11-JAN-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-320-30-01 11-JAN-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-320-29-02 5-FEB-05	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-320-29-01 5-FEB-05	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-320-25-04 1-JAN-05	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-320-25-03 1-JAN-05	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-320-25-02 1-JAN-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-320-25-01 1-JAN-05	-	-	-	Granite	8.6	0.25	6.9	5.0	-	-	960	1.7	1	1.8	0.25	-	22	345	-	10	1.9	-	
MG-320-20-02 18-DEC-04	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-320-20-01 18-DEC-04	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-310-10-02 20-FEB-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-310-10-01 20-FEB-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-310-09-02 20-FEB-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-310-09-01 20-FEB-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-310-07-02 15-FEB-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-310-07-01 15-FEB-05	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-300-13-06 25-Mar-05	-	-	-	Granite	9.0	0.25	7.1	2.5	-	-	630	1.8	1	1.2	0.25	-	8.0	74	-	6.0	1.2	-	
MG-300-13-05 25-Mar-05	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-300-13-04 25-Mar-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																	
		From	To		-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
						Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe
unit	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	
Granite (continued)																						
Misery (continued)																						
MG-300-13-03	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-300-13-02	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-300-13-01	-	-	-	Granite	8.6	0.25	6.9	2.5	-	-	660	2.0	1	1.5	0.25	-	9.0	110	-	10	1.3	
MG-290-10-04	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-290-10-03	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-290-10-02	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MG-290-10-01	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
MGT-39 100-103	-	-	-	Granite	9.8	0.05	0.46	0.6	0.25	10	32	-	0.05	0.10	0.05	-	1.8	64	-	2.3	0.78	3.0
MGT-39 200-203	-	-	-	Granite	9.6	0.05	0.44	1.3	0.70	10	34	-	0.4	0.17	0.05	-	2.1	80	-	3.3	0.80	3.0
MGT-49 58.28-60.08	-	-	-	Granite	9.4	0.05	0.59	5.0	1.5	10	24	-	1.4	0.14	0.05	-	2.9	99	-	9.1	0.89	2.0
MGT-49 65.82-67.00	-	-	-	Granite	9.7	0.05	0.38	5.7	0.90	10	10	-	0.6	0.15	0.05	-	1.1	69	-	3.0	0.52	2.0
MGT-69 7.3-9.5	-	-	-	Granite	9.3	0.05	0.42	0.8	0.80	10	34	-	1.1	0.20	0.05	-	1.7	84	-	6.8	0.63	3.0
MGT-69 166-169	-	-	-	Granite	9.3	0.05	0.44	0.9	2.2	10	32	-	0.3	0.34	0.05	-	2.5	61	-	6.3	0.83	3.0
MGT-44 213-216	-	-	-	Granite	9.5	0.05	1.1	7.9	2.6	10	87	-	0.4	0.18	0.05	-	8.1	99	-	22	1.7	5.0
MGT-60 35-38	-	-	-	Granite	9.6	0.05	0.57	4.0	0.25	10	23	-	0.05	0.17	0.05	-	1.9	72	-	3.2	0.92	3.0
MGT-63 220-223	-	-	-	Granite	9.2	0.05	0.49	2.7	0.25	10	12	-	0.5	0.62	0.05	-	2.9	89	-	20	0.76	2.0
MGT-66 55-58	-	-	-	Granite	9.8	0.05	0.64	2.9	2.0	10	42	-	0.5	0.36	0.05	-	4.1	101	-	3.4	1.0	3.0
MGT-66 76-79	-	-	-	Granite	9.8	0.05	0.69	1.9	2.2	10	40	-	0.3	0.14	0.05	-	3.5	89	-	1.6	1.1	3.0
MGT-70 15-18	-	-	-	Granite	9.6	0.05	0.44	0.25	1.3	10	33	-	0.2	0.08	0.05	-	1.8	53	-	2.9	0.76	3.0
MGT-70 33-36	-	-	-	Granite	9.7	0.05	0.41	0.6	0.25	10	25	-	0.3	0.12	0.05	-	1.5	69	-	1.4	0.66	2.0
MGT-70 51-54	-	-	-	Granite	9.7	0.05	0.45	0.25	0.25	10	30	-	0.1	0.09	0.05	-	1.8	70	-	1.6	0.79	3.0
MGT-70 69-72	-	-	-	Granite	9.8	0.05	0.42	0.25	1.5	10	37	-	0.1	0.09	0.05	-	1.9	69	-	2.3	0.74	2.0
MGT-51 174-177	-	-	-	Granite	9.6	0.05	0.57	1.0	1.4	10	30	-	0.4	0.19	0.05	-	3.0	79	-	2.8	0.86	3.0
MGT-52 50-53	-	-	-	Granite	9.3	0.05	0.51	0.5	0.25	10	44	-	1.3	0.24	0.05	-	2.1	67	-	7.1	0.83	3.0
MGT-52 57-60	-	-	-	Granite	9.3	0.05	0.55	0.6	0.25	10	42	-	1.4	0.26	0.05	-	2.3	82	-	10	0.89	3.0
MGT-52 150-153	-	-	-	Granite	9.6	0.05	0.52	0.5	0.25	10	43	-	0.2	0.12	0.05	-	2.1	86	-	2.4	0.85	3.0
MGT-52 157-160	-	-	-	Granite	9.5	0.05	0.58	0.25	0.25	10	47	-	0.05	0.12	0.05	-	2.4	95	-	2.1	1.0	4.0
MGT-52 250-253	-	-	-	Granite	9.4	0.05	0.53	0.25	0.25	10	41	-	0.05	0.20	0.05	-	2.4	86	-	3.0	0.87	3.0
MGT-52 257-260	-	-	-	Granite	9.4	0.05	0.55	0.25	0.25	10	43	-	0.05	0.11	0.05	-	2.3	81	-	2.6	0.90	4.0
MGT-54 240-243	-	-	-	Granite	9.3	0.05	0.49	0.25	0.25	10	35	-	0.05	0.17	0.05	-	2.1	64	-	4.4	0.80	3.0
MGT-54 247-250	-	-	-	Granite	9.4	0.05	0.51	0.25	0.25	10	37	-	0.05	0.13	0.05	-	2.2	60	-	4.4	0.83	3.0
MDC-4 64.69	-	-	-	Granite	9.4	0.25	8.4	10	-	-	660	1.5	1	0.88	0.25	-	11	66	-	26	2.2	-
MS G 420 19 1A	-	-	-	Granite	9.0	0.25	7.9	2.5	-	-	570	1.0	1	1.1	0.25	-	3.0	63	-	1.0	0.73	-
MS G 420 19 1B	-	-	-	Granite	8.8	0.25	8.2	2.5	-	-	540	1.5	1	1.0	0.25	-	2.0	64	-	4.0	0.64	-
MS G 410 03 1A	-	-	-	Granite	9.0	0.25	9.2	5.0	-	-	480	1.5	1	0.87	0.25	-	21	175	-	44	3.5	-
MS G 410 03 1B	-	-	-	Granite	8.9	0.25	9.1	2.5	-	-	460	1.5	1	0.87	0.25	-	21	190	-	50	3.6	-
MS/G-410-27 1A	-	-	-	Granite	8.9	0.25	8.6	15	-	-	580	2.5	1	0.62	0.25	-	19	96	-	39	4.0	-
MS/G-410-27 2A	-	-	-	Granite	8.8	0.25	8.6	2.5	-	-	580	3.0	1	0.55	0.25	-	21	131	-	45	4.3	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					unit	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																							
Misery (continued)																							
MS 400-38 1a	-	-	-	Granite	9.5	0.25	8.6	35	-	-	530	2.5	1	1.8	0.25	-	24	131	-	85	5.1	-	
MS 400-38 2a	-	-	-	Granite	9.6	0.25	8.4	45	-	-	520	2.5	1	0.90	0.25	-	15	126	-	29	3.2	-	
MGT-49 171.23-173.14	-	-	-	Granite	9.4	0.05	0.24	3.6	12	10	14	-	26	0.10	0.05	-	1.3	86	-	10	0.33	0.5	
MGT-51 184-187	-	-	-	Granite	9.6	0.05	0.38	1.2	0.60	10	21	-	2.2	0.11	0.05	-	1.4	82	-	1.8	0.50	2.0	
MGT-52 125.26-126.8	-	-	-	Granite	9.4	0.05	0.33	1.3	0.25	10	40	-	0.4	0.14	0.05	-	1.0	87	-	2.1	0.37	2.0	
MGT-52 137.8-139.3	-	-	-	Granite	9.6	0.05	0.20	1.8	0.25	10	8	-	0.6	0.07	0.05	-	0.4	100	-	2.8	0.18	0.5	
MGT-56 38-41	-	-	-	Granite	8.9	0.05	1.1	4.7	0.60	10	26	-	0.5	0.67	0.05	-	8.7	100	-	26	1.8	3.0	
Median					9.1	0.25	7.8	2.5	0.25	10	605	1.7	1	1.1	0.25	-	2.9	70	-	6.0	0.94	3.0	
Minimum					6.5	0.03	0.20	0.20	0.25	10	8	0.50	0.05	0.07	0.02	-	0.4	5.0	-	1.0	0.18	0.5	
Maximum					10.1	0.5	12	205	12	10	1,240	3.5	26	4.8	0.50	-	39	345	-	188	8.7	21	
Count					370	130	130	130	29	29	130	101	130	130	130	0	130	130	0	130	130	41	
Panda																							
PG-210-12-1	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PG-210-12-2	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PG-210-08-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PG-210-08-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-210-06-1	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-210-06-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-195-10-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-195-10-2	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Panda-UG-Granite	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Median					9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Minimum					9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Maximum					9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Count					9	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	
Pigeon																							
97-54	97-54	188.69	189.09	Granite	9.7	0.1	1.5	2.5	-	-	170	0.25	2.5	0.28	0.5	-	10	169	-	1.0	2.4	-	
97-54	97-54	373.1	373.38	Granite	9.7	0.1	2.3	2.5	-	-	340	0.25	2.5	0.33	0.5	-	15	168	-	2.0	3.1	-	
97-55	97-55	295.01	295.75	Granite	9.8	0.1	1.2	2.5	-	-	100	0.25	2.5	0.18	0.5	-	7.0	179	-	0.5	1.8	-	
97-55	97-55	56	56.59	Granite	9.5	0.1	2.7	2.5	-	-	350	0.25	2.5	0.18	0.5	-	20	213	-	4.0	4.4	-	
HC-Pdef-6	-	-	-	Granite	9.6	0.01	7.5	0.6	-	-	400	1.6	0.01	1.4	0.02	91	12	60	8.0	2.1	2.3	17	
HC-Pdef-7	-	-	-	Granite	9.0	0.04	8.5	0.8	-	-	590	1.4	0.03	0.91	0.02	63	25	155	13	2.3	5.0	24	
HC-Pdef-12	-	-	-	Granite	9.0	0.01	7.9	1.9	-	-	400	1.7	0.01	0.71	0.01	48	12	69	3.1	6.0	2.4	19	
HC-PDef-17	-	-	-	Granite	9.5	0.005	8.3	0.4	-	-	530	1.7	0.04	0.74	0.02	52	20	124	11	1.5	4.0	23	
HC-PDef-24	-	-	-	Granite	9.2	0.08	8.6	1.0	-	-	590	1.6	0.05	0.46	0.11	41	16	122	6.8	17	4.0	19	
HC-PDef-25	-	-	-	Granite	9.3	0.01	8.3	1.9	-	-	390	2.3	0.02	0.96	0.02	55	20	122	7.1	7.6	4.1	22	
HC-PDef-27	-	-	-	Granite	9.9	0.01	8.5	0.3	-	-	490	1.3	0.04	1.5	0.03	54	14	74	14	1.0	2.9	20	
HC-PDef-29	-	-	-	Granite	10.0	0.005	9.1	0.7	-	-	620	1.8	0.08	1.1	0.01	75	30	174	21	2.4	5.5	28	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																						
Pigeon (continued)																						
HC-PDef-30	-	-	-	Granite	9.7	0.005	8.5	1.9	-	-	420	2.4	0.02	1.5	0.01	72	19	101	11	10	3.5	20
HC-PDef-33	-	-	-	Granite	9.3	0.005	7.6	0.6	-	-	380	1.4	0.02	0.54	0.01	49	18	113	14	9.2	3.4	18
HC-PDef-34	-	-	-	Granite	9.0	0.03	6.8	1.9	-	-	260	1.1	0.02	0.83	0.01	29	12	53	3.6	30	2.0	14
Median					9.5	0.01	7.9	1.9	-	-	400	1.4	0.04	0.74	0.02	54	16	122	11	2.4	3.4	20
Minimum					9.0	0.005	1.2	0.3	-	-	100	0.25	0.01	0.18	0.01	29	7.0	53	3.1	0.5	1.8	14
Maximum					10.0	0.1	9.1	2.5	-	-	620	2.4	2.5	1.5	0.5	91	30	213	21	30	5.5	28
Count					15	15	15	15	0	0	15	15	15	15	15	11	15	15	11	15	15	11
Sable																						
SDC-07	SDC-07	152.3	152.73	Granite	7.5	0.1	1.5	2.5	-	-	500	0.25	2.5	0.52	1.0	-	14	142	-	7.0	3.8	-
SDC-02	SDC-02	48.58	49.28	Granite	9.1	0.1	0.06	2.5	-	-	5	0.25	2.5	0.03	1.0	-	1.0	343	-	7.0	0.44	-
SDC-05	SDC-05	152	152.5	Granite	9.8	0.2	0.37	2.5	-	-	20	0.25	2.5	0.13	0.5	-	3.0	148	-	18	0.80	-
SDC-07	SDC-07	150.37	150.6	Granite	9.7	0.1	0.28	2.5	-	-	30	0.25	2.5	0.07	0.5	-	0.5	219	-	0.5	0.26	-
SDC-07	SDC-07	91.35	91.8	Granite	9.7	0.1	0.47	2.5	-	-	20	0.25	2.5	0.29	0.5	-	1.0	162	-	1.0	1.0	-
SDC-04	SDC-04	47.5	47.5	Granite	9.6	0.1	0.26	2.5	-	-	10	0.25	2.5	0.04	0.5	-	1.0	188	-	0.5	0.38	-
SDC-12	SDC-12	11.28	11.68	Granite	9.3	0.1	0.22	2.5	-	-	10	0.25	2.5	0.05	0.5	-	1.0	176	-	0.5	0.31	-
SDC-07	SDC-07	113	113.3	Granite	9.6	0.1	0.30	2.5	-	-	20	0.25	2.5	0.05	0.5	-	1.0	177	-	0.5	0.47	-
SDC-04	SDC-04	47	47.3	Granite	9.7	0.1	0.53	2.5	-	-	10	0.25	2.5	0.05	0.5	-	2.0	177	-	0.5	1.1	-
SDC-02	SDC-02	56	56.3	Granite	9.5	0.1	0.28	2.5	-	-	10	0.25	2.5	0.05	0.5	-	1.0	187	-	0.5	0.44	-
SDC-11	SDC-11	52	52	Granite	9.7	0.1	0.27	2.5	-	-	20	0.25	2.5	0.16	0.5	-	1.0	193	-	0.5	0.50	-
SDC-12	SDC-12	88.89	89.259	Granite	9.7	0.1	0.51	2.5	-	-	30	0.25	2.5	0.07	0.5	-	2.0	217	-	1.0	1.0	-
SDC-13	SDC-13	37.52	37.79	Granite	9.7	0.1	0.47	2.5	-	-	30	0.25	2.5	0.10	0.5	-	3.0	224	-	0.5	1.0	-
SDC-12	SDC-12	186.64	187.04	Granite	9.4	0.1	0.31	2.5	-	-	20	0.25	2.5	0.19	0.5	-	1.0	174	-	1.0	0.63	-
SDC-02	SDC-02	20.5	20.5	Granite	9.2	0.2	0.37	2.5	-	-	10	0.25	2.5	0.18	0.5	-	1.0	206	-	0.5	0.62	-
SDC-03	SDC-03	26	26.3	Granite	9.7	0.2	0.55	2.5	-	-	40	0.25	2.5	0.16	0.5	-	2.0	214	-	0.5	1.1	-
SDC-13	SDC-13	154.64	154.89	Granite	9.2	0.1	0.41	2.5	-	-	20	0.25	2.5	0.12	0.5	-	1.0	202	-	3.0	0.64	-
SDC-12	SDC-12	303.89	304.39	Granite	9.8	0.1	0.38	2.5	-	-	30	0.25	2.5	0.34	0.5	-	2.0	187	-	0.5	0.68	-
SDC-08	SDC-08	54.1	54.43	Granite	9.4	0.1	1.1	2.5	-	-	60	0.50	2.5	0.26	0.5	-	6.0	145	-	2.0	1.9	-
SDC-13	SDC-13	106.58	1069.89	Granite	10.0	0.1	2.0	2.5	-	-	280	0.25	2.5	0.17	1.0	-	22	292	-	60	3.9	-
SDC-05	SDC-05	233.9	234.17	Granite	9.5	0.1	0.87	2.5	-	-	60	0.25	2.5	0.32	0.5	-	6.0	189	-	0.5	1.7	-
SDC-05	SDC-05	224	224.23	Granite	9.8	0.1	0.62	2.5	-	-	90	0.25	2.5	0.21	0.5	-	5.0	225	-	3.0	1.4	-
SDC-07	SDC-07	114.32	144.68	Granite	9.2	0.1	1.4	2.5	-	-	350	0.25	2.5	0.52	0.5	-	11	160	-	11	3.3	-
SDC-12	SDC-12	386.18	386.58	Granite	9.6	0.1	2.4	2.5	-	-	470	0.50	2.5	0.59	1.0	-	13	144	-	0.5	3.3	-
SDC-07	SDC-07	157.03	157.42	Granite	9.8	0.1	1.5	2.5	-	-	330	0.25	2.5	0.52	0.5	-	13	137	-	11	3.8	-
SDC-06	SDC-06	117.93	118.36	Granite	9.8	0.1	1.5	2.5	-	-	420	0.25	2.5	0.44	1.0	-	12	202	-	6.0	2.8	-
SDC-04	SDC-04	77	77.42	Granite	9.4	0.1	0.21	2.5	-	-	20	0.25	2.5	0.06	0.5	-	0.5	146	-	0.5	0.20	-
SDC-13	SDC-13	30.14	30.45	Granite	9.4	0.1	1.9	2.5	-	-	630	0.25	2.5	0.53	0.5	-	16	188	-	0.5	3.1	-
SDC-13	SDC-13	96.97	97.23	Granite	9.5	0.1	1.9	2.5	-	-	710	0.25	2.5	0.61	0.5	-	17	202	-	0.5	3.2	-
SDC-05	SDC-05	98.73	98.88	Granite	9.5	0.1	0.33	2.5	-	-	10	0.25	2.5	0.08	0.5	-	1.0	183	-	2.0	0.57	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm	
Granite (continued)																							
Jay (continued)																							
2014-DD-052	JGT-02	125.42	134.04	Granite	8.54	0.02	0.73	0.5	-	5	36	0.1	0.09	0.14	0.04	46.2	3.3	192	1.88	7.8	1.19	4.8	
2014-DD-053	JGT-02	64.04	74	Granite	8.60	0.04	0.55	0.5	-	5	28	0.5	0.07	0.15	0.04	32	3.6	200	1.09	2.4	0.93	3.7	
2014-DD-055	JGT-02	60.16	65.55	Granite	8.44	0.03	0.57	0.5	-	5	31	0.1	0.05	0.09	0.05	29.5	6.9	202	1	2.3	0.93	3.5	
2014-DD-056	JGT-02	29.89	38.2	Granite	9.07	0.03	0.49	0.5	-	5	27	0.5	0.04	0.15	0.04	31.3	1.8	180	1.06	1.4	0.8	3.4	
2014-DD-057	JGT-02	451.14	459.98	Granite	9.50	0.05	0.67	1	-	5	23	0.5	0.08	0.17	0.05	45.3	2.1	186	2.66	1.3	1.04	4.5	
2014-DD-058	JGT-02	244.19	252.39	Granite	9.55	0.07	0.38	0.5	-	5	13	0.5	0.05	0.1	0.04	16.8	1.3	189	0.76	2	0.63	2.1	
2014-DD-059	JGT-02	377.69	383.33	Granite	9.50	0.05	0.45	0.5	-	5	13	0.5	0.04	0.09	0.03	25.1	1.4	180	1.11	1.4	0.72	2.5	
2014-DD-060	JGT-02	307	313.09	Granite	9.48	0.05	0.7	0.5	-	5	22	0.5	0.05	0.14	0.04	44.8	3.2	169	1.88	7.5	1.18	4.7	
Median					9.3	0.04	0.49	1.0	-	5	20	0.5	0.08	0.15	0.045	29.3	1.8	193	1.1	2.3	0.9	3.2	
Minimum					8.1	0.01	0.38	0.5	-	5	13	0.1	0.04	0.06	0.02	2.6	1.2	150	0.19	1.3	0.40	1.8	
Maximum					9.6	0.16	4.2	14.0	-	60	457	0.80	0.39	0.38	0.4	46.2	25	238	8.01	44	5.0	14.7	
Count					30	30	30	30	0	30	30	30	30	30	30	30	30	30	30	30	30	30	30
Kimberlite																							
Beartooth																							
64	BCD-01	49m	49	Kimberlite	8.1	0.1	0.86	2.5	-	-	550	0.25	2.5	1.0	0.5	-	74	458	-	9.0	4.8	-	
64	BCD-01	49m	49	Kimberlite	-	0.1	0.83	2.5	-	-	540	0.25	2.5	1.0	0.5	-	73	435	-	8.0	4.8	-	
65	BCD-01	186m	186	Kimberlite	8.6	0.1	0.78	2.5	-	-	660	0.25	2.5	1.6	0.5	-	59	384	-	10	4.1	-	
66	BCD-04	100m	100	Kimberlite	8.3	0.1	1.5	5.0	-	-	930	0.50	2.5	2.3	0.5	-	46	353	-	24	4.2	-	
67	BCD-04	190m	190	Kimberlite	8.5	0.1	0.89	2.5	-	-	820	0.25	2.5	1.5	0.5	-	66	389	-	9.0	4.6	-	
Median					8.4	0.1	0.86	2.5	-	-	660	0.25	2.5	1.5	0.5	-	66	389	-	9.0	4.6	-	
Minimum					8.1	0.1	0.78	2.5	-	-	540	0.25	2.5	1.0	0.5	-	46	353	-	8.0	4.1	-	
Maximum					8.6	0.1	1.5	5.0	-	-	930	0.50	2.5	2.3	0.5	-	74	458	-	24	4.8	-	
Count					4	5	5	5	0	0	5	5	5	5	5	0	5	5	0	5	5	0	
Fox																							
FUC 3-3 - 30	FUC 3-3	30	30.3	Kimberlite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 35	FUC 3-3	35	35.3	Kimberlite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 40	FUC 3-3	40	40.3	Kimberlite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 66.1	F1-1	66.1	66.2	Kimberlite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 66.2	F1-1	66.2	66.3	Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 72	F1-1	72	74	Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 94	F1-1	94	96	Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 110	F1-1	110	112	Kimberlite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 116	F1-1	116	118	Kimberlite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 122	F1-1	122	124	Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 158	F1-1	158	160	Kimberlite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 160	F1-1	160	162	Kimberlite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 184	F1-1	184	186	Kimberlite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 186	F1-1	186	188	Kimberlite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Kimberlite (continued)																						
Fox (continued)																						
F1-1 - 196	F1-1	196	198	Kimberlite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
F1-1 - 210	F1-1	210	212	Kimberlite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
F1-1 - 216	F1-1	216	218	Kimberlite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 4-3 - 151.5	FUC 4-3	151.5	155.2	Kimberlite	8.8	0.2	4.3	0.5	-	-	1,570	1.0	1	3.6	0.25	-	50	549	-	47	4.2	-
F19 - 176	F19	176	177	Kimberlite	8.9	0.1	3.7	2.0	-	-	1,070	0.50	1	3.4	0.50	-	54	344	-	34	4.0	-
F19 - 122	F19	122	123	Kimberlite	8.6	0.1	3.7	1.0	-	-	1,480	1.0	1	4.3	0.25	-	45	351	-	33	3.6	-
F17 - 200	F17	200	201	Kimberlite	8.6	0.1	3.7	0.5	-	-	1,220	0.50	1	3.8	0.50	-	61	363	-	36	4.4	-
F17 - 100	F17	100	101	Kimberlite	8.3	0.1	5.6	5.0	-	-	1,410	1.5	1	2.4	1.0	-	26	239	-	27	3.3	-
FWK405-13-1	-	-	-	Kimberlite	7.4	0.25	4.9	8.0	-	-	320	1.4	1	2.4	0.80	-	27	220	-	28	3.2	-
FWK405-13-2	-	-	-	Kimberlite	7.5	0.25	5.4	13	-	-	1,300	1.5	1	3.6	0.70	-	27	227	-	27	3.3	-
FK-390-20-1	-	-	-	Kimberlite	8.0	0.25	3.5	5.0	-	-	1,600	1.0	1	3.4	0.25	-	41	540	-	35	3.7	-
FK-390-20-2	-	-	-	Kimberlite	8.0	0.25	3.4	6.0	-	-	1,700	0.90	1	3.6	0.25	-	44	592	-	37	3.7	-
FK-375-09R1-1	-	-	-	Kimberlite	8.3	0.25	3.3	7.0	-	-	1,550	0.90	1	3.5	0.25	-	45	548	-	35	3.7	-
FK-375-09R1-2	-	-	-	Kimberlite	8.3	0.25	3.3	9.0	-	-	1,530	0.90	1	3.4	0.25	-	45	552	-	38	3.6	-
FK-375-13-1	-	-	-	Kimberlite	8.4	0.25	4.6	9.0	-	-	1,160	1.1	1	2.9	0.25	-	32	421	-	31	3.3	-
FK-375-13-2	-	-	-	Kimberlite	8.3	0.25	3.8	10	-	-	1,400	0.90	1	3.3	0.25	-	41	476	-	36	3.6	-
FK-375-21-1	-	-	-	Kimberlite	8.2	0.25	4.4	6.0	-	-	1,310	1.1	1	2.8	0.25	-	30	428	-	34	3.3	-
FK-375-21-2	-	-	-	Kimberlite	8.1	0.25	4.0	5.0	-	-	1,380	1.1	1	3.2	0.25	-	32	452	-	36	3.4	-
FK-375-23-1	-	-	-	Kimberlite	8.3	0.25	4.3	2.5	-	-	1,480	1.1	1	4.1	0.25	-	34	483	-	35	3.3	-
FK-375-23-2	-	-	-	Kimberlite	8.1	0.25	3.9	2.5	-	-	1,540	1.0	1	3.9	0.25	-	36	559	-	37	3.5	-
FK-375-23-3	-	-	-	Kimberlite	8.3	0.25	3.9	2.5	-	-	1,560	1.0	1	3.7	0.25	-	36	527	-	36	3.4	-
FK-375-23-4	-	-	-	Kimberlite	8.4	0.25	3.4	6.0	-	-	1,460	0.90	1	3.9	0.25	-	38	642	-	37	3.5	-
FK-375-29-1	-	-	-	Kimberlite	8.2	0.25	3.2	2.5	-	-	1,420	0.80	1	3.3	0.25	-	34	500	-	34	3.2	-
FK-375-29-2	-	-	-	Kimberlite	8.2	0.25	3.5	2.5	-	-	1,540	0.90	1	3.8	0.25	-	39	540	-	37	3.5	-
FK-375-29-3	-	-	-	Kimberlite	8.3	0.25	3.2	2.5	-	-	1,750	0.90	1	4.2	0.25	-	39	559	-	38	3.4	-
FK-375-29-4	-	-	-	Kimberlite	8.2	0.25	3.1	2.5	-	-	1,700	0.90	1	3.7	0.25	-	37	558	-	38	3.4	-
FK-375-34-1	-	-	-	Kimberlite	8.3	0.25	4.1	8.0	-	-	1,480	1.1	1	3.0	0.25	-	32	537	-	35	3.5	-
FK-375-34-2	-	-	-	Kimberlite	8.3	0.25	3.9	7.0	-	-	1,610	1.1	1	3.6	0.25	-	38	563	-	36	3.6	-
FK-375-34-3	-	-	-	Kimberlite	8.3	0.25	4.3	2.5	-	-	1,520	1.0	1	3.3	0.25	-	34	457	-	41	3.4	-
FK-375-34-4	-	-	-	Kimberlite	8.3	0.25	3.6	2.5	-	-	1,380	1.0	1	3.4	0.25	-	33	491	-	32	3.3	-
FK-375-35-1	-	-	-	Kimberlite	8.3	0.25	3.7	5.0	-	-	1,510	0.90	1	3.5	0.25	-	38	499	-	35	3.5	-
FK-375-35-2	-	-	-	Kimberlite	8.3	0.25	3.5	2.5	-	-	1,340	0.90	1	3.2	0.25	-	36	469	-	34	3.3	-
FK-375-35-3	-	-	-	Kimberlite	8.3	0.25	3.8	2.5	-	-	1,500	0.90	1	3.4	0.25	-	37	491	-	35	3.4	-
FK-375-35-4	-	-	-	Kimberlite	8.4	0.25	3.9	2.5	-	-	1,340	0.90	1	3.3	0.25	-	34	476	-	33	3.4	-
FWK-375-12-01	-	-	-	Kimberlite	8.1	0.25	3.9	9.0	-	-	1,280	1.0	1	3.2	0.25	-	35	471	-	33	3.3	-
FWK-375-12-02	-	-	-	Kimberlite	8.4	0.25	3.5	8.0	-	-	1,460	0.90	1	3.6	0.25	-	41	586	-	39	3.6	-
FWK-375-14KB1-	-	-	-	Kimberlite	8.6	0.25	3.4	7.0	-	-	1,500	0.90	1	3.2	0.25	-	39	483	-	34	3.4	-
FWK-375-14KB2-	-	-	-	Kimberlite	8.4	0.25	4.2	2.5	-	-	1,760	1.1	1	3.9	0.25	-	45	575	-	39	4.1	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Kimberlite (continued)																						
Fox (continued)																						
FWK-375-14KB3-	-	-	-	Kimberlite	8.4	0.25	3.5	2.5	-	-	1,700	1.0	1	3.7	0.25	-	41	618	-	34	3.8	-
FWK-375-14KB4-	-	-	-	Kimberlite	8.5	0.25	3.8	9.0	-	-	1,640	1.1	1	3.3	0.25	-	34	467	-	30	3.4	-
FWK-375-15kb-1	-	-	-	Kimberlite	8.4	0.25	3.8	2.5	-	-	1,580	1.0	1	3.7	0.25	-	41	636	-	38	3.7	-
FWK-375-15kb-2	-	-	-	Kimberlite	8.5	0.25	3.7	11	-	-	1,680	1.0	1	3.8	0.25	-	42	596	-	40	3.8	-
FWK-375-15kb-3	-	-	-	Kimberlite	8.3	0.25	4.0	2.5	-	-	1,560	1.1	1	3.8	0.25	-	40	543	-	38	3.7	-
FWK-375-15kb-4	-	-	-	Kimberlite	8.3	0.25	4.0	5.0	-	-	1,580	1.1	1	3.8	0.25	-	39	534	-	37	3.6	-
FWK-375-38-1	-	-	-	Kimberlite	8.7	0.25	3.8	2.5	-	-	1,680	0.90	1	3.6	0.25	-	43	586	-	38	3.7	-
FWK-375-38-2	-	-	-	Kimberlite	8.6	0.25	3.4	2.5	-	-	1,560	0.80	1	3.6	0.25	-	42	533	-	40	3.6	-
FWK-375-38-3	-	-	-	Kimberlite	8.7	0.25	3.6	2.5	-	-	1,560	0.80	1	4.1	0.25	-	43	557	-	44	3.8	-
FWK-375-38-4	-	-	-	Kimberlite	8.4	0.25	3.5	5.0	-	-	1,650	0.90	1	3.6	0.25	-	43	570	-	40	3.7	-
FWK-375-36-04 6-OCT-04	-	-	-	Kimberlite	7.4	0.7	4.4	2.5	-	-	1,540	1.0	2	3.2	0.25	-	40	580	-	37	3.8	-
FWK-375-36-03 6-OCT-04	-	-	-	Kimberlite	7.5	0.25	3.9	2.5	-	-	1,800	0.90	1	3.5	0.25	-	46	600	-	38	3.9	-
FWK-375-36-02 6-OCT-04	-	-	-	Kimberlite	8.0	0.25	4.1	8.0	-	-	1,800	1.0	1	3.3	0.25	-	42	589	-	37	3.8	-
FWK-375-36-01 6-OCT-04	-	-	-	Kimberlite	7.8	0.25	3.8	2.5	-	-	1,730	0.90	1	3.5	0.25	-	50	701	-	40	4.0	-
FWK-360-29-02 26-DEC-04	-	-	-	Kimberlite	7.6	0.25	4.1	7.0	-	-	1,340	1.0	1	2.7	0.25	-	36	480	-	32	3.4	-
FWK-360-29-02 1-JAN-05	-	-	-	Kimberlite	7.8	0.25	4.2	7.0	-	-	1,490	1.1	1	3.5	0.25	-	42	607	-	36	3.9	-
FWK-360-29-01 26-DEC-04	-	-	-	Kimberlite	7.6	0.25	4.2	2.5	-	-	1,560	1.1	1	3.3	0.25	-	39	572	-	35	3.7	-
FWK-360-29-01 1-JAN-05	-	-	-	Kimberlite	7.8	0.6	3.7	2.5	-	-	1,640	0.90	1	4.2	0.25	-	46	715	-	38	3.8	-
FWK-360-24-04 19-DEC-04	-	-	-	Kimberlite	7.4	0.7	3.7	5.0	-	-	1,700	0.90	1	3.6	0.25	-	43	648	-	36	3.7	-
FWK-360-24-03 19-DEC-04	-	-	-	Kimberlite	7.7	0.25	3.8	2.5	-	-	1,920	0.90	1	3.8	0.25	-	45	726	-	42	3.9	-
FWK-360-24-02 19-DEC-04	-	-	-	Kimberlite	7.7	0.25	3.7	2.5	-	-	1,660	0.90	1	3.6	0.25	-	45	635	-	36	3.8	-
FWK-360-24-01 19-DEC-04	-	-	-	Kimberlite	7.4	0.25	3.8	8.0	-	-	1,680	1.0	1	3.6	0.25	-	45	659	-	38	3.9	-
FWK-360-14-04 3-DEC-04	-	-	-	Kimberlite	7.8	0.25	3.6	2.5	-	-	1,320	0.90	1	3.5	0.25	-	47	684	-	37	3.8	-
FWK-360-14-03 3-DEC-04	-	-	-	Kimberlite	8.1	0.25	3.5	2.5	-	-	1,280	0.90	1	3.5	0.25	-	48	641	-	35	3.9	-
FWK-360-14-02 3-DEC-04	-	-	-	Kimberlite	8.0	0.25	4.2	2.5	-	-	1,640	1.0	1	3.8	0.25	-	41	603	-	36	3.7	-
FWK-360-14-01 3-DEC-04	-	-	-	Kimberlite	7.7	0.25	3.6	2.5	-	-	1,310	1.0	1	3.5	0.25	-	44	628	-	34	3.7	-
FWK-360-09-02 22-NOV-04	-	-	-	Kimberlite	8.1	0.25	3.8	6.0	-	-	1,720	1.0	2	3.8	0.25	-	38	567	-	36	3.6	-
FWK-360-09-01 22-NOV-04	-	-	-	Kimberlite	8.1	0.25	3.8	2.5	-	-	1,660	1.0	1	3.9	0.25	-	42	606	-	38	3.7	-
FWK-360-07-02 12-NOV-04	-	-	-	Kimberlite	8.3	0.25	3.9	2.5	-	-	1,840	1.0	1	3.9	0.25	-	46	650	-	40	3.9	-
FWK-360-07-01 12-NOV-04	-	-	-	Kimberlite	8.0	0.25	5.1	2.5	-	-	1,660	1.2	1	3.4	0.25	-	34	438	-	34	3.6	-
FWK-360-05-04 29-OCT-04	-	-	-	Kimberlite	7.1	0.25	5.2	16	-	-	1,150	1.3	1	3.0	0.25	-	36	394	-	40	4.2	-
FWK-360-05-03 29-OCT-04	-	-	-	Kimberlite	7.5	0.25	4.1	2.5	-	-	1,230	1.0	2	2.5	0.25	-	35	475	-	36	3.7	-
FWK-360-05-02 29-OCT-04	-	-	-	Kimberlite	7.7	0.25	3.8	11	-	-	1,620	0.90	1	3.4	0.25	-	46	564	-	35	3.8	-
FWK-360-05-01 29-OCT-04	-	-	-	Kimberlite	7.7	0.25	4.9	8.0	-	-	1,580	1.1	1	3.1	0.25	-	38	483	-	39	3.8	-
FWK-345-33-04 8-Apr-05	-	-	-	Kimberlite	8.3	0.5	3.7	2.5	-	-	1,600	1.0	1	3.6	0.25	-	43	567	-	37	3.9	-
FWK-345-33-03 8-Apr-05	-	-	-	Kimberlite	8.4	0.25	3.7	12	-	-	1,600	1.0	1	3.6	0.25	-	43	591	-	38	3.8	-
FWK-345-33-02 8-Apr-05	-	-	-	Kimberlite	8.5	0.25	3.7	12	-	-	1,680	0.90	1	4.0	0.25	-	45	527	-	37	4.2	-
FWK-345-33-01 8-Apr-05	-	-	-	Kimberlite	8.2	0.25	3.9	2.5	-	-	1,390	1.0	1	4.6	0.25	-	40	461	-	37	4.1	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To	General Rock Type	Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
					unit	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																						
Fox (continued)																						
FWK-345-29-04- 8-Apr-05	-	-	-	Kimberlite	8.3	0.5	3.6	11	-	-	1,640	1.0	1	3.8	0.25	-	42	542	-	36	3.7	-
FWK-345-29-03- 8-Apr-05	-	-	-	Kimberlite	8.4	0.25	3.8	2.5	-	-	1,560	1.0	1	3.5	0.25	-	38	493	-	32	3.7	-
FWK-345-29-02- 8-Apr-05	-	-	-	Kimberlite	8.3	0.25	3.5	2.5	-	-	1,640	1.0	1	3.6	0.25	-	40	563	-	37	3.8	-
FWK-345-29-01- 8-Apr-05	-	-	-	Kimberlite	7.9	0.25	4.0	2.5	-	-	1,100	1.1	1	3.1	0.50	-	38	516	-	40	3.8	-
FWK-345-24-06-26-Mar-05	-	-	-	Kimberlite	8.6	0.25	3.6	2.5	-	-	1,570	0.80	1	3.6	0.25	-	40	524	-	38	3.8	-
FWK-345-24-05-26-Mar-05	-	-	-	Kimberlite	8.1	0.25	3.8	10	-	-	1,440	0.90	1	3.2	0.25	-	36	499	-	35	3.6	-
FWK-345-24-04-26-Mar-05	-	-	-	Kimberlite	8.1	0.25	4.0	10	-	-	1,050	1.0	1	3.3	0.25	-	37	511	-	38	3.8	-
FWK-345-24-03-26-Mar-05	-	-	-	Kimberlite	8.7	0.25	3.9	5.0	-	-	1,620	1.0	1	3.5	0.25	-	42	552	-	38	4.0	-
FWK-345-24-02-26-Mar-05	-	-	-	Kimberlite	8.5	0.25	3.8	2.5	-	-	1,630	0.90	1	3.6	0.25	-	42	567	-	40	3.9	-
FWK-345-24-01-26-Mar-05	-	-	-	Kimberlite	8.5	0.25	3.8	5.0	-	-	1,630	1.0	1	4.3	0.25	-	39	556	-	37	3.7	-
FWK-345-20-04- 8-Mar-05	-	-	-	Kimberlite	8.7	0.25	3.2	2.5	-	-	1,190	0.80	1	3.3	0.25	-	47	470	-	38	3.8	-
FWK-345-20-03- 8-Mar-05	-	-	-	Kimberlite	8.3	0.25	3.9	2.5	-	-	1,190	1.0	1	2.3	0.25	-	27	333	-	27	2.9	-
FWK-345-20-02- 8-Mar-05	-	-	-	Kimberlite	8.7	0.25	3.5	5.0	-	-	1,340	0.80	1	3.4	0.25	-	45	443	-	36	3.9	-
FWK-345-20-01- 8-Mar-05	-	-	-	Kimberlite	8.3	0.25	3.4	2.5	-	-	1,200	0.80	1	3.4	0.25	-	47	507	-	38	4.1	-
FWK-345-15-02 9-FEB-05	-	-	-	Kimberlite	8.1	0.25	4.1	9.0	-	-	1,330	1.1	1	3.3	0.25	-	32	486	-	33	3.3	-
FWK-345-15-01 9-FEB-05	-	-	-	Kimberlite	8.0	0.25	3.7	2.5	-	-	1,720	1.0	1	4.0	0.25	-	45	653	-	39	4.0	-
FWK-345-13-02 18-FEB-05	-	-	-	Kimberlite	8.0	0.25	4.4	9.0	-	-	1,490	1.2	2	3.2	0.60	-	37	478	-	41	3.8	-
FWK-345-13-01 18-FEB-05	-	-	-	Kimberlite	8.0	0.25	4.1	2.5	-	-	1,410	1.2	1	3.2	0.70	-	31	397	-	36	3.3	-
FWK-345-08-04 7-FEB-05	-	-	-	Kimberlite	8.1	0.25	3.9	8.0	-	-	1,690	1.2	1	3.3	0.60	-	34	487	-	34	3.3	-
FWK-345-08-03 7-FEB-05	-	-	-	Kimberlite	7.9	0.25	4.6	14	-	-	1,360	1.1	1	3.0	0.50	-	32	420	-	33	3.5	-
FWK-345-08-02 7-FEB-05	-	-	-	Kimberlite	8.0	0.25	4.1	2.5	-	-	1,520	1.1	1	3.3	0.25	-	31	446	-	35	3.2	-
FWK-345-08-01 7-FEB-05	-	-	-	Kimberlite	8.1	0.25	4.1	2.5	-	-	1,600	1.2	1	3.1	0.70	-	33	448	-	33	3.3	-
FWK-345-07-02 4-FEB-05	-	-	-	Kimberlite	8.2	0.25	3.7	2.5	-	-	1,570	1.1	1	3.3	0.25	-	34	530	-	33	3.3	-
FWK-345-07-01 4-FEB-05	-	-	-	Kimberlite	8.0	0.25	3.9	2.5	-	-	1,750	1.1	1	3.5	0.70	-	38	611	-	36	3.5	-
FWK-345-06-02 1-FEB-05	-	-	-	Kimberlite	7.9	0.25	4.5	2.5	-	-	1,420	1.3	1	2.8	0.25	-	29	390	-	30	3.1	-
FWK-345-06-01 1-FEB-05	-	-	-	Kimberlite	8.0	0.25	4.8	5.0	-	-	1,520	1.3	1	3.2	0.80	-	32	444	-	34	3.3	-
FWK-345-04-02 30-JAN-05	-	-	-	Kimberlite	8.2	0.25	3.6	2.5	-	-	1,550	1.0	1	3.8	0.25	-	40	584	-	35	3.7	-
FWK-345-04-01 30-JAN-05	-	-	-	Kimberlite	8.1	0.25	4.1	2.5	-	-	1,480	1.0	1	3.8	0.25	-	38	564	-	41	3.9	-
FWK-345-03-04 28-JAN-05	-	-	-	Kimberlite	7.8	0.25	4.1	6.0	-	-	1,380	0.90	1	4.0	0.25	-	45	524	-	56	4.5	-
FWK-345-03-03 28-JAN-05	-	-	-	Kimberlite	7.8	0.25	3.5	2.5	-	-	1,790	0.90	1	3.8	0.25	-	44	576	-	40	3.8	-
FWK-345-03-02 24-JAN-05	-	-	-	Kimberlite	8.1	0.25	3.8	7.0	-	-	1,710	1.0	1	3.7	0.25	-	41	561	-	37	3.6	-
FWK-345-03-01 24-JAN-05	-	-	-	Kimberlite	8.0	0.25	5.4	2.5	-	-	1,190	1.2	1	2.7	0.25	-	51	638	-	43	3.9	-
FWK-345-02-02 20-JAN-05	-	-	-	Kimberlite	8.1	0.25	3.6	6.0	-	-	1,430	0.90	1	3.2	0.25	-	45	525	-	35	3.8	-
FWK-345-02-01 20-JAN-05	-	-	-	Kimberlite	8.2	0.25	4.3	2.5	-	-	1,270	0.90	1	3.3	0.25	-	39	453	-	37	3.6	-
FWK-345-01-04 14-JAN-05	-	-	-	Kimberlite	7.8	0.25	4.3	7.0	-	-	1,340	1.0	1	2.9	0.25	-	41	489	-	37	3.7	-
FWK-345-01-03 14-JAN-05	-	-	-	Kimberlite	7.8	0.25	5.1	13	-	-	1,170	0.80	1	2.8	0.25	-	34	424	-	28	3.2	-
FWK-345-01-02 14-JAN-05	-	-	-	Kimberlite	7.6	0.25	4.3	13	-	-	1,250	1.1	1	2.8	0.25	-	37	488	-	34	3.8	-
FWK-345-01-01 14-JAN-05	-	-	-	Kimberlite	7.8	0.25	4.8	5.0	-	-	1,130	0.90	1	2.3	0.25	-	31	400	-	31	3.2	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm	
Kimberlite (continued)																							
Fox (continued)																							
FWK-330-14-08	-	-	-	Kimberlite	8.3	0.25	4.0	11	-	-	1,590	1.1	1	3.7	0.25	-	35	475	-	34	3.5	-	
FWK-330-14-07	-	-	-	Kimberlite	8.2	0.25	4.1	9.0	-	-	1,500	1.1	1	3.8	0.25	-	34	502	-	36	3.7	-	
FWK-330-14-06	-	-	-	Kimberlite	8.4	0.25	3.9	8.0	-	-	1,710	1.1	1	3.5	0.25	-	39	526	-	36	3.7	-	
FWK-330-14-05	-	-	-	Kimberlite	8.5	0.25	3.8	2.5	-	-	1,850	1.1	1	3.7	0.25	-	39	518	-	36	3.6	-	
FWK-330-14-04	-	-	-	Kimberlite	8.5	0.25	3.6	6.0	-	-	1,850	1.0	1	3.4	0.25	-	35	542	-	32	3.4	-	
FWK-330-14-03	-	-	-	Kimberlite	8.3	0.25	3.8	12	-	-	1,700	1.1	1	3.0	0.25	-	34	499	-	31	3.3	-	
FWK-330-14-02	-	-	-	Kimberlite	8.5	0.25	3.8	9.0	-	-	1,790	1.1	1	3.9	0.25	-	36	558	-	35	3.5	-	
FWK-330-14-01	-	-	-	Kimberlite	8.4	0.25	3.7	13	-	-	1,810	1.0	1	3.4	0.25	-	38	759	-	38	3.9	-	
FWK-330-05-04	-	-	-	Kimberlite	8.4	0.25	4.4	2.5	-	-	1,380	1.0	1	3.6	0.25	-	32	501	-	32	3.3	-	
FWK-330-05-04	-	-	-	Kimberlite	8.3	0.25	3.6	10	-	-	1,770	1.0	1	3.9	0.25	-	37	553	-	34	3.5	-	
FWK-330-05-03	-	-	-	Kimberlite	8.4	0.25	4.1	7.0	-	-	1,710	1.0	1	3.8	0.25	-	39	557	-	39	3.8	-	
FWK-330-05-03	-	-	-	Kimberlite	8.3	0.25	3.8	6.0	-	-	1,150	1.1	1	4.0	0.25	-	41	527	-	35	3.8	-	
FWK-330-05-02	-	-	-	Kimberlite	8.5	0.25	3.8	2.5	-	-	1,750	0.90	1	3.7	0.25	-	43	591	-	46	4.0	-	
FWK-330-05-02	-	-	-	Kimberlite	8.3	0.25	3.4	6.0	-	-	1,760	0.90	1	3.8	0.25	-	44	564	-	35	3.8	-	
FWK-330-05-01	-	-	-	Kimberlite	8.5	0.25	3.9	2.5	-	-	1,830	1.0	1	3.8	0.25	-	42	591	-	38	3.8	-	
FWK-330-05-01	-	-	-	Kimberlite	8.3	0.25	4.0	2.5	-	-	1,450	1.1	1	3.8	0.25	-	34	497	-	33	3.4	-	
FWK-330-01-04	-	-	-	Kimberlite	8.3	0.25	3.5	2.5	-	-	1,710	1.0	1	5.0	0.25	-	38	463	-	33	3.6	-	
FWK-330-01-03	-	-	-	Kimberlite	8.4	0.25	3.5	2.5	-	-	1,770	0.90	1	4.3	0.25	-	40	546	-	40	3.9	-	
FWK-330-01-02	-	-	-	Kimberlite	8.4	0.25	3.8	2.5	-	-	1,550	1.1	1	2.5	0.50	-	32	393	-	29	3.1	-	
FWK-330-01-02	-	-	-	Kimberlite	8.3	0.25	3.9	2.5	-	-	1,600	1.1	1	3.2	0.25	-	36	513	-	33	3.5	-	
FWK-330-01-01	-	-	-	Kimberlite	8.4	0.25	3.9	2.5	-	-	1,740	1.1	1	3.9	0.25	-	39	531	-	33	3.6	-	
FWK-330-01-01	-	-	-	Kimberlite	8.5	0.25	3.5	2.5	-	-	1,910	1.0	1	4.0	0.25	-	42	535	-	36	3.9	-	
FWK-315-02-06	-	-	-	Kimberlite	8.6	0.25	4.2	10	-	-	1,810	0.90	1	5.1	0.25	-	39	511	-	47	4.1	-	
FWK-315-02-05	-	-	-	Kimberlite	8.4	0.25	5.0	7.0	-	-	1,470	1.0	1	4.3	0.25	-	37	459	-	60	3.7	-	
FWK-315-02-04	-	-	-	Kimberlite	8.6	0.25	4.9	6.0	-	-	1,820	1.0	1	5.0	0.25	-	38	499	-	42	3.8	-	
FWK-315-02-03	-	-	-	Kimberlite	8.8	0.25	4.3	6.0	-	-	1,600	1.0	1	4.5	0.25	-	39	508	-	35	3.8	-	
FWK-315-02-02	-	-	-	Kimberlite	8.6	0.25	3.8	2.5	-	-	1,570	0.90	1	4.3	0.25	-	42	491	-	34	3.6	-	
FWK-315-02-01	-	-	-	Kimberlite	8.5	0.25	3.6	2.5	-	-	1,520	0.90	1	4.3	0.25	-	41	535	-	36	3.7	-	
FWK-315-01-04	-	-	-	Kimberlite	8.3	0.25	3.4	9.0	-	-	2,000	1.0	1	4.2	0.25	-	38	559	-	35	3.6	-	
FWK-315-01-03	-	-	-	Kimberlite	8.2	0.25	3.5	10	-	-	1,510	1.0	1	3.7	0.25	-	43	510	-	35	3.8	-	
FWK-315-01-02	-	-	-	Kimberlite	8.3	0.25	3.5	7.0	-	-	1,480	0.90	1	3.9	0.25	-	42	521	-	34	3.7	-	
FWK-315-01-01	-	-	-	Kimberlite	8.3	0.25	3.6	9.0	-	-	1,860	1.0	1	3.8	0.25	-	43	584	-	38	3.9	-	
FWK-285-35-01	-	-	-	Kimberlite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FWK-285-36-01	-	-	-	Kimberlite	7.9	0.25	3.9	12	-	-	1,720	1.0	1	3.5	0.90	-	40	546	-	40	3.9	-	
FWK-285-36-02	-	-	-	Kimberlite	8.1	0.25	4.0	12	-	-	1,630	1.0	1	3.2	0.25	-	39	493	-	36	3.7	-	
FWK-285-36-03	-	-	-	Kimberlite	7.8	0.25	4.4	15	-	-	1,620	1.1	1	3.1	0.25	-	33	418	-	38	3.5	-	
FWK-285-36-04	-	-	-	Kimberlite	8.1	0.25	3.8	8.0	-	-	1,550	1.0	1	3.2	0.50	-	34	401	-	29	3.3	-	
Fox-260-WK-3a	-	-	-	Kimberlite	8.8	0.25	3.4	6.0	-	-	2,160	0.90	1	4.8	0.25	-	40	705	-	38	3.7	10	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm
Kimberlite (continued)																						
Fox (continued)																						
Fox-260-WK-2a 26-Jan-09	-	-	-	Kimberlite	8.9	0.25	6.1	2.5	-	-	1,010	1.2	1	3.8	0.25	-	21	359	-	33	3.0	10
Fox-260-WK-1a 26-Jan-09	-	-	-	Kimberlite	9.2	0.25	7.7	2.5	-	-	750	1.3	1	2.9	0.25	-	15	127	-	16	3.1	30
Median					8.3	0.25	3.8	3.8	-	-	1,560	1.0	1	3.6	0.25	-	39	527	-	36	3.7	10
Minimum					7.1	0.1	3.1	0.5	-	-	320	0.50	1	2.3	0.25	-	15	127	-	16	2.9	10
Maximum					9.8	0.7	7.7	16	-	-	2,160	1.5	2	5.1	1.0	-	61	759	-	60	4.5	30
Count					168	150	150	150	0	0	150	150	150	150	150	0	150	150	0	150	150	3
Koala																						
KK-DUMP-1A	-	-	-	Kimberlite	7.9	0.25	1.4	2.5	-	-	350	0.25	1	1.6	0.25	-	89	1,120	-	15	4.7	-
KK-DUMP-2A	-	-	-	Kimberlite	7.7	0.25	1.8	10	-	-	520	0.50	1	1.7	0.25	-	90	1,025	-	21	5.0	-
KK-DUMP-3A-1	-	-	-	Kimberlite	8.0	0.25	1.6	2.5	-	-	510	0.50	1	1.7	0.25	-	95	803	-	16	4.9	-
KK-DUMP-3A-2	-	-	-	Kimberlite	8.0	0.25	1.5	2.5	-	-	490	0.50	1	1.6	0.25	-	91	861	-	16	4.6	-
KK-DUMP-4A	-	-	-	Kimberlite	7.8	0.25	1.5	2.5	-	-	480	0.50	1	2.3	0.25	-	86	896	-	17	4.2	-
KK-DUMP-5A	-	-	-	Kimberlite	7.3	0.25	2.0	5.0	-	-	520	0.50	1	1.2	0.25	-	70	600	-	21	3.6	-
KWK-380-50-1	-	-	-	Kimberlite	8.2	0.5	4.5	8.0	-	-	1,370	0.80	2	2.0	0.50	-	42	441	-	31	3.7	-
KWK-380-50-2	-	-	-	Kimberlite	8.3	0.5	2.2	8.0	-	-	490	0.50	2	1.7	0.50	-	66	679	-	19	4.1	-
KWK-360-18-1A	-	-	-	Kimberlite	8.0	0.5	1.6	11	-	-	650	0.50	2	1.4	0.50	-	59	617	-	16	3.6	-
KWK-360-18-2A	-	-	-	Kimberlite	8.1	0.5	1.6	9.0	-	-	630	0.50	2	1.4	0.50	-	59	630	-	12	3.7	-
KWK-360-17-1A	-	-	-	Kimberlite	7.7	0.5	1.4	5.0	-	-	440	0.50	2	1.1	0.50	-	70	663	-	11	4.0	-
KWK-360-17-2A	-	-	-	Kimberlite	7.7	0.5	1.6	9.0	-	-	440	0.50	2	1.2	0.50	-	65	611	-	10	3.8	-
KWK-345-17-1	-	-	-	Kimberlite	8.0	0.5	1.7	10	-	-	640	0.50	2	1.4	0.50	-	60	644	-	13	3.7	-
KWK-345-17-2	-	-	-	Kimberlite	8.0	0.5	1.5	7.0	-	-	480	0.50	2	1.2	0.50	-	77	740	-	11	4.2	-
KWK-345-17-1A	-	-	-	Kimberlite	7.9	0.5	1.7	7.0	-	-	760	0.50	2	1.3	0.50	-	61	620	-	12	3.8	-
KWK-345-17-2A	-	-	-	Kimberlite	8.0	0.5	1.7	8.0	-	-	650	0.50	2	1.4	0.50	-	63	685	-	14	3.8	-
KWK-345-17-1A	-	-	-	Kimberlite	8.0	0.5	1.6	10	-	-	680	0.50	2	1.4	0.50	-	64	648	-	12	3.8	-
KWK-345-17-2A	-	-	-	Kimberlite	7.8	0.5	1.7	6.0	-	-	620	0.50	2	1.4	0.50	-	63	737	-	13	3.9	-
KWK-345-21-1A	-	-	-	Kimberlite	7.9	0.5	1.6	10	-	-	640	0.50	2	1.3	0.50	-	64	607	-	12	3.7	-
KWK-345-21-2A	-	-	-	Kimberlite	8.0	0.5	1.8	7.0	-	-	620	0.50	2	1.4	0.50	-	62	653	-	13	3.8	-
KS-280-04-1A	-	-	-	Kimberlite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-280-04-1B	-	-	-	Kimberlite	7.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Median					7.9	0.5	1.6	7.5	-	-	570	0.50	2	1.4	0.50	-	65	658	-	14	3.8	-
Minimum					7.3	0.25	1.4	2.5	-	-	350	0.25	1	1.1	0.25	-	42	441	-	10	3.6	-
Maximum					8.3	0.5	4.5	11	-	-	1,370	0.80	2	2.3	0.50	-	95	1,120	-	31	5.0	-
Count					22	20	20	20	0	0	20	20	20	20	20	0	20	20	0	20	20	0
Misery																						
MDC-10 149.47	-	-	-	Kimberlite	9.3	0.25	1.4	5.0	-	-	830	0.25	18	4.9	0.25	-	79	705	-	69	5.4	-
SRK MISERY 1	-	-	-	Kimberlite	7.8	0.25	5.6	30	-	-	90	0.50	6	1.0	0.50	-	40	332	-	49	4.1	-
SRK MISERY 2	-	-	-	Kimberlite	8.2	0.25	3.7	15	-	-	180	0.50	12	2.7	0.25	-	51	559	-	34	3.7	-
SRK MISERY 3	-	-	-	Kimberlite	9.1	0.25	2.1	5.0	-	-	1,470	0.50	18	3.6	0.25	-	65	727	-	34	3.9	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Kimberlite (continued)																						
Misery (continued)																						
MK- 430-04-1A	-	-	-	Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK- 430-04-2A	-	-	-	Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK- 430-06-A1	-	-	-	Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK- 430-06-A2	-	-	-	Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK- 430-06-A3	-	-	-	Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK-400-52T-1a	-	-	-	Kimberlite	8.3	0.25	2.6	5.0	-	-	500	1.0	1	3.4	0.25	-	58	846	-	33	3.9	-
MWKB-380-20-1a	-	-	-	Kimberlite	8.5	0.25	5.6	15	-	-	2,380	1.5	1	1.1	0.25	-	29	478	-	28	3.4	-
MWKB-380-20-2a	-	-	-	Kimberlite	8.5	0.25	2.0	2.5	-	-	270	0.50	1	1.1	0.25	-	44	645	-	15	2.8	-
MGT-60 143.42-145.0	-	-	-	Kimberlite	5.1	0.3	1.2	19	1.3	10	141	-	0.3	0.29	1.3	-	13	58	-	37	2.2	4.0
MGT-60 308.0-309.85	-	-	-	Kimberlite	8.6	0.05	1.6	5.2	0.25	10	762	-	0.05	3.2	0.20	-	61	297	-	33	3.8	4.0
MGT-53 245-248	-	-	-	Kimberlite	8.2	0.05	1.6	5.8	0.25	10	421	-	0.05	2.2	0.30	-	54	239	-	24	3.5	4.0
MGT-54 297-300	-	-	-	Kimberlite	8.6	0.2	1.8	5.5	1.1	10	441	-	0.2	0.94	0.30	-	62	238	-	26	3.9	4.0
MGT-51 98.0-99.59	-	-	-	Kimberlite	8.5	0.1	1.2	9.2	0.25	10	1,652	-	0.05	6.0	0.05	-	68	515	-	35	4.0	4.0
MGT-51 113-116	-	-	-	Kimberlite	8.7	0.1	1.1	5.2	0.25	10	2,273	-	0.05	5.8	0.10	-	68	503	-	35	4.2	3.0
MGT-51 116-119	-	-	-	Kimberlite	8.8	0.1	1.1	5.4	2.3	10	2,333	-	0.05	5.7	0.05	-	69	498	-	33	4.3	3.0
MGT-51 119-122	-	-	-	Kimberlite	8.8	0.1	1.1	5.8	0.70	10	2,192	-	0.05	5.6	0.05	-	66	478	-	32	4.2	3.0
MGT-51 122-125	-	-	-	Kimberlite	8.5	0.1	1.0	4.9	1.0	10	1,825	-	0.05	5.9	0.05	-	65	472	-	32	4.1	3.0
MGT-64 255-258	-	-	-	Kimberlite	9.1	0.05	0.68	1.8	0.25	10	1,479	-	0.05	4.5	0.05	-	77	495	-	35	4.6	2.0
MGT-64 258-261	-	-	-	Kimberlite	8.9	0.05	0.92	2.0	0.25	10	2,163	-	0.05	5.1	0.05	-	73	537	-	29	4.5	3.0
MGT-64 261-264	-	-	-	Kimberlite	9.0	0.05	1.0	2.5	0.70	10	1,759	-	0.05	4.7	0.05	-	89	617	-	21	4.8	2.0
MGT-64 264-267	-	-	-	Kimberlite	8.9	0.1	1.0	2.2	1.7	10	2,229	-	0.05	4.4	0.05	-	90	641	-	43	5.0	3.0
MGT-64 267-270	-	-	-	Kimberlite	8.8	0.1	1.1	2.9	1.1	10	3,395	-	0.05	5.4	0.05	-	85	592	-	38	4.7	2.0
MGT-51 100-103	-	-	-	Kimberlite	8.4	0.05	1.5	14	12	10	1,605	-	0.2	5.2	0.05	-	73	459	-	40	4.3	3.0
MGT-51 103-106	-	-	-	Kimberlite	8.4	0.1	1.4	8.8	2.6	10	1,613	-	0.1	5.7	0.05	-	75	483	-	42	4.3	4.0
MGT-51 106-109	-	-	-	Kimberlite	8.4	0.1	1.8	15	4.7	10	1,338	-	0.2	5.6	0.20	-	69	475	-	46	4.2	5.0
MGT-52 283-285	-	-	-	Kimberlite	8.9	0.05	0.68	1.8	0.25	10	755	-	0.05	5.7	0.05	-	68	478	-	32	4.0	3.0
MGT-52 287-290	-	-	-	Kimberlite	8.6	0.2	2.4	10	1.9	20	320	-	0.2	3.8	0.40	-	53	195	-	45	4.0	6.0
MGT-54 294-296	-	-	-	Kimberlite	8.5	0.2	1.8	10	0.60	10	440	-	0.1	1.4	0.30	-	65	222	-	32	4.0	5.0
Median					8.5	0.1	1.4	5.4	0.85	10	1,470	0.50	0.1	4.5	0.20	-	66	483	-	34	4.1	3.0
Minimum					5.1	0.05	0.68	1.8	0.25	10	90	0.25	0.05	0.29	0.05	-	13	58	-	15	2.2	2.0
Maximum					9.3	0.3	5.6	30	12	20	3,395	1.5	18	6.0	1.3	-	90	846	-	69	5.4	6.0
Count					32	27	27	27	20	20	27	7	27	27	27	0	27	27	0	27	27	20
Pigeon																						
97-54	97-54	113	113	Kimberlite	8.8	0.1	2.0	10	-	-	7,000	0.25	2.5	9.3	0.5	-	39	123	-	87	5.3	-
97-54	97-54	117	117	Kimberlite	8.7	0.1	1.6	10	-	-	6,400	0.25	2.5	9.1	0.5	-	37	118	-	91	5.1	-
97-54	97-54	145	150	Kimberlite	8.7	0.1	2.4	10	-	-	5,640	0.25	2.5	7.7	0.5	-	38	126	-	74	5.1	-
97-54	97-54	172	174	Kimberlite	8.4	0.1	1.7	2.5	-	-	1,190	0.50	2.5	2.7	0.5	-	59	230	-	15	4.4	-
97-54	97-54	210	215	Kimberlite	8.9	0.1	2.0	2.5	-	-	1,470	0.25	2.5	2.8	0.5	-	67	557	-	40	5.2	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Kimberlite (continued)																						
Pigeon (continued)																						
97-54	97-54	310	310	Kimberlite	8.8	0.1	2.0	2.5	-	-	1,440	0.25	2.5	3.6	0.5	-	59	613	-	47	5.1	-
97-55	97-55	79	83	Kimberlite	7.6	0.1	2.1	2.5	-	-	1,490	0.25	2.5	3.6	0.5	-	59	616	-	47	5.1	-
97-55	97-55	137	137	Kimberlite	7.8	0.1	1.6	5.0	-	-	1,490	0.50	2.5	3.5	1.0	-	39	227	-	30	3.8	-
97-55	97-55	198	198	Kimberlite	8.2	0.1	1.7	2.5	-	-	380	0.25	2.5	1.7	0.5	-	65	306	-	30	4.8	-
94-07	94-07	120	120	Kimberlite	8.0	0.1	1.0	5.0	-	-	1,810	0.50	2.5	3.2	1.0	-	34	251	-	25	3.5	-
94-07	94-07	170	170	Kimberlite	8.1	0.1	1.7	2.5	-	-	610	0.50	2.5	1.6	0.5	-	61	236	-	19	4.6	-
94-07	94-07	225	225	Kimberlite	8.9	0.1	2.2	2.5	-	-	1,630	0.25	2.5	3.6	0.5	-	63	676	-	50	5.3	-
97-55	97-55	205	210	Kimberlite	8.9	0.1	2.0	2.5	-	-	1,320	0.25	2.5	3.4	0.5	-	64	519	-	43	5.2	-
97-55	97-55	250	250	Kimberlite	8.6	0.1	1.9	2.5	-	-	1,880	0.25	2.5	3.3	0.5	-	61	545	-	42	4.9	-
94-7 72-77	94-7	72	77	Kimberlite	-	-	9.8	5.0	-	-	570	1.5	1	0.79	0.25	-	22	109	-	48	4.1	-
94-7 77-80.2	94-7	77	80.2	Kimberlite	8.9	-	11	2.5	-	-	600	1.0	1	1.4	0.25	-	21	183	-	47	3.9	-
Median					8.7	0.1	2.0	2.5	-	-	1,480	0.25	2.5	3.3	0.5	-	59	244	-	45	5.0	-
Minimum					7.6	0.1	1.0	2.5	-	-	380	0.25	1	0.79	0.25	-	21	109	-	15	3.5	-
Maximum					8.9	0.1	11	10	-	-	7,000	1.5	2.5	9.3	1.0	-	67	676	-	91	5.3	-
Count					15	14	16	16	0	0	16	16	16	16	16	0	16	16	0	16	16	0
Sable																						
95-25	95-25	138	138	Kimberlite	8.1	0.1	1.2	2.5	-	-	410	0.50	2.5	1.7	1.0	-	59	234	-	15	4.4	-
95-25	95-25	297	297	Kimberlite	8.4	0.1	1.7	2.5	-	-	3,800	0.50	2.5	1.4	0.5	-	57	255	-	14	4.2	-
SDC-01	SDC-01	126	126	Kimberlite	8.0	0.1	1.4	2.5	-	-	1,300	0.50	2.5	2.1	0.5	-	59	286	-	24	4.4	-
SDC-03	SDC-03	132	132	Kimberlite	7.8	0.1	1.1	2.5	-	-	1,570	0.50	2.5	4.7	0.5	-	59	307	-	28	4.2	-
SDC-03	SDC-03	132	132	Kimberlite	7.8	0.1	1.1	2.5	-	-	1,590	0.50	2.5	4.8	0.5	-	61	316	-	29	4.3	-
SDC-03	SDC-03	266	266	Kimberlite	8.8	0.1	1.3	2.5	-	-	1,070	0.50	2.5	1.8	0.5	-	66	319	-	19	4.6	-
SDC-04	SDC-04	130	130	Kimberlite	8.1	0.1	1.3	2.5	-	-	1,220	0.50	2.5	1.8	0.5	-	66	286	-	20	4.7	-
SDC-06	SDC-06	155	155	Kimberlite	8.0	0.1	0.89	2.5	-	-	1,920	0.25	2.5	4.7	0.5	-	54	300	-	32	4.6	-
SDC-06	SDC-06	290	290	Kimberlite	8.9	0.1	1.5	2.5	-	-	1,620	0.50	2.5	3.4	0.5	-	41	237	-	26	3.6	-
SDC-08	SDC-08	126	126	Kimberlite	8.2	0.1	1.5	2.5	-	-	1,160	0.50	2.5	2.1	0.5	-	53	232	-	19	4.3	-
SDC-10	SDC-10	207	207	Kimberlite	8.7	0.1	1.4	2.5	-	-	1,560	0.50	2.5	2.7	1.0	-	58	271	-	18	4.4	-
SDC-12	SDC-12	423	423	Kimberlite	9.6	0.1	0.9	2.5	-	-	1,530	0.50	2.5	2.3	0.5	-	62	321	-	23	4.6	-
SDC-13	SDC-13	236	236	Kimberlite	8.8	0.1	1.3	2.5	-	-	1,160	0.50	2.5	2.3	0.5	-	63	296	-	29	4.8	-
SDC-08	SDC-08	16	126	Kimberlite	-	0.1	1.5	2.5	-	-	1,150	0.50	2.5	2.0	0.5	-	52	228	-	19	4.2	-
Median					8.2	0.1	1.3	2.5	-	-	1,415	0.50	2.5	2.2	0.5	-	59	286	-	22	4.4	-
Minimum					7.8	0.1	0.89	2.5	-	-	410	0.25	2.5	1.4	0.5	-	41	228	-	14	3.6	-
Maximum					9.6	0.1	1.7	2.5	-	-	3,800	0.50	2.5	4.8	1.0	-	66	321	-	32	4.8	-
Count					13	14	14	14	0	0	14	14	14	14	14	0	14	14	0	14	14	0

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Kimberlite (continued)																						
Jay																						
2014-DD-042	JGT-03	40.8	47.22	Kimberlite	7.72	0.46	1.75	6	-	20	544	0.6	0.11	3.02	0.64	78.9	43.1	255	1.04	28.8	3.12	4.4
2014-DD-054	JGT-02	63.4	64.04	Kimberlite	7.81	0.03	0.73	2	-	10	152	0.5	0.03	0.24	0.07	139	27.1	560	0.54	25.4	5.33	2.8
Median					7.8	0.245	1.2	4.0	-	15	348	0.55	0.07	1.6	0.355	108.95	35	408	0.79	27	4.2	3.6
Minimum					7.7	0.03	0.73	2.0	-	10	152	0.5	0.03	0.2	0.07	78.9	27	255	0.54	25	3.1	2.8
Maximum					7.8	0.46	1.8	6.0	-	20	544	0.60	0.11	3.0	0.6	139	43	560	1.04	29	5.3	4.4
Count					2	2	2	2	0	2	2	2	2	2	2	2	2	2	2	2	2	2
Coarse Processed Kimberlite																						
TP-SRK-0-0.7m	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-01-4m	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-02-0.07m	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-02-1.8m	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-02B-2.5m	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-04-0-0.5m	-	-	-	Coarse Processed Kimberlite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-04-3.0m	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-05-0m	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-06-0-0.6m	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-09-0-10	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-09-10-20m	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-09B-0-15m	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-10-0-5m	-	-	-	Coarse Processed Kimberlite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-10-0-0.05	-	-	-	Coarse Processed Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-10-DARKm	-	-	-	Coarse Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-13-10-15m	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-14-0-10m	-	-	-	Coarse Processed Kimberlite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-CK-OCT/02	-	-	-	Coarse Processed Kimberlite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.7	0.1	4.1	2.0	-	-	1,030	0.50	2	2.4	1.5	-	61	653	-	22	4.0	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.1	4.5	2.0	-	-	1,050	1.5	2	2.4	1.0	-	57	536	-	20	3.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.6	0.1	3.3	2.0	-	-	810	0.50	1	2.0	1.0	-	67	705	-	16	3.6	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	0.1	3.7	5.0	-	-	810	0.50	8	2.7	0.50	-	56	548	-	48	3.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.8	0.1	2.1	4.0	-	-	730	0.50	1	2.3	0.50	-	79	952	-	17	3.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.8	0.1	2.5	4.0	-	-	830	0.50	6	2.5	0.25	-	70	784	-	21	3.6	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.1	2.4	3.0	-	-	800	0.50	6	2.5	0.25	-	69	816	-	24	3.5	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.8	0.1	3.1	4.0	-	-	1,010	0.50	2	2.5	0.25	-	65	775	-	22	3.6	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.1	5.5	4.0	-	-	890	0.50	1	2.2	0.25	-	33	502	-	26	3.1	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	0.1	3.2	5.0	-	-	910	0.50	1	1.7	0.25	-	70	891	-	16	4.5	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Kimberlite (continued)																						
Coarse Processed Kimberlite (continued)																						
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	0.2	3.0	7.0	-	-	870	0.25	10	1.8	1.5	-	68	1,510	-	23	4.6	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.2	3.4	7.0	-	-	1,160	0.50	4	2.0	1.5	-	60	602	-	24	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.2	4.2	19	-	-	1,060	0.50	2	2.1	1.0	-	55	454	-	30	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.1	3.3	5.0	-	-	580	0.50	6	2.2	1.0	-	65	598	-	23	4.4	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	0.1	3.2	3.0	-	-	860	0.25	6	2.0	1.0	-	67	743	-	20	4.4	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.8	0.1	3.4	4.0	-	-	970	0.50	6	2.0	1.5	-	66	694	-	22	4.5	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.1	3.2	6.0	-	-	830	0.25	2	1.9	1.0	-	71	720	-	19	4.6	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	0.1	3.1	4.0	-	-	790	0.25	10	1.9	1.5	-	75	817	-	21	4.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	0.1	4.2	4.0	-	-	1,080	0.50	2	2.4	1.0	-	57	619	-	23	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	0.1	4.3	9.0	-	-	1,140	0.50	1	2.6	1.0	-	51	546	-	26	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	0.1	4.2	3.0	-	-	1,260	0.50	6	2.8	1.0	-	56	721	-	30	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	3.4	5.0	-	-	380	0.50	1	2.0	0.25	-	65	829	-	21	3.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	0.1	3.8	5.0	-	-	1,080	0.50	4	2.7	1.0	-	59	775	-	30	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	3.4	5.0	-	-	950	0.50	1	2.1	0.25	-	58	764	-	25	3.5	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	3.0	5.0	-	-	880	0.50	1	1.7	0.25	-	64	670	-	20	3.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.25	4.0	5.0	-	-	790	0.50	1	2.2	0.25	-	56	576	-	21	3.5	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	0.25	3.6	10	-	-	1,050	0.25	2	2.6	0.50	-	46	554	-	24	3.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	3.3	5.0	-	-	1,010	0.25	4	2.0	0.50	-	51	605	-	20	3.5	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	4.6	10	-	-	1,070	0.25	2	2.3	0.50	-	45	492	-	20	3.4	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.5	3.5	2.5	-	-	1,010	1.5	1	2.4	0.25	-	47	636	-	32	3.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	0.25	3.3	10	-	-	730	1.0	2	2.4	0.25	-	73	1,055	-	33	5.1	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	0.25	3.1	5.0	-	-	890	1.0	1	1.8	0.50	-	63	892	-	25	4.4	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	0.25	3.5	2.5	-	-	830	1.0	1	2.0	0.25	-	52	571	-	25	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	2.9	2.5	-	-	430	0.50	1	1.5	0.25	-	71	846	-	15	4.1	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	0.25	2.8	10	-	-	870	1.0	1	1.7	0.25	-	59	554	-	28	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	3.9	10	-	-	1,000	1.0	1	2.0	2.5	-	52	414	-	28	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.5	2.7	5.0	-	-	660	0.50	6	1.8	0.25	-	81	1,055	-	22	5.0	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.25	2.6	2.5	-	-	790	1.5	1	2.0	0.25	-	69	1,150	-	25	4.4	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	0.25	3.9	2.5	-	-	880	1.0	1	2.1	0.50	-	50	539	-	25	3.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.25	3.7	5.0	-	-	820	1.0	1	2.1	0.25	-	51	533	-	27	3.8	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Kimberlite (continued)																						
Coarse Processed Kimberlite (continued)																						
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	4.0	2.5	-	-	800	1.5	1	2.0	0.25	-	48	537	-	22	3.6	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	0.25	2.9	2.5	-	-	750	1.0	1	1.6	0.25	-	64	801	-	21	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	1.7	2.5	-	-	470	0.50	1	1.2	0.25	-	50	574	-	16	3.0	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	2.4	2.5	-	-	800	0.50	1	2.0	0.50	-	70	953	-	24	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	0.5	2.9	2.5	-	-	890	1.0	1	1.8	0.25	-	57	679	-	27	4.1	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	3.3	10	-	-	870	1.0	1	1.8	1.0	-	60	546	-	26	4.4	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	3.0	5.0	-	-	830	0.50	1	1.8	2.0	-	62	484	-	23	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.25	3.5	2.5	-	-	910	1.0	2	2.0	1.0	-	54	493	-	28	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	0.25	3.6	5.0	-	-	1,080	1.5	6	2.7	1.0	-	48	503	-	37	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.25	4.6	2.5	-	-	800	1.5	1	2.1	0.25	-	45	461	-	27	3.5	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.25	4.1	2.5	-	-	870	0.80	1	2.7	0.25	-	63	736	-	28	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	0.25	4.4	8.0	-	-	950	1.0	1	2.1	0.25	-	53	604	-	29	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.7	0.25	6.6	2.5	-	-	1,180	2.0	1	2.8	0.25	-	38	333	-	32	3.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	4.2	2.5	-	-	770	0.70	1	2.4	0.25	-	60	758	-	24	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.25	4.3	11	-	-	1,000	1.0	1	2.2	0.25	-	49	488	-	32	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	0.25	4.2	2.5	-	-	900	0.90	1	2.0	0.25	-	49	594	-	28	4.1	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.25	2.9	2.5	-	-	620	0.50	1	1.9	0.25	-	75	963	-	21	4.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	2.8	2.5	-	-	670	0.60	1	2.0	0.25	-	77	946	-	22	4.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	0.25	7.3	2.5	-	-	870	1.3	1	2.7	0.25	-	29	231	-	26	3.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.25	4.6	2.5	-	-	870	0.80	1	2.7	0.25	-	57	598	-	24	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	4.7	2.5	-	-	990	1.0	1	2.3	0.25	-	56	519	-	37	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	2.4	2.5	-	-	550	0.50	1	1.6	0.25	-	82	1,010	-	20	4.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.6	0.25	4.8	7.0	-	-	740	0.70	1	2.1	0.25	-	48	467	-	20	3.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.25	4.8	14	-	-	750	0.60	1	2.1	0.25	-	48	539	-	24	3.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.25	2.9	2.5	-	-	620	0.50	1	1.9	0.25	-	75	963	-	21	4.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.25	4.1	2.5	-	-	870	0.80	1	2.7	0.25	-	63	736	-	28	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	4.4	2.5	-	-	640	0.80	1	2.2	0.25	-	56	594	-	24	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	5.0	6.0	-	-	770	0.90	1	2.5	0.25	-	43	496	-	22	3.5	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	4.5	2.5	-	-	760	0.90	1	2.7	0.25	-	45	673	-	29	3.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	0.25	3.7	2.5	-	-	710	0.80	1	2.4	0.25	-	44	720	-	28	3.5	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	4.7	2.5	-	-	800	0.80	1	2.6	0.25	-	40	486	-	26	3.4	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	0.25	4.4	2.5	-	-	870	0.90	1	2.8	0.25	-	50	692	-	35	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	3.2	2.5	-	-	650	0.70	1	2.1	0.25	-	50	782	-	26	3.6	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	4.6	2.5	-	-	610	0.80	1	2.0	0.25	-	46	574	-	18	3.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	4.0	2.5	-	-	690	0.80	1	2.0	0.25	-	51	583	-	28	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	3.7	2.5	-	-	600	0.70	10	2.1	0.25	-	51	711	-	24	3.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	3.4	2.5	-	-	590	0.60	1	2.0	0.25	-	60	632	-	23	4.1	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	3.7	2.5	-	-	570	0.60	1	2.1	0.25	-	55	576	-	20	3.9	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Kimberlite (continued)																						
Coarse Processed Kimberlite (continued)																						
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	4.7	8.0	-	-	690	0.80	1	2.5	0.25	-	46	734	-	24	3.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	4.7	2.5	-	-	960	1.0	1	2.1	0.25	-	36	506	-	29	3.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.6	0.25	3.8	6.0	-	-	620	0.70	1	2.2	0.25	-	47	649	-	17	3.5	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.7	0.25	4.5	6.0	-	-	940	0.80	1	1.9	0.25	-	48	690	-	22	3.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.4	0.25	4.4	6.0	-	-	720	0.80	1	2.0	0.25	-	50	790	-	25	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	0.25	4.6	8.0	-	-	890	0.90	1	2.2	0.25	-	50	749	-	28	4.0	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	0.25	4.2	2.5	-	-	940	0.80	1	2.4	0.25	-	51	849	-	30	4.0	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.25	5.2	6.0	-	-	720	0.90	1	2.2	0.25	-	45	575	-	23	3.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	0.25	3.9	2.5	-	-	720	0.80	1	2.1	0.25	-	59	766	-	25	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.25	5.2	2.5	-	-	870	0.80	1	2.1	0.25	-	46	559	-	21	3.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	0.25	4.6	2.5	-	-	740	0.80	1	2.0	0.25	-	52	650	-	23	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	4.8	2.5	-	-	890	0.80	1	2.2	0.25	-	49	592	-	25	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	3.6	5.0	-	-	730	0.60	1	1.8	0.25	-	54	792	-	21	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	2.9	2.5	-	-	700	0.60	1	1.7	0.25	-	52	764	-	23	4.0	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.25	3.6	2.5	-	-	810	0.70	2	1.8	0.25	-	45	651	-	22	3.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	3.3	2.5	-	-	790	0.60	1	2.5	0.25	-	63	1,230	-	23	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	3.4	2.5	-	-	680	0.70	1	1.8	0.25	-	51	732	-	21	3.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	3.5	6.0	-	-	720	0.70	1	2.0	0.25	-	53	725	-	44	4.1	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	2.6	2.5	-	-	700	0.60	1	2.0	0.25	-	61	751	-	22	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	3.8	2.5	-	-	660	0.70	1	2.0	0.25	-	53	586	-	21	3.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	0.25	3.4	5.0	-	-	740	0.70	1	1.8	0.25	-	52	575	-	22	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	0.25	4.1	2.5	-	-	770	0.70	1	2.1	0.25	-	48	551	-	24	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	0.25	3.5	2.5	-	-	1,230	0.80	1	3.8	0.25	-	45	480	-	35	3.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	0.25	3.6	2.5	-	-	1,270	0.80	1	3.9	0.25	-	48	481	-	37	4.0	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	0.25	4.1	2.5	-	-	940	0.80	1	3.1	0.25	-	49	535	-	38	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	0.25	3.9	2.5	-	-	960	0.80	1	3.0	0.25	-	48	581	-	31	4.0	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.7	0.25	5.2	13	-	-	900	0.90	1	3.2	0.25	-	40	289	-	31	3.7	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	0.25	5.2	2.5	-	-	910	0.90	1	3.1	0.25	-	43	284	-	39	3.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.4	0.25	4.5	6.0	-	-	1,090	0.90	1	3.0	0.25	-	52	487	-	35	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.8	0.25	4.4	2.5	-	-	1,120	0.90	1	2.8	0.25	-	50	484	-	28	4.1	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.0	0.25	3.7	2.5	-	-	950	0.70	3	3.1	0.25	-	50	459	-	32	4.0	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.2	0.25	3.6	2.5	-	-	940	0.70	1	3.1	0.25	-	50	432	-	32	4.0	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.2	0.25	4.3	2.5	-	-	890	0.80	1	2.8	0.25	-	46	375	-	33	3.8	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	6.5	0.25	4.1	2.5	-	-	870	0.80	3	2.6	0.25	-	46	367	-	29	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	0.25	3.8	2.5	-	-	880	0.80	3	2.7	0.25	-	52	711	-	30	4.0	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.8	0.25	3.8	2.5	-	-	870	0.80	1	2.7	0.25	-	51	682	-	32	4.1	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	0.25	5.5	5.0	-	-	1,100	0.90	1	3.3	0.25	-	52	476	-	40	4.4	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	0.25	5.3	2.5	-	-	1,120	0.90	1	3.2	0.25	-	53	461	-	41	4.4	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Kimberlite (continued)																						
Coarse Processed Kimberlite (continued)																						
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	0.25	5.2	2.5	-	-	1,090	1.0	1	2.8	0.25	-	53	490	-	36	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	0.25	4.9	2.5	-	-	970	0.90	1	2.6	0.25	-	46	451	-	34	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.6	0.25	4.8	2.5	-	-	1,030	0.80	1	3.2	0.25	-	54	438	-	43	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.7	0.25	5.1	2.5	-	-	1,010	0.80	1	3.3	0.25	-	53	412	-	36	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	0.25	4.0	2.5	-	-	1,000	0.80	1	2.9	0.25	-	49	623	-	32	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	0.25	4.3	7.0	-	-	960	0.80	1	2.9	0.25	-	48	638	-	29	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.5	0.25	3.7	8.0	-	-	1,000	0.70	1	3.3	0.25	-	52	525	-	38	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	0.25	3.7	2.5	-	-	1,000	0.70	1	3.3	0.25	-	49	488	-	38	4.1	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.5	0.25	4.0	10	-	-	1,010	0.80	1	2.9	0.25	-	46	634	-	36	4.0	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	0.25	4.4	5.0	-	-	1,050	0.90	1	3.1	0.25	-	48	593	-	34	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.4	0.25	4.1	7.0	-	-	1,080	0.80	1	3.2	0.25	-	49	673	-	40	4.1	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	0.25	4.1	2.5	-	-	1,070	0.80	1	3.2	0.25	-	49	603	-	35	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	0.005	2.7	2.5	-	-	860	0.74	0.08	2.4	0.21	-	66	937	-	36	4.6	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	0.005	2.9	2.6	-	-	870	0.66	0.06	2.3	0.18	-	65	836	-	20	4.5	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.4	1.0	4.1	2.5	-	-	890	0.80	1	2.9	0.25	-	45	618	-	28	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	0.25	3.7	2.5	-	-	920	0.70	1	2.9	0.25	-	49	618	-	35	3.9	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.25	4.5	2.5	-	-	1,060	0.80	1	3.3	0.25	-	51	514	-	30	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	0.25	4.5	2.5	-	-	1,000	0.80	1	3.2	0.25	-	50	492	-	38	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	0.25	5.1	2.5	-	-	1,040	0.90	2	3.4	0.25	-	50	460	-	33	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	0.25	4.9	2.5	-	-	1,020	1.1	2	3.4	0.25	-	53	466	-	35	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	0.25	3.7	10	-	-	1,020	0.80	1	3.5	0.25	-	47	743	-	35	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.7	0.25	3.8	12	-	-	1,000	0.80	3	3.4	0.25	-	46	755	-	37	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	0.25	4.0	2.5	-	-	1,070	0.80	2	3.4	0.25	-	60	498	-	45	4.4	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	0.25	3.9	2.5	-	-	1,090	0.80	1	3.4	0.25	-	58	502	-	37	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	0.25	4.1	9.0	-	-	1,010	0.80	1	3.4	0.25	-	56	470	-	35	4.4	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	0.25	4.1	2.5	-	-	1,000	0.80	1	3.3	0.25	-	55	542	-	34	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	0.7	5.0	5.0	-	-	970	0.90	1	3.5	0.25	-	53	372	-	33	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.5	0.25	4.9	2.5	-	-	910	0.90	1	3.4	0.25	-	51	359	-	32	4.1	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.6	0.25	4.5	7.0	-	-	1,000	0.80	1	3.6	0.25	-	55	429	-	47	4.6	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.7	1.1	4.4	5.0	-	-	940	0.80	1	3.4	0.25	-	52	430	-	36	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	0.25	4.9	6.0	-	-	1,050	0.80	2	3.8	0.25	-	52	439	-	35	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	0.25	4.6	6.0	-	-	990	0.80	1	3.7	0.25	-	51	361	-	43	4.3	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	0.25	4.5	2.5	-	-	980	0.80	2	3.5	0.25	-	50	416	-	44	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	0.25	4.5	2.5	-	-	1,000	0.80	1	3.5	0.25	-	50	394	-	39	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.6	0.25	4.7	2.5	-	-	1,110	0.80	2	3.5	0.25	-	54	515	-	36	4.4	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	0.25	3.9	7.0	-	-	1,250	0.80	1	4.0	0.25	-	51	390	-	41	4.0	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	0.25	4.0	2.5	-	-	1,100	0.80	1	3.6	0.25	-	47	524	-	36	4.2	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.6	0.25	4.6	2.5	-	-	1,020	0.90	1	3.7	0.25	-	49	306	-	34	4.1	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Kimberlite (continued)																						
Coarse Processed Kimberlite (continued)																						
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	0.25	4.1	2.5	-	-	1,100	0.80	1	3.7	0.25	-	52	420	-	29	4.1	-
CK 00-11-20	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
CK 00-11-21	-	-	-	Coarse Processed Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
CK 00-11-24	-	-	-	Coarse Processed Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
CK 00-11-25	-	-	-	Coarse Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
CKC 3SS 11- 26 3	-	-	-	Coarse Processed Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Median					8.4	0.25	4.0	2.5	-	-	890	0.80	1	2.4	0.25	-	52	586	-	28	4.1	-
Minimum					6.5	0.005	1.7	2.0	-	-	380	0.25	0.06	1.2	0.18	-	29	231	-	15	3.0	-
Maximum					9.8	1.1	7.3	19	-	-	1,270	2.0	10	4.0	2.5	-	82	1,510	-	48	5.1	-
Count					189	155	155	155	0	0	155	155	155	155	155	0	155	155	0	155	155	0
Fine Processed Kimberlite																						
FK 13-SEP-04	-	-	-	Fine Processed Kimberlite	8.1	0.5	0.78	5.0	-	-	630	0.50	2	1.7	0.50	-	81	912	-	22	4.7	-
FK 3-JAN-04	-	-	-	Fine Processed Kimberlite	8.1	0.5	2.6	6.0	-	-	630	0.50	2	2.0	0.50	-	87	1,080	-	22	4.9	-
FK 7-FEB-04	-	-	-	Fine Processed Kimberlite	8.1	0.5	1.3	5.0	-	-	470	0.50	2	1.2	0.50	-	93	774	-	15	5.0	-
FK 4-APR-04	-	-	-	Fine Processed Kimberlite	8.1	0.5	1.6	6.0	-	-	480	0.50	2	1.4	0.50	-	88	895	-	16	4.9	-
FK 7-JUN-04	-	-	-	Fine Processed Kimberlite	8.1	0.5	1.8	5.0	-	-	550	0.50	2	1.6	0.50	-	84	738	-	17	4.8	-
FK 5-JUL-04	-	-	-	Fine Processed Kimberlite	8.1	0.5	2.5	5.0	-	-	780	0.60	2	2.0	0.50	-	81	848	-	26	4.8	-
FK 6-AUG-04	-	-	-	Fine Processed Kimberlite	7.9	0.5	3.9	8.0	-	-	970	0.90	2	2.9	0.50	-	56	851	-	40	4.2	-
FK 8-AUG-04	-	-	-	Fine Processed Kimberlite	8.2	0.5	1.9	5.0	-	-	770	0.50	2	2.0	0.50	-	73	648	-	23	4.3	-
FK 11-AUG-04	-	-	-	Fine Processed Kimberlite	7.9	0.5	3.9	9.0	-	-	1,060	0.90	2	2.9	0.50	-	55	811	-	41	4.1	-
FK 12-AUG-04	-	-	-	Fine Processed Kimberlite	8.2	0.5	2.1	5.0	-	-	730	0.60	2	1.7	0.50	-	62	787	-	20	4.0	-
FK 15-AUG-04	-	-	-	Fine Processed Kimberlite	8.0	0.5	3.5	5.0	-	-	1,060	0.80	2	2.7	0.50	-	66	787	-	37	4.5	-
FK 16-AUG-04	-	-	-	Fine Processed Kimberlite	8.1	0.5	3.2	5.0	-	-	840	0.80	2	2.4	0.50	-	61	735	-	32	4.2	-
FK 23-AUG-04	-	-	-	Fine Processed Kimberlite	8.1	0.5	2.6	5.0	-	-	700	0.60	2	1.7	0.50	-	73	866	-	24	4.5	-
FK 28-AUG-04	-	-	-	Fine Processed Kimberlite	8.2	0.5	2.6	10	-	-	780	0.60	2	2.1	0.50	-	76	811	-	27	4.7	-
FK 31-AUG-04	-	-	-	Fine Processed Kimberlite	8.3	0.5	2.7	5.0	-	-	610	0.50	2	2.0	0.50	-	68	665	-	24	4.4	-
FK 12-SEP-04	-	-	-	Fine Processed Kimberlite	8.2	0.5	1.6	5.0	-	-	590	0.50	2	1.7	0.50	-	76	688	-	18	4.4	-
FK 20-SEP-04	-	-	-	Fine Processed Kimberlite	8.3	0.5	1.8	7.0	-	-	580	0.50	2	1.5	0.50	-	85	923	-	19	4.8	-
FK 1-OCT-04	-	-	-	Fine Processed Kimberlite	8.1	0.5	3.1	6.0	-	-	950	0.80	2	2.2	0.50	-	66	879	-	33	4.5	-
FK 18-OCT-04	-	-	-	Fine Processed Kimberlite	8.2	0.5	2.9	5.0	-	-	820	0.70	2	2.2	0.50	-	71	832	-	29	4.4	-
FK 25-OCT-04	-	-	-	Fine Processed Kimberlite	8.1	0.5	3.0	5.0	-	-	840	0.80	2	2.1	0.50	-	67	785	-	25	4.5	-
FINE KIMBERLITE 30-OCT-04	-	-	-	Fine Processed Kimberlite	8.1	0.5	2.3	8.0	-	-	750	0.50	2	1.6	0.50	-	58	557	-	21	3.9	-
FINE KIMBERLITE 25-DEC-04	-	-	-	Fine Processed Kimberlite	8.2	0.5	2.6	6.0	-	-	700	0.60	2	1.8	0.50	-	58	871	-	25	4.2	-
FINE KIMBERLITE 23-JAN-05	-	-	-	Fine Processed Kimberlite	8.2	0.5	2.6	14	-	-	830	0.60	2	1.8	0.50	-	58	778	-	27	4.1	-
FINE KIMBERLITE 25-FEB-05	-	-	-	Fine Processed Kimberlite	8.2	0.5	2.4	5.0	-	-	710	0.50	2	1.6	0.50	-	62	866	-	23	4.1	-
FINE KIMBERLITE 24-MAR-05	-	-	-	Fine Processed Kimberlite	8.3	0.5	2.6	8.0	-	-	740	0.60	2	1.8	0.50	-	50	676	-	29	3.7	-
FINE KIMBERLITE 24-APR-05	-	-	-	Fine Processed Kimberlite	7.9	0.5	2.7	5.0	-	-	910	0.60	2	2.0	0.50	-	53	680	-	38	4.0	-
FINE KIMBERLITE 25-MAY-05	-	-	-	Fine Processed Kimberlite	8.2	0.5	2.0	5.0	-	-	640	0.50	2	1.6	0.50	-	61	697	-	21	4.0	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Kimberlite (continued)																						
<i>Fine Processed Kimberlite (continued)</i>																						
FINE KIMBERLITE 23-JUN-05	-	-	-	Fine Processed Kimberlite	8.3	0.5	1.6	7.0	-	-	570	0.50	2	1.5	0.50	-	70	827	-	19	4.4	-
FINE KIMBERLITE 24-JUL-05	-	-	-	Fine Processed Kimberlite	8.3	0.5	1.9	5.0	-	-	680	0.50	2	1.8	0.50	-	74	772	-	24	4.7	-
FINE KIMBERLITE 23-AUG-05	-	-	-	Fine Processed Kimberlite	8.2	0.5	2.1	5.0	-	-	750	0.50	2	1.7	0.50	-	73	944	-	25	4.6	-
FINE KIMBERLITE 28-SEP-05A	-	-	-	Fine Processed Kimberlite	8.4	0.5	2.4	6.0	-	-	540	0.50	2	1.4	0.50	-	68	958	-	19	4.3	-
FINE KIMBERLITE 28-SEP-05B	-	-	-	Fine Processed Kimberlite	8.5	0.5	2.8	5.0	-	-	600	0.60	2	1.6	0.50	-	71	1,025	-	26	4.5	-
FINE KIMBERLITE 24-OCT-05	-	-	-	Fine Processed Kimberlite	8.0	0.5	2.7	6.0	-	-	790	0.60	2	1.8	0.50	-	57	684	-	23	4.3	-
FINE KIMBERLITE 28-NOV-05A	-	-	-	Fine Processed Kimberlite	8.5	0.5	3.1	5.0	-	-	1,300	0.70	2	3.0	0.50	-	59	639	-	37	4.3	-
FINE KIMBERLITE 28-NOV-05B	-	-	-	Fine Processed Kimberlite	8.3	0.5	3.1	5.0	-	-	1,320	0.70	2	2.9	0.50	-	60	618	-	34	4.2	-
FINE KIMBERLITE 23-DEC-05	-	-	-	Fine Processed Kimberlite	8.4	0.5	2.3	6.0	-	-	940	0.50	2	2.2	0.50	-	62	769	-	26	4.4	-
FINE KIMBERLITE PPD	-	-	-	Fine Processed Kimberlite	8.2	0.5	1.6	7.0	-	-	500	0.50	2	1.4	0.50	-	82	849	-	18	4.5	-
FK 00-11- 09 15	-	-	-	Fine Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FK 00-11- 20 27	-	-	-	Fine Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Median					8.2	0.5	2.6	5.0	-	-	740	0.60	2	1.8	0.50	-	68	787	-	24	4.4	-
Minimum					7.9	0.5	0.78	5.0	-	-	470	0.50	2	1.2	0.50	-	50	557	-	15	3.7	-
Maximum					8.5	0.5	3.9	14	-	-	1,320	0.90	2	3.0	0.50	-	93	1,080	-	41	5.0	-
Count					39	37	37	37	0	0	37	37	37	37	37	0	37	37	0	37	37	0
Metasediment																						
<i>Beartooth</i>																						
13	BDC-05	48.01	48.44	Metasediment	9.9	0.1	2.8	2.5	-	-	610	0.25	2.5	0.23	0.5	-	23	295	-	5.0	4.6	-
BDC 2-41.76	BDC 2	41.76	46.16	Metasediment	-	0.25	10	2.5	-	-	530	1.5	1	1.4	0.25	-	31	285	-	82	5.4	-
BDC 2-50.9	BDC 2	50.9	56	Metasediment	-	0.25	9.4	5.0	-	-	930	1.0	2	2.4	0.25	-	31	262	-	359	5.1	-
BDC 5-41.76	BDC 5	41.76	47.85	Metasediment	-	0.25	9.5	2.5	-	-	610	1.5	4	1.7	0.25	-	29	244	-	65	5.0	-
BDC 5-49.47	BDC 5	49.47	55.04	Metasediment	-	0.25	9.5	5.0	-	-	540	0.50	2	2.6	0.25	-	23	194	-	77	4.2	-
BDC 5-55.04	BDC 5	55.04	58.9	Metasediment	-	0.25	8.2	2.5	-	-	500	0.50	1	3.2	0.25	-	25	313	-	68	3.8	-
Median					9.9	0.25	9.5	2.5	-	-	575	0.75	2	2.0	0.25	-	27	274	-	73	4.8	-
Minimum					9.9	0.1	2.8	2.5	-	-	500	0.25	1	0.23	0.25	-	23	194	-	5.0	3.8	-
Maximum					9.9	0.25	10	5.0	-	-	930	1.5	4	3.2	0.5	-	31	313	-	359	5.4	-
Count					1	6	6	6	0	0	6	6	6	6	6	0	6	6	0	6	6	0
Koala																						
KS 390-25 1a	-	-	-	Metasediment	9.7	0.25	9.7	5.0	-	-	710	2.0	1	3.5	0.25	-	16	75	-	19	3.1	-
KS 390-25 2a	-	-	-	Metasediment	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-23 1a	-	-	-	Metasediment	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-23 2a	-	-	-	Metasediment	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-24-1a	-	-	-	Metasediment	9.6	0.25	9.8	2.5	-	-	730	1.5	1	3.3	0.25	-	18	72	-	39	3.4	-
KS-390-24-1a	-	-	-	Metasediment	9.3	0.25	8.9	2.5	-	-	680	1.5	1	3.2	0.25	-	14	67	-	21	3.1	-
KS-390-24-2a	-	-	-	Metasediment	9.6	0.25	9.1	2.5	-	-	690	1.5	1	2.9	0.25	-	14	84	-	42	2.8	-
KS-390-24-2a	-	-	-	Metasediment	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-26T-1a	-	-	-	Metasediment	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Metasediment (continued)																						
Koala (continued)																						
KS-390-26T-2a	-	-	-	Metasediment	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-27-1a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-27-2a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-37-1a	-	-	-	Metasediment	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-37-2a	-	-	-	Metasediment	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-38-1a	-	-	-	Metasediment	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-38-2a	-	-	-	Metasediment	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS 375-03 1a	-	-	-	Metasediment	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS 375-03 2a	-	-	-	Metasediment	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS 375-05 1a	-	-	-	Metasediment	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS 375-05 2a	-	-	-	Metasediment	9.4	0.25	8.6	5.0	-	-	340	1.5	1	0.76	0.25	-	9.0	66	-	8.0	1.9	-
KS-375-09-1a	-	-	-	Metasediment	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-09-2a	-	-	-	Metasediment	8.8	0.25	8.1	2.5	-	-	490	1.5	1	1.6	0.25	-	11	76	-	8.0	1.9	-
KS-375-10-1a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-10-2a	-	-	-	Metasediment	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-11-1a	-	-	-	Metasediment	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-11-2a	-	-	-	Metasediment	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-12-1a	-	-	-	Metasediment	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-12-2a	-	-	-	Metasediment	9.5	0.25	9.3	2.5	-	-	640	2.0	1	2.3	0.25	-	8.0	45	-	12	1.9	-
KS-375-14-1a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-14-1a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-14-2a	-	-	-	Metasediment	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-14-2a	-	-	-	Metasediment	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-20-1A	-	-	-	Metasediment	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-20-2A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-22REV1-1A	-	-	-	Metasediment	8.9	0.25	8.9	2.5	-	-	500	1.5	1	2.6	0.25	-	9.0	68	-	13	2.1	-
KS-375-22REV1-2A	-	-	-	Metasediment	8.2	0.25	9.0	2.5	-	-	680	1.5	1	2.8	0.25	-	11	61	-	26	2.5	-
KS-360-05-1A	-	-	-	Metasediment	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-360-05-2A	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Median					9.5	0.25	9.0	2.5	-	-	680	1.5	1	2.8	0.25	-	11	68	-	19	2.5	-
Minimum					8.2	0.25	8.1	2.5	-	-	340	1.5	1	0.76	0.25	-	8.0	45	-	8.0	1.9	-
Maximum					9.8	0.25	9.8	5.0	-	-	730	2.0	1	3.5	0.25	-	18	84	-	42	3.4	-
Count					38	9	9	9	0	0	9	9	9	9	9	0	9	9	0	9	9	0
Misery																						
MGT-66 45-48	-	-	-	Metasediment	9.2	0.1	3.1	23	2.3	10	312	-	0.3	0.27	0.05	-	27	179	-	44	4.5	10
MGT-66 50-53	-	-	-	Metasediment	9.4	0.05	2.9	26	2.1	10	279	-	0.6	0.38	0.05	-	26	177	-	50	4.1	10
MGT-66 81.03-82.28	-	-	-	Metasediment	9.4	0.05	2.4	15	3.1	10	142	-	0.7	0.12	0.05	-	18	177	-	44	3.4	10
MGT-66 100.58-102.04	-	-	-	Metasediment	9.1	0.05	3.0	7.2	4.2	10	194	-	0.4	0.17	0.05	-	26	171	-	64	4.3	11

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Metasediment (continued)																						
Misery (continued)																						
MGT-49 273-276	-	-	-	Metasediment	9.2	0.05	3.4	1.2	1.9	10	342	-	0.5	0.12	0.05	-	28	205	-	70	4.5	12
MDC-4 15.02	-	-	-	Metasediment	7.4	0.25	8.4	10	-	-	590	1.0	1	0.60	0.25	-	22	145	-	49	3.8	-
MDC-4 26.4	-	-	-	Metasediment	8.7	0.25	8.4	10	-	-	600	1.0	1	0.79	0.25	-	22	142	-	43	4.0	-
MDC-4 31.5	-	-	-	Metasediment	9.1	0.25	7.7	10	-	-	500	0.50	1	1.1	0.25	-	20	121	-	53	3.4	-
MDC-4 37.06	-	-	-	Metasediment	8.9	0.25	8.7	10	-	-	610	1.0	1	0.73	0.25	-	24	153	-	59	4.0	-
MDC-4 46.8	-	-	-	Metasediment	8.4	0.25	9.0	10	-	-	540	1.5	1	0.72	0.25	-	24	147	-	51	4.2	-
MDC-4 53.4	-	-	-	Metasediment	8.3	0.25	8.2	2.5	-	-	520	2.0	1	0.93	0.25	-	17	88	-	53	2.9	-
MDC-4 59.04	-	-	-	Metasediment	8.9	0.25	8.2	20	-	-	620	1.0	1	0.61	0.25	-	24	203	-	90	4.0	-
MDC-4 70.78	-	-	-	Metasediment	9.2	0.25	8.3	25	-	-	330	1.5	1	0.86	0.25	-	21	144	-	58	3.5	-
MDC-6 14.32	-	-	-	Metasediment	9.6	0.25	8.6	140	-	-	430	1.0	1	0.83	0.25	-	18	139	-	31	3.7	-
MDC-6 75.69	-	-	-	Metasediment	9.4	0.25	7.8	10	-	-	350	1.5	1	0.66	0.25	-	13	80	-	42	2.7	-
MDC-6 104.66	-	-	-	Metasediment	9.0	0.25	7.6	15	-	-	570	1.0	1	0.59	0.25	-	13	92	-	31	2.7	-
MDC-6 144.7	-	-	-	Metasediment	9.1	0.25	7.9	15	-	-	520	1.5	1	0.86	0.25	-	21	120	-	80	3.4	-
MDC-6 190	-	-	-	Metasediment	9.1	0.25	8.0	5.0	-	-	390	2.0	1	0.52	0.25	-	19	124	-	49	3.5	-
MDC-8 18.85	-	-	-	Metasediment	8.3	0.25	7.1	150	-	-	390	0.50	1	2.3	0.25	-	19	140	-	59	3.4	-
MDC-8 46.48	-	-	-	Metasediment	9.3	0.25	6.7	60	-	-	380	0.50	1	1.6	0.25	-	19	134	-	46	3.4	-
MDC-8 157.28	-	-	-	Metasediment	8.8	0.25	7.9	5.0	-	-	570	0.50	1	0.78	0.25	-	21	132	-	51	3.7	-
MDC-4 25.7	-	-	-	Metasediment	9.1	0.25	8.6	35	-	-	370	1.5	1	0.66	0.25	-	12	85	-	25	2.9	-
MDC-4 87.47	-	-	-	Metasediment	9.3	0.25	8.7	60	-	-	700	1.0	1	0.93	0.25	-	19	117	-	38	3.4	-
MS 450-30 A	-	-	-	Metasediment	9.3	0.1	8.2	1.0	-	-	610	2.0	1	1.4	0.25	-	3.0	122	-	28	0.82	-
MS 450-30 B	-	-	-	Metasediment	9.1	0.2	7.9	1.0	-	-	650	1.5	1	1.3	0.25	-	2.0	119	-	23	0.82	-
MS 450-34-1A	-	-	-	Metasediment	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 450-34-2A	-	-	-	Metasediment	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 450-35-2A	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS-440-E-01	-	-	-	Metasediment	9.3	0.25	7.9	21	-	-	660	1.6	1	0.94	0.25	-	22	135	-	46	4.0	20
MS-440-E-02	-	-	-	Metasediment	9.2	0.25	8.0	11	-	-	580	1.5	3	1.1	0.25	-	21	130	-	49	3.8	20
MS-440-SE-01	-	-	-	Metasediment	8.7	0.25	8.2	6.0	-	-	600	1.4	2	0.84	0.25	-	22	140	-	49	4.1	20
MPS 440-01 A	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A1	-	-	-	Metasediment	8.1	0.2	7.6	14	-	-	570	1.0	1	0.74	0.50	-	24	261	-	41	3.3	-
MPS 440-01-05 A2	-	-	-	Metasediment	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A3	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A4	-	-	-	Metasediment	8.3	0.1	7.6	11	-	-	570	1.5	1	0.82	1.0	-	22	250	-	33	3.2	-
MPS 440-01-05 A5	-	-	-	Metasediment	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A6	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A7	-	-	-	Metasediment	8.6	0.1	7.7	4.0	-	-	430	1.5	1	1.4	1.5	-	25	279	-	49	3.3	-
MPS 440-01-05 A8	-	-	-	Metasediment	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-06 A	-	-	-	Metasediment	8.5	0.1	7.8	2.0	-	-	510	1.5	1	0.79	0.25	-	21	239	-	27	3.1	-
MPS 440-06 AA	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Metasediment (continued)																						
Misery (continued)																						
MPS 440-06 AAA	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-01 1A	-	-	-	Metasediment	8.4	0.6	7.1	9.0	-	-	430	1.0	1	0.87	1.5	-	15	251	-	23	2.4	-
MS 440-01 2A	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-01 2AA	-	-	-	Metasediment	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-10 1A	-	-	-	Metasediment	8.5	0.1	7.0	4.0	-	-	510	1.5	1	1.1	1.0	-	14	268	-	20	2.1	-
MS 440-10 2A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-13 1A	-	-	-	Metasediment	7.8	0.1	7.8	3.0	-	-	570	1.5	1	0.76	0.25	-	19	248	-	45	3.1	-
MS 440-13 2A	-	-	-	Metasediment	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-16 A	-	-	-	Metasediment	9.3	0.6	7.5	15	-	-	470	1.0	1	0.98	0.25	-	19	223	-	64	2.7	-
MS 440-16 B	-	-	-	Metasediment	8.7	0.1	7.9	5.0	-	-	450	1.5	1	0.86	0.50	-	23	263	-	47	3.4	-
MS 440-18 1A	-	-	-	Metasediment	8.4	0.2	8.5	17	-	-	640	1.5	1	0.70	0.25	-	28	232	-	57	3.8	-
MS 440-19 1A	-	-	-	Metasediment	7.6	0.2	7.8	13	-	-	520	1.0	2	0.96	0.25	-	23	254	-	47	3.4	-
MS 440-19 2A	-	-	-	Metasediment	7.7	0.1	7.9	3.0	-	-	550	1.5	1	0.47	0.25	-	22	264	-	52	3.5	-
MS 440-21 1A	-	-	-	Metasediment	7.1	0.2	7.8	13	-	-	570	1.5	1	1.1	0.25	-	17	244	-	35	2.5	-
MS 440-21 2A	-	-	-	Metasediment	7.2	0.1	8.0	16	-	-	680	1.5	2	1.2	0.25	-	15	262	-	41	2.5	-
MS 440-23 1A	-	-	-	Metasediment	8.7	0.2	7.9	14	-	-	590	1.0	1	0.89	0.25	-	21	258	-	48	3.1	-
MS 440-27 28-1A	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-27 28-2A	-	-	-	Metasediment	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-27-1A	-	-	-	Metasediment	7.8	0.2	7.8	52	-	-	500	2.0	2	1.8	0.25	-	30	235	-	101	4.7	-
MS 440-27-2A	-	-	-	Metasediment	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-29-1A	-	-	-	Metasediment	8.2	0.1	8.1	8.0	-	-	530	1.0	1	0.89	0.25	-	23	236	-	50	3.7	-
MS 440-29-2A	-	-	-	Metasediment	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-30-1A	-	-	-	Metasediment	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-30-2A	-	-	-	Metasediment	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-31-1A	-	-	-	Metasediment	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-31-2A	-	-	-	Metasediment	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-33-1A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-33-2A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-35-1A	-	-	-	Metasediment	8.5	0.1	7.9	1.0	-	-	640	1.5	1	2.2	0.25	-	15	176	-	76	3.3	-
MS 440-36-1A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-36-2A	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 440-38-1A	-	-	-	Metasediment	8.7	0.1	8.1	221	-	-	470	1.0	1	0.90	0.50	-	15	195	-	36	3.1	-
MS- 440-38-2A	-	-	-	Metasediment	7.7	0.2	8.0	10	-	-	510	1.0	1	0.63	0.25	-	5.0	190	-	7.0	1.5	-
MS- 440-43-1A	-	-	-	Metasediment	8.3	0.2	10	14	-	-	620	3.0	1	1.1	0.25	-	25	272	-	63	4.5	-
MS- 440-43-2A	-	-	-	Metasediment	7.3	0.1	7.5	6.0	-	-	780	1.5	1	1.1	0.25	-	10	136	-	18	2.1	-
MS K 440 46 1A	-	-	-	Metasediment	8.2	0.5	9.4	2.5	-	-	540	0.50	1	0.88	0.25	-	23	193	-	44	3.9	-
MS K 440 46 1B	-	-	-	Metasediment	8.3	0.25	8.9	5.0	-	-	510	0.50	1	0.98	0.25	-	21	185	-	50	3.5	-
MS- 440-49-1A	-	-	-	Metasediment	7.3	0.2	7.2	2.0	-	-	440	2.0	1	0.76	0.25	-	18	184	-	40	3.1	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Metasediment (continued)																						
Misery (continued)																						
MS 430 14 1A	-	-	-	Metasediment	8.5	0.25	8.2	5.0	-	-	640	1.5	1	0.50	0.25	-	22	209	-	30	4.2	-
MS 430 14 2A	-	-	-	Metasediment	8.7	0.25	7.9	10	-	-	670	1.0	1	0.48	0.25	-	20	227	-	19	3.7	-
MS 430 16 1A	-	-	-	Metasediment	8.7	0.25	7.3	5.0	-	-	490	1.0	1	0.67	0.25	-	22	173	-	35	3.4	-
MS 430 16 2A	-	-	-	Metasediment	8.4	0.25	7.1	10	-	-	500	0.50	1	0.30	0.25	-	19	204	-	22	3.5	-
MS 430 17 1A	-	-	-	Metasediment	9.0	0.25	7.0	15	-	-	290	0.50	1	2.2	0.25	-	31	135	-	144	6.4	-
MS 430 17 2A	-	-	-	Metasediment	9.0	0.25	6.5	15	-	-	330	0.50	1	2.1	0.25	-	28	150	-	106	5.6	-
MS 430 22 1A	-	-	-	Metasediment	7.9	0.25	7.5	30	-	-	520	0.50	1	0.95	0.25	-	26	258	-	58	3.2	-
MS 430 22 2A	-	-	-	Metasediment	9.0	0.25	8.1	5.0	-	-	440	1.0	1	0.88	0.25	-	25	225	-	43	3.3	-
MS 430 24 1A	-	-	-	Metasediment	8.7	0.25	8.6	60	-	-	580	1.0	1	1.1	0.25	-	26	234	-	57	3.6	-
MS 430 24 2A	-	-	-	Metasediment	8.7	0.25	8.4	5.0	-	-	580	1.0	1	1.1	0.25	-	25	213	-	48	3.4	-
MS 430 26 1A	-	-	-	Metasediment	8.6	0.25	7.7	15	-	-	470	1.0	1	1.9	0.25	-	29	179	-	104	4.7	-
MS 430 26 2A	-	-	-	Metasediment	8.5	0.25	7.8	15	-	-	540	1.5	1	1.1	0.25	-	20	212	-	42	2.9	-
MS 430 32 1A	-	-	-	Metasediment	9.1	0.25	8.5	85	-	-	550	1.5	1	1.1	0.25	-	24	229	-	44	3.4	-
MS 430 32 2A	-	-	-	Metasediment	8.8	0.25	8.3	40	-	-	530	1.5	1	0.80	0.25	-	25	201	-	43	3.4	-
MS- 430-38-1A	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 430-38-2A	-	-	-	Metasediment	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 430-39-1A	-	-	-	Metasediment	7.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 430-39-2A	-	-	-	Metasediment	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 430-40-1A	-	-	-	Metasediment	8.2	0.25	6.8	185	-	-	1,140	2.0	1	1.5	0.25	-	33	257	-	25	4.7	-
MS- 430-40-2A	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG/S-430-44-1A	-	-	-	Metasediment	8.7	0.25	11	15	-	-	620	1.5	4	0.76	0.25	-	20	163	-	46	4.2	-
MS-430-38-1A	-	-	-	Metasediment	8.8	0.5	6.4	35	-	-	340	1.5	1	0.87	0.25	-	17	153	-	40	3.3	-
MS-430-38-2A	-	-	-	Metasediment	9.0	0.25	6.9	480	-	-	380	1.5	1	1.2	0.25	-	29	256	-	54	4.4	-
MS-430-43-1A	-	-	-	Metasediment	8.8	0.5	7.4	220	-	-	460	1.5	4	1.5	0.25	-	18	182	-	36	3.4	-
MS-430-43-2A	-	-	-	Metasediment	8.6	0.5	7.4	5.0	-	-	350	2.0	2	0.54	0.25	-	5.0	103	-	25	1.3	-
MS-430-49-1A	-	-	-	Metasediment	8.2	0.5	11	2.5	-	-	580	1.5	2	1.1	0.25	-	21	158	-	56	4.3	-
MS-430-49-2A	-	-	-	Metasediment	8.4	0.5	7.5	2.5	-	-	490	1.5	4	0.96	0.25	-	17	147	-	44	3.1	-
MS-430-50-1A	-	-	-	Metasediment	8.6	0.5	6.7	2.5	-	-	580	1.5	2	0.96	0.50	-	10	106	-	26	2.1	-
MS-430-50-2A	-	-	-	Metasediment	8.5	0.25	7.1	10	-	-	520	1.5	1	0.83	0.25	-	20	154	-	46	3.5	-
MS-430-52-1A	-	-	-	Metasediment	8.8	0.25	6.3	2.5	-	-	200	1.5	1	4.9	0.50	-	43	115	-	242	10	-
MS-430-52-2A	-	-	-	Metasediment	9.4	0.25	6.6	35	-	-	250	3.5	1	0.53	0.25	-	9.0	118	-	26	2.0	-
MS-430-53-1A	-	-	-	Metasediment	8.8	0.5	6.8	2.5	-	-	520	1.5	1	0.89	0.25	-	8.0	117	-	28	1.9	-
MS-430-53-2A	-	-	-	Metasediment	8.5	0.5	7.6	2.5	-	-	560	1.5	1	0.95	0.25	-	16	166	-	44	3.1	-
MS-430-54-1A	-	-	-	Metasediment	8.3	0.25	12	25	-	-	460	2.5	1	0.80	0.25	-	20	185	-	46	4.5	-
MS-430-54-2A	-	-	-	Metasediment	8.2	0.25	9.4	5.0	-	-	610	1.5	1	0.32	0.25	-	16	158	-	45	3.9	-
MS-430-57-1A	-	-	-	Metasediment	8.4	0.5	7.0	15	-	-	500	2.0	2	1.2	0.25	-	21	178	-	53	3.7	-
MS-430-57-2A	-	-	-	Metasediment	8.5	0.25	6.6	2.5	-	-	410	3.0	1	0.83	0.25	-	17	161	-	37	3.2	-
MS-430-59-1A	-	-	-	Metasediment	8.7	0.25	8.3	2.5	-	-	590	1.5	1	0.80	0.50	-	22	161	-	51	4.0	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Metasediment (continued)																						
Misery (continued)																						
MS-430-59-2A	-	-	-	Metasediment	9.1	0.25	8.8	20	-	-	620	2.0	6	1.3	0.25	-	23	164	-	65	4.4	-
MS-420-18-01	-	-	-	Metasediment	9.4	0.11	8.2	127	-	-	580	1.4	0.31	1.0	0.11	-	22	140	-	43	4.1	22
MS-420-20-01	-	-	-	Metasediment	9.3	0.07	8.4	23	-	-	530	1.9	0.35	0.82	0.09	-	22	134	-	41	4.0	23
MS-420-24-01	-	-	-	Metasediment	8.3	0.11	7.6	9.3	-	-	620	1.5	0.29	0.83	0.08	-	24	135	-	56	3.7	21
MS-420-24-02	-	-	-	Metasediment	8.2	0.1	7.9	20	-	-	680	1.6	0.34	1.0	0.09	-	19	111	-	51	3.2	22
MS-420-25-01	-	-	-	Metasediment	8.8	0.08	7.8	5.2	-	-	600	1.2	0.26	0.93	0.11	-	22	141	-	46	3.8	20
MS-420-25-02	-	-	-	Metasediment	8.8	0.04	7.8	3.5	-	-	470	1.1	0.27	0.94	0.09	-	21	160	-	32	3.8	20
MS- 420-01-1A	-	-	-	Metasediment	8.4	0.25	1.8	20	-	-	890	0.25	6	3.4	0.50	-	57	611	-	24	4.7	-
MS- 420-01-2A	-	-	-	Metasediment	8.4	0.25	7.8	25	-	-	620	0.50	1	0.79	0.25	-	23	260	-	47	3.7	-
MS- 420-05-1A	-	-	-	Metasediment	8.6	0.25	7.9	5.0	-	-	540	0.50	1	0.98	0.25	-	22	195	-	46	3.9	-
MS- 420-05-2A	-	-	-	Metasediment	9.1	0.25	7.8	5.0	-	-	740	1.5	1	0.92	0.25	-	3.0	79	-	3.0	0.68	-
MS- 420-06-1A	-	-	-	Metasediment	8.5	0.25	7.1	25	-	-	540	1.0	1	0.82	0.25	-	23	182	-	55	3.7	-
MS- 420-06-2A	-	-	-	Metasediment	8.6	0.25	8.5	25	-	-	430	1.5	1	0.85	0.25	-	19	192	-	35	3.3	-
MS- 420-08-1A	-	-	-	Metasediment	8.8	0.25	7.2	30	-	-	500	0.50	1	1.1	0.25	-	23	218	-	54	4.0	-
MS- 420-08-2A	-	-	-	Metasediment	8.9	0.25	7.9	20	-	-	600	0.50	1	1.7	0.25	-	26	195	-	72	4.5	-
MS- 420-09-1A	-	-	-	Metasediment	8.3	0.25	7.4	40	-	-	500	1.0	1	0.80	0.25	-	20	164	-	48	3.1	-
MS- 420-09-2A	-	-	-	Metasediment	8.5	0.25	7.1	15	-	-	510	0.50	1	0.77	0.25	-	22	170	-	44	3.6	-
MS- 420-12-1B	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 420-12-2B	-	-	-	Metasediment	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 420-16-1B	-	-	-	Metasediment	8.4	0.25	7.5	5.0	-	-	600	1.5	1	0.58	0.25	-	25	200	-	48	4.0	-
MS- 420-16-2B	-	-	-	Metasediment	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 420 22 1A	-	-	-	Metasediment	8.4	0.25	9.3	340	-	-	580	0.50	1	0.89	0.25	-	22	197	-	43	3.8	-
MS 420 22 1A	-	-	-	Metasediment	9.1	0.25	6.6	10	-	-	420	1.5	1	0.58	0.25	-	4.0	119	-	10	0.79	-
MS 420 22 1B	-	-	-	Metasediment	8.7	0.25	9.6	5.0	-	-	410	1.0	1	1.1	0.25	-	22	202	-	34	3.7	-
MS 420 22 1B	-	-	-	Metasediment	8.3	0.25	5.4	15	-	-	1,140	1.0	1	2.1	0.25	-	34	601	-	24	2.9	-
MS-420-32-1A	-	-	-	Metasediment	8.2	0.5	7.0	195	-	-	410	1.5	1	1.35	0.25	-	19	210	-	61	3.5	-
MS-420-32-2A	-	-	-	Metasediment	8.3	0.5	7.6	55	-	-	380	1.5	1	2.2	0.25	-	19	185	-	60	4.0	-
MS-420-33-1A	-	-	-	Metasediment	8.7	0.25	6.8	55	-	-	550	1.5	1	1.1	0.25	-	21	187	-	60	3.8	-
MS-420-33-2A	-	-	-	Metasediment	8.6	0.25	6.8	10	-	-	480	2.5	4	0.71	0.25	-	20	188	-	53	3.4	-
MS-420-34-1A	-	-	-	Metasediment	8.6	0.25	7.6	15	-	-	560	1.5	1	0.76	0.25	-	20	170	-	39	3.8	-
MS-420-34-2A	-	-	-	Metasediment	8.8	0.25	7.0	2.5	-	-	500	1.5	1	0.84	0.25	-	21	164	-	40	3.7	-
MS-420-35-1A	-	-	-	Metasediment	8.5	0.25	11	15	-	-	630	1.5	1	0.89	0.25	-	21	165	-	53	4.4	-
MS-420-35-2A	-	-	-	Metasediment	8.7	0.5	8.0	15	-	-	570	1.5	2	0.66	0.25	-	21	156	-	42	3.9	-
MS-420-37-1A	-	-	-	Metasediment	8.5	0.5	11	10	-	-	570	1.5	1	1.0	0.25	-	22	187	-	56	4.2	-
MS-420-37-2A	-	-	-	Metasediment	8.5	0.5	7.0	5.0	-	-	530	1.5	1	0.82	0.25	-	21	189	-	58	3.8	-
MS-420-39 1A	-	-	-	Metasediment	9.1	0.25	8.5	10	-	-	670	2.5	1	0.68	0.25	-	13	66	-	52	2.5	-
MS-420-39 2A	-	-	-	Metasediment	8.7	0.25	8.6	2.5	-	-	660	3.0	1	0.63	0.25	-	19	98	-	37	3.3	-
MS-420-40 2A	-	-	-	Metasediment	9.1	0.25	8.2	20	-	-	450	3.0	1	0.70	0.25	-	18	95	-	35	3.6	-

**Table C-1 Metal Contents of Solid Samples
 Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga	
unit	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm			
<i>Metasediment (continued)</i>																							
<i>Misery (continued)</i>																							
MS-420-40 1A	-	-	-	Metasediment	8.8	0.25	8.5	25	-	-	580	3.0	1	0.77	0.25	-	23	109	-	48	4.4	-	
MS-420-40B 1B	-	-	-	Metasediment	9.3	0.25	7.7	60	-	-	460	3.0	1	1.5	0.25	-	23	119	-	74	4.3	-	
MS-420-40B 2B	-	-	-	Metasediment	9.3	0.25	8.0	75	-	-	510	3.0	1	1.4	0.25	-	22	105	-	72	4.4	-	
MS-420-41 1B	-	-	-	Metasediment	8.1	0.25	4.1	2.5	-	-	640	2.5	1	2.1	0.25	-	47	404	-	23	4.1	-	
MS-420-41 2B	-	-	-	Metasediment	9.0	0.25	8.0	40	-	-	560	3.0	1	0.93	0.25	-	15	86	-	41	3.0	-	
MS-420-43 1A	-	-	-	Metasediment	9.1	0.25	8.6	30	-	-	650	3.0	1	0.91	0.25	-	20	92	-	43	3.6	-	
MS-420-43 2A	-	-	-	Metasediment	9.1	0.25	7.7	40	-	-	450	2.5	1	0.80	0.25	-	19	117	-	44	3.7	-	
MS-420-44-1a	-	-	-	Metasediment	9.1	0.25	8.8	15	-	-	640	1.5	1	0.98	0.25	-	24	126	-	57	4.2	-	
MS-420-44-2a	-	-	-	Metasediment	8.8	0.25	7.7	25	-	-	550	1.5	4	0.90	0.25	-	21	106	-	43	3.6	-	
MS-410-01-01	-	-	-	Metasediment	9.1	0.04	8.5	6.8	-	-	540	2.7	0.38	0.53	0.06	-	23	147	-	30	4.3	23	
MS-410-01-02	-	-	-	Metasediment	8.8	0.06	8.6	3.3	-	-	680	1.8	0.49	0.51	0.07	-	24	161	-	38	4.6	23	
MS 410 02 1A	-	-	-	Metasediment	8.7	0.25	9.2	30	-	-	440	1.0	1	0.97	0.25	-	23	203	-	48	3.5	-	
MS 410 02 1B	-	-	-	Metasediment	8.7	0.25	8.3	30	-	-	450	1.5	1	0.72	0.25	-	22	166	-	45	3.6	-	
MS 410 08 1A	-	-	-	Metasediment	8.9	0.25	8.0	2.5	-	-	580	1.5	1	0.82	0.25	-	13	147	-	46	2.1	-	
MS 410 08 1B	-	-	-	Metasediment	8.8	0.25	8.3	2.5	-	-	450	1.5	1	0.94	0.25	-	9.0	101	-	31	1.8	-	
MS 410 11 1A	-	-	-	Metasediment	8.3	0.25	9.2	2.5	-	-	540	0.50	1	0.62	0.25	-	21	188	-	44	3.6	-	
MS 410 11 1B	-	-	-	Metasediment	8.4	0.25	9.4	2.5	-	-	590	1.0	1	0.59	0.25	-	23	166	-	36	3.9	-	
MS-410-29 1B	-	-	-	Metasediment	8.7	0.25	8.5	35	-	-	660	3.0	1	0.83	0.25	-	23	119	-	48	4.2	-	
MS-410-29 2B	-	-	-	Metasediment	8.2	0.25	2.5	2.5	-	-	570	2.0	1	2.6	0.25	-	51	445	-	10	3.4	-	
MS-410-30B 1B	-	-	-	Metasediment	9.2	0.25	8.5	485	-	-	580	3.0	1	1.9	0.50	-	22	126	-	49	3.6	-	
MS-410-30B 2B	-	-	-	Metasediment	8.9	0.25	7.6	270	-	-	750	3.0	1	2.1	0.25	-	34	281	-	58	3.9	-	
MS-410-33 1A	-	-	-	Metasediment	8.7	0.25	8.2	10	-	-	560	3.5	1	0.76	0.25	-	16	130	-	39	3.4	-	
MS-410-33 2B	-	-	-	Metasediment	8.6	0.25	7.4	2.5	-	-	630	2.5	1	1.0	0.25	-	24	192	-	39	3.3	-	
MS-410-34 1A	-	-	-	Metasediment	8.8	0.25	7.9	5.0	-	-	490	3.0	1	0.83	0.50	-	20	94	-	44	3.4	-	
MS-410-34 2A	-	-	-	Metasediment	8.7	0.25	7.7	2.5	-	-	580	2.5	1	0.87	0.25	-	19	121	-	47	3.6	-	
MS-410-35 1A	-	-	-	Metasediment	8.4	0.25	2.6	2.5	-	-	880	2.5	1	2.5	0.25	-	52	531	-	13	3.8	-	
MS-410-35 2A	-	-	-	Metasediment	8.5	0.25	7.7	5.0	-	-	490	2.5	2	0.98	0.25	-	19	113	-	43	3.3	-	
MS-410-37 1A	-	-	-	Metasediment	9.1	0.25	8.1	2.5	-	-	620	2.5	1	0.95	0.25	-	20	104	-	42	3.7	-	
MS-410-37 2A	-	-	-	Metasediment	9.0	0.25	8.3	2.5	-	-	710	3.0	1	0.56	0.25	-	22	110	-	50	4.2	-	
MS-410-39 1A	-	-	-	Metasediment	9.3	0.25	7.6	40	-	-	570	2.5	1	0.88	0.25	-	19	121	-	41	3.4	-	
MS-410-39 2A	-	-	-	Metasediment	9.2	0.25	7.8	15	-	-	510	2.5	1	0.72	0.25	-	15	112	-	34	2.5	-	
MS-410-42 1A	-	-	-	Metasediment	9.2	0.25	8.2	2.5	-	-	530	3.0	1	0.76	0.25	-	19	118	-	54	3.6	-	
MS-410-42 2A	-	-	-	Metasediment	9.0	0.25	6.9	15	-	-	310	4.5	1	3.9	0.50	-	38	101	-	220	9.2	-	
MS-410-43 1A	-	-	-	Metasediment	9.2	0.25	7.8	15	-	-	460	2.5	1	0.98	0.25	-	20	95	-	49	3.4	-	
MS-410-43 2A	-	-	-	Metasediment	9.2	0.25	7.7	2.5	-	-	370	2.5	1	0.84	0.25	-	19	117	-	47	3.2	-	
MS-410-45-1A	-	-	-	Metasediment	9.0	0.25	7.6	2.5	-	-	440	1.5	1	1.0	0.50	-	21	107	-	48	3.7	-	
MS-410-45-2A	-	-	-	Metasediment	9.1	0.25	7.4	2.5	-	-	490	1.5	1	2.0	0.25	-	28	121	-	95	5.7	-	
MS-410-46 1A	-	-	-	Metasediment	9.1	0.25	7.8	95	-	-	500	2.5	1	0.73	0.25	-	19	98	-	34	3.4	-	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Metasediment (continued)																						
Misery (continued)																						
MS-410-46 2A	-	-	-	Metasediment	9.2	0.25	8.4	155	-	-	400	3.0	1	1.5	0.25	-	23	127	-	53	4.3	-
MS-410-47-1A	-	-	-	Metasediment	9.2	0.25	7.4	2.5	-	-	470	1.5	1	0.92	0.25	-	18	108	-	31	3.4	-
MS-410-47-1A	-	-	-	Metasediment	9.3	0.25	7.8	75	-	-	500	1.5	12	1.1	0.25	-	21	109	-	55	3.6	-
MS-410-47-2A	-	-	-	Metasediment	8.9	0.25	7.8	5.0	-	-	600	1.5	14	0.83	0.25	-	20	117	-	45	3.8	-
MS-410-48-1A	-	-	-	Metasediment	8.7	0.25	8.0	65	-	-	610	1.5	1	1.5	1.0	-	23	189	-	54	4.1	-
MS-410-48-2A	-	-	-	Metasediment	8.7	0.25	7.8	55	-	-	520	1.5	1	1.1	0.25	-	22	135	-	48	3.8	-
MS-410-52-1A	-	-	-	Metasediment	8.7	0.25	7.7	280	-	-	650	1.5	1	0.84	0.50	-	22	125	-	52	4.2	-
MS-410-52-2A	-	-	-	Metasediment	8.7	0.25	7.8	15	-	-	650	1.5	2	0.84	0.50	-	17	85	-	41	3.3	-
MS-410-53-1A	-	-	-	Metasediment	8.7	0.25	7.5	15	-	-	590	1.5	1	0.83	0.25	-	22	119	-	48	3.8	-
MS-410-53-2A	-	-	-	Metasediment	8.9	0.25	7.3	20	-	-	470	2.0	2	0.93	0.25	-	20	138	-	58	3.7	-
MS-410-54-1A	-	-	-	Metasediment	9.1	0.25	8.3	55	-	-	660	1.5	10	0.94	0.25	-	23	116	-	92	4.0	-
MS-410-54-2A	-	-	-	Metasediment	9.1	0.25	7.6	15	-	-	610	1.5	1	1.0	1.5	-	21	120	-	55	3.7	-
MS-410-55-1A	-	-	-	Metasediment	9.0	0.25	8.0	45	-	-	580	1.5	1	1.1	0.50	-	20	178	-	42	3.5	-
MS-410-55-2A	-	-	-	Metasediment	8.8	0.25	8.2	20	-	-	610	1.5	1	0.60	1.5	-	22	162	-	45	4.1	-
MS-410-58-1A	-	-	-	Metasediment	8.5	0.25	9.1	20	-	-	700	1.5	1	0.95	0.25	-	25	135	-	55	4.5	-
MS-410-58-2A	-	-	-	Metasediment	8.7	0.25	8.9	35	-	-	580	1.5	2	1.3	0.25	-	24	166	-	60	4.2	-
MS 400-38-1a	-	-	-	Metasediment	9.3	0.25	9.1	135	-	-	730	2.5	1	1.2	0.25	-	23	141	-	52	4.3	-
MS 400-38-2a	-	-	-	Metasediment	9.5	0.25	7.8	50	-	-	650	2.0	1	0.90	0.25	-	21	167	-	56	4.2	-
MS 400-41 2a	-	-	-	Metasediment	9.5	0.25	9.1	2.5	-	-	690	2.5	1	0.88	0.25	-	19	128	-	47	3.7	-
MS 400-42-2a	-	-	-	Metasediment	9.2	0.25	8.7	15	-	-	540	2.0	1	2.5	0.25	-	34	143	-	152	6.8	-
MS 400-43 1a	-	-	-	Metasediment	9.7	0.25	8.4	5.0	-	-	530	1.5	1	1.3	0.25	-	21	129	-	51	3.8	-
MS 400-43 2a	-	-	-	Metasediment	9.3	0.25	8.8	2.5	-	-	640	2.0	1	0.89	0.25	-	23	206	-	45	4.3	-
MS 400-45-1a	-	-	-	Metasediment	8.7	0.25	7.7	20	-	-	800	1.5	1	1.2	0.25	-	21	186	-	48	3.2	-
MS 400-45-2a	-	-	-	Metasediment	9.3	0.25	8.5	5.0	-	-	410	2.0	1	0.74	0.25	-	18	138	-	34	3.6	-
MS-400-12-1A	-	-	-	Metasediment	8.5	0.25	5.8	5.0	-	-	740	1.5	1	1.5	0.50	-	35	251	-	40	3.8	-
MS-400-12-2A	-	-	-	Metasediment	8.5	0.25	7.1	2.5	-	-	640	1.5	1	1.2	0.25	-	23	144	-	42	3.2	-
MS-400-13-1A	-	-	-	Metasediment	8.3	0.25	7.4	2.5	-	-	570	1.5	6	0.69	0.25	-	22	146	-	49	4.0	-
MS-400-13-2A	-	-	-	Metasediment	8.4	0.25	8.0	2.5	-	-	640	1.5	1	0.71	1.0	-	22	151	-	56	4.0	-
MS-400-14-1A	-	-	-	Metasediment	8.7	0.25	8.0	5.0	-	-	370	2.0	1	1.3	0.50	-	19	113	-	29	3.6	-
MS-400-14-2A	-	-	-	Metasediment	8.4	0.25	7.6	10	-	-	640	1.5	1	0.57	0.25	-	21	128	-	51	4.0	-
MS-400-16-1A	-	-	-	Metasediment	8.8	0.25	8.0	195	-	-	510	2.0	1	0.74	0.50	-	20	115	-	39	4.0	-
MS-400-16-2A	-	-	-	Metasediment	8.8	0.25	7.4	5.0	-	-	560	1.5	1	0.69	0.50	-	17	146	-	36	3.6	-
MS-400-18-1A	-	-	-	Metasediment	8.8	0.25	7.3	40	-	-	400	1.5	1	1.4	0.25	-	21	129	-	56	3.8	-
MS-400-18-2A	-	-	-	Metasediment	9.1	0.25	7.6	80	-	-	510	1.5	1	1.7	0.50	-	17	93	-	46	3.1	-
MS-400-20-1A	-	-	-	Metasediment	9.1	0.25	8.0	5.0	-	-	430	2.0	1	0.87	0.50	-	21	114	-	50	3.7	-
MS-400-20-2A	-	-	-	Metasediment	8.6	0.25	7.7	2.5	-	-	510	1.5	2	0.62	0.25	-	20	124	-	35	3.6	-
MS-400-23-1A	-	-	-	Metasediment	8.2	0.25	7.1	2.5	-	-	670	2.0	8	1.6	1.5	-	21	251	-	43	3.6	-
MS-400-23-2A	-	-	-	Metasediment	8.1	0.25	8.0	2.5	-	-	470	1.5	6	0.76	0.50	-	21	161	-	49	3.9	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Metasediment (continued)																						
Misery (continued)																						
MS-400-28-1A	-	-	-	Metasediment	9.2	0.25	7.7	15	-	-	520	1.5	1	1.4	1.0	-	17	149	-	38	3.1	-
MS-400-28-2A	-	-	-	Metasediment	9.3	0.25	8.0	120	-	-	510	2.0	2	1.4	0.25	-	20	234	-	42	3.5	-
MS-400-35-1A	-	-	-	Metasediment	8.3	0.25	8.2	5.0	-	-	530	2.5	6	0.52	1.5	-	19	132	-	43	3.7	-
MS-400-35-2A	-	-	-	Metasediment	8.4	0.25	8.4	15	-	-	570	2.5	1	0.61	0.50	-	21	159	-	49	3.9	-
MS-400-46-1a	-	-	-	Metasediment	9.5	0.25	8.4	130	-	-	600	2.0	1	1.2	0.25	-	20	111	-	47	3.7	-
MS-400-46-2a	-	-	-	Metasediment	9.2	0.25	8.6	115	-	-	650	2.0	1	1.3	0.25	-	24	130	-	49	4.1	-
MS-400-47-2A	-	-	-	Metasediment	9.4	0.25	7.9	125	-	-	550	1.5	8	1.3	1.0	-	21	105	-	59	4.0	-
MS-400-48-1a	-	-	-	Metasediment	9.1	0.25	9.3	80	-	-	550	2.0	4	0.51	0.25	-	24	138	-	57	5.0	-
MS-400-48-2a	-	-	-	Metasediment	9.3	0.25	8.7	25	-	-	560	2.0	1	1.4	0.25	-	23	124	-	59	4.0	-
MS-400-49-1a	-	-	-	Metasediment	9.4	0.25	8.6	370	-	-	510	2.0	1	0.99	0.25	-	19	89	-	31	4.0	-
MS-400-51-1a	-	-	-	Metasediment	9.5	0.25	6.9	50	-	-	430	1.5	1	0.84	0.50	-	10	73	-	26	2.1	-
MS-400-51-2a	-	-	-	Metasediment	8.9	0.25	8.6	20	-	-	540	1.5	1	0.95	0.25	-	22	118	-	53	3.9	-
MS-400-52T-2a	-	-	-	Metasediment	9.3	0.25	8.3	80	-	-	600	2.5	1	0.60	0.25	-	22	164	-	36	3.9	-
MS-400-53-1a	-	-	-	Metasediment	9.2	0.25	7.9	60	-	-	600	1.5	1	1.0	0.25	-	21	97	-	42	3.6	-
MS-400-53-2a	-	-	-	Metasediment	9.1	0.25	7.9	30	-	-	560	3.0	1	0.75	0.25	-	19	122	-	45	3.5	-
MS-400-54-1a	-	-	-	Metasediment	9.4	0.25	8.1	50	-	-	560	1.5	1	1.7	0.25	-	19	130	-	51	3.4	-
MS-400-54-2a	-	-	-	Metasediment	9.3	0.25	8.0	50	-	-	530	2.0	2	1.7	0.25	-	18	123	-	40	3.3	-
MS 390-13-1a	-	-	-	Metasediment	9.1	0.25	8.9	5.0	-	-	650	2.0	1	0.93	0.25	-	20	126	-	51	4.0	-
MS 390-13-2a	-	-	-	Metasediment	9.0	0.25	8.8	10	-	-	710	2.0	2	0.82	0.25	-	20	131	-	49	4.1	-
MS-390-01-1A	-	-	-	Metasediment	8.4	0.25	8.7	45	-	-	570	2.0	1	0.69	1.0	-	22	206	-	44	4.2	-
MS-390-01-2A	-	-	-	Metasediment	8.3	0.25	8.0	2.5	-	-	600	1.5	6	0.77	0.25	-	20	167	-	44	3.8	-
MS 390-12T 1a	-	-	-	Metasediment	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 390-12T 2a	-	-	-	Metasediment	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS-390-21-1a	-	-	-	Metasediment	9.4	0.25	8.5	5.0	-	-	890	2.5	1	0.87	0.25	-	22	118	-	51	4.3	-
MS-390-21-2a	-	-	-	Metasediment	9.3	0.25	8.2	2.5	-	-	570	2.0	1	0.90	0.25	-	22	116	-	51	4.0	-
MS-390-25-1a	-	-	-	Metasediment	9.7	0.5	8.2	5.0	-	-	620	2.5	1	1.2	0.25	-	3.0	52	-	8.0	1.0	-
MS-390-25-2a	-	-	-	Metasediment	9.0	0.25	8.1	5.0	-	-	530	2.0	1	1.0	0.25	-	20	126	-	62	3.7	-
MS-390-27-1a	-	-	-	Metasediment	9.1	0.25	8.5	5.0	-	-	500	1.5	1	1.5	0.25	-	21	101	-	43	3.7	-
MS-390-27-2a	-	-	-	Metasediment	9.0	0.25	8.7	2.5	-	-	540	2.0	1	1.1	0.25	-	26	114	-	71	4.8	-
MS-390-28-1a	-	-	-	Metasediment	9.0	0.25	7.8	2.5	-	-	660	2.0	1	1.2	0.25	-	23	140	-	53	3.5	-
MS-390-28-2a	-	-	-	Metasediment	9.7	0.25	8.2	2.5	-	-	570	2.5	1	1.1	0.25	-	2	27	-	3.0	0.79	-
MS-390-30-1a	-	-	-	Metasediment	8.2	0.25	9.4	25	-	-	730	2.0	1	0.85	0.25	-	35	102	-	155	4.5	-
MS-390-30-2a	-	-	-	Metasediment	9.4	0.25	8.4	5.0	-	-	540	2.0	1	1.1	0.25	-	15	78	-	38	2.6	-
MS-390-31-1a	-	-	-	Metasediment	9.2	0.25	7.9	940	-	-	470	2.0	1	0.86	0.25	-	21	89	-	50	3.1	-
MS-390-31-2a	-	-	-	Metasediment	9.5	0.25	8.5	175	-	-	540	2.0	8	1.2	0.25	-	20	97	-	53	3.3	-
MS-390-32-1a	-	-	-	Metasediment	9.3	0.25	9.1	75	-	-	740	2.0	1	0.94	0.25	-	20	108	-	57	3.9	-
MS-390-32-2a	-	-	-	Metasediment	9.2	0.25	9.9	30	-	-	720	1.5	1	0.94	0.25	-	29	126	-	68	4.7	-
MS-390-33-1a	-	-	-	Metasediment	9.3	0.25	8.7	15	-	-	450	2.0	1	1.3	0.25	-	20	104	-	52	3.6	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Metasediment (continued)																						
Misery (continued)																						
MS-390-33-1a	-	-	-	Metasediment	9.2	0.25	8.4	5.0	-	-	470	1.5	1	1.4	0.25	-	21	97	-	64	3.7	-
MS-390-34-1a	-	-	-	Metasediment	9.2	0.25	8.4	35	-	-	500	1.5	1	1.4	0.25	-	22	98	-	66	4.3	-
MS-390-34-2a	-	-	-	Metasediment	9.7	0.25	8.5	20	-	-	400	1.5	2	0.98	0.25	-	21	97	-	44	3.8	-
MS-390-36-1a	-	-	-	Metasediment	9.2	0.25	6.9	2.5	-	-	220	1.0	1	5.8	1.0	-	50	79	-	315	11	-
MS-390-36-2a	-	-	-	Metasediment	9.2	0.25	8.6	2.5	-	-	460	1.5	1	1.1	0.25	-	22	108	-	68	3.6	-
MS-390-37-1A	-	-	-	Metasediment	8.9	0.25	9.2	20	-	-	530	1.5	1	1.1	0.25	-	24	194	-	64	4.3	-
MS-390-37-2A	-	-	-	Metasediment	8.7	0.25	7.8	95	-	-	480	1.5	1	1.2	0.25	-	20	117	-	45	3.6	-
MS-390-38-1A	-	-	-	Metasediment	9.3	0.25	8.7	25	-	-	440	2.0	1	0.82	0.25	-	25	224	-	44	4.5	-
MS-390-39-1A	-	-	-	Metasediment	8.8	0.25	7.8	15	-	-	470	1.5	1	1.3	0.25	-	23	218	-	69	3.7	-
MS-390-39-2A	-	-	-	Metasediment	8.9	0.25	8.6	180	-	-	550	2.0	1	1.1	0.25	-	24	238	-	44	4.0	-
MS-390-40-1A	-	-	-	Metasediment	8.6	0.25	9.9	95	-	-	560	2.0	2	0.97	0.25	-	25	188	-	41	4.5	-
MS-390-40-2A	-	-	-	Metasediment	8.7	0.25	7.4	75	-	-	280	1.5	1	0.62	0.25	-	19	256	-	34	3.2	-
MS-380-32-2A	-	-	-	Metasediment	8.8	0.25	9.6	2.5	-	-	630	2.0	6	0.77	0.25	-	26	220	-	47	5.0	-
MS-380-60-1	-	-	-	Metasediment	8.9	0.25	8.6	14	-	-	420	1.9	2	0.86	0.50	-	23	128	-	86	3.9	-
MS-380-60-2	-	-	-	Metasediment	8.9	0.25	8.0	2.5	-	-	400	1.6	2	0.92	0.50	-	20	110	-	38	3.8	-
MS-380-58-1	-	-	-	Metasediment	8.8	0.25	7.9	2.5	-	-	410	1.3	2	0.80	0.50	-	20	136	-	52	3.8	-
MS-380-58-2	-	-	-	Metasediment	8.6	0.25	7.9	2.5	-	-	410	1.3	3	0.84	0.50	-	20	146	-	48	3.7	-
MS-370-18-2	-	-	-	Metasediment	8.7	0.25	8.5	11	-	-	590	1.4	1	0.88	0.25	-	21	233	-	55	4.2	-
MS-360-22T-1	-	-	-	Metasediment	8.8	0.25	8.0	92	-	-	470	1.2	1	1.5	0.60	-	24	282	-	48	3.8	-
MS-360-22T-2	-	-	-	Metasediment	8.5	0.25	6.2	2.5	-	-	320	0.90	1	0.53	0.25	-	4.0	166	-	4.0	1.3	-
MS-360-22T-3	-	-	-	Metasediment	8.7	0.25	7.3	53	-	-	390	1.9	1	0.85	0.25	-	12	225	-	27	2.5	-
MS-360-22T-4	-	-	-	Metasediment	8.6	0.25	7.2	17	-	-	200	2.2	1	0.51	0.25	-	2	128	-	3.0	1.0	-
MS-360-26-1	-	-	-	Metasediment	8.7	0.25	7.9	29	-	-	500	1.7	1	0.63	0.25	-	22	242	-	54	3.7	-
MS-360-26-2	-	-	-	Metasediment	8.7	0.25	7.8	12	-	-	600	1.8	1	0.64	0.25	-	21	204	-	45	4.0	-
MS-360-26-3	-	-	-	Metasediment	8.7	0.25	8.2	35	-	-	620	2.0	1	0.80	0.25	-	23	242	-	53	3.9	-
MS-360-26-4	-	-	-	Metasediment	8.4	0.25	8.2	2.5	-	-	620	2.6	1	0.58	0.25	-	22	190	-	60	4.2	-
MS-360-26-5	-	-	-	Metasediment	8.7	0.25	8.1	11	-	-	570	2.5	2	0.72	0.25	-	22	193	-	59	3.5	-
MS-360-26-6	-	-	-	Metasediment	8.7	0.25	7.7	14	-	-	510	1.3	1	1.0	0.25	-	20	197	-	64	3.7	-
MS-320-19-02 14-DEC-04	-	-	-	Metasediment	8.9	0.6	7.4	8.0	-	-	760	1.6	1	1.2	0.25	-	23	333	-	45	3.3	-
MS-320-19-01 14-DEC-04	-	-	-	Metasediment	8.5	0.25	7.8	6.0	-	-	560	1.6	1	0.79	0.25	-	19	282	-	44	3.5	-
MS-310-10-02 20-FEB-05	-	-	-	Metasediment	8.1	0.25	4.4	2.5	-	-	920	0.90	1	3.4	0.25	-	45	513	-	43	4.0	-
MS-310-10-01 20-FEB-05	-	-	-	Metasediment	8.3	0.25	2.1	5.0	-	-	390	0.50	1	2.5	0.25	-	70	827	-	28	4.3	-
MS-290-12-04- 3-Apr-05	-	-	-	Metasediment	9.3	0.25	6.6	2.5	-	-	610	1.7	1	1.1	0.25	-	18	176	-	37	2.8	-
MS-290-12-03- 3-Apr-05	-	-	-	Metasediment	9.1	0.25	6.1	2.5	-	-	570	1.4	1	1.1	0.25	-	22	200	-	35	3.1	-
MS-290-12-02- 3-Apr-05	-	-	-	Metasediment	9.2	0.25	7.8	8.0	-	-	680	1.6	2	0.95	0.25	-	20	158	-	42	3.5	-
MS-290-12-01- 3-Apr-05	-	-	-	Metasediment	8.7	0.25	6.7	12	-	-	660	1.6	1	1.4	0.25	-	21	237	-	40	3.1	-
MGT-49 70-73	-	-	-	Metasediment	9.4	0.05	3.2	38	2.3	10	452	-	0.2	0.43	0.05	-	21	195	-	52	3.8	11
MGT-49 125-128	-	-	-	Metasediment	9.4	0.05	2.9	37	3.6	10	390	-	0.2	0.39	0.05	-	20	154	-	48	3.9	10

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm
Metasediment (continued)																						
Misery (continued)																						
MGT-49 200-203	-	-	-	Metasediment	9.2	0.05	2.7	1.5	0.70	10	340	-	0.3	0.13	0.05	-	19	178	-	46	3.8	11
MGT-49 264-267	-	-	-	Metasediment	9.2	0.05	2.4	4.0	2.4	10	218	-	0.5	0.09	0.05	-	18	131	-	55	3.5	9.0
MGT-51 169-172	-	-	-	Metasediment	9.2	0.05	2.9	1.8	0.25	10	319	-	0.2	0.15	0.05	-	21	171	-	48	4.0	11
MGT-56 230-233	-	-	-	Metasediment	9.2	0.1	2.4	5.9	1.1	10	248	-	0.2	0.15	0.05	-	19	181	-	44	3.5	9.0
MGT-56 290-293	-	-	-	Metasediment	9.4	0.05	2.3	2.8	0.50	10	289	-	0.2	0.12	0.05	-	18	178	-	47	3.5	9.0
MGT-66 9-12	-	-	-	Metasediment	9.0	0.05	0.66	5.3	1.8	10	18	-	3.2	0.28	0.05	-	3.6	121	-	17	0.89	3.0
MGT-66 21-24	-	-	-	Metasediment	9.6	0.1	2.6	5.6	4.5	10	353	-	0.3	0.10	0.05	-	22	178	-	51	3.5	9.0
MGT-66 33-36	-	-	-	Metasediment	9.4	0.05	3.3	1.1	6.5	10	454	-	0.4	0.15	0.05	-	26	204	-	55	4.3	12
MGT-66 41-44	-	-	-	Metasediment	9.8	0.1	2.2	4.1	4.3	10	261	-	0.3	0.39	0.05	-	24	230	-	68	3.5	9.0
MGT-66 52-65	-	-	-	Metasediment	9.6	0.1	2.5	37	0.50	10	254	-	0.3	0.24	0.05	-	22	184	-	36	3.4	9.0
MGT-66 72.47-74.64	-	-	-	Metasediment	10.0	0.1	2.7	20	2.1	10	241	-	0.3	0.14	0.05	-	24	185	-	37	3.8	10
MGT-66 83-86	-	-	-	Metasediment	9.5	0.05	2.4	12	3.6	10	187	-	0.4	0.12	0.05	-	19	167	-	33	3.2	9.0
MGT-66 95-98	-	-	-	Metasediment	9.7	0.1	2.5	10	5.4	10	288	-	0.3	0.11	0.05	-	23	185	-	53	3.6	10
MGT-44 45-48	-	-	-	Metasediment	8.6	0.05	2.6	28	2.0	10	172	-	0.4	0.14	0.05	-	27	165	-	90	4.1	9.0
MGT-44 52-55	-	-	-	Metasediment	8.7	0.05	3.1	4.6	2.6	10	355	-	0.3	0.23	0.05	-	23	177	-	41	4.1	11
MGT-44 70.5-73.5	-	-	-	Metasediment	8.5	0.1	2.8	2.0	2.9	10	351	-	0.8	0.12	0.20	-	24	184	-	94	3.8	11
MGT-51 72-75	-	-	-	Metasediment	9.3	0.1	3.1	44	3.2	10	416	-	0.4	0.30	0.05	-	24	197	-	60	3.8	11
MGT-51 79-82	-	-	-	Metasediment	9.1	0.1	2.6	88	7.6	10	247	-	0.7	0.27	0.10	-	23	204	-	54	3.6	10
MGT-51 220-223	-	-	-	Metasediment	9.3	0.05	0.92	3.8	1.0	10	66	-	0.5	0.15	0.05	-	5.8	105	-	21	1.3	4.0
MGT-51 250-253	-	-	-	Metasediment	9.0	0.05	2.6	1.4	2.6	10	260	-	0.5	0.14	0.05	-	23	168	-	67	3.7	9.0
MGT-51 257-260	-	-	-	Metasediment	9.0	0.05	2.8	1.4	4.0	10	277	-	0.5	0.14	0.05	-	24	181	-	70	3.9	10
MGT-51 328-330	-	-	-	Metasediment	8.7	0.2	1.6	5.1	3.4	10	457	-	0.1	0.80	0.20	-	72	262	-	22	3.9	3.0
MS K 430 45 1A	-	-	-	Metasediment	8.3	0.25	2.6	2.5	-	-	1,060	0.25	1	4.0	0.25	-	52	784	-	23	3.6	-
MS K 430 45 1B	-	-	-	Metasediment	8.3	0.25	2.5	10	-	-	950	0.50	1	3.2	0.25	-	53	847	-	21	3.8	-
Median					8.7	0.25	7.9	13	2.6	10	540	1.5	1	0.89	0.25	-	21	164	-	46	3.7	11
Minimum					7.1	0.04	0.66	1.0	0.25	10	18	0.25	0.1	0.09	0.05	-	2.0	27	-	3.0	0.68	3.0
Maximum					10.0	1.0	12	940	7.6	10	1,190	4.5	16	5.8	1.5	-	72	847	-	315	11	23
Count					370	333	333	333	29	29	333	303	333	333	333	0	333	333	0	333	333	43
Pigeon																						
97-54	97-54	29.57	30	Metasediment	8.4	0.1	2.9	2.5	-	-	70	0.50	2.5	0.15	0.5	-	23	136	-	21	4.5	-
94-7 6.71-10	94-7	6.71	10	Metasediment	8.2	-	8.2	2.5	-	-	450	1.0	1	0.68	0.25	-	25	189	-	48	4.3	-
94-7 10-15	94-7	10	15	Metasediment	-	-	8.3	2.5	-	-	460	1.0	1	0.62	0.25	-	24	118	-	56	4.3	-
94-7 15-19.3	94-7	15	19.3	Metasediment	-	-	7.9	5.0	-	-	550	1.0	1	1.1	0.25	-	29	150	-	35	5.0	-
94-7 19.3-22	94-7	19.3	22	Metasediment	-	-	8.7	2.5	-	-	510	0.50	1	1.6	0.25	-	23	95	-	46	4.3	-
94-7 22-27	94-7	22	27	Metasediment	-	-	8.8	2.5	-	-	550	0.50	1	1.6	0.25	-	22	93	-	55	4.5	-
94-7 27-32	94-7	27	32	Metasediment	8.4	-	8.4	5.0	-	-	460	0.50	1	0.40	0.25	-	26	120	-	56	4.7	-
94-7 32-37	94-7	32	37	Metasediment	-	-	9.5	2.5	-	-	520	0.50	1	0.54	0.25	-	23	133	-	43	4.4	-
94-7 37-42	94-7	37	42	Metasediment	-	-	8.9	2.5	-	-	470	1.0	1	0.90	0.25	-	20	105	-	30	3.8	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga	
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm
Metasediment (continued)																							
Pigeon (continued)																							
94-7 42-47	94-7	42	47	Metasediment	-	-	9.5	2.5	-	-	540	0.50	1	0.55	0.25	-	25	134	-	52	4.6	-	
94-7 47-52	94-7	47	52	Metasediment	-	-	9.2	2.5	-	-	560	0.50	1	0.67	0.25	-	21	108	-	46	4.0	-	
94-7 52-57	94-7	52	57	Metasediment	8.8	-	9.5	2.5	-	-	520	1.0	1	1.4	0.25	-	23	105	-	28	4.4	-	
94-7 57-62	94-7	57	62	Metasediment	-	-	10	5.0	-	-	640	1.5	1	0.89	0.25	-	29	150	-	41	5.0	-	
94-7 62-67	94-7	62	67	Metasediment	-	-	9.2	2.5	-	-	530	1.0	1	1.3	0.25	-	23	127	-	41	4.2	-	
94-7 67-72	94-7	67	72	Metasediment	-	-	9.2	2.5	-	-	540	0.50	1	1.2	0.25	-	21	92	-	45	3.8	-	
HC-Pdef-2	-	-	-	Metasediment	8.8	0.14	8.9	2.9	-	-	580	1.4	0.02	0.18	0.27	49	29	161	4.1	24	4.7	29	
HC-Pdef-3	-	-	-	Metasediment	9.5	0.06	9.4	0.2	-	-	640	2.4	0.04	0.60	0.03	58	28	163	14	74	5.0	27	
HC-Pdef-4	-	-	-	Metasediment	9.6	0.06	8.0	0.8	-	-	460	1.4	0.04	3.0	0.08	49	32	145	7.8	70	4.8	24	
HC-Pdef-5	-	-	-	Metasediment	9.6	0.08	8.7	0.4	-	-	340	0.85	0.04	3.9	0.05	36	29	25	13	133	5.4	23	
HC-Pdef-8	-	-	-	Metasediment	9.4	0.06	9.0	1.0	-	-	660	1.9	0.03	0.66	0.02	66	30	179	12	50	5.3	28	
HC-Pdef-9	-	-	-	Metasediment	9.4	0.02	8.2	0.5	-	-	460	1.9	0.03	0.71	0.03	64	23	138	11	2.4	4.1	24	
HC-Pdef-10	-	-	-	Metasediment	9.7	0.07	6.1	7.1	-	-	640	1.7	0.12	6.9	0.30	87	44	449	24	78	6.6	17	
HC-Pdef-11	-	-	-	Metasediment	9.2	0.06	8.1	0.6	-	-	410	1.5	0.03	0.63	0.01	61	22	139	7.6	125	4.3	22	
HC-Pdef-13	-	-	-	Metasediment	9.5	0.02	9.2	0.7	-	-	540	1.8	0.02	1.0	0.01	76	22	138	13	16	4.6	25	
HC-Pdef-14	-	-	-	Metasediment	9.5	0.03	8.3	4.2	-	-	460	1.9	0.02	0.73	0.01	64	21	149	11	6.2	4.1	21	
HC-Pdef-15	-	-	-	Metasediment	9.4	0.05	8.0	1.4	-	-	470	1.3	0.03	0.59	0.01	61	23	148	8.3	8.9	4.3	23	
HC-Pdef-16	-	-	-	Metasediment	8.0	0.07	8.9	4.0	-	-	550	1.2	0.03	0.32	0.04	65	26	152	4.9	79	4.7	27	
HC-PDef-18	-	-	-	Metasediment	9.2	0.11	8.8	2.2	-	-	440	1.9	0.03	0.69	0.02	59	21	129	7.8	35	4.0	22	
HC-PDef-19	-	-	-	Metasediment	9.8	0.01	7.7	0.2	-	-	580	1.7	0.03	0.66	0.01	44	25	153	11	2.7	4.8	25	
HC-PDef-20	-	-	-	Metasediment	9.3	0.13	9.7	0.3	-	-	550	2.2	0.03	0.36	0.01	49	27	169	9.9	44	5.3	26	
HC-PDef-21	-	-	-	Metasediment	9.6	0.01	9.9	2.1	-	-	650	2.4	0.04	1.1	0.01	47	28	184	13	6.3	5.5	30	
HC-PDef-22	-	-	-	Metasediment	9.8	0.005	8.3	0.2	-	-	570	1.9	0.02	1.2	0.01	63	15	80	9.3	2.4	3.0	20	
HC-PDef-23	-	-	-	Metasediment	9.5	0.11	8.8	0.1	-	-	490	2.0	0.05	0.75	0.02	55	20	129	9.9	51	4.1	21	
HC-PDef-26	-	-	-	Metasediment	9.3	0.13	9.5	0.3	-	-	510	1.9	0.03	0.32	0.01	47	24	161	4.5	50	5.0	25	
HC-PDef-28	-	-	-	Metasediment	9.8	0.01	8.3	0.1	-	-	310	1.4	0.02	2.1	0.02	41	12	29	5.4	3.9	2.2	20	
HC-PDef-31	-	-	-	Metasediment	9.2	0.02	9.1	12	-	-	510	1.3	0.02	0.39	0.01	49	25	139	6.1	1.7	4.2	25	
HC-PDef-32	-	-	-	Metasediment	9.0	0.005	8.4	0.9	-	-	430	1.6	0.02	0.49	0.01	37	20	106	5.3	3.0	4.3	23	
HC-PDef-35	-	-	-	Metasediment	9.4	0.005	7.8	2.1	-	-	510	1.5	0.01	1.2	0.01	56	17	89	7.2	0.6	3.1	19	
Median					9.4	0.06	8.8	2.5	-	-	515	1.4	0.04	0.70	0.05	56	23	137	9.3	42	4.4	24	
Minimum					8.0	0.005	2.9	0.1	-	-	70	0.50	0.01	0.15	0.01	36	12	25	4.1	0.6	2.2	17	
Maximum					9.8	0.14	10	12	-	-	660	2.4	2.5	6.9	0.50	87	44	449	24	133	6.6	30	
Count					27	24	38	38	0	0	38	38	38	38	38	23	38	38	23	38	38	23	
Jay																							
2014-DD-001	JGT-04	35.58	41.58	Metasediment	8.30	0.05	3.48	8	-	-	40	497	0.7	0.72	0.2	0.02	37.7	21.1	244	9.82	24.3	4.44	12.4
2014-DD-002	JGT-04	41.58	48.98	Metasediment	7.94	0.03	3.71	6	-	-	40	490	0.7	0.27	0.13	0.03	44.2	21.9	212	12.6	30.4	4.6	13.1
2014-DD-005	JGT-04	74.58	83.58	Metasediment	9.05	0.02	0.24	0.5	-	-	5	17	0.05	0.82	0.08	0.03	1.21	0.7	203	0.3	5.3	0.32	0.9
2014-DD-006	JGT-04	86.17	95.58	Metasediment	8.29	0.12	4.19	15	-	-	50	418	0.7	0.44	0.13	0.09	42.1	26.1	254	9.79	50	5.33	14.4

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19		
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga		
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	
Metasediment (continued)																								
Jay (continued)																								
2014-DD-007	JGT-04	100	107.7	Metasediment	8.58	0.12	3.8	7	-	60	671	0.7	0.26	0.62	0.08	47.9	24.1	276	11.2	52.6	4.59	13.5		
2014-DD-008	JGT-04	114.12	122.54	Metasediment	8.26	0.06	4.11	7	-	60	391	0.6	0.29	0.12	0.04	41.7	28.2	294	6.85	58.5	4.86	14.3		
2014-DD-009	JGT-04	125.58	135.9	Metasediment	8.69	0.05	3.38	9	-	40	222	1.1	0.56	0.34	0.05	39.5	19.7	269	21.6	48.3	4.29	12		
2014-DD-010	JGT-04	142.21	147.1	Metasediment	8.24	0.13	4.37	16	-	40	407	0.5	0.61	0.13	0.05	53.1	27.7	239	13.8	48.4	5.16	15		
2014-DD-011	JGT-04	147.1	152.58	Metasediment	8.01	0.08	4.28	19	-	40	493	0.5	0.29	0.09	0.03	56	28.8	213	11.9	42.5	5.15	14.8		
2014-DD-012	JGT-04	155.58	163.58	Metasediment	8.14	0.04	4.25	6	-	50	507	0.4	0.28	0.09	0.02	49.9	24.5	229	9.23	18	5.13	14.6		
2014-DD-013	JGT-04	163.38	171.69	Metasediment	8.48	0.05	4.15	5	-	40	473	0.6	0.19	0.46	0.03	52	21	216	9.75	32.9	4.44	13.9		
2014-DD-014	JGT-04	174.5	180	Metasediment	8.88	0.04	2.63	1	-	30	430	0.3	0.15	0.43	0.04	42.2	14.7	175	6.13	18.9	3.42	10		
2014-DD-015	JGT-04	188	196.2	Metasediment	8.38	0.12	4.96	75	-	50	511	0.8	0.31	0.53	0.06	58.5	29	206	13.6	32	5.34	15.9		
2014-DD-016	JGT-04	199	206.58	Metasediment	8.17	0.14	4.21	13	-	40	459	0.8	0.61	0.12	0.03	59.4	27.2	226	12.2	56.1	5.05	14.8		
2014-DD-017	JGT-04	221	230	Metasediment	8.57	0.17	3.25	7	-	30	300	1.1	0.61	0.19	0.12	49.4	23	265	15.7	62.3	4.29	11.7		
2014-DD-018	JGT-04	231.28	241	Metasediment	8.64	0.14	2.91	2	-	20	283	1.1	0.43	0.1	0.05	45	23.1	266	19.2	52.5	3.75	11.1		
2014-DD-019	JGT-04	241	251	Metasediment	9.10	0.11	2.66	2	-	20	242	1	0.53	0.24	0.11	46.9	19.5	250	20.1	37.1	3.55	10.1		
2014-DD-020	JGT-04	251	260	Metasediment	9.51	0.03	1.54	2	-	10	86	0.9	0.45	0.47	0.03	34.5	11.5	203	9.92	7.6	2.52	6.4		
2014-DD-022	JGT-05	15.2	16.44	Metasediment	8.99	0.08	2.39	2	-	20	130	0.3	0.07	0.07	0.06	29.9	12.6	268	10.2	54.5	4.38	12.7		
2014-DD-033	JGT-05	281.55	287.77	Metasediment	9.12	0.12	3.65	3	-	20	474	0.7	0.15	0.14	0.03	39.4	28	281	11.5	65.9	4.73	13.5		
2014-DD-034	JGT-05	287.77	292.77	Metasediment	9.48	0.08	3.09	3	-	20	150	0.3	0.07	0.07	0.02	47.9	23.3	275	9.39	23.1	4.05	12.2		
2014-DD-035	JGT-05	299.18	308.77	Metasediment	9.13	0.13	3.69	2	-	20	417	0.3	0.17	0.12	0.06	40.8	28.1	250	12.4	80.5	4.96	15.5		
2014-DD-036	JGT-05	308.77	317	Metasediment	9.29	0.09	2.56	3	-	10	120	0.2	0.11	0.22	0.07	42.2	19.2	241	8.08	48.7	3.58	13.4		
2014-DD-037	JGT-05	336	346	Metasediment	9.87	0.13	2.3	0.5	-	10	221	0.6	0.12	0.06	0.07	47.4	21.5	273	9.41	61.3	3.32	10		
Median					8.6	0.085	3.6	5.5	-	35	412	0.65	0.29	0.13	0.045	44.6	23	247	10.7	48	4.4	13.25		
Minimum					7.9	0.02	0.2	0.5	-	5	17	0.05	0.07	0.06	0.02	1.21	1	175	0.3	5	0.3	0.9		
Maximum					9.9	0.17	5.0	75.0	-	60	671	1.1	0.82	0.62	0.12	59.4	29	294	21.6	81	5.3	15.9		
Count					24	24	24	24	0	24	24	24	24	24	24	24	24	24	24	24	24	24	24	
Waste Rock																								
Fox																								
SRK FOX 2	SRK FOX 2	0	0.3	Mixed Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
SRK FOX 4	SRK FOX 4	0	0.3	Mixed Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
SRK FOX 1	SRK FOX 1	0	0.3	Mixed Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
SRK FOX 3	SRK FOX 3	0	0.3	Mixed Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
SRK FOX 5	SRK FOX 5	0	0.3	Mixed Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
Median					9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Minimum					8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Maximum					9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Count					5	0	0	0	0	0	-	0	0	0	0	0	0	0	0	0	0	0	0	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm	
Waste Rock (continued)																							
Koala																							
KNW 420 06+07 1A	-	-	-	Waste Rock	8.0	0.1	3.4	0.5	-	-	860	1.0	2	3.1	0.50	-	55	567	-	23	3.8	-	
KNW 420 06+07 2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 465-1 2-1A	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 465-1 2-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-16 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450- 18+21 1	-	-	-	Waste Rock	9.6	0.1	9.3	1.0	-	-	580	1.0	1	2.8	0.50	-	17	124	-	11	2.5	-	
KSW 450- 18+21 2	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-20 1A	-	-	-	Waste Rock	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-20 2A	-	-	-	Waste Rock	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-22 2A	-	-	-	Waste Rock	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-22 2AA	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-23 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-23 2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-25-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-25-2A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-28-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-28-2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-29-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-29-2A	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-31-1A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450-31-2A	-	-	-	Waste Rock	9.0	0.1	9.6	0.5	-	-	690	1.5	1	3.2	0.25	-	16	175	-	16	3.2	-	
KSW- 450-34-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW- 450-34-2A	-	-	-	Waste Rock	9.1	0.2	10	0.5	-	-	700	0.50	1	3.7	0.25	-	17	156	-	11	3.2	-	
KSW- 450-35-1A	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW- 450-35-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW- 450-36-1A	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW- 450-36-2A	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW- 450-38-1A	-	-	-	Waste Rock	8.5	0.1	9.8	5.0	-	-	700	1.5	1	2.6	0.25	-	16	190	-	18	3.2	-	
KSW- 450-38-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450 39 1A	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 450 39 2A	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 443-27 1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 443-27 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 443-28 1A	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 443-28 2A	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 443-32-1A	-	-	-	Waste Rock	9.3	0.1	9.9	1.0	-	-	690	1.0	2	2.9	0.25	-	17	206	-	21	3.2	-	
KSW 443-32-1AA	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW 443-32-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Koala (continued)																						
KSW 443-32-2AA	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-33-1A	-	-	-	Waste Rock	9.4	0.1	9.5	0.5	-	-	610	1.5	1	3.2	0.25	-	15	148	-	10	2.7	-
KSW 443-33-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-34-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-34-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-35-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-35-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-36-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-36-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-38-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-38-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 445-40-2A	-	-	-	Waste Rock	8.7	0.1	11	0.5	-	-	850	1.5	1	3.6	0.25	-	18	169	-	8.0	3.5	-
KSW- 445-40-1A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-41-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-41-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-42-1A	-	-	-	Waste Rock	7.4	0.1	8.2	6.0	-	-	490	1.5	1	1.0	0.25	-	12	216	-	22	2.2	-
KSW- 443-42-2A	-	-	-	Waste Rock	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-43-1A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-43-2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443+450 2A	-	-	-	Waste Rock	9.6	0.1	9.4	0.5	-	-	590	1.0	1	3.2	0.25	-	19	131	-	9.0	2.9	-
KSW 443+450 1A	-	-	-	Waste Rock	9.4	0.2	8.7	0.5	-	-	570	1.0	1	3.0	0.25	-	20	131	-	10	2.6	-
KSW 443 46 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443 46 2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-6 1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-6 2A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-7 1A	-	-	-	Waste Rock	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-7 2A	-	-	-	Waste Rock	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-10-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-10-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-15-1A	-	-	-	Waste Rock	9.1	0.1	7.6	3.0	-	-	470	1.5	1	1.5	0.25	-	8.0	173	-	30	2.0	-
KSW 435-15-2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-16-1A	-	-	-	Waste Rock	8.7	0.1	9.9	0.5	-	-	640	1.0	1	3.0	0.25	-	12	147	-	29	2.4	-
KSW- 435-16-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-23-1A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-23-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 24 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 24 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-25 1A	-	-	-	Waste Rock	9.3	1.2	6.3	2.0	-	-	390	1.5	1	0.95	0.25	-	11	176	-	29	1.8	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Koala (continued)																						
KSW 435 26 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 26 2A	-	-	-	Waste Rock	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 27 1A	-	-	-	Waste Rock	9.7	0.25	9.3	5.0	-	-	660	1.0	1	3.0	0.25	-	16	107	-	22	3.1	-
KSW 435 27 2A	-	-	-	Waste Rock	9.6	0.25	8.8	15	-	-	600	1.0	1	2.9	0.25	-	18	139	-	53	3.3	-
KSW 435 30 1A	-	-	-	Waste Rock	8.4	0.25	7.1	5.0	-	-	570	1.5	1	0.72	0.25	-	9.0	107	-	17	1.9	-
KSW 435 30 2A	-	-	-	Waste Rock	9.4	0.25	7.6	5.0	-	-	420	2.5	1	1.7	0.25	-	16	151	-	21	2.8	-
KSW 435 31 1A	-	-	-	Waste Rock	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 31 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 34 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 34 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 42 1A	-	-	-	Waste Rock	9.2	0.25	8.4	5.0	-	-	530	1.5	1	1.9	0.25	-	18	120	-	21	2.3	-
KSW 435 42 2A	-	-	-	Waste Rock	9.5	0.25	8.8	2.5	-	-	770	1.0	1	2.4	0.25	-	24	150	-	132	2.9	-
KSW 435 51 1A	-	-	-	Waste Rock	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 51 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 52 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 52 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 53 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 53 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 54 1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 54 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 55 1A	-	-	-	Waste Rock	9.8	0.25	9.3	10	-	-	700	0.50	1	2.6	0.25	-	19	101	-	31	2.7	-
KSW 435 55 2A	-	-	-	Waste Rock	9.7	0.25	8.8	2.5	-	-	770	0.50	1	2.5	0.25	-	22	116	-	53	3.0	-
KSW 435 60 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 60 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 66 1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 66 2A	-	-	-	Waste Rock	7.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-59-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-59-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-77-1A	-	-	-	Waste Rock	9.3	0.25	9.0	5.0	-	-	700	0.50	1	3.3	0.25	-	18	96	-	21	3.1	-
KSW- 435-77-2A	-	-	-	Waste Rock	9.3	0.25	8.1	5.0	-	-	700	0.50	1	3.0	0.25	-	17	94	-	28	2.8	-
KSW- 435-81-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-81-2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-07-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-07-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-09-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-09-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-14-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-14-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Koala (continued)																						
KSW 420 34 1A	-	-	-	Waste Rock	9.0	0.25	9.7	2.5	-	-	610	0.50	8	3.5	0.25	-	20	117	-	21	3.1	-
KSW 420 34 2A	-	-	-	Waste Rock	9.0	0.25	9.4	2.5	-	-	610	0.50	1	3.3	0.25	-	18	120	-	32	3.0	-
KSW 420 36 1A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 36 2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 37 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 37 2A	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 39 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 39 2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-30-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-30-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-38-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-38-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-38A-1A	-	-	-	Waste Rock	9.7	0.25	9.6	2.5	-	-	640	1.5	4	3.4	0.25	-	16	129	-	14	3.1	-
KSW-420-38A-2A	-	-	-	Waste Rock	9.5	0.25	9.9	5.0	-	-	670	1.5	2	1.6	0.25	-	12	84	-	25	2.6	-
KSW-420-40-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-40-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-41-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-41-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-46 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-46 2A	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405 04 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405 04 2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405 05 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405 05 2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405-25 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-06-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-06-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-10-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-10-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-11-1A	-	-	-	Waste Rock	8.8	0.25	9.0	2.5	-	-	710	1.5	1	2.4	0.25	-	12	98	-	37	2.7	-
KSW-405-11-2A	-	-	-	Waste Rock	8.7	0.5	7.4	2.5	-	-	520	1.0	2	1.8	0.25	-	15	97	-	74	2.4	-
KSW-405-13-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-13-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-17-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-17-2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-19-1A	-	-	-	Waste Rock	8.9	0.25	11	2.5	-	-	640	1.5	1	3.0	0.25	-	15	127	-	26	2.9	-
KSW-405-19-2A	-	-	-	Waste Rock	8.7	0.25	7.5	2.5	-	-	820	1.5	1	3.3	0.25	-	16	156	-	48	2.7	-
KSW-405-25 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Koala (continued)																						
KSW-405-38 1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-38 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-40 1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-40 2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-45 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-45 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-49 1A	-	-	-	Waste Rock	9.3	0.25	8.2	5.0	-	-	620	2.5	1	3.1	0.25	-	16	73	-	11	2.8	-
KSW-405-49 2A	-	-	-	Waste Rock	9.6	0.25	8.5	2.5	-	-	720	2.5	1	3.2	0.25	-	17	150	-	51	3.3	-
KSW-405-52-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-52-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-57-1A	-	-	-	Waste Rock	9.2	0.25	9.2	2.5	-	-	660	1.5	2	3.4	0.25	-	17	66	-	18	3.2	-
KSW-405-57-2A	-	-	-	Waste Rock	9.3	0.25	8.4	2.5	-	-	600	1.5	4	2.9	0.50	-	14	66	-	29	2.8	-
KSW-405-63-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-63-2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 390-21 1a	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 390-21 2a	-	-	-	Waste Rock	9.8	0.25	9.4	2.5	-	-	800	1.5	1	3.0	0.25	-	14	89	-	24	2.8	-
KSW-390-03-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-03-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-05-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-05-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-06-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-06-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-08-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-08-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-09-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-09-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-10-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-10-2A	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-11-1A	-	-	-	Waste Rock	8.5	0.25	9.2	2.5	-	-	620	1.5	10	2.7	0.50	-	16	105	-	8.0	3.0	-
KSW-390-11-2A	-	-	-	Waste Rock	8.8	0.25	9.2	2.5	-	-	620	1.5	1	2.9	0.25	-	14	95	-	11	2.7	-
KSW-390-12-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-12-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-24-1a	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-24-2a	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 375-03 1a	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 375-03 2a	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 375-06 1a	-	-	-	Waste Rock	9.6	0.25	9.8	2.5	-	-	590	1.5	1	2.5	0.25	-	9.0	48	-	13	2.2	-
KSW 375-06 2a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Koala (continued)																						
KSW-375-13-1a	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-375-13-2a	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Median					9.2	0.25	9.2	2.5	-	-	640	1.5	1	3.0	0.25	-	16	126	-	22	2.8	-
Minimum					7.2	0.1	3.4	0.5	-	-	390	0.50	1	0.72	0.25	-	8.0	48	-	8.0	1.8	-
Maximum					10.1	1.2	11	15	-	-	860	2.5	10	3.7	0.50	-	55	567	-	132	3.8	-
Count					192	40	40	40	0	0	40	40	40	40	40	0	40	40	0	40	40	0
Panda																						
PPW 360-76 1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-76 2A	-	-	-	Waste Rock	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-76-1B	-	-	-	Waste Rock	9.7	0.1	10	0.5	-	-	640	1.5	1	3.7	0.25	-	20	129	-	35	2.9	-
PPW- 360-76-2B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-77 1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-77 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-77-1B	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-77-2B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-78 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-78 2A	-	-	-	Waste Rock	9.5	0.1	9.3	1.0	-	-	710	1.5	1	3.3	0.50	-	22	200	-	44	3.0	-
PPW- 360-78-1B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-78-2B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-79 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-79 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-79-1B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-79-2B	-	-	-	Waste Rock	9.8	0.1	9.6	0.5	-	-	690	1.5	1	3.2	0.25	-	20	130	-	56	3.0	-
PPW 360-80 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-80 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-80-1B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-80-2B	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-82 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-82 2A	-	-	-	Waste Rock	9.4	0.1	9.5	3.0	-	-	630	2.0	1	3.5	0.50	-	22	184	-	29	3.0	-
PPW- 360-82-1B	-	-	-	Waste Rock	9.6	0.1	9.9	0.5	-	-	660	1.0	1	3.5	0.25	-	20	112	-	40	2.9	-
PPW- 360-82-2B	-	-	-	Waste Rock	9.7	0.1	9.8	0.5	-	-	650	1.5	1	3.5	0.25	-	19	112	-	40	2.8	-
PPW 360-89 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-89 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-29 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-29-1B	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-33 1A	-	-	-	Waste Rock	9.5	0.1	9.8	3.0	-	-	660	1.5	1	3.6	0.50	-	22	167	-	26	3.0	-
PPW 345-33 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-33-1B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Panda (continued)																						
PPW- 345-33-2B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-34 1A	-	-	-	Waste Rock	12.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-34 2A	-	-	-	Waste Rock	10.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-34-1B	-	-	-	Waste Rock	11.8	0.1	9.2	1.0	-	-	670	1.0	1	5.9	0.25	-	18	132	-	49	2.7	-
PPW- 345-34-2B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-35 1A	-	-	-	Waste Rock	10.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-35 2A	-	-	-	Waste Rock	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-35-1B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-35-2B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-36 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-36 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-36-1B	-	-	-	Waste Rock	9.3	0.1	9.1	0.5	-	-	700	1.5	1	2.8	0.25	-	21	173	-	50	2.7	-
PPW- 345-36-2B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-37 1A	-	-	-	Waste Rock	9.8	0.1	8.9	2.0	-	-	610	1.5	6	3.3	0.25	-	19	125	-	46	2.8	-
PPW 345-37 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-37-1B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-37-2B	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-41-1	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-42 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-42 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-42-1	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-42-2	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-43 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-43 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-43-1	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-43-2	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-48 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-49 1A	-	-	-	Waste Rock	9.6	0.2	9.5	0.5	-	-	620	1.5	1	3.4	0.25	-	20	229	-	10	2.7	-
PPW 345-49 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-50-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-50-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-52 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-52 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-55 1A	-	-	-	Waste Rock	9.5	0.2	9.5	0.5	-	-	620	1.5	1	3.3	0.50	-	20	183	-	20	2.8	-
PPW 345-55 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-56 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-56 2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-13 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Panda (continued)																						
PPW- 330-13-1B	-	-	-	Waste Rock	9.0	0.1	9.8	0.5	-	-	710	1.5	1	3.2	0.25	-	16	159	-	68	2.9	-
PPW- 330-16-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-16-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-17 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-17 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-17-1B	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-17-2B	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-18 1A	-	-	-	Waste Rock	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-18 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-18-1B	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-18-2B	-	-	-	Waste Rock	9.5	0.1	9.4	0.5	-	-	630	1.5	1	3.3	0.25	-	18	158	-	59	2.9	-
PPW 330-20 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-20 2A	-	-	-	Waste Rock	9.4	0.2	9.3	3.0	-	-	600	1.5	1	3.1	0.25	-	20	176	-	73	2.8	-
PPW- 330-20-1B	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-20-2B	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-28 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-28 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-28-1B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-28-2B	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-30 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-30 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-32-1A	-	-	-	Waste Rock	9.3	0.2	9.6	0.5	-	-	620	1.5	1	3.3	0.25	-	18	193	-	22	3.2	-
PPW 330-32-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-37-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-37-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-38 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-38 2A	-	-	-	Waste Rock	9.6	0.1	9.8	0.5	-	-	600	1.5	1	3.7	0.50	-	22	183	-	22	3.1	-
PPW 330-41-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-41-1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-41-2	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-41-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-44 1A	-	-	-	Waste Rock	9.7	0.1	9.5	0.5	-	-	590	1.5	1	3.4	0.25	-	21	209	-	10	3.0	-
PPW 330-44 1AA	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-44 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-44 2AA	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-47 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-47 2A	-	-	-	Waste Rock	9.6	0.1	9.1	0.5	-	-	580	1.5	1	3.3	1.0	-	24	201	-	39	2.8	-
PPW 330-48 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Panda (continued)																						
PPW 330-49 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-49 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-50 1A	-	-	-	Waste Rock	9.5	0.1	9.6	0.5	-	-	600	1.5	4	3.2	0.25	-	19	200	-	14	2.7	-
PPW 330-50 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-56 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-56 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-59 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-59 2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-61 1A	-	-	-	Waste Rock	9.5	0.1	10	2.0	-	-	670	1.5	1	3.7	0.25	-	21	141	-	42	3.1	-
PPW 330-61 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-62 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-62 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-63 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-63 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-64 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-64 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-65-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-65-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-66-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-66-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-70-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-70-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-71-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-71-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-72-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-72-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-73-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-73-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 332-75-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 332-75-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-76-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-77-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-77-2A	-	-	-	Waste Rock	9.2	0.1	9.8	0.5	-	-	700	1.5	1	3.4	0.25	-	17	173	-	30	3.2	-
PWP- 330-80-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-80-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-82-1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-03 1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-03 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Panda (continued)																						
PPW 315-04 1A	-	-	-	Waste Rock	9.5	0.2	9.3	3.0	-	-	620	1.5	2	3.4	0.50	-	22	171	-	27	3.0	-
PPW 315-04 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-05 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-05 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-06 1A	-	-	-	Waste Rock	9.8	0.2	9.4	3.0	-	-	580	1.5	1	3.2	0.25	-	16	135	-	25	2.7	-
PPW 315-06 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-10-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-10-2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-11-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-11-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-13-1A	-	-	-	Waste Rock	9.2	0.1	9.5	0.5	-	-	660	1.0	1	3.1	0.25	-	15	188	-	35	2.9	-
PPW 315-13-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-14-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-14-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-16-1A	-	-	-	Waste Rock	9.2	0.1	9.9	2.0	-	-	650	1.5	1	3.7	0.25	-	18	169	-	42	3.4	-
PPW 315-16-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-17-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 317-17-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-18-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-18-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-19-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-19-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-20-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-20-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-22-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-22-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-23-1A	-	-	-	Waste Rock	9.0	0.2	8.5	0.5	-	-	490	1.5	1	1.7	0.25	-	4.0	178	-	6.0	1.2	-
PPW 315-23-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-24-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-24-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-25-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-25-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-28-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-28-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-26-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-26-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-27-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-27-2A	-	-	-	Waste Rock	9.3	0.1	9.7	1.0	-	-	630	1.0	1	3.4	0.25	-	17	173	-	15	3.1	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Panda (continued)																						
PWP- 315-28-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-28-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-31-1A	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-31-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-31-2A	-	-	-	Waste Rock	8.4	0.1	8.6	1.0	-	-	430	1.5	1	0.35	0.25	-	13	153	-	1.0	3.3	-
PWP- 315-31-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-33-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-33-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-34-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-34-2A	-	-	-	Waste Rock	9.1	0.1	10	0.5	-	-	720	1.0	1	3.9	0.25	-	18	149	-	35	3.4	-
PWP- 315-35-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-35-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-36-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-36-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-42-1A	-	-	-	Waste Rock	9.4	0.1	11	0.5	-	-	680	1.5	1	4.5	0.25	-	19	179	-	39	3.6	-
PWP- 315-42-2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-43-1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-43-2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-44-1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-44-2A	-	-	-	Waste Rock	9.7	0.1	11	0.5	-	-	690	1.5	1	3.7	0.25	-	17	176	-	11	3.1	-
PWP- 315-45-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-45-2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-46-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-46-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315 48 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315 48 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-76-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-22-1A	-	-	-	Waste Rock	8.8	0.1	11	0.5	-	-	750	1.5	1	3.9	0.25	-	19	176	-	13	3.5	-
PWP- 300-22-2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-24-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-24-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-35-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-35-2A	-	-	-	Waste Rock	9.4	0.1	11	1.0	-	-	700	1.5	1	4.1	0.25	-	19	188	-	8.0	3.5	-
PWP- 300-36-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-36-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-38-1A	-	-	-	Waste Rock	9.8	0.1	11	3.0	-	-	760	1.0	1	3.9	0.25	-	18	184	-	21	3.6	-
PWP- 300-38-2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-42-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Panda (continued)																						
PWP- 300-42-2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-48-1A	-	-	-	Waste Rock	9.7	0.1	11	0.5	-	-	680	1.5	1	4.0	0.25	-	19	160	-	12	3.3	-
PWP- 300-48-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 50 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 50 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 53 1A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 53 1A	-	-	-	Waste Rock	9.6	0.25	9.9	2.5	-	-	590	1.0	1	3.9	0.25	-	22	131	-	27	3.0	-
PPW 300 53 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 53 2A	-	-	-	Waste Rock	9.7	0.25	9.6	5.0	-	-	620	1.0	1	3.6	0.25	-	21	130	-	22	2.8	-
PPW 300 54 1A	-	-	-	Waste Rock	9.7	0.25	9.8	15	-	-	630	1.0	1	3.4	0.25	-	18	153	-	12	3.2	-
PPW 300 54 2A	-	-	-	Waste Rock	9.3	0.25	9.3	10	-	-	530	1.0	1	3.2	0.25	-	19	167	-	25	3.2	-
PPW 300 55 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 55 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 57 1A	-	-	-	Waste Rock	9.5	0.25	9.2	2.5	-	-	570	0.50	1	3.4	0.25	-	19	120	-	28	3.1	-
PPW 300 57 2A	-	-	-	Waste Rock	9.7	0.25	8.6	15	-	-	530	0.50	1	3.2	0.25	-	19	121	-	14	2.9	-
PPW 300 61 1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 61 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 63 1A	-	-	-	Waste Rock	9.7	0.25	9.3	15	-	-	700	1.0	1	3.0	0.25	-	20	144	-	46	3.2	-
PPW 300 63 2A	-	-	-	Waste Rock	9.6	0.25	9.3	5.0	-	-	560	1.0	1	3.2	0.25	-	18	128	-	10	3.0	-
PPW 300 65 1A	-	-	-	Waste Rock	9.8	0.25	9.2	5.0	-	-	560	1.0	1	3.3	0.25	-	22	144	-	12	2.9	-
PPW 300 65 2A	-	-	-	Waste Rock	9.8	0.25	9.0	10	-	-	550	1.0	1	3.2	0.25	-	20	111	-	4.0	2.7	-
PPW 300 66 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 66 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 68 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 68 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 69 1A	-	-	-	Waste Rock	8.6	0.25	7.5	2.5	-	-	670	1.0	1	2.9	0.25	-	24	212	-	7.0	2.6	-
PPW 300 69 2A	-	-	-	Waste Rock	9.9	0.25	8.9	2.5	-	-	620	1.0	1	3.0	0.25	-	20	131	-	3.0	2.5	-
PPW- 300-71-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-71-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-72-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-72-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-73-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-73-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-75-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-75-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 02 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 02 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 03 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19	
					unit	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Cu ppm	Fe %	Ga ppm	
Waste Rock (continued)																							
Panda (continued)																							
PPW 285 03 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 04 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 04 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 05 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 05 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 06 1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 06 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 10 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 10 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 23 1	-	-	-	Waste Rock	8.9	0.25	9.5	2.5	-	-	580	1.0	1	2.2	0.25	-	16	117	-	37	2.2		
PPW 285 23 1A	-	-	-	Waste Rock	9.3	0.25	9.1	2.5	-	-	600	1.0	1	1.9	0.25	-	10	77	-	10	1.8		
PPW 285 27 1	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 27 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 28 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 28 1B	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 30 1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 30 1B	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 32 1	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 32 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 33 1	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW 285 33 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW- 285-07-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW- 285-07-1A	-	-	-	Waste Rock	9.4	0.25	8.2	5.0	-	-	610	0.50	1	3.1	0.25	-	18	109	-	34	3.1		
PPW- 285-07-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW- 285-07-2A	-	-	-	Waste Rock	9.2	0.25	9.1	5.0	-	-	540	0.50	1	3.6	0.25	-	17	92	-	25	2.9		
PPW- 285-08-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW- 285-08-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW- 285-10-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW- 285-10-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW- 285-12-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW- 285-12-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW- 285-15-1A	-	-	-	Waste Rock	9.1	0.25	8.6	5.0	-	-	620	0.50	1	3.3	0.25	-	18	115	-	33	3.2		
PPW- 285-15-2A	-	-	-	Waste Rock	9.2	0.25	8.1	5.0	-	-	630	0.50	1	3.0	0.25	-	17	112	-	44	2.9		
PPW- 285-16-1A	-	-	-	Waste Rock	9.3	0.25	7.2	5.0	-	-	570	0.50	1	2.6	0.25	-	17	169	-	50	2.6		
PPW- 285-16-2A	-	-	-	Waste Rock	9.4	0.25	8.4	5.0	-	-	670	0.50	1	2.7	0.25	-	24	177	-	142	3.3		
PPW- 285-19-1A	-	-	-	Waste Rock	9.3	0.5	7.4	2.5	-	-	780	1.0	1	3.1	0.25	-	19	136	-	21	3.1		
PPW- 285-19-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
PPW- 285-24-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Panda (continued)																						
PPW- 285-24-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 270-02-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 270-02-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 03 1	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 03 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 04 1	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 04 1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 05 1	-	-	-	Waste Rock	9.3	0.25	9.2	2.5	-	-	520	0.50	1	3.3	0.25	-	16	120	-	20	2.8	-
PPW 270 05 1A	-	-	-	Waste Rock	9.4	0.25	10	2.5	-	-	630	0.50	1	3.2	0.25	-	20	143	-	21	3.1	-
PPW 270 07 1	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 07 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 10 1	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 10 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 13 1	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 13 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 14 1	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 14 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PG-270-27 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PG-270-27 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-07-1A	-	-	-	Waste Rock	9.4	0.25	13	2.5	-	-	520	1.5	2	3.8	0.25	-	16	112	-	12	3.1	-
PPW-270-07-2A	-	-	-	Waste Rock	9.4	0.5	12	2.5	-	-	540	1.5	2	3.7	0.25	-	14	113	-	12	2.9	-
PPW-270-16-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-16-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-17-1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-17-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-18-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-18-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-21-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-21-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-22-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-22-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-24-1A	-	-	-	Waste Rock	9.6	0.25	7.7	2.5	-	-	630	1.5	2	3.1	0.25	-	14	98	-	19	2.9	-
PPW-270-24-2A	-	-	-	Waste Rock	9.3	0.5	8.5	2.5	-	-	890	1.5	2	3.1	0.25	-	15	140	-	13	2.9	-
PPW-270-25-1A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-25-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-29 1A	-	-	-	Waste Rock	9.8	0.25	8.2	2.5	-	-	560	2.0	1	2.0	0.25	-	6	38	-	12	1.5	-
PPW-270-29 2A	-	-	-	Waste Rock	9.5	0.25	8.2	2.5	-	-	680	2.5	1	3.3	0.25	-	16	74	-	37	3.1	-
PG-255-11 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Panda (continued)																						
PG-255-11 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-03-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-03-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-04-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-04-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-05-1A	-	-	-	Waste Rock	9.4	0.25	7.6	2.5	-	-	520	1.5	1	2.9	0.25	-	13	100	-	15	2.5	-
PPW-255-05-2A	-	-	-	Waste Rock	9.5	0.25	7.7	2.5	-	-	740	1.5	1	3.0	0.25	-	15	112	-	21	2.9	-
PPW-255-07 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-07 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-08-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-08-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-13 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-13 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-15 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-15 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-17 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-17 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-19 1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-19 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-21 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-21 2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-24-1A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-24-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-26-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-26-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-27-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-27-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-29-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-29-2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-32-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-32-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-33-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-33-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-02-240-28-1a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-02-240-28-2a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-02-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-02-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-03-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Panda (continued)																						
PPW-240-03-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-15-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-15-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-31-1a	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-31-2a	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-32-1a	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-32-2a	-	-	-	Waste Rock	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-38-1a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-38-2a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-39-1a	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-39-2a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PP-225-09-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PP-225-14-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PP-225-14-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-225-07-1a	-	-	-	Waste Rock	9.4	0.25	8.8	5.0	-	-	740	1.5	2	3.1	0.25	-	16	89	-	30	2.9	-
PPW-225-07-2a	-	-	-	Waste Rock	9.6	0.25	8.3	2.5	-	-	620	1.5	2	3.2	0.25	-	14	84	-	8.0	2.7	-
SRK-ROAD-18B	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
SRK-PPWR-18B	-	-	-	Waste Rock	9.0	0.25	9.9	2.5	-	-	620	1.5	1	3.3	0.25	-	17	122	-	24	3.2	-
Median					9.5	0.2	9.4	2.5	-	-	625	1.5	1	3.3	0.25	-	19	144	-	25	2.9	-
Minimum					8.4	0.1	7.2	0.5	-	-	430	0.50	1	0.35	0.25	-	4.0	38	-	1.0	1.2	-
Maximum					12.1	0.5	13	15	-	-	890	2.5	6	5.9	1.0	-	24	229	-	142	3.6	-
Count					391	70	70	70	0	0	70	70	70	70	70	0	70	70	0	70	70	0
Waste Rock Dump																						
BH-00-01 0-2	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 2-4	-	-	-	Waste Rock	8.9	0.2	9.4	88	-	-	690	1.5	1	3.1	0.25	-	19	188	-	63	2.9	-
BH-00-01 4-6	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 6-8	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 8-10	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 10-12	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 12-14	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 14-16	-	-	-	Waste Rock	9.4	0.1	9.5	0.5	-	-	560	1.0	1	3.1	0.25	-	16	140	-	277	2.6	-
BH-00-01 16-18	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 18-19	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 0-2	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 2-4	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 4-6	-	-	-	Waste Rock	9.0	0.1	10	0.5	-	-	720	1.5	1	3.5	0.25	-	18	177	-	49	2.9	-
BH-00-02 6-8	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 8-10	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Waste Rock Dump (continued)																						
BH-00-02 10-12	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 12-14	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 14-16	-	-	-	Waste Rock	9.6	0.1	10	0.5	-	-	740	1.5	1	3.5	0.25	-	21	184	-	149	3.1	-
BH-00-02 16-18	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 18-19	-	-	-	Waste Rock	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 0-2	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 2-4	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 4-6	-	-	-	Waste Rock	8.3	0.1	9.8	0.5	-	-	820	1.5	1	3.2	0.25	-	19	242	-	69	3.1	-
BH-00-02A 6-8	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 8-10	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 10-12	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 12-14	-	-	-	Waste Rock	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 16-18	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 18-19	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03 0-2	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03 2-4	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03 4-6	-	-	-	Waste Rock	9.5	0.1	9.5	0.5	-	-	640	1.5	1	3.4	0.25	-	20	155	-	49	3.0	-
BH-00-03 6-8	-	-	-	Waste Rock	7.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03A 0-2	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03A 2-4	-	-	-	Waste Rock	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03A 4-6	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03A 6-8	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 0-2	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 2-4	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 4-6	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 6-8	-	-	-	Waste Rock	9.2	0.1	9.8	0.5	-	-	720	1.5	1	3.3	0.25	-	19	239	-	66	3.0	-
BH-00-06 8-10	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 10-12	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 12-14	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 14-16	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 16-18	-	-	-	Waste Rock	8.9	0.1	9.0	1.0	-	-	700	1.0	1	3.4	0.25	-	26	243	-	51	3.0	-
BH-00-06 18-20	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 20-22	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 22-24	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 24-26	-	-	-	Waste Rock	9.6	0.1	9.9	0.5	-	-	740	1.5	1	3.2	0.25	-	23	183	-	95	3.2	-
BH-00-06 26-28	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part A**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.075	8.23	1.8	0.004	10	425	3	0.01	4.15	3	-	25	102	-	60	5.63	19
		From	To		Paste pH	Ag	Al	As	Au	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	Ga
		unit	ppm		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																						
Waste Rock Dump (continued)																						
BH-00-06 28-30	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 30-32	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Median					9.2	0.1	9.8	0.5	-	-	720	1.5	1	3.3	0.25	-	19	184	-	66	3.0	-
Minimum					7.4	0.1	9.0	0.5	-	-	560	1.0	1	3.1	0.25	-	16	140	-	49	2.6	-
Maximum					9.7	0.2	10	88	-	-	820	1.5	1	3.5	0.25	-	26	243	-	277	3.2	-
Count					53	9	9	9	0	0	9	9	9	9	9	0	9	9	0	9	9	0

Note:

a) Typical crustal abundance for continental rocks taken from Price WL. 1997. Draft Guidelines and Recommended Methods for the Prediction of Metal Leaching and Acid Rock Drainage at Mine sites in British Columbia. British Columbia Ministry of Employment and Investment, Energy and Minerals Division: Victoria, BC, Canada.

- >1 x = Concentration greater than typical crustal abundance.
- >5 x = Concentration greater than 5 x the typical crustal abundance.
- >10 x = Concentration greater than 10 x the typical crustal abundance.
- 0.1 Below detection limit, given half detection limit value
- 15.01 Above upper detection, given value of detection limit +0.01

No. = number; - = not available; % = percent; pH = potential of hydrogen, provides measure of the acidity or alkalinity of a solution on a scale of 0 to 14; ppm = parts per million; > = greater than.

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Overburden																							
Koala Black Clay																							
KBC-405-1	-	-	-	Black Clay	7.7	-	-	20	-	1.4	-	-	8.5	1,085	1.0	0.13	-	437	1,840	34	-	-	0.39
KBC-405-2	-	-	-	Black Clay	7.8	-	-	10	-	1.3	-	-	8.2	1,785	9.0	0.15	-	421	1,750	40	-	-	0.38
KBC-405-3	-	-	-	Black Clay	7.7	-	-	20	-	1.4	-	-	7.8	1,030	3.0	0.24	-	423	1,960	32	-	-	0.40
KBC-405-4	-	-	-	Black Clay	7.7	-	-	10	-	1.4	-	-	7.2	1,210	3.0	0.42	-	346	1,970	40	-	-	0.38
KBC-405-5	-	-	-	Black Clay	7.7	-	-	10	-	1.0	-	-	9.0	875	6.0	0.10	-	575	1,680	34	-	-	0.36
KBC-405-6	-	-	-	Black Clay	7.7	-	-	10	-	1.2	-	-	8.4	1,000	0.5	0.26	-	493	1,860	36	-	-	0.36
KBC-405-7	-	-	-	Black Clay	7.8	-	-	20	-	1.2	-	-	6.9	1,060	3.0	0.25	-	407	2,090	40	-	-	0.44
KBC-405-8	-	-	-	Black Clay	7.9	-	-	10	-	1.3	-	-	8.1	980	1.0	0.23	-	435	1,780	10	-	-	0.38
KBC-405-46-1A	-	-	-	Black Clay	7.4	-	-	10	-	1.3	-	-	9.7	1,255	1.0	0.22	-	471	1,990	54	-	-	0.50
KBC-408	-	-	-	Black Clay	7.2	-	-	50	-	0.78	-	-	4.8	630	3.0	0.67	-	236	1,400	26	-	-	0.88
KBC-DUMP-1A	-	-	-	Black Clay	7.7	-	-	20	-	1.4	-	-	10	1,055	0.5	0.17	-	513	1,980	48	-	-	0.37
KBC-DUMP-2A	-	-	-	Black Clay	7.5	-	-	50	-	1.2	-	-	9.1	770	4.0	0.12	-	532	1,570	54	-	-	0.46
KBC-DUMP-3A	-	-	-	Black Clay	7.4	-	-	20	-	1.4	-	-	9.5	775	6.0	0.39	-	632	1,390	46	-	-	0.50
KBC-DUMP-4A	-	-	-	Black Clay	7.8	-	-	30	-	1.3	-	-	9.0	955	0.5	0.20	-	474	1,790	48	-	-	0.36
KBC-DUMP-5A	-	-	-	Black Clay	7.2	-	-	10	-	1.8	-	-	8.5	935	1.0	0.43	-	421	2,080	56	-	-	0.39
KBC-DUMP-6A	-	-	-	Black Clay	7.3	-	-	20	-	1.5	-	-	9.8	1,080	1.0	0.26	-	497	1,960	50	-	-	0.39
KBC-DUMP-7A	-	-	-	Black Clay	7.3	-	-	10	-	1.1	-	-	11	760	1.0	0.11	-	681	1,590	44	-	-	0.37
KBC-DUMP-8A	-	-	-	Black Clay	7.4	-	-	20	-	1.1	-	-	10	810	4.0	0.17	-	651	1,180	40	-	-	0.45
KBC-DUMP-9A	-	-	-	Black Clay	7.3	-	-	10	-	1.2	-	-	9.3	800	3.0	0.21	-	570	1,280	42	-	-	0.39
KBC-DUMP-10A	-	-	-	Black Clay	7.4	-	-	10	-	1.2	-	-	9.3	1,160	1.0	0.15	-	495	1,810	50	-	-	0.36
Median					7.6	-	-	15	-	1.3	-	-	9.0	990	2.0	0.22	-	484	1,800	41	-	-	0.39
Minimum					7.2	-	-	10	-	0.78	-	-	4.8	630	0.5	0.10	-	236	1,180	10	-	-	0.36
Maximum					7.9	-	-	50	-	1.8	-	-	11	1,785	9.0	0.67	-	681	2,090	56	-	-	0.88
Count					20	0	0	20	0	20	0	0	20	20	20	20	0	20	20	20	0	0	20
Koala Till																							
KT-420-47 1A	-	-	-	Till	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KT-420-47 2A	-	-	-	Till	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Median					8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Minimum					8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Maximum					8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Count					2	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	Price Crustal Abundances																		
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Diabase																							
Beartooth																							
60	96-35	36.98	37.43	Diabase	9.6	-	-	-	-	0.86	-	-	1.7	380	1.0	0.07	-	79	2,550	6	-	-	-
61	96-35	42.02	42.63	Diabase	9.7	-	-	-	-	1.6	-	-	2.1	400	2.0	0.06	-	94	2,350	8	-	-	-
Median					9.6	-	-	-	-	1.2	-	-	1.9	390	1.5	0.07	-	87	2,450	7	-	-	-
Minimum					9.6	-	-	-	-	0.86	-	-	1.7	380	1.0	0.06	-	79	2,350	6	-	-	-
Maximum					9.7	-	-	-	-	1.6	-	-	2.1	400	2.0	0.07	-	94	2,550	8	-	-	-
Count					2	0	0	0	0	2	0	0	2	2	2	2	0	2	2	2	0	0	0
Fox																							
FUC 3-3 - 65	FUC 3-3	65	65.3	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 66	FUC 3-3	66	66.3	Diabase	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 67	FUC 3-3	67	67.3	Diabase	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 70	FUC 3-3	70	70.3	Diabase	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 75	FUC 3-3	75	75.3	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 80	FUC 3-3	80	80.3	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 85	FUC 3-3	85	85.3	Diabase	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 90	FUC 3-3	90	90.3	Diabase	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 95	FUC 3-3	95	95.3	Diabase	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 712	Decline	712	712.1	Diabase	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 1202.2	Decline	1202.2	1202.3	Diabase	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 1-2 - 87.78	FUC 1-2	87.78	93.72	Diabase	8.2	-	-	5	-	0.30	-	-	3.8	1,385	2.0	1.7	-	11	60	6	-	-	-
FUC 1-2 - 93.72	FUC 1-2	93.72	99.61	Diabase	8.1	-	-	5	-	0.26	-	-	4.0	1,395	0.5	1.6	-	89	430	6	-	-	-
FUC 1-2 - 99.61	FUC 1-2	99.61	108.66	Diabase	8.1	-	-	5	-	0.45	-	-	3.7	1,270	0.5	1.8	-	72	460	6	-	-	-
FUC 1-2 - 108.66	FUC 1-2	108.66	113.03	Diabase	8.3	-	-	5	-	0.39	-	-	3.9	1,285	2.0	1.7	-	53	310	6	-	-	-
FGT-05 - 11.4	FGT-05	11.4	14.3	Diabase	-	-	-	5	-	0.73	-	-	3.3	1,110	1.0	1.8	-	79	660	2	-	-	-
FGT-05 - 134.9	FGT-05	134.9	142	Diabase	8.5	-	-	5	-	0.20	-	-	3.7	1,485	0.5	1.5	-	82	520	6	-	-	-
FGT-05 - 142	FGT-05	142	149.5	Diabase	-	-	-	5	-	0.15	-	-	3.9	1,425	1.0	1.5	-	91	420	4	-	-	-
FGT-05 - 149.5	FGT-05	149.5	157	Diabase	-	-	-	5	-	0.26	-	-	3.5	1,455	0.5	1.6	-	79	690	8	-	-	-
FGT-05 - 157	FGT-05	157	164.5	Diabase	-	-	-	5	-	0.18	-	-	3.9	1,480	0.5	1.5	-	92	470	8	-	-	-
FGT-05 - 164.5	FGT-05	164.5	172	Diabase	-	-	-	5	-	0.15	-	-	3.6	1,455	0.5	1.4	-	83	560	2	-	-	-
FGT-05 - 172	FGT-05	172	175.36	Diabase	-	-	-	5	-	0.21	-	-	3.7	1,485	0.5	1.5	-	86	510	1	-	-	-
Fox-250-Diabase 8-Oct-09	-	-	-	Diabase	9.0	-	-	5	-	0.65	5	-	3.6	1,525	0.5	1.7	-	75	590	1	-	-	-
Median					8.6	-	-	5	-	0.26	5	-	3.7	1,440	0.5	1.6	-	81	490	6	-	-	-
Minimum					8.1	-	-	5	-	0.15	5	-	3.3	1,110	0.5	1.4	-	11	60	1	-	-	-
Maximum					9.3	-	-	5	-	0.73	5	-	4.0	1,525	2.0	1.8	-	92	690	8	-	-	-
Count					17	0	0	12	0	12	1	0	12	12	12	12	0	12	12	12	0	0	0
Misery																							
MDC-10 142.36	-	-	-	Diabase	9.4	-	-	5	-	0.84	-	-	2.4	1,830	1.0	1.8	-	56	900	16	-	-	0.09
MDC-10 159.49	-	-	-	Diabase	9.3	-	-	5	-	0.74	-	-	2.4	1,630	1.0	1.8	-	57	840	16	-	-	0.08
MDC-10 171.12	-	-	-	Diabase	9.2	-	-	5	-	0.78	-	-	2.4	1,910	1.0	2.0	-	51	950	22	-	-	0.09

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Diabase (continued)																							
Misery (continued)																							
MD 450-26 1A	-	-	-	Diabase	8.8	-	-	5	-	0.84	-	-	2.9	1,540	0.5	1.9	-	57	850	12	-	-	-
MD 430 21 1A	-	-	-	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD 430 21 2A	-	-	-	Diabase	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD 430 25 1A	-	-	-	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD 430 25 2A	-	-	-	Diabase	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD- 430-33-1A	-	-	-	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD- 430-34-2A	-	-	-	Diabase	8.8	-	-	5	-	0.73	-	-	2.7	1,745	0.5	2.2	-	55	1,010	8	-	-	0.10
MD-430-91-01	-	-	-	Diabase	8.7	-	-	0.005	-	0.82	20	-	3.1	1,600	0.8	2.0	-	65	1,030	5	-	-	0.11
MD-430-91-02	-	-	-	Diabase	9.5	-	-	0.005	-	2.7	25	-	1.6	512	2.0	2.3	-	77	780	12	-	-	0.07
MD- 420-04-1A	-	-	-	Diabase	8.3	-	-	5	-	0.94	-	-	3.2	1,595	0.5	2.1	-	64	970	6	-	-	0.09
MD- 420-04-2A	-	-	-	Diabase	8.3	-	-	5	-	0.94	-	-	3.1	1,605	0.5	2.4	-	65	930	8	-	-	0.08
MD-420-12-01	-	-	-	Diabase	9.1	-	-	0.005	-	0.84	19	-	3.3	1,970	0.8	1.9	-	68	1,090	11	-	-	0.12
MD-410-08-01	-	-	-	Diabase	8.8	-	-	0.005	-	0.90	18	-	2.9	1,760	0.7	2.3	-	59	1,010	13	-	-	0.09
MD-410-08-02	-	-	-	Diabase	8.9	-	-	0.005	-	1.0	17	-	2.7	1,660	0.6	2.2	-	54	980	9	-	-	0.09
MD-410-07-01	-	-	-	Diabase	9.4	-	-	0.005	-	0.95	20	-	3.1	1,940	0.7	1.8	-	60	1,050	5	-	-	0.10
MD-410-07-02	-	-	-	Diabase	9.1	-	-	0.005	-	0.77	20	-	3.1	1,930	0.6	1.9	-	54	1,130	6	-	-	0.11
MD 400-42-1a	-	-	-	Diabase	8.7	-	-	5	-	0.78	-	-	3.1	1,840	0.5	2.0	-	63	1,010	14	-	-	0.12
MD-400-49-2a	-	-	-	Diabase	8.7	-	-	5	-	0.83	-	-	3.6	2,030	0.5	2.2	-	72	990	10	-	-	0.08
MD-390-38-2A	-	-	-	Diabase	9.2	-	-	5	-	1.1	-	-	3.5	1,940	0.5	1.9	-	79	730	6	-	-	0.10
MD-380-32-1A	-	-	-	Diabase	8.8	-	-	5	-	0.93	-	-	3.1	1,830	0.5	1.9	-	65	950	8	-	-	0.11
MD-370-22-1	-	-	-	Diabase	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD-370-22-2	-	-	-	Diabase	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MDC-28 3.9-7	-	-	-	Diabase	9.0	-	-	0.005	-	0.26	12	-	0.89	412	0.5	0.14	-	32	1,030	3	-	-	0.09
MDC-28 7-10	-	-	-	Diabase	9.2	-	-	0.005	-	0.33	10	-	0.78	393	0.5	0.14	-	30	980	1	-	-	0.08
MDC-28 10-13	-	-	-	Diabase	9.4	-	-	0.005	-	0.27	8.0	-	0.75	323	0.5	0.13	-	33	840	2	-	-	0.09
MDC-28 13-16	-	-	-	Diabase	9.3	-	-	0.005	-	0.33	8.0	-	0.81	388	0.4	0.12	-	34	890	2	-	-	0.08
MDC-28 16-19	-	-	-	Diabase	9.2	-	-	0.005	-	0.37	9.0	-	0.86	432	0.6	0.09	-	35	980	2	-	-	0.09
MDC-28 19-22	-	-	-	Diabase	9.1	-	-	0.005	-	0.40	9.0	-	0.88	462	0.5	0.08	-	31	960	2	-	-	0.09
MDC-28 23-26.07	-	-	-	Diabase	9.1	-	-	0.005	-	0.29	11	-	1.1	448	0.5	0.10	-	48	1,080	3	-	-	0.09
MGT-57 28.7-32	-	-	-	Diabase	9.1	-	-	0.005	-	0.14	10	-	0.26	139	0.2	0.05	-	4	580	2	-	-	0.025
MGT-57 40-43	-	-	-	Diabase	9.2	-	-	0.005	-	0.33	10	-	0.84	404	0.5	0.09	-	29	1,050	2	-	-	0.09
MGT-57 51-54	-	-	-	Diabase	9.4	-	-	0.005	-	0.33	9.0	-	1.0	474	0.4	0.07	-	40	1,040	3	-	-	0.10
MGT-57 62-65	-	-	-	Diabase	9.4	-	-	0.005	-	0.30	8.0	-	0.90	452	0.4	0.08	-	33	960	8	-	-	0.09
MGT-57 74-77	-	-	-	Diabase	8.3	-	-	0.005	-	0.36	10	-	0.83	374	1.2	0.11	-	31	1,010	2	-	-	0.14
MGT-66 16-19	-	-	-	Diabase	9.8	-	-	0.005	-	0.47	31	-	0.35	171	1.3	0.03	-	6	570	10	-	-	0.025
MGT-43 286-289	-	-	-	Diabase	9.0	-	-	0.01	-	0.34	11	-	0.74	382	0.5	0.11	-	27	910	5	-	-	0.12
MGT-43 289-292	-	-	-	Diabase	8.9	-	-	0.005	-	0.38	10	-	0.90	396	0.6	0.10	-	29	960	5	-	-	0.10
MGT-43 292-295	-	-	-	Diabase	8.9	-	-	0.005	-	0.39	9.0	-	0.95	414	0.7	0.07	-	31	900	7	-	-	0.09

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	Price Crustal Abundances																		
		From	To		- Paste pH unit	- Ge ppm	- Hf ppm	0.08 Hg ppm	- In ppm	2.085 K %	39 La ppm	20 Li ppm	2.33 Mg %	950 Mn ppm	1.3 Mo ppm	2.355 Na %	- Nb ppm	84 Ni ppm	1,050 P ppm	19 Pb ppm	- Rb ppm	- Re ppm	0.035 S %
Diabase (continued)																							
Misery (continued)																							
MGT-43 300-303	-	-	-	Diabase	8.9	-	-	0.005	-	0.22	9.0	-	1.3	553	0.5	0.07	-	46	870	24	-	-	0.09
MGT-43 303-306	-	-	-	Diabase	8.8	-	-	0.005	-	0.27	9.0	-	1.3	461	0.5	0.09	-	55	810	15	-	-	0.08
MGT-43 306-309	-	-	-	Diabase	9.1	-	-	0.005	-	0.40	10	-	0.72	362	0.5	0.14	-	27	930	5	-	-	0.09
MGT-43 309-311.13	-	-	-	Diabase	9.0	-	-	0.005	-	0.30	11	-	1.0	458	0.5	0.09	-	34	920	8	-	-	0.10
MGT-54 211-213.47	-	-	-	Diabase	9.2	-	-	0.005	-	0.38	9.0	-	0.90	415	0.5	0.09	-	32	910	5	-	-	0.08
MGT-54 208-211	-	-	-	Diabase	9.1	-	-	0.005	-	0.41	11	-	0.91	444	0.6	0.08	-	36	1,090	4	-	-	0.10
97-54	97-54	126.14	126.46	Diabase	9.1	-	-	-	-	0.43	-	-	1.1	380	2.0	0.18	-	34	1,470	18	-	-	-
97-54	97-54	18.88	19.08	Diabase	9.1	-	-	-	-	0.32	-	-	1.0	415	1.0	0.15	-	30	1,500	16	-	-	-
97-54	97-54	20.54	20.65	Diabase	8.2	-	-	-	-	0.33	-	-	2.8	350	1.0	0.04	-	62	1,820	10	-	-	-
97-54	97-54	41.3	42.03	Diabase	8.6	-	-	-	-	0.73	-	-	1.1	230	1.0	0.17	-	30	1,510	6	-	-	-
97-54	97-54	52.75	53.29	Diabase	9.5	-	-	-	-	0.64	-	-	0.94	270	2.0	0.24	-	23	1,390	8	-	-	-
97-54	97-54	81.07	81.38	Diabase	9.4	-	-	-	-	0.34	-	-	1.0	365	1.0	0.13	-	35	1,360	6	-	-	-
HC-Pdef-1	-	-	-	Diabase	8.7	0.15	2.7	-	0.084	0.19	5.9	16.2	4.2	1,440	0.6	1.5	4.8	97	550	2	6.8	0.002	0.05
				Median	9.0	0.15	2.7	0.005	0.084	0.40	10	16.2	1.1	458	0.5	0.14	4.8	40	970	6	6.8	0.002	0.09
				Minimum	8.2	0.15	2.7	0.005	0.084	0.14	5.9	16.2	0.26	139	0.2	0.03	4.8	4	550	1	6.8	0.002	0.03
				Maximum	9.8	0.15	2.7	5	0.084	2.7	31	16.2	4.2	2,030	2.0	2.4	4.8	97	1,820	24	6.8	0.002	0.14
				Count	54	1	1	40	1	47	30	1	47	47	47	47	1	47	47	47	1	1	40
Sable																							
SDC-13	SDC-13	164.64	164.91	Diabase	8.9	-	-	-	-	0.15	-	-	1.0	590	1.0	0.2	-	36	1,100	10	-	-	-
				Median	8.9	-	-	-	-	0.15	-	-	1.0	590	1.0	0.2	-	36	1,100	10	-	-	-
				Minimum	8.9	-	-	-	-	0.15	-	-	1.0	590	1.0	0.2	-	36	1,100	10	-	-	-
				Maximum	8.9	-	-	-	-	0.15	-	-	1.0	590	1.0	0.2	-	36	1,100	10	-	-	-
				Count	1	0	0	0	0	1	0	0	1	1	1	1	0	1	1	1	0	0	0
Jay																							
2014-DD-040	JGT-03	349.4	356.81	Diabase	9.10	0.05	0.28	0.005	0.01	0.15	6.1	15	0.98	343	2.92	0.28	0.28	22	520	2	12.2	-	0.05
2014-DD-043	JGT-03	47.22	57.11	Diabase	9.05	0.05	0.37	0.005	0.01	0.2	6.1	17	0.79	372	2.91	0.13	0.41	20	580	1.7	23.5	-	0.04
2014-DD-044	JGT-03	57.95	65.48	Diabase	9.05	0.05	0.34	0.005	0.01	0.2	6.1	17	0.75	374	1.96	0.17	0.42	20	510	0.7	23.6	-	0.05
2014-DD-049	JGT-02	413.02	421.45	Diabase	9.02	0.05	0.25	0.005	0.01	0.15	6.5	14	0.79	347	2.63	0.25	0.26	20	550	2.9	11	-	0.05
				Median	9.1	0.05	0.31	0.005	0.01	0.18	6.1	16	0.8	359.5	2.8	0.2	0.345	20	535	2	17.85	-	0.05
				Minimum	9.0	0.05	0.25	0.005	0.01	0.15	6.1	14	0.8	343	2.0	0.1	0.26	20	510	1	11	-	0.04
				Maximum	9.1	0.05	0.37	0.005	0.01	0.20	6.5	17	1.0	374	2.9	0.3	0.42	22	580	3	23.6	-	0.05
				Count	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	0	4
Granite																							
Beartooth																							
58	96-35	13.5	13.95	Granite	9.8	-	-	-	-	2.1	-	-	2.1	390	4.0	0.15	-	54	1,090	6	-	-	-
59	96-35	30	30.62	Granite	9.8	-	-	-	-	1.9	-	-	1.8	355	2.0	0.08	-	49	980	6	-	-	-
62	96-35	30.14	46.78	Granite	9.8	-	-	-	-	2.1	-	-	2.0	415	2.0	0.11	-	47	1,050	8	-	-	-
63	96-35	221.27	221.83	Granite	9.1	-	-	-	-	2.0	-	-	2.0	365	2.0	0.08	-	48	1,170	10	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Beartooth (continued)																							
12	BDC-05	40.2	40.53	Granite	9.8	-	-	-	-	1.8	-	-	1.6	275	4.0	0.11	-	39	550	4	-	-	-
14	BDC-05	63.74	64.07	Granite	9.5	-	-	-	-	2.0	-	-	2.1	355	2.0	0.09	-	55	1,090	16	-	-	-
15	BDC-07	224.63	225.02	Granite	9.9	-	-	-	-	2.0	-	-	2.0	360	2.0	0.10	-	47	1,080	4	-	-	-
BDC 4-54.64	BDC 4	54.64	60.21	Granite	-	-	-	5	-	2.4	-	-	1.8	355	1.0	2.7	-	47	1,160	4	-	-	0.01
BGT 01-108	BGT 01	108	112.35	Granite	-	-	-	5	-	2.3	-	-	1.6	345	0.5	2.4	-	50	640	8	-	-	0.005
BGT 01-125.34	BGT 01	125.34	129.61	Granite	-	-	-	5	-	2.1	-	-	2.1	365	0.5	2.7	-	41	890	1	-	-	0.04
BGT 02-60.12	BGT 02	60.12	64.52	Granite	-	-	-	5	-	2.0	-	-	1.6	280	0.5	2.3	-	45	150	8	-	-	0.04
BGT 03-18.28	BGT 03	18.28	22.62	Granite	-	-	-	5	-	2.2	-	-	2.0	410	0.5	2.6	-	49	920	6	-	-	0.01
BGT 03-64.95	BGT 03	64.95	69.2	Granite	-	-	-	5	-	2.0	-	-	2.0	400	0.5	2.6	-	53	930	8	-	-	0.01
BGT 03-107.6	BGT 03	107.6	111.82	Granite	-	-	-	5	-	1.9	-	-	1.8	390	0.5	2.5	-	49	910	6	-	-	0.03
BGT 04-70.03	BGT 04	70.03	74.32	Granite	-	-	-	5	-	1.9	-	-	1.9	410	1.0	2.6	-	50	970	2	-	-	0.03
BGT 05-104.77	BGT 05	104.77	109.66	Granite	-	-	-	5	-	2.0	-	-	1.8	310	0.5	2.8	-	45	1,070	6	-	-	0.01
BGT 05-135.31	BGT 05	135.31	139.58	Granite	-	-	-	5	-	1.7	-	-	1.9	405	0.5	2.6	-	53	960	12	-	-	0.02
DDH 96-35-64.19	DDH 96-35	64.19	70.65	Granite	-	-	-	5	-	2.6	-	-	2.1	555	1.0	2.6	-	88	120	8	-	-	0.15
BDC 2-88.19	BDC 2	88.19	90.86	Granite	-	-	-	5	-	1.8	-	-	2.5	570	2.0	1.9	-	115	170	24	-	-	0.15
BDC 3-38	BDC 3	38	42	Granite	-	-	-	5	-	1.9	-	-	3.0	665	1.0	2.3	-	85	1,690	2	-	-	0.12
BGT 01-99.36	BGT 01	99.36	103.64	Granite	-	-	-	5	-	2.2	-	-	1.5	290	0.5	2.4	-	54	50	10	-	-	0.04
BGT 04-48.38	BGT 04	48.38	52.7	Granite	-	-	-	5	-	2.5	-	-	2.4	415	1.0	2.4	-	67	1,260	6	-	-	0.18
BGT 05-78.58	BGT 05	78.58	81.93	Granite	-	-	-	5	-	2.3	-	-	2.2	350	2.0	2.3	-	89	100	10	-	-	0.18
BDC 5-17	BDC 5	17	18	Granite	-	-	-	5	-	3.2	-	-	1.5	3,330	1.0	0.23	-	20	480	1	-	-	0.09
BDC 3-42	BDC 3	42	57	Granite	-	-	-	5	-	2.3	-	-	6.2	740	5.0	1.7	-	378	740	1	-	-	0.06
BDC 4-38.7	BDC 4	38.7	42	Granite	-	-	-	5	-	2.6	-	-	2.1	415	1.0	2.5	-	60	960	12	-	-	0.05
BDC 5-20.96	BDC 5	20.96	26.65	Granite	-	-	-	5	-	2.1	-	-	1.8	480	0.5	2.4	-	43	900	6	-	-	0.03
BDC 7-20.28	BDC 7	20.28	26.93	Granite	-	-	-	5	-	2.5	-	-	2.5	485	0.5	2.1	-	127	110	4	-	-	0.11
BDC 7-32.42	BDC 7	32.42	36.9	Granite	-	-	-	5	-	1.8	-	-	1.8	410	0.5	2.7	-	44	920	8	-	-	0.005
BDC 7-36.9	BDC 7	36.9	42	Granite	-	-	-	5	-	2.0	-	-	1.9	410	0.5	2.2	-	81	180	12	-	-	0.18
BDC 7-53.95	BDC 7	53.95	58.98	Granite	-	-	-	5	-	2.1	-	-	1.6	415	0.5	2.5	-	46	470	8	-	-	0.03
BDC 7-64.09	BDC 7	64.09	69.29	Granite	-	-	-	5	-	2.2	-	-	2.1	460	0.5	2.0	-	98	70	8	-	-	0.18
BGT 01-65.18	BGT 01	65.18	69.43	Granite	-	-	-	5	-	2.4	-	-	1.9	390	0.5	2.7	-	57	630	8	-	-	0.07
BGT 01-82.23	BGT 01	82.23	86.35	Granite	-	-	-	5	-	2.2	-	-	1.7	340	0.5	2.4	-	49	380	8	-	-	0.005
BGT 02-107.4	BGT 02	107.4	111.73	Granite	-	-	-	5	-	1.9	-	-	1.8	395	0.5	2.8	-	45	910	2	-	-	0.03
BGT 02-146.12	BGT 02	146.12	150.45	Granite	-	-	-	5	-	2.2	-	-	2.0	285	1.0	2.3	-	73	530	10	-	-	0.20
BGT 03-39.31	BGT 03	39.31	43.66	Granite	-	-	-	5	-	2.0	-	-	1.7	350	1.0	2.4	-	54	560	10	-	-	0.05
BGT 04-35.95	BGT 04	35.95	41	Granite	-	-	-	5	-	1.1	-	-	4.9	1,215	0.5	2.3	-	176	2,260	1	-	-	0.005
BGT 04-91.65	BGT 04	91.65	95.95	Granite	-	-	-	5	-	1.9	-	-	1.9	430	0.5	2.6	-	48	960	1	-	-	0.01
BGT 04-130.5	BGT 04	130.5	134.87	Granite	-	-	-	5	-	1.9	-	-	2.0	430	2.0	2.6	-	62	820	4	-	-	0.07
BGT 05-25.9	BGT 05	25.9	30.95	Granite	-	-	-	5	-	2.6	-	-	2.4	510	0.5	2.4	-	88	360	6	-	-	0.13
BGT 05-56.78	BGT 05	56.78	61.17	Granite	-	-	-	5	-	2.3	-	-	2.0	360	1.0	2.6	-	49	880	6	-	-	0.04

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																							
Beartooth (continued)																							
BGT 05-165.49	BGT 05	165.49	169.74	Granite	-	-	-	5	-	1.4	-	-	1.7	310	1.0	2.2	-	43	810	2	-	-	0.02
BTG-460-25-01	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-460-25-02	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-04-02	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-03-01	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-03-02	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-2	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-3	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-4	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-5	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-6	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-7	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-8	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-10-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTGS-440-09-1	-	-	-	Granite	9.5	-	-	0.005	-	2.2	-	-	1.9	397	3.0	3.0	-	44	980	6	-	-	0.04
BTGS-440-09-2	-	-	-	Granite	9.7	-	-	0.005	-	2.1	-	-	2.3	496	4.0	2.7	-	58	1,020	7	-	-	0.03
BTGS-440-09-3	-	-	-	Granite	9.3	-	-	0.005	-	1.9	-	-	1.9	391	1.0	2.9	-	47	880	3	-	-	0.05
BTGS-440-09-4	-	-	-	Granite	9.8	-	-	0.005	-	1.9	-	-	1.8	344	3.0	2.8	-	45	1,010	5	-	-	0.02
BG-440-11-1	-	-	-	Granite	9.0	-	-	0.005	-	2.7	-	-	2.1	398	1.0	2.3	-	79	670	20	-	-	0.07
BG-440-11-2	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-11-3	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-11-4	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-12-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-12-2	-	-	-	Granite	8.8	-	-	0.005	-	2.4	-	-	1.7	318	2.0	2.3	-	54	870	16	-	-	0.04
BG-440-12-3	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-12-4	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-13-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-13-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-15-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-15-2	-	-	-	Granite	8.8	-	-	0.005	-	2.1	-	-	2.0	461	1.0	2.6	-	49	1,020	8	-	-	0.03
BG-440-20-04	-	-	-	Granite	9.7	-	-	0.005	-	2.1	-	-	1.7	418	0.5	2.5	-	48	1,060	8	-	-	0.01
BG-440-20-03	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-20-02	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-20-01	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-22-04	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-22-03	-	-	-	Granite	9.6	-	-	0.005	-	1.9	-	-	1.7	420	0.5	2.7	-	47	990	9	-	-	0.01

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Beartooth (continued)																							
BG-440-22-02	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-22-01	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-440-26-1	-	-	-	Granite	9.2	-	-	0.005	-	2.5	-	-	2.0	424	1.0	2.5	-	66	960	11	-	-	0.05
BTG-440-26-2	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-440-26-3	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-440-26-4	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-21-02	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-21-01	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-19-04	-	-	-	Granite	7.9	-	-	0.005	-	2.2	-	-	2.6	482	0.5	2.0	-	126	370	17	-	-	0.06
BG-430-19-03	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-19-02	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-19-01	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-18-04	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-18-03	-	-	-	Granite	9.6	-	-	0.005	-	1.9	-	-	1.7	400	0.5	2.5	-	47	980	8	-	-	0.005
BG-430-18-02	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-18-01	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-17-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-17-03	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-17-02	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-17-01	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-05-02	-	-	-	Granite	9.6	-	-	0.005	-	2.3	-	-	1.7	328	1.0	2.7	-	46	1,150	10	-	-	0.01
BG-430-05-01	-	-	-	Granite	9.6	-	-	0.005	-	2.3	-	-	1.7	320	1.0	2.7	-	52	1,040	8	-	-	0.01
BG-430-04-01	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-02-02	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-02-01	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-04	-	-	-	Granite	8.2	-	-	0.005	-	2.2	-	-	1.7	354	1.0	2.1	-	71	430	8	-	-	0.22
BG-420-04-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-03	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-03	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-02	-	-	-	Granite	8.8	-	-	0.005	-	1.9	-	-	2.1	484	0.5	2.0	-	89	590	11	-	-	0.17
BG-420-04-02	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-01	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-01	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-410-05-01	-	-	-	Granite	9.9	-	-	0.01	-	1.9	-	-	1.8	357	0.5	2.6	-	54	970	14	-	-	0.02
BTG-410-05-02	-	-	-	Granite	9.5	-	-	0.005	-	2.2	-	-	1.8	321	0.5	2.7	-	46	1,070	14	-	-	0.01
BT-310-Granite-3	-	-	-	Granite	9.5	-	-	5	-	1.8	20	-	1.8	419	0.5	2.6	-	45	1,150	10	-	-	0.03
BT-310-Granite-2	-	-	-	Granite	9.7	-	-	5	-	1.8	10	-	2.3	509	0.5	2.5	-	90	1,050	10	-	-	0.08
BT-310-Granite-1	-	-	-	Granite	9.8	-	-	5	-	1.8	10	-	1.6	435	0.5	2.7	-	42	920	11	-	-	0.02

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH unit	Ge ppm	Hf ppm	0.08 Hg ppm	- In ppm	2.085 K %	39 La ppm	20 Li ppm	2.33 Mg %	950 Mn ppm	1.3 Mo ppm	2.355 Na %	- Nb ppm	84 Ni ppm	1,050 P ppm	19 Pb ppm	- Rb ppm	- Re ppm	0.035 S %
Granite (continued)																							
Beartooth (continued)																							
BT-300-Granite-3	-	-	-	Granite	8.9	-	-	5	-	1.5	30	-	6.4	664	0.5	2.0	-	409	1,190	8	-	-	0.15
BT-300-Granite-2	-	-	-	Granite	9.1	-	-	5	-	1.6	40	-	7.4	599	1.0	1.8	-	479	870	7	-	-	0.13
BT-300-Granite-1	-	-	-	Granite	10.1	-	-	5	-	1.7	10	-	1.7	435	0.5	2.7	-	49	930	8	-	-	0.02
BT-290-Granite-2	-	-	-	Granite	10.1	-	-	5	-	1.5	10	-	1.6	420	0.5	2.8	-	47	1,020	9	-	-	0.01
BT-290-Granite-1	-	-	-	Granite	9.2	-	-	5	-	1.6	20	-	3.3	453	0.5	2.4	-	171	980	8	-	-	0.05
BT-290-Granite-3	-	-	-	Granite	9.8	-	-	5	-	1.7	10	-	1.7	420	0.5	2.7	-	48	1,000	8	-	-	0.02
BT-280-Granite-2	-	-	-	Granite	10.0	-	-	5	-	1.6	10	-	1.6	417	0.5	2.8	-	45	950	9	-	-	0.02
BT-280-Granite-1	-	-	-	Granite	9.9	-	-	5	-	1.5	10	-	1.6	427	0.5	2.8	-	46	1,030	11	-	-	0.05
Median					9.3	-	-	5	-	2.0	10	-	1.9	410	0.5	2.5	-	50	930	8	-	-	0.04
Minimum					7.8	-	-	0.005	-	1.1	10	-	1.5	275	0.5	0.08	-	20	50	1	-	-	0.005
Maximum					10.1	-	-	5	-	3.2	40	-	7.4	3,330	5.0	3.0	-	479	2,260	24	-	-	0.22
Count					90	0	0	65	0	72	11	0	72	72	72	72	0	72	72	72	0	0	65
Fox																							
FUC-2B - 56	FUC-2B	56	56.3	Granite	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 45	FUC 3-3	45	45.3	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 50	FUC 3-3	50	50.3	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 55	FUC 3-3	55	55.3	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 60	FUC 3-3	60	60.3	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 4-3 - 144	FUC 4-3	144	144.3	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 4-4 - 144	FUC 4-4	144	144.3	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 4-5 - 128	FUC 4-5	128	128.3	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FX 4-1 - 188	FX 4-1	188	188.3	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - -	Decline	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - -	Decline	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 69	Decline	69	69.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 200	Decline	200	200.1	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 245	Decline	245	245.1	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 296	Decline	296	296.1	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 365	Decline	365	365.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 372	Decline	372	372.1	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 377	Decline	377	377.1	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 447	Decline	447	447.1	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 500	Decline	500	500.1	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 552	Decline	552	552.1	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 610	Decline	610	610.1	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 660	Decline	660	660.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 764	Decline	764	764.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Fox (continued)																							
Decline - 809	Decline	809	809.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 822	Decline	822	822.1	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 851	Decline	851	851.1	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 901	Decline	901	901.1	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 951	Decline	951	951.1	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 1001	Decline	1001	1001.1	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 1055.9	Decline	1055.9	1056	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 1106.2	Decline	1106.2	1106.3	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 1168.8	Decline	1168.8	1168.9	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 1276.1	Decline	1276.1	1276.2	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 1326.1	Decline	1326.1	1326.2	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 1-2 - 70.15	FUC 1-2	70.15	76.02	Granite	8.2	-	-	5	-	2.4	-	-	2.1	340	0.5	2.9	-	53	930	10	-	-	-
FUC 1-2 - 76.02	FUC 1-2	76.02	80.38	Granite	8.6	-	-	5	-	2.5	-	-	2.0	330	0.5	2.8	-	53	950	12	-	-	-
FUC 1-2 - 80.38	FUC 1-2	80.38	87.78	Granite	8.4	-	-	10	-	0.30	-	-	4.0	1,270	0.5	1.7	-	87	600	4	-	-	-
FUC 1-2 - 113.03	FUC 1-2	113.03	116.91	Granite	8.5	-	-	5	-	2.5	-	-	2.0	400	2.0	2.9	-	44	870	12	-	-	-
FUC 1-2 - 116.91	FUC 1-2	116.91	122.67	Granite	8.6	-	-	5	-	2.6	-	-	2.1	430	5.0	2.7	-	45	930	12	-	-	-
FUC 4-3 - 146.96	FUC 4-3	146.96	151.5	Granite	8.8	-	-	5	-	2.3	-	-	1.8	365	5.0	2.8	-	40	870	14	-	-	-
FUC 4-3 - 155.2	FUC 4-3	155.2	163.4	Granite	8.3	-	-	5	-	2.3	-	-	1.9	380	6.0	2.8	-	41	840	12	-	-	-
FDC 11 - 108.25	FDC 11	108.25	118.8	Granite	8.5	-	-	5	-	2.6	-	-	2.0	340	3.0	2.7	-	35	840	10	-	-	-
FDC 11 - 118.8	FDC 11	118.8	123	Granite	8.6	-	-	5	-	1.9	-	-	1.4	265	4.0	2.8	-	26	810	10	-	-	-
FDC 11 - 122.5	FDC 11	122.5	128.02	Granite	8.2	-	-	5	-	3.0	-	-	3.0	295	2.0	2.4	-	38	940	6	-	-	-
FGT-03 - 1.52	FGT-03	1.52	10.82	Granite	9.1	-	-	5	-	2.3	-	-	1.9	485	1.0	2.7	-	50	870	16	-	-	-
FGT-03 - 10.82	FGT-03	10.82	18.32	Granite	-	-	-	5	-	2.2	-	-	2.1	520	1.0	2.8	-	55	990	28	-	-	-
FGT-03 - 18.32	FGT-03	18.32	25.82	Granite	-	-	-	5	-	2.3	-	-	1.8	420	3.0	3.1	-	47	810	14	-	-	-
FGT-03 - 25.82	FGT-03	25.82	30.24	Granite	-	-	-	5	-	2.2	-	-	1.5	395	1.0	2.5	-	41	700	24	-	-	-
FGT-03 - 30.24	FGT-03	30.24	37.74	Granite	-	-	-	5	-	2.2	-	-	1.7	445	1.0	2.7	-	45	770	14	-	-	-
FGT-03 - 37.74	FGT-03	37.74	45.24	Granite	-	-	-	5	-	2.2	-	-	1.6	460	1.0	2.8	-	47	810	24	-	-	-
FGT-03 - 45.24	FGT-03	45.24	52.74	Granite	-	-	-	5	-	2.2	-	-	1.8	490	3.0	2.8	-	57	800	20	-	-	-
FGT-03 - 52.74	FGT-03	52.74	58.29	Granite	-	-	-	5	-	2.5	-	-	1.8	460	1.0	2.8	-	47	800	14	-	-	-
FGT-03 - 58.29	FGT-03	58.29	65.79	Granite	-	-	-	5	-	2.2	-	-	1.6	445	1.0	2.8	-	46	810	10	-	-	-
FGT-03 - 65.79	FGT-03	65.79	73.29	Granite	-	-	-	5	-	2.3	-	-	1.7	445	0.5	2.8	-	49	810	20	-	-	-
FGT-03 - 73.29	FGT-03	73.29	80.79	Granite	9.6	-	-	5	-	2.3	-	-	1.7	480	3.0	3.0	-	49	850	14	-	-	-
FGT-03 - 80.79	FGT-03	80.79	83.82	Granite	-	-	-	5	-	2.2	-	-	1.6	420	2.0	2.8	-	44	750	14	-	-	-
FGT-03 - 83.82	FGT-03	83.82	90.22	Granite	-	-	-	5	-	2.1	-	-	1.7	440	2.0	2.7	-	46	790	12	-	-	-
FGT-03 - 90.22	FGT-03	90.22	97.72	Granite	-	-	-	5	-	2.2	-	-	1.8	475	3.0	3.0	-	53	870	14	-	-	-
FGT-03 - 97.72	FGT-03	97.72	105.22	Granite	-	-	-	5	-	1.9	-	-	1.6	425	3.0	2.5	-	46	770	14	-	-	-
FGT-03 - 105.22	FGT-03	105.22	112.72	Granite	-	-	-	5	-	2.2	-	-	1.8	480	1.0	2.8	-	50	940	18	-	-	-
FGT-03 - 112.72	FGT-03	112.72	115.5	Granite	-	-	-	5	-	2.3	-	-	1.7	475	3.0	2.8	-	50	840	12	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	Price Crustal Abundances																		
		From	To		-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
					Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Fox (continued)																							
FGT-03 - 115.5	FGT-03	115.5	123	Granite	-	-	-	5	-	2.3	-	-	2.1	575	4.0	2.7	-	75	870	10	-	-	-
FGT-03 - 123	FGT-03	123	130.5	Granite	-	-	-	5	-	2.3	-	-	1.8	455	3.0	2.7	-	47	820	12	-	-	-
FGT-03 - 130.5	FGT-03	130.5	138	Granite	-	-	-	5	-	2.3	-	-	2.0	440	3.0	2.8	-	48	860	10	-	-	-
FGT-03 - 138	FGT-03	138	148.68	Granite	8.9	-	-	5	-	2.5	-	-	2.1	440	1.0	3.0	-	49	880	10	-	-	-
FGT-03 - 148.68	FGT-03	148.68	153.11	Granite	-	-	-	5	-	2.4	-	-	1.9	485	1.0	2.8	-	49	880	8	-	-	-
FGT-03 - 153.11	FGT-03	153.11	160.61	Granite	-	-	-	5	-	2.0	-	-	1.8	400	1.0	2.5	-	42	720	12	-	-	-
FGT-03 - 160.61	FGT-03	160.61	168.11	Granite	-	-	-	5	-	2.1	-	-	1.8	455	3.0	3.0	-	46	820	12	-	-	-
FGT-03 - 168.11	FGT-03	168.11	172.05	Granite	-	-	-	5	-	2.3	-	-	1.9	465	2.0	2.8	-	51	880	14	-	-	-
FGT-03 - 172.05	FGT-03	172.05	179.55	Granite	-	-	-	5	-	2.1	-	-	1.8	440	3.0	2.8	-	50	890	12	-	-	-
FGT-03 - 179.55	FGT-03	179.55	187.05	Granite	-	-	-	5	-	2.0	-	-	1.7	445	3.0	2.9	-	50	830	14	-	-	-
FGT-03 - 187.05	FGT-03	187.05	193.21	Granite	-	-	-	5	-	2.2	-	-	1.9	475	1.0	3.0	-	53	930	14	-	-	-
FGT-03 - 193.21	FGT-03	193.21	198.77	Granite	-	-	-	5	-	2.0	-	-	1.8	465	1.0	3.0	-	52	900	12	-	-	-
FGT-03 - 198.77	FGT-03	198.77	206.27	Granite	-	-	-	5	-	2.1	-	-	1.8	485	3.0	3.0	-	50	900	12	-	-	-
FGT-03 - 206.27	FGT-03	206.27	213.77	Granite	9.6	-	-	5	-	1.8	-	-	1.9	505	1.0	2.9	-	56	840	14	-	-	-
FGT-03 - 213.77	FGT-03	213.77	221.27	Granite	-	-	-	5	-	2.0	-	-	1.7	470	1.0	2.9	-	48	830	14	-	-	-
FGT-03 - 221.27	FGT-03	221.27	228.77	Granite	-	-	-	5	-	2.0	-	-	1.8	480	3.0	3.0	-	50	840	10	-	-	-
FGT-03 - 228.77	FGT-03	228.77	235.73	Granite	-	-	-	5	-	2.1	-	-	1.9	495	2.0	2.9	-	51	900	8	-	-	-
FGT-03 - 235.73	FGT-03	235.73	243.23	Granite	-	-	-	5	-	1.8	-	-	1.8	460	3.0	2.7	-	46	820	8	-	-	-
FGT-03 - 243.23	FGT-03	243.23	251.46	Granite	-	-	-	5	-	1.9	-	-	1.7	425	3.0	2.9	-	49	860	10	-	-	-
FGT-05 - 1.1	FGT-05	1.1	5.5	Granite	8.9	-	-	5	-	2.0	-	-	1.8	470	0.5	2.8	-	50	810	18	-	-	-
FGT-05 - 5.5	FGT-05	5.5	11.4	Granite	-	-	-	5	-	2.1	-	-	1.7	425	3.0	2.5	-	45	790	8	-	-	-
FGT-05 - 14.3	FGT-05	14.3	20.34	Granite	-	-	-	5	-	1.9	-	-	1.6	415	2.0	2.5	-	47	750	12	-	-	-
FGT-05 - 20.34	FGT-05	20.34	26	Granite	-	-	-	5	-	2.0	-	-	1.6	435	1.0	2.6	-	49	860	12	-	-	-
FGT-05 - 26	FGT-05	26	30.8	Granite	-	-	-	5	-	2.1	-	-	1.7	425	1.0	2.5	-	45	810	14	-	-	-
FGT-05 - 30.8	FGT-05	30.8	37.7	Granite	-	-	-	5	-	2.5	-	-	1.7	385	3.0	2.5	-	45	830	12	-	-	-
FGT-05 - 37.7	FGT-05	37.7	45	Granite	-	-	-	5	-	2.1	-	-	1.6	430	2.0	2.7	-	49	800	14	-	-	-
FGT-05 - 45	FGT-05	45	52.5	Granite	-	-	-	5	-	2.0	-	-	1.5	415	3.0	2.6	-	45	730	16	-	-	-
FGT-05 - 52.5	FGT-05	52.5	60	Granite	-	-	-	5	-	2.0	-	-	1.6	425	2.0	2.6	-	46	790	14	-	-	-
FGT-05 - 60	FGT-05	60	67.5	Granite	9.5	-	-	5	-	2.0	-	-	1.6	425	3.0	2.7	-	47	820	12	-	-	-
FGT-05 - 67.5	FGT-05	67.5	75	Granite	-	-	-	5	-	1.8	-	-	1.6	415	1.0	2.7	-	45	760	12	-	-	-
FGT-05 - 75	FGT-05	75	82.5	Granite	-	-	-	5	-	1.9	-	-	1.8	480	2.0	2.5	-	50	820	10	-	-	-
FGT-05 - 82.5	FGT-05	82.5	90	Granite	-	-	-	5	-	2.0	-	-	1.6	425	1.0	2.6	-	46	810	10	-	-	-
FGT-05 - 90	FGT-05	90	97.5	Granite	-	-	-	5	-	2.0	-	-	1.6	425	3.0	2.7	-	46	790	10	-	-	-
FGT-05 - 97.5	FGT-05	97.5	105	Granite	-	-	-	5	-	1.9	-	-	1.5	430	2.0	2.7	-	47	820	16	-	-	-
FGT-05 - 105	FGT-05	105	112.5	Granite	-	-	-	5	-	2.2	-	-	1.6	350	1.0	2.7	-	49	1,010	14	-	-	-
FGT-05 - 112.5	FGT-05	112.5	120	Granite	-	-	-	5	-	2.3	-	-	1.6	355	2.0	2.8	-	54	1,020	14	-	-	-
FGT-05 - 120	FGT-05	120	128	Granite	-	-	-	5	-	2.2	-	-	1.7	430	1.0	2.7	-	46	870	10	-	-	-
FGT-05 - 128	FGT-05	128	134.9	Granite	-	-	-	5	-	2.4	-	-	1.7	430	1.0	2.6	-	46	830	14	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	Price Crustal Abundances																		
		From	To		-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
					Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Fox (continued)																							
FGT-05 - 175.36	FGT-05	175.36	183	Granite	-	-	-	5	-	2.1	-	-	1.8	470	2.0	2.9	-	54	850	12	-	-	-
FGT-05 - 183	FGT-05	183	190.5	Granite	-	-	-	5	-	2.3	-	-	1.7	465	1.0	2.8	-	47	840	14	-	-	-
FGT-05 - 190.5	FGT-05	190.5	198	Granite	-	-	-	5	-	2.1	-	-	1.7	465	0.5	2.8	-	47	850	10	-	-	-
FGT-05 - 198	FGT-05	198	205.5	Granite	-	-	-	5	-	2.2	-	-	1.7	450	1.0	2.5	-	45	840	12	-	-	-
FGT-05 - 205.5	FGT-05	205.5	213	Granite	9.4	-	-	5	-	2.0	-	-	1.6	455	3.0	2.6	-	49	810	16	-	-	-
FGT-05 - 213	FGT-05	213	220.5	Granite	-	-	-	5	-	2.0	-	-	1.6	440	1.0	2.6	-	45	800	14	-	-	-
FGT-05 - 220.5	FGT-05	220.5	228	Granite	-	-	-	5	-	2.0	-	-	1.5	420	0.5	2.5	-	43	750	16	-	-	-
FGT-05 - 228	FGT-05	228	235.5	Granite	-	-	-	5	-	2.0	-	-	1.5	415	2.0	2.5	-	46	770	14	-	-	-
FGT-05 - 235.5	FGT-05	235.5	243	Granite	-	-	-	5	-	2.0	-	-	1.6	435	1.0	2.5	-	44	780	14	-	-	-
FGT-05 - 243	FGT-05	243	250.5	Granite	-	-	-	5	-	2.0	-	-	1.6	430	3.0	2.5	-	44	770	12	-	-	-
FGT-05 - 250.5	FGT-05	250.5	258	Granite	-	-	-	5	-	2.0	-	-	1.6	430	1.0	2.6	-	44	820	16	-	-	-
FGT-05 - 258	FGT-05	258	265.5	Granite	-	-	-	5	-	2.0	-	-	1.9	500	1.0	2.5	-	54	830	16	-	-	-
FGT-05 - 265.5	FGT-05	265.5	273	Granite	-	-	-	5	-	1.9	-	-	1.7	465	1.0	2.5	-	45	790	16	-	-	-
FGT-05 - 273	FGT-05	273	280.5	Granite	-	-	-	5	-	1.9	-	-	1.8	495	0.5	2.5	-	50	950	10	-	-	-
FGT-05 - 280.5	FGT-05	280.5	288	Granite	9.3	-	-	5	-	1.9	-	-	1.7	450	1.0	2.5	-	48	860	16	-	-	-
FGT-05 - 288	FGT-05	288	295	Granite	-	-	-	5	-	2.0	-	-	1.7	455	1.0	2.5	-	49	970	18	-	-	-
FGT-05 - 295	FGT-05	295	EOH	Granite	-	-	-	5	-	2.0	-	-	1.7	450	2.0	2.6	-	48	830	12	-	-	-
FGT-07 - 4	FGT-07	4	14.21	Granite	9.1	-	-	5	-	2.7	-	-	1.0	335	1.0	3.0	-	26	590	14	-	-	-
FGT-07 - 14.21	FGT-07	14.21	20.12	Granite	-	-	-	5	-	2.7	-	-	0.99	320	0.5	2.9	-	24	540	14	-	-	-
FGT-07 - 20.12	FGT-07	20.12	31.45	Granite	-	-	-	5	-	2.1	-	-	1.1	305	0.5	2.9	-	27	620	10	-	-	-
FGT-07 - 31.45	FGT-07	31.45	39	Granite	-	-	-	5	-	2.3	-	-	1.1	325	0.5	2.7	-	28	690	6	-	-	-
FGT-07 - 39	FGT-07	39	46.5	Granite	-	-	-	5	-	2.5	-	-	1.2	345	0.5	2.9	-	32	790	12	-	-	-
FGT-07 - 46.5	FGT-07	46.5	54	Granite	-	-	-	5	-	2.7	-	-	1.3	320	1.0	2.7	-	30	790	8	-	-	-
FGT-07 - 54	FGT-07	54	61.5	Granite	-	-	-	5	-	3.1	-	-	1.3	290	0.5	2.6	-	27	680	10	-	-	-
FGT-07 - 61.5	FGT-07	61.5	69	Granite	-	-	-	5	-	3.4	-	-	1.2	270	0.5	2.3	-	23	510	6	-	-	-
FGT-07 - 69	FGT-07	69	76.5	Granite	-	-	-	5	-	2.1	-	-	1.3	270	0.5	2.8	-	28	680	2	-	-	-
FGT-07 - 76.5	FGT-07	76.5	86.23	Granite	-	-	-	5	-	2.1	-	-	1.8	380	1.0	2.6	-	43	860	10	-	-	-
FGT-07 - 86.23	FGT-07	86.23	94	Granite	9.3	-	-	5	-	1.8	-	-	1.7	415	0.5	2.7	-	48	950	1	-	-	-
FGT-07 - 94	FGT-07	94	101.5	Granite	-	-	-	5	-	1.8	-	-	1.8	405	0.5	2.7	-	47	910	6	-	-	-
FGT-07 - 101.5	FGT-07	101.5	109	Granite	-	-	-	5	-	1.8	-	-	1.8	405	1.0	2.8	-	49	880	6	-	-	-
FGT-07 - 109	FGT-07	109	116.5	Granite	-	-	-	5	-	2.0	-	-	1.8	395	0.5	2.9	-	55	820	8	-	-	-
FGT-07 - 116.5	FGT-07	116.5	124	Granite	-	-	-	5	-	2.0	-	-	1.8	405	0.5	2.9	-	50	920	6	-	-	-
FGT-07 - 124	FGT-07	124	131.78	Granite	-	-	-	5	-	1.8	-	-	1.8	405	1.0	2.8	-	49	910	8	-	-	-
FGT-07 - 131.78	FGT-07	131.78	135.64	Granite	-	-	-	5	-	2.0	-	-	2.0	420	1.0	2.8	-	52	920	4	-	-	-
FGT-07 - 135.64	FGT-07	135.64	143	Granite	-	-	-	5	-	1.9	-	-	1.8	395	1.0	2.8	-	50	960	2	-	-	-
FGT-07 - 143	FGT-07	143	149	Granite	-	-	-	5	-	0.19	-	-	0.20	45	0.5	0.26	-	6	90	2	-	-	-
FGT-07 - 149	FGT-07	149	156.5	Granite	-	-	-	5	-	0.29	-	-	0.30	60	0.5	0.41	-	8	130	1	-	-	-
FGT-07 - 156.5	FGT-07	156.5	162.63	Granite	9.1	-	-	5	-	1.9	-	-	1.9	415	0.5	2.7	-	50	870	2	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Fox (continued)																							
FGT-07 - 162.63	FGT-07	162.63	170	Granite	-	-	-	5	-	1.8	-	-	1.7	365	0.5	2.6	-	51	790	2	-	-	-
FGT-07 - 170	FGT-07	170	177.5	Granite	-	-	-	5	-	2.1	-	-	2.1	445	0.5	2.5	-	66	900	2	-	-	-
FGT-07 - 177.5	FGT-07	177.5	188.55	Granite	-	-	-	5	-	2.1	-	-	2.0	420	0.5	2.6	-	62	900	2	-	-	-
FGT-07 - 188.55	FGT-07	188.55	193.27	Granite	-	-	-	5	-	1.9	-	-	1.9	380	0.5	2.6	-	59	860	4	-	-	-
FGT-07 - 193.27	FGT-07	193.27	199.62	Granite	-	-	-	5	-	2.0	-	-	1.8	370	1.0	2.6	-	53	930	6	-	-	-
FGT-07 - 199.62	FGT-07	199.62	204.78	Granite	-	-	-	5	-	1.8	-	-	2.0	465	0.5	2.8	-	49	1,520	10	-	-	-
FGT-07 - 204.78	FGT-07	204.78	212.28	Granite	-	-	-	5	-	1.9	-	-	1.9	410	0.5	2.9	-	51	1,050	2	-	-	-
FGT-07 - 212.28	FGT-07	212.28	219.78	Granite	-	-	-	5	-	1.9	-	-	1.9	440	0.5	2.7	-	52	910	6	-	-	-
FGT-07 - 219.78	FGT-07	219.78	227.28	Granite	-	-	-	5	-	1.8	-	-	1.8	420	0.5	2.7	-	51	870	8	-	-	-
FGT-07 - 227.28	FGT-07	227.28	234.78	Granite	9.3	-	-	5	-	1.8	-	-	1.7	395	1.0	2.6	-	51	830	4	-	-	-
FGT-07 - 234.78	FGT-07	234.78	242.28	Granite	-	-	-	5	-	1.9	-	-	1.8	395	1.0	2.6	-	56	810	8	-	-	-
FGT-07 - 242.28	FGT-07	242.28	249.78	Granite	-	-	-	5	-	1.8	-	-	1.7	405	0.5	2.8	-	46	870	4	-	-	-
FGT-07 - 249.78	FGT-07	249.78	257.28	Granite	-	-	-	5	-	1.8	-	-	1.9	425	0.5	2.8	-	52	910	4	-	-	-
FGT-07 - 257.28	FGT-07	257.28	267.52	Granite	-	-	-	5	-	1.8	-	-	1.9	430	0.5	2.7	-	56	890	10	-	-	-
FG-470-01-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-470-01-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-450-23-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-450-23-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-24-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-24-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-25-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-25-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-26-1	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-26-2	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-31-1	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-31-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-03-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-03-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-03-1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-03-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-04-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-04-2	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-06-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-06-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-07-1	-	-	-	Granite	9.5	-	-	5	-	2.1	-	-	1.9	435	1.0	3.3	-	51	920	13	-	-	-
FG-435-07-2	-	-	-	Granite	9.6	-	-	5	-	1.8	-	-	1.8	456	1.0	3.2	-	50	990	13	-	-	-
FG-435-08-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-08-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Fox (continued)																							
FG-435-13-1	-	-	-	Granite	9.4	-	-	5	-	1.9	-	-	1.9	419	4.0	3.4	-	51	990	9	-	-	-
FG-435-13-2	-	-	-	Granite	9.5	-	-	5	-	2.1	-	-	1.8	414	2.0	3.3	-	48	1,010	13	-	-	-
FG-435-18-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-18-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-27-1a	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-27-1b	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-34-1a	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-34-1b	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-30-1a	-	-	-	Granite	9.3	-	-	5	-	2.2	-	-	1.9	416	2.0	3.0	-	50	920	10	-	-	-
FG-435-30-2a	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-31-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-31-2	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-38-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-38-2	-	-	-	Granite	9.1	-	-	5	-	2.5	-	-	1.8	393	2.0	3.0	-	44	870	14	-	-	-
FG-435-44-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-44-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-48-1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-48-1b	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-06-1	-	-	-	Granite	9.4	-	-	5	-	2.4	-	-	2.1	387	1.0	2.9	-	46	940	7	-	-	-
FG-420-06-2	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-14-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-14-2	-	-	-	Granite	9.4	-	-	5	-	2.3	-	-	1.8	389	1.0	2.9	-	43	850	7	-	-	-
FG-420-21-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-21-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-25-1	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-25-2	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-27-1	-	-	-	Granite	9.4	-	-	5	-	2.4	-	-	1.7	395	1.0	3.0	-	41	930	9	-	-	-
FG-420-27-2	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-36-1	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-36-2	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-38-1	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-38-2	-	-	-	Granite	9.3	-	-	5	-	2.7	-	-	2.3	373	1.0	2.6	-	46	870	6	-	-	-
F420	-	-	-	Granite	9.3	-	-	5	-	2.7	-	-	2.3	373	1.0	2.6	-	46	870	6	-	-	-
F420	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
F420	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
F420	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-25-1	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-25-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Fox (continued)																							
FG-420-27-1	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-27-2	-	-	-	Granite	9.4	-	-	5	-	2.4	-	-	1.7	395	1.0	3.0	-	41	930	9	-	-	-
FG-420-51-A	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-51-B	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-05-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-05-2	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-05-1	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-05-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-09-A	-	-	-	Granite	9.3	-	-	0.005	-	2.2	-	-	1.9	400	3.0	3.1	-	46	1,000	4	-	-	-
FG-405-09-B	-	-	-	Granite	9.4	-	-	0.005	-	2.2	-	-	1.8	399	1.0	2.8	-	43	970	8	-	-	-
FG-405-48-1	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-48-2	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-53-1	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-53-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
F-390-25-1A	-	-	-	Granite	9.6	-	-	0.005	-	2.2	-	-	1.8	382	4.0	3.0	-	47	880	9	-	-	-
F-390-25-1B	-	-	-	Granite	9.4	-	-	0.005	-	2.0	-	-	1.7	350	2.0	2.8	-	43	790	8	-	-	-
FG-390-20-1	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-20-2	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-25-1A	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-25-1B	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-37-1	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-37-2	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-38-1	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-38-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-42-1	-	-	-	Granite	9.6	-	-	0.005	-	2.0	-	-	1.8	370	2.0	2.9	-	48	910	7	-	-	-
FG-390-42-2	-	-	-	Granite	9.6	-	-	0.005	-	1.9	-	-	1.7	350	4.0	2.9	-	48	850	7	-	-	-
FG-390-43-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-43-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-43-3	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-43-4	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-44-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-44-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-45-1	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-45-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-45-3	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-45-4	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-46-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-46-2	-	-	-	Granite	8.9	-	-	0.005	-	1.8	-	-	1.9	401	0.5	2.8	-	46	1,000	8	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Fox (continued)																							
FG-390-46-3	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-46-4	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-48-1	-	-	-	Granite	9.1	-	-	0.005	-	2.2	-	-	1.8	377	1.0	2.5	-	46	880	7	-	-	-
FG-390-48-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-48-3	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-48-4	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-49-1	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-49-2	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-50-1	-	-	-	Granite	9.2	-	-	0.005	-	2.1	-	-	1.9	441	1.0	2.7	-	56	950	10	-	-	-
FG-390-50-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-50-3	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-50-4	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-08-1	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-08-1	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-08-2	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-08-2	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-09R1-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-09R1-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-12-01	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-12-02	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-18-1	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-18-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-18-3	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-18-4	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-22-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-22-2	-	-	-	Granite	8.6	-	-	0.005	-	2.5	-	-	2.4	399	0.5	2.5	-	67	1,050	7	-	-	-
FG-375-24-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-24-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-24-3	-	-	-	Granite	9.5	-	-	0.005	-	2.0	-	-	1.6	367	1.0	2.6	-	45	800	10	-	-	-
FG-375-24-4	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-28-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-28-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-28-3	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-28-4	-	-	-	Granite	9.4	-	-	0.005	-	2.1	-	-	1.9	428	1.0	2.9	-	51	900	13	-	-	-
FG-375-30-1	-	-	-	Granite	9.3	-	-	0.005	-	2.1	-	-	2.0	435	0.5	2.7	-	51	930	12	-	-	-
FG-375-30-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-30-3	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-30-4	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035	
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %	
Granite (continued)																								
Fox (continued)																								
FG-375-31-1	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-31-2	-	-	-	Granite	8.5	-	-	0.005	-	2.1	-	-	3.0	467	1.0	2.5	-	132	1,030	11	-	-	-	-
FG-375-31-3	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-31-4	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-37-1	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-37-2	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-37-3	-	-	-	Granite	8.3	-	-	0.005	-	2.3	-	-	1.9	371	2.0	2.8	-	47	880	9	-	-	-	-
FG-375-37-4	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-1	-	-	-	Granite	9.8	-	-	0.005	-	2.3	-	-	1.8	369	1.0	2.9	-	47	880	10	-	-	-	-
FG-375-40-2	-	-	-	Granite	9.6	-	-	0.005	-	2.1	-	-	1.7	346	2.0	3.0	-	42	800	10	-	-	-	-
FOX-375-07-1A	-	-	-	Granite	9.8	-	-	0.005	-	2.1	-	-	1.9	423	1.0	3.1	-	53	960	7	-	-	-	-
FOX-375-07-1B	-	-	-	Granite	9.7	-	-	0.005	-	1.9	-	-	1.9	420	3.0	3.0	-	51	890	3	-	-	-	-
FG-375-52-02 22-NOV-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-52-01 22-NOV-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-45-04 29-OCT-04	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-45-03 29-OCT-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-45-02 29-OCT-04	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-45-01 29-OCT-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-04 24-OCT-04	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-04 20-OCT-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-03 24-OCT-04	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-03 20-OCT-04	-	-	-	Granite	9.3	-	-	0.005	-	1.9	-	-	1.7	419	1.0	2.9	-	51	870	5	-	-	-	-
FG-375-42-02 24-OCT-04	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-02 20-OCT-04	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-01 24-OCT-04	-	-	-	Granite	8.6	-	-	0.005	-	2.4	-	-	1.9	414	0.5	2.6	-	52	900	2	-	-	-	-
FG-375-42-01 20-OCT-04	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-41-04 13-OCT-04	-	-	-	Granite	8.8	-	-	0.005	-	2.1	-	-	1.8	373	0.5	2.7	-	46	850	8	-	-	-	-
FG-375-41-03 13-OCT-04	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-41-02 13-OCT-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-41-01 13-OCT-04	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-04 12-OCT-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-03 12-OCT-04	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-02 12-OCT-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-01 12-OCT-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-39-04 6-SEP-04	-	-	-	Granite	8.1	-	-	0.005	-	1.9	-	-	1.8	452	1.0	2.6	-	61	850	5	-	-	-	-
FG-375-39-03 6-SEP-04	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-39-02 6-SEP-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-39-01 6-SEP-04	-	-	-	Granite	7.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035	
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S	
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																								
Fox (continued)																								
FG-375-33-04 6-OCT-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-33-03 6-OCT-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-33-02 6-OCT-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-33-01 6-OCT-04	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-370-06-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-01-01	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-01-02	-	-	-	Granite	9.6	-	-	0.005	-	2.1	-	-	1.7	375	1.0	2.7	-	49	850	229	-	-	-	-
FG-360-01-03	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-01-04	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-52-04 8-Apr-05	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-52-03 8-Apr-05	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-52-02 8-Apr-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-52-01 8-Apr-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-06 8-Apr-05	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-05 8-Apr-05	-	-	-	Granite	8.3	-	-	0.01	-	2.2	-	-	3.0	454	1.0	2.2	-	122	910	8	-	-	-	-
FG-360-51-04 23-Mar-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-03 23-Mar-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-02 23-Mar-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-01 23-Mar-05	-	-	-	Granite	9.3	-	-	0.01	-	2.1	-	-	1.8	388	0.5	2.5	-	63	820	10	-	-	-	-
FG-360-47-06 8-Mar-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-47-05 8-Mar-05	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-47-04 8-Mar-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-47-03 8-Mar-05	-	-	-	Granite	9.6	-	-	0.005	-	2.0	-	-	1.7	398	0.5	2.7	-	46	900	8	-	-	-	-
FG-360-47-02 8-Mar-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-47-01 8-Mar-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-46-04 28-FEB-05	-	-	-	Granite	9.5	-	-	0.005	-	1.9	-	-	1.6	402	0.5	2.7	-	43	860	13	-	-	-	-
FG-360-46-03 28-FEB-05	-	-	-	Granite	9.5	-	-	0.005	-	2.0	-	-	1.7	402	0.5	2.8	-	50	900	11	-	-	-	-
FG-360-46-02 28-FEB-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-46-01 28-FEB-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-44-04 18-FEB-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-44-03 18-FEB-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-44-02 18-FEB-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-44-01 18-FEB-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-42-06 1-FEB-05	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-42-05 1-FEB-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-42-04 30-JAN-05	-	-	-	Granite	8.9	-	-	0.005	-	2.4	-	-	2.1	416	1.0	2.6	-	68	890	8	-	-	-	-
FG-360-42-03 30-JAN-05	-	-	-	Granite	8.8	-	-	0.005	-	2.4	-	-	2.2	408	1.0	2.8	-	76	900	5	-	-	-	-
FG-360-42-02 28-JAN-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																							
Fox (continued)																							
FG-360-42-01 28-JAN-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-41-04 1-FEB-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-41-03 1-FEB-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-41-02 24-JAN-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-41-01 24-JAN-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-40-04 4-FEB-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-40-03 4-FEB-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-40-02 4-FEB-05	-	-	-	Granite	9.7	-	-	0.005	-	2.0	-	-	1.8	420	1.0	2.9	-	50	980	11	-	-	-
FG-360-40-01 4-FEB-05	-	-	-	Granite	9.6	-	-	0.005	-	2.0	-	-	1.7	441	1.0	2.9	-	54	990	10	-	-	-
FG-360-39-06 1-FEB-05	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-05 1-FEB-05	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-04 23-JAN-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-04 18-JAN-05	-	-	-	Granite	9.5	-	-	0.005	-	2.1	-	-	1.8	383	1.0	2.9	-	43	850	7	-	-	-
FG-360-39-03 23-JAN-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-03 18-JAN-05	-	-	-	Granite	9.2	-	-	0.005	-	1.9	-	-	1.9	369	1.0	3.2	-	42	870	4	-	-	-
FG-360-39-02 22-JAN-05	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-02 18-JAN-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-01 22-JAN-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-01 18-JAN-05	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-38-04 23-JAN-05	-	-	-	Granite	9.8	-	-	0.01	-	2.0	-	-	1.8	406	1.0	2.9	-	48	940	10	-	-	-
FG-360-38-03 23-JAN-05	-	-	-	Granite	9.0	-	-	0.005	-	2.0	-	-	2.3	470	0.5	2.9	-	81	1,050	7	-	-	-
FG-360-38-02 22-JAN-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-38-01 22-JAN-05	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-36-02 30-JAN-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-36-01 30-JAN-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-35-04 14-JAN-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-35-03 14-JAN-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-35-02 14-JAN-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-35-01 14-JAN-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-04 23-JAN-05	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-03 23-JAN-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-02 20-JAN-05	-	-	-	Granite	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-02 11-JAN-05	-	-	-	Granite	9.3	-	-	0.005	-	2.1	-	-	1.6	351	1.0	3.0	-	43	810	8	-	-	-
FG-360-30-01 20-JAN-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-01 11-JAN-05	-	-	-	Granite	9.4	-	-	0.005	-	1.9	-	-	1.8	380	1.0	2.9	-	45	900	7	-	-	-
FG-360-29-04 26-DEC-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-29-03 26-DEC-04	-	-	-	Granite	8.0	-	-	0.01	-	1.7	-	-	6.2	606	0.5	1.6	-	379	1,180	10	-	-	-
FG-360-29-02 1-JAN-05	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																							
Fox (continued)																							
FG-360-29-01 1-JAN-05	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-28-02 26-DEC-04	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-28-01 26-DEC-04	-	-	-	Granite	8.1	-	-	0.005	-	0.94	-	-	3.2	1,235	1.0	2.2	-	70	740	1	-	-	-
FG-360-25-02 11-JAN-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-25-01 11-JAN-05	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-22-04 13-DEC-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-22-03 13-DEC-04	-	-	-	Granite	8.8	-	-	0.005	-	2.1	-	-	1.8	423	1.0	2.8	-	50	910	4	-	-	-
FG-360-22-02 13-DEC-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-22-01 13-DEC-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-18-02 1-JAN-05	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-18-01 1-JAN-05	-	-	-	Granite	8.5	-	-	0.005	-	2.1	-	-	1.7	441	1.0	2.7	-	47	830	5	-	-	-
FG-360-11-04 26-FEB-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-11-03 26-FEB-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-11-02 3-DEC-04	-	-	-	Granite	8.2	-	-	0.005	-	2.3	-	-	2.5	368	1.0	2.8	-	48	920	1	-	-	-
FG-360-11-02 26-FEB-05	-	-	-	Granite	8.9	-	-	0.005	-	1.7	-	-	2.4	616	6.0	2.8	-	80	900	5	-	-	-
FG-360-11-01 3-DEC-04	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-11-01 26-FEB-05	-	-	-	Granite	9.2	-	-	0.005	-	1.6	-	-	2.5	775	1.0	2.8	-	69	1,020	8	-	-	-
FG-360-03-04 13-OCT-04	-	-	-	Granite	8.3	-	-	0.005	-	2.2	-	-	1.8	419	2.0	2.7	-	53	920	6	-	-	-
FG-360-03-03 13-OCT-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-03-02 13-OCT-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-03-01 13-OCT-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-02-04 6-OCT-04	-	-	-	Granite	8.2	-	-	0.005	-	2.2	-	-	1.9	406	1.0	2.7	-	44	870	4	-	-	-
FG-360-02-03 6-OCT-04	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-02-02 6-OCT-04	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-02-01 6-OCT-04	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-4 17-May-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-3 17-May-05	-	-	-	Granite	9.1	-	-	0.005	-	1.2	-	-	3.4	1,120	1.0	2.1	-	77	730	13	-	-	-
FG-345-42-2 17-May-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-1 17-May-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-08 11-May-05	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-07 11-May-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-06 11-May-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-05 11-May-05	-	-	-	Granite	8.9	-	-	0.005	-	0.66	-	-	3.7	1,375	0.5	1.9	-	88	640	7	-	-	-
FG-345-42-04 10-May-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-03 10-May-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-02 10-May-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-01 10-May-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-41-04 4-May-05	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Fox (continued)																							
FG-345-41-03	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-41-02	-	-	-	Granite	9.2	-	-	0.005	-	2.1	-	-	1.9	348	1.0	3.0	-	41	860	3	-	-	-
FG-345-41-01	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-40-04	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-40-03	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-40-02	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-40-01	-	-	-	Granite	9.3	-	-	0.005	-	2.1	-	-	2.2	483	0.5	2.8	-	63	960	7	-	-	-
FG-345-38-06	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-04	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-03	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-02	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-01	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-37-04	-	-	-	Granite	9.3	-	-	0.005	-	2.0	-	-	1.8	369	1.0	2.7	-	49	840	4	-	-	-
FG-345-37-03	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-37-02	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-37-01	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-36-04	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-36-03	-	-	-	Granite	9.2	-	-	0.005	-	1.9	-	-	1.9	408	0.5	2.8	-	62	910	7	-	-	-
FG-345-36-02	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-36-01	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-35-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-35-03	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-35-02	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-35-01	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-34-04	-	-	-	Granite	9.8	-	-	0.01	-	2.0	-	-	1.6	355	0.5	2.6	-	49	750	7	-	-	-
FG-345-34-03	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-34-02	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-34-01	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-06	-	-	-	Granite	9.3	-	-	0.005	-	2.0	-	-	2.1	375	0.5	2.7	-	48	840	2	-	-	-
FG-345-27-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-04	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-03	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-02	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-01	-	-	-	Granite	9.4	-	-	0.005	-	2.0	-	-	1.9	393	0.5	2.7	-	47	920	12	-	-	-
FG-345-21-04	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-21-03	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-21-02	-	-	-	Granite	9.4	-	-	0.005	-	1.8	-	-	1.8	389	0.5	2.8	-	56	850	8	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																							
Fox (continued)																							
FG-345-21-01 24-Mar-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-16-04 28-FEB-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-16-03 28-FEB-05	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-16-02 28-FEB-05	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-16-01 28-FEB-05	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-14-02 16-FEB-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-14-01 16-FEB-05	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-12-06 26-Mar-05	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-12-05 26-Mar-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-12-04 26-Mar-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-12-03 26-Mar-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-12-02 26-Mar-05	-	-	-	Granite	8.3	-	-	0.01	-	2.7	-	-	3.3	377	0.5	2.0	-	86	980	2	-	-	-
FG-345-12-01 26-Mar-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-10-04 15-FEB-05	-	-	-	Granite	9.9	-	-	0.005	-	1.9	-	-	1.8	441	2.0	3.1	-	58	960	9	-	-	-
FG-345-10-03 15-FEB-05	-	-	-	Granite	9.7	-	-	0.005	-	2.0	-	-	2.3	480	1.0	2.9	-	106	830	3	-	-	-
FG-345-10-02 15-FEB-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-10-01 15-FEB-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-09-04 7-FEB-05	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-09-03 7-FEB-05	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-09-02 7-FEB-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-09-01 7-FEB-05	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-07-04 16-FEB-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-07-03 16-FEB-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-07-02 4-FEB-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-07-01 4-FEB-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-25-04 24-Jun-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-25-03 24-Jun-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-25-02 24-Jun-05	-	-	-	Granite	9.6	-	-	0.005	-	1.8	-	-	1.6	417	1.0	2.7	-	47	930	10	-	-	-
FG-330-25-01 24-Jun-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-24-04 24-Jun-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-24-03 24-Jun-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-24-02 24-Jun-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-24-01 24-Jun-05	-	-	-	Granite	9.8	-	-	0.005	-	2.0	-	-	1.7	414	0.5	2.7	-	46	880	12	-	-	-
FG-330-23-04 15-Jun-05	-	-	-	Granite	9.0	-	-	0.005	-	2.4	-	-	2.2	389	0.5	2.8	-	44	900	11	-	-	-
FG-330-23-03 15-Jun-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-23-02 15-Jun-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-23-01 15-Jun-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-22-08 20-Jun-05	-	-	-	Granite	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035	
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S	
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																								
Fox (continued)																								
FG-330-22-07	20-Jun-05	-	-	Granite	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-22-06	20-Jun-05	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-22-05	20-Jun-05	-	-	Granite	9.7	-	-	0.005	-	1.9	-	-	1.8	441	2.0	2.6	-	49	900	11	-	-	-	-
FG-330-22-04	20-Jun-05	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-22-03	20-Jun-05	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-22-02	20-Jun-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-22-01	20-Jun-05	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-20-04	10-Jun-05	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-20-03	10-Jun-05	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-20-02	10-Jun-05	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-20-01	10-Jun-05	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-18-02	11-Jun-05	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-18-01	11-Jun-05	-	-	Granite	8.9	-	-	0.005	-	2.0	-	-	2.7	419	0.5	2.4	-	111	910	13	-	-	-	-
FG-330-15-04	4-Jun-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-15-03	4-Jun-05	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-15-02	4-Jun-05	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-15-01	4-Jun-05	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-13-04	1-Jun-05	-	-	Granite	9.3	-	-	0.005	-	2.0	-	-	1.9	379	0.5	2.6	-	57	810	7	-	-	-	-
FG-330-13-03	1-Jun-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-13-02	1-Jun-05	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-13-01	1-Jun-05	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-08	18-May-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-07	18-May-05	-	-	Granite	9.6	-	-	0.005	-	1.9	-	-	1.7	396	0.5	2.7	-	46	880	8	-	-	-	-
FG-330-09-06	18-May-05	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-05	18-May-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-04	17-May-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-03	17-May-05	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-02	17-May-05	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-330-09-01	17-May-05	-	-	Granite	9.4	-	-	0.005	-	1.7	-	-	2.2	503	0.5	2.6	-	79	910	10	-	-	-	-
FG-315-13-02	14-07-05	-	-	Granite	8.9	-	-	0.01	-	2.2	-	-	1.9	381	2.0	2.5	-	48	850	12	-	-	-	-
FG-315-13-03	14-07-05	-	-	Granite	9.4	-	-	0.01	-	2.3	-	-	2.3	426	0.5	3.1	-	57	1,060	11	-	-	-	-
FG-315-13-04	14-07-05	-	-	Granite	9.2	-	-	0.005	-	2.3	-	-	2.1	412	2.0	2.7	-	53	930	9	-	-	-	-
FG-315-16-01	24-07-05	-	-	Granite	9.7	-	-	0.005	-	1.8	-	-	1.6	387	1.0	2.6	-	47	860	8	-	-	-	-
FG-315-16-02	24-07-05	-	-	Granite	9.5	-	-	0.005	-	2.1	-	-	1.7	403	0.5	2.6	-	46	900	14	-	-	-	-
FG-315-16-03	24-07-05	-	-	Granite	9.6	-	-	0.01	-	1.9	-	-	1.7	399	0.5	2.5	-	45	910	15	-	-	-	-
FG-315-16-04	24-07-05	-	-	Granite	9.5	-	-	0.01	-	2.0	-	-	1.7	402	0.5	2.6	-	46	900	11	-	-	-	-
FG-275-20-1		-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-275-20-2		-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
 Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																							
Fox (continued)																							
FG-275-20-3	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-275-20-4	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-270-16-01	-	-	-	Granite	9.8	-	-	0.005	-	2.4	-	-	2.3	447	0.5	2.5	-	48	960	14	-	-	-
Fox-260-Granite-2 31-Mar-09	-	-	-	Granite	9.3	-	-	5	-	1.8	10	-	0.49	100	1.0	3.8	-	4	200	5	-	-	-
Fox-260-Granite-1 31-Mar-09	-	-	-	Granite	9.4	-	-	5	-	1.6	10	-	1.8	344	0.5	2.7	-	41	820	4	-	-	-
Fox-250-Granite-2 26-Jan-09	-	-	-	Granite	9.4	-	-	5	-	1.5	10	-	1.9	416	0.5	2.8	-	69	890	8	-	-	-
Fox-250-Granite-1 26-Jan-09	-	-	-	Granite	9.9	-	-	5	-	1.6	10	-	1.7	401	0.5	2.7	-	43	890	11	-	-	-
Fox-250-Gr.Xenolith 8-Oct-09	-	-	-	Granite	9.9	-	-	5	-	1.9	20	-	1.8	422	0.5	2.8	-	46	990	9	-	-	-
Fox-250-Granite-3 8-Oct-09	-	-	-	Granite	9.7	-	-	5	-	2.1	20	-	2.3	516	0.5	2.5	-	63	1,080	10	-	-	-
Fox-250-Granite-4 8-Oct-09	-	-	-	Granite	9.6	-	-	5	-	1.9	20	-	2.4	437	0.5	2.6	-	106	970	12	-	-	-
Fox-240-Granite-3a 26-Jan-09	-	-	-	Granite	9.8	-	-	5	-	1.5	10	-	1.6	419	0.5	2.7	-	48	870	10	-	-	-
Fox-240-Granite-2a 26-Jan-09	-	-	-	Granite	9.9	-	-	5	-	1.5	10	-	1.7	416	0.5	2.7	-	46	920	8	-	-	-
Fox-240-Granite-1a 26-Jan-09	-	-	-	Granite	9.6	-	-	5	-	1.6	10	-	1.6	409	0.5	2.6	-	42	860	10	-	-	-
Fox-240-Granite-2 31-Mar-09	-	-	-	Granite	9.5	-	-	5	-	1.6	20	-	1.8	408	0.5	2.7	-	45	890	8	-	-	-
Fox-240-Granite-1 31-Mar-09	-	-	-	Granite	9.8	-	-	5	-	1.6	20	-	1.9	456	0.5	2.6	-	61	880	8	-	-	-
Median					9.3	-	-	5	-	2.0	10	-	1.8	419	1.0	2.7	-	48	870	10	-	-	-
Minimum					7.5	-	-	0.005	-	0.19	10	-	0.20	45	0.5	0.26	-	4	90	1	-	-	-
Maximum					10.0	-	-	10	-	3.4	20	-	6.2	1,375	6.0	3.8	-	379	1,520	229	-	-	-
Count					475	0	0	218	0	218	12	0	218	218	218	218	0	218	218	218	0	0	0
Koala																							
KG-345-27-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-27-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-28-1	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-28-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-30-1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-30-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-33-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-33-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-36-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-36-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-28-1	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-28-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-13-2	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-05-1A	-	-	-	Granite	9.0	-	-	0.005	-	1.9	-	-	3.4	432	6.0	3.0	-	158	990	11	-	-	0.07
KG-330-05-2A	-	-	-	Granite	8.6	-	-	0.005	-	2.1	-	-	4.4	446	5.0	2.7	-	235	1,040	5	-	-	0.11
KG-330-15-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-15-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-13-1	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																							
Koala (continued)																							
KG-330-13-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-26-1	-	-	-	Granite	8.8	-	-	0.005	-	1.2	-	-	2.8	377	4.0	4.8	-	53	1,040	4	-	-	0.03
KG-330-26-2	-	-	-	Granite	9.2	-	-	0.005	-	1.2	-	-	1.1	128	2.0	6.8	-	16	510	4	-	-	0.02
KG-330-17-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-17-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-10-1	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-10-2	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-21-1	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-21-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-12-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-12-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-27-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-27-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-05-1A	-	-	-	Granite	9.5	-	-	0.01	-	1.7	-	-	1.8	419	3.0	3.2	-	52	920	10	-	-	0.04
KG-315-05-2A	-	-	-	Granite	9.3	-	-	0.005	-	1.9	-	-	1.8	381	1.0	3.3	-	48	1,000	12	-	-	0.06
KG-315-28-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-28-2	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-17-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-17-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-20-1	-	-	-	Granite	9.0	-	-	0.005	-	2.0	-	-	1.9	391	1.0	3.2	-	57	900	10	-	-	0.05
KSG-300-20-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-20-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-20-2	-	-	-	Granite	9.0	-	-	5	-	2.0	-	-	1.9	391	1.0	3.2	-	57	900	10	-	-	0.05
KSG-290-01-1	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-01-2	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-06-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-06-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-06-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-06-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-290-11-A	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-290-11-B	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-16-1	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-16-2	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-1	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-1	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-1	-	-	-	Granite	9.7	-	-	0.005	-	2.2	-	-	1.8	379	1.0	2.8	-	53	990	2	-	-	0.05

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Koala (continued)																							
KG-280-18-2	-	-	-	Granite	9.2	-	-	0.005	-	2.0	-	-	2.2	369	3.0	3.0	-	44	1,010	1	-	-	0.13
KG-270-08-1	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-270-08-2	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-270-08-01	-	-	-	Granite	9.1	-	-	0.005	-	1.9	-	-	1.6	214	0.5	3.6	-	26	640	1	-	-	0.05
KG-270-08-02	-	-	-	Granite	9.2	-	-	0.005	-	1.6	-	-	1.4	228	1.0	4.1	-	27	650	1	-	-	0.08
KG-270-17-02	-	-	-	Granite	8.1	-	-	0.005	-	1.8	-	-	2.0	390	1.0	3.1	-	51	960	1	-	-	0.07
KG-270-17-01	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-290-13-1A	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-290-13-1B	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-280-16-1A	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-280-16-1B	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Koala-UG-Granite	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
			Median		9.1	-	-	0.005	-	1.9	-	-	1.9	381	1.0	3.2	-	52	960	4	-	-	0.05
			Minimum		7.8	-	-	0.005	-	1.2	-	-	1.1	128	0.5	2.7	-	16	510	1	-	-	0.02
			Maximum		9.9	-	-	5	-	2.2	-	-	4.4	446	6.0	6.8	-	235	1,040	12	-	-	0.13
			Count		68	0	0	13	0	13	0	0	13	13	13	13	0	13	13	13	0	0	13
Misery																							
MDC-1 31.7	-	-	-	Granite	8.8	-	-	5	-	1.8	-	-	0.20	155	2.0	3.9	-	14	440	20	-	-	0.005
MDC-1 61.21	-	-	-	Granite	9.2	-	-	5	-	2.1	-	-	0.19	155	1.0	3.8	-	9	300	24	-	-	0.005
MDC-1 90.8	-	-	-	Granite	9.4	-	-	5	-	1.8	-	-	0.22	175	2.0	3.7	-	1	250	20	-	-	0.005
MDC-6 218.2	-	-	-	Granite	9.7	-	-	5	-	2.1	-	-	0.21	195	3.0	3.5	-	1	270	24	-	-	0.005
MDC-4 23.6	-	-	-	Granite	8.7	-	-	5	-	3.5	-	-	0.37	150	1.0	2.4	-	5	780	34	-	-	0.005
MDC-4 56	-	-	-	Granite	9.5	-	-	5	-	3.5	-	-	0.48	170	3.0	2.9	-	6	1,080	42	-	-	0.01
MDC-6 161.4	-	-	-	Granite	9.5	-	-	5	-	3.4	-	-	0.27	180	6.0	2.3	-	8	610	22	-	-	0.03
MDC-8 82	-	-	-	Granite	9.7	-	-	5	-	3.8	-	-	0.38	180	1.0	2.1	-	4	880	26	-	-	0.005
MDC-4 41.14	-	-	-	Granite	8.9	-	-	10	-	4.4	-	-	0.31	115	2.0	2.2	-	5	890	34	-	-	0.005
MDC-4 45.8	-	-	-	Granite	9.4	-	-	5	-	4.7	-	-	0.78	240	3.0	2.2	-	13	1,930	26	-	-	0.03
MDC-6 54.5	-	-	-	Granite	9.4	-	-	5	-	2.2	-	-	1.4	450	3.0	2.2	-	45	690	22	-	-	0.13
MDC-8 106.45	-	-	-	Granite	9.5	-	-	5	-	3.4	-	-	1.1	315	2.0	2.0	-	43	500	24	-	-	0.08
MPG 450- A	-	-	-	Granite	9.5	-	-	5	-	1.9	-	-	0.26	140	0.5	3.8	-	5	240	22	-	-	-
MPG 450- AA	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPG 450-AAA	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-26 2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-27 1A	-	-	-	Granite	9.3	-	-	5	-	2.0	-	-	0.22	140	0.5	3.8	-	3	190	24	-	-	-
MG 450-27 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-31 1A	-	-	-	Granite	8.1	-	-	5	-	1.8	-	-	0.66	285	0.5	3.3	-	20	440	10	-	-	-
MG 450-34 1A	-	-	-	Granite	9.2	-	-	5	-	1.8	-	-	0.23	160	0.5	4.0	-	3	280	18	-	-	-
MG 450-39-1A	-	-	-	Granite	8.6	-	-	5	-	2.2	-	-	0.29	160	0.5	3.8	-	5	270	16	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Misery (continued)																							
MG 450-39-1AA	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-39-1AAA	-	-	-	Granite	8.3	-	-	5	-	1.1	-	-	2.5	1,325	0.5	2.5	-	57	790	1	-	-	-
MG 450-39-2A	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-39-2AA	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-39-2AAA	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-41-1A	-	-	-	Granite	8.9	-	-	5	-	1.9	-	-	0.25	165	0.5	4.2	-	4	250	12	-	-	-
MG 450-41-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-45-1A	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-45-2A	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-46-1A	-	-	-	Granite	7.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-46-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-48-1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-48-2A	-	-	-	Granite	8.9	-	-	5	-	1.8	-	-	0.26	160	0.5	4.3	-	3	310	20	-	-	-
MG- 450-49-1A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-49-2A	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-50-1A	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-50-2A	-	-	-	Granite	7.2	-	-	5	-	2.6	-	-	0.32	145	0.5	4.3	-	8	210	16	-	-	-
MG-440-SE-01	-	-	-	Granite	9.9	-	-	0.005	-	2.1	10	-	0.29	166	0.5	4.0	-	6	360	17	-	-	0.005
MG-440-SE-02	-	-	-	Granite	9.6	-	-	0.005	-	1.9	10	-	0.22	148	0.5	3.9	-	2	300	16	-	-	0.005
MG-440-SE-03	-	-	-	Granite	9.7	-	-	0.005	-	2.0	10	-	0.22	160	0.5	3.9	-	2	380	17	-	-	0.005
MG 440-01 1A	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-37-1A	-	-	-	Granite	9.2	-	-	5	-	1.4	-	-	0.24	165	1.0	3.7	-	5	400	26	-	-	0.005
MG- 440-37-2A	-	-	-	Granite	7.7	-	-	5	-	1.5	-	-	0.79	260	2.0	2.6	-	36	500	14	-	-	0.05
MG 440-39-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440-39-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-40-1A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-40-2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-44-1A	-	-	-	Granite	8.7	-	-	5	-	2.5	-	-	0.35	210	0.5	4.3	-	4	550	18	-	-	-
MG- 440-44-1A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-44-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-44-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-46-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-46-2A	-	-	-	Granite	8.7	-	-	5	-	2.8	-	-	0.35	170	0.5	4.2	-	5	420	18	-	-	-
MG- 440-53-1A	-	-	-	Granite	7.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-53-2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-54-1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-54-2A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-55-1A	-	-	-	Granite	7.6	-	-	5	-	1.9	-	-	0.37	190	1.0	4.3	-	7	440	16	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																							
Misery (continued)																							
MG- 440-55-2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 57 1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 57 1B	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 59 1A	-	-	-	Granite	9.4	-	-	5	-	1.8	-	-	0.66	220	3.0	3.5	-	25	360	12	-	-	0.05
MG 440 59 2A	-	-	-	Granite	9.6	-	-	5	-	2.0	-	-	0.54	190	1.0	3.3	-	21	320	22	-	-	0.03
MG 440 60 1A	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 60 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 61 1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 61 2A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 62 1A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 62 2A	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 65 1A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 65 2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 66 1A	-	-	-	Granite	8.5	-	-	5	-	2.7	-	-	0.29	165	1.0	3.1	-	7	390	26	-	-	0.005
MG 440 66 2A	-	-	-	Granite	7.9	-	-	5	-	1.8	-	-	0.55	270	3.0	3.0	-	14	410	16	-	-	0.01
MG- 440-67-1A	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-67-2A	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-68-1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-68-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-440-70-1A	-	-	-	Granite	8.9	-	-	5	-	1.1	-	-	2.1	1,205	1.0	2.5	-	40	760	10	-	-	0.07
MG-440-70-2A	-	-	-	Granite	8.4	-	-	5	-	1.7	-	-	2.1	835	2.0	2.1	-	68	680	10	-	-	0.10
MG-430-W-01	-	-	-	Granite	9.7	-	-	0.005	-	2.1	10	-	0.23	173	0.5	3.8	-	2	480	17	-	-	0.005
MG-430-W-02	-	-	-	Granite	9.9	-	-	0.05	-	1.9	10	-	0.27	160	0.5	3.8	-	6	360	17	-	-	0.005
MG-430-W-03	-	-	-	Granite	9.6	-	-	0.005	-	2.1	10	-	0.22	145	0.5	3.7	-	1	260	14	-	-	0.005
MG- 430-11-1A	-	-	-	Granite	8.7	-	-	5	-	2.6	-	-	1.8	405	0.5	2.2	-	73	480	12	-	-	-
MG- 430-13-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-13-2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-13-3A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 18 1A	-	-	-	Granite	9.3	-	-	5	-	2.0	-	-	0.27	260	3.0	3.5	-	8	270	20	-	-	0.01
MG 430 18 2A	-	-	-	Granite	9.6	-	-	5	-	2.3	-	-	0.20	130	1.0	3.5	-	4	380	14	-	-	0.005
MG 430 19 1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 19 2A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 20 1A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 20 2A	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 27 2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 28 1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 28 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 29 1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																							
Misery (continued)																							
MG 430 29 2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 30 1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 30 2A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 31 1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 31 2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-33-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-34-1A	-	-	-	Granite	9.1	-	-	5	-	1.4	-	-	0.23	140	0.5	3.8	-	4	380	20	-	-	0.005
MG- 430-35-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-35-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-36-1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-36-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-41-1B	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-41-2B	-	-	-	Granite	6.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 47 1A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 47 1B	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 27 1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG/S-430-44-2A	-	-	-	Granite	9.1	-	-	5	-	2.0	-	-	0.25	155	1.0	3.6	-	6	300	18	-	-	0.005
MG-430-42-1A	-	-	-	Granite	8.6	-	-	5	-	2.0	-	-	0.61	230	1.0	3.1	-	25	580	14	-	-	0.03
MG-430-42-2A	-	-	-	Granite	7.8	-	-	5	-	2.3	-	-	0.39	180	4.0	3.2	-	14	430	24	-	-	0.005
MG-430-58 1A	-	-	-	Granite	9.0	-	-	5	-	2.1	-	-	0.35	215	0.5	2.8	-	14	310	20	-	-	0.01
MG-430-58 2A	-	-	-	Granite	8.9	-	-	5	-	1.8	-	-	1.2	685	0.5	2.7	-	32	520	8	-	-	0.04
MG-420-SW-01	-	-	-	Granite	9.8	-	-	0.005	-	1.9	10	-	0.22	139	0.5	3.9	-	3	260	16	-	-	0.005
MG-420-SW-02	-	-	-	Granite	10.0	-	-	0.005	-	1.8	10	-	0.27	147	0.5	3.9	-	5	250	12	-	-	0.005
MG-420-SW-03	-	-	-	Granite	9.9	-	-	0.05	-	1.9	10	-	0.21	146	0.5	3.8	-	2	270	16	-	-	0.005
MG- 420-07-1A	-	-	-	Granite	9.0	-	-	5	-	1.7	-	-	0.29	180	0.5	4.2	-	11	300	20	-	-	0.005
MG- 420-07-2A	-	-	-	Granite	9.0	-	-	5	-	1.6	-	-	0.23	175	1.0	4.3	-	3	300	20	-	-	0.005
MG- 420-10-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-10-2A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-13-1A	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-13-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-14-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-14-2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-15-1B	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-15-2B	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 420 20 1A	-	-	-	Granite	8.4	-	-	10	-	2.4	-	-	0.40	180	0.5	2.7	-	9	490	12	-	-	0.005
MG 420 20 1B	-	-	-	Granite	8.4	-	-	20	-	2.3	-	-	0.38	180	1.0	2.8	-	8	400	16	-	-	0.005
MG/S-420-30-1A	-	-	-	Granite	9.3	-	-	5	-	2.8	-	-	0.20	160	4.0	2.9	-	2	1,600	22	-	-	0.005
MG/S-420-30-2A	-	-	-	Granite	9.4	-	-	5	-	1.8	-	-	0.21	155	3.0	3.7	-	4	390	18	-	-	0.005

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																							
Misery (continued)																							
MG-420-18-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-18-2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-24-1A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-24-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-25/26-1A	-	-	-	Granite	9.2	-	-	5	-	2.4	-	-	1.0	315	2.0	2.4	-	48	660	18	-	-	0.14
MG-420-25/26-2A	-	-	-	Granite	8.9	-	-	5	-	2.4	-	-	1.3	320	7.0	1.6	-	58	510	16	-	-	0.10
MG-420-26-1A	-	-	-	Granite	9.1	-	-	5	-	2.1	-	-	0.68	210	0.5	2.9	-	30	580	20	-	-	0.01
MG-420-26-2A	-	-	-	Granite	9.2	-	-	5	-	3.3	-	-	2.1	1,315	0.5	5.5	-	39	1,330	18	-	-	0.06
MG-420-27-1A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-27-2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-28-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-28-2A	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-30-1A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-30-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-31-1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-31-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-36-1A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-36-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-02-01	-	-	-	Granite	9.6	-	-	0.005	-	3.2	33	-	0.27	176	0.5	3.0	-	4	590	25	-	-	0.005
MG-410-03-01	-	-	-	Granite	9.5	-	-	0.005	-	1.8	19	-	0.34	162	0.9	3.6	-	9	430	19	-	-	0.01
MG-410-07-01	-	-	-	Granite	8.8	-	-	0.005	-	1.8	9.7	-	0.31	165	0.5	4.1	-	2	350	16	-	-	0.02
MG 410 04 1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 04 1B	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 05 1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 05 2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 06 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 06 1B	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 07 1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 07 1B	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 09 1A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 09 1B	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 10 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 10 1B	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-12-1A	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-12-2A	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-16-1A	-	-	-	Granite	9.1	-	-	5	-	1.8	-	-	0.19	125	2.0	3.2	-	4	290	16	-	-	0.005
MG-410-16-2A	-	-	-	Granite	8.7	-	-	5	-	2.4	-	-	0.28	150	3.0	3.1	-	4	670	26	-	-	0.005
MG-410-17-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Misery (continued)																							
MG-410-17-2A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-19-1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-19-2A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-20 1A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-20 2A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-24 1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-24 2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-26 1A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-26 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-28 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-28 2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-31 1A	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-31 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-32 1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-32 2A	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-36 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-36 2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-38 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-38 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-40 1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-40 2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG/D-410-41 -1A	-	-	-	Granite	9.1	-	-	5	-	2.9	-	-	0.54	185	0.5	2.4	-	6	510	20	-	-	0.03
MG/D-410-41 -2A	-	-	-	Granite	9.4	-	-	5	-	2.0	-	-	0.41	185	0.5	3.0	-	11	400	18	-	-	0.01
MG 400-34 1a	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 400-34 2a	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 400-41 1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-01-1A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-01-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-02 1A	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-02 2A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-03 1A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-03 2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-05 1A	-	-	-	Granite	9.3	-	-	5	-	2.3	-	-	0.34	145	1.0	2.8	-	14	240	24	-	-	0.005
MG-400-05 2A	-	-	-	Granite	8.9	-	-	5	-	2.1	-	-	0.61	175	0.5	2.9	-	39	690	18	-	-	0.01
MG-400-07 1A	-	-	-	Granite	9.5	-	-	5	-	1.7	-	-	0.30	175	4.0	3.1	-	10	370	18	-	-	0.005
MG-400-07 2A	-	-	-	Granite	9.6	-	-	5	-	2.1	-	-	0.22	145	0.5	3.1	-	7	370	22	-	-	0.005
MG-400-08-1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-08-2A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Misery (continued)																							
MG-400-09-1A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-09-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-11-1A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-11-2A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-15-1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-15-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-21-1A	-	-	-	Granite	9.4	-	-	5	-	2.6	-	-	0.23	155	7.0	3.6	-	9	620	26	-	-	0.005
MG-400-21-2A	-	-	-	Granite	9.3	-	-	5	-	2.3	-	-	0.38	200	6.0	3.2	-	16	570	26	-	-	0.01
MG-400-24-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-24-2A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-25-1A	-	-	-	Granite	8.8	-	-	5	-	2.0	-	-	1.6	360	4.0	2.3	-	77	550	16	-	-	0.23
MG-400-25-2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-31-1A	-	-	-	Granite	8.9	-	-	5	-	2.2	-	-	1.6	475	3.0	2.5	-	79	610	16	-	-	0.24
MG-400-31-2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-32-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-32-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-36-1A	-	-	-	Granite	8.9	-	-	5	-	2.0	-	-	0.20	280	0.5	3.7	-	6	320	18	-	-	0.005
MG-400-36-2A	-	-	-	Granite	9.2	-	-	5	-	2.0	-	-	0.21	170	4.0	3.8	-	4	360	20	-	-	0.005
MG-400-37-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-37-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-05 1a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-05 2a	-	-	-	Granite	9.9	-	-	5	-	2.0	-	-	0.25	165	3.0	3.9	-	8	550	24	-	-	0.005
MG 390-06 1a	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-06 2a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-09 1a	-	-	-	Granite	9.7	-	-	5	-	3.7	-	-	0.24	155	1.0	2.8	-	7	1,000	26	-	-	0.005
MG 390-09 1a	-	-	-	Granite	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-09 2a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-09 2a	-	-	-	Granite	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-10 1a	-	-	-	Granite	9.5	-	-	5	-	2.0	-	-	0.21	135	1.0	3.7	-	13	270	20	-	-	0.005
MG 390-10 2a	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-11G 1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-11G 2a	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-13 1a	-	-	-	Granite	9.6	-	-	5	-	2.3	-	-	0.28	180	2.0	3.6	-	9	500	24	-	-	0.005
MG 390-13 2a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-14T 1a	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-14T 2a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-02-1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-02-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Misery (continued)																							
MG-390-03-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-03-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-04-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-04-2A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-17-1a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-17-1a	-	-	-	Granite	8.8	-	-	5	-	2.7	-	-	0.35	145	2.0	3.9	-	9	370	12	-	-	0.005
MG-390-17-2a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-17-2a	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-20-1a	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-20-2a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-21-1a	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-21-2a	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-22-1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-22-1a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-22-2a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-22-2a	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-23T-1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-23T-2a	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 380-10 1a	-	-	-	Granite	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 380-10 2a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 380-14 1a	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 380-14 2a	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-16-1a	-	-	-	Granite	9.8	-	-	5	-	2.3	-	-	0.20	130	0.5	2.8	-	7	360	22	-	-	0.005
MG-380-16-2a	-	-	-	Granite	9.9	-	-	5	-	2.2	-	-	0.17	220	0.5	2.9	-	6	360	18	-	-	0.005
MG-380-18-1a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-18-2a	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-19-1a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-19-2a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-23-1A	-	-	-	Granite	8.7	-	-	5	-	2.5	-	-	0.25	130	0.5	3.5	-	4	320	18	-	-	0.005
MG-380-23-2A	-	-	-	Granite	9.1	-	-	5	-	2.0	-	-	0.24	140	0.5	3.6	-	3	400	22	-	-	0.005
MG-380-26-1A	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-26-2A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-27-1A	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-27-2A	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-29T-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-29T-2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-31T-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-31T-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Granite (continued)																							
Misery (continued)																							
MG-370-06-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-370-06-2	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-370-24-B	-	-	-	Granite	6.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-360-28-1	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-360-28-2	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-360-31-1	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-360-31-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MGS-360-18-01	-	-	-	Granite	9.2	-	-	0.005	-	2.2	-	-	1.5	398	2.0	2.3	-	72	560	12	-	-	0.17
MGS-360-18-02	-	-	-	Granite	9.3	-	-	0.005	-	2.0	-	-	1.4	365	5.0	2.1	-	63	460	11	-	-	0.14
MG-350-35-1	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-350-35-2	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-340-23-02 10-DEC-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-340-23-01 10-DEC-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-330-19-02 27-DEC-04	-	-	-	Granite	7.8	-	-	0.005	-	2.5	-	-	0.31	154	1.0	3.4	-	10	440	19	-	-	0.01
MG-330-19-01 27-DEC-04	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-330-18-02 26-DEC-04	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-330-18-01 26-DEC-04	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-31-02 15-JAN-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-31-01 15-JAN-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-30-02 11-JAN-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-30-01 11-JAN-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-29-02 5-FEB-05	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-29-01 5-FEB-05	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-25-04 1-JAN-05	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-25-03 1-JAN-05	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-25-02 1-JAN-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-25-01 1-JAN-05	-	-	-	Granite	8.6	-	-	0.005	-	2.0	-	-	5.2	371	1.0	2.7	-	397	630	13	-	-	0.03
MG-320-20-02 18-DEC-04	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-20-01 18-DEC-04	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-310-10-02 20-FEB-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-310-10-01 20-FEB-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-310-09-02 20-FEB-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-310-09-01 20-FEB-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-310-07-02 15-FEB-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-310-07-01 15-FEB-05	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-300-13-06 25-Mar-05	-	-	-	Granite	9.0	-	-	0.01	-	1.8	-	-	1.5	204	0.5	3.4	-	86	360	14	-	-	0.06
MG-300-13-05 25-Mar-05	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-300-13-04 25-Mar-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																							
Misery (continued)																							
MG-300-13-03 25-Mar-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-300-13-02 25-Mar-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-300-13-01 25-Mar-05	-	-	-	Granite	8.6	-	-	0.01	-	1.9	-	-	1.7	211	0.5	3.1	-	124	410	14	-	-	0.13
MG-290-10-04 31-Mar-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-290-10-03 31-Mar-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-290-10-02 31-Mar-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-290-10-01 31-Mar-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MGT-39 100-103	-	-	-	Granite	9.8	-	-	0.005	-	0.29	5.0	-	0.22	137	0.2	0.060	-	4	150	2	-	-	0.025
MGT-39 200-203	-	-	-	Granite	9.6	-	-	0.005	-	0.19	14	-	0.34	147	0.3	0.048	-	12	360	7	-	-	0.025
MGT-49 58.28-60.08	-	-	-	Granite	9.4	-	-	0.005	-	0.28	4.0	-	0.33	112	0.4	0.048	-	12	450	4	-	-	0.05
MGT-49 65.82-67.00	-	-	-	Granite	9.7	-	-	0.005	-	0.17	5.0	-	0.14	100	0.7	0.035	-	4	730	3	-	-	0.025
MGT-69 7.3-9.5	-	-	-	Granite	9.3	-	-	0.005	-	0.16	11	-	0.21	132	0.2	0.045	-	6	210	4	-	-	0.025
MGT-69 166-169	-	-	-	Granite	9.3	-	-	0.005	-	0.10	23	-	0.38	163	0.3	0.039	-	12	370	4	-	-	0.025
MGT-44 213-216	-	-	-	Granite	9.5	-	-	0.005	-	0.68	24	-	0.58	244	1.3	0.030	-	20	700	8	-	-	0.07
MGT-60 35-38	-	-	-	Granite	9.6	-	-	0.005	-	0.37	17	-	0.23	148	0.6	0.031	-	3	800	5	-	-	0.025
MGT-63 220-223	-	-	-	Granite	9.2	-	-	0.005	-	0.15	13	-	0.43	188	1.0	0.037	-	10	1,150	4	-	-	0.11
MGT-66 55-58	-	-	-	Granite	9.8	-	-	0.005	-	0.29	34	-	0.36	224	1.1	0.036	-	7	660	10	-	-	0.025
MGT-66 76-79	-	-	-	Granite	9.8	-	-	0.005	-	0.46	29	-	0.34	161	0.9	0.031	-	6	510	10	-	-	0.025
MGT-70 15-18	-	-	-	Granite	9.6	-	-	0.005	-	0.23	5.0	-	0.24	142	0.2	0.052	-	3	130	3	-	-	0.025
MGT-70 33-36	-	-	-	Granite	9.7	-	-	0.005	-	0.21	4.0	-	0.21	144	0.2	0.049	-	4	270	3	-	-	0.025
MGT-70 51-54	-	-	-	Granite	9.7	-	-	0.005	-	0.26	8.0	-	0.23	159	0.2	0.051	-	4	160	4	-	-	0.025
MGT-70 69-72	-	-	-	Granite	9.8	-	-	0.005	-	0.25	6.0	-	0.23	149	0.2	0.050	-	6	180	3	-	-	0.025
MGT-51 174-177	-	-	-	Granite	9.6	-	-	0.005	-	0.37	26	-	0.26	141	1.3	0.036	-	5	580	11	-	-	0.025
MGT-52 50-53	-	-	-	Granite	9.3	-	-	0.005	-	0.33	8.0	-	0.21	172	0.2	0.055	-	5	1,040	3	-	-	0.025
MGT-52 57-60	-	-	-	Granite	9.3	-	-	0.005	-	0.36	9.0	-	0.23	184	0.2	0.053	-	5	1,070	3	-	-	0.025
MGT-52 150-153	-	-	-	Granite	9.6	-	-	0.005	-	0.34	7.0	-	0.22	152	0.3	0.060	-	4	300	4	-	-	0.025
MGT-52 157-160	-	-	-	Granite	9.5	-	-	0.005	-	0.34	9.0	-	0.25	156	0.3	0.063	-	5	260	5	-	-	0.025
MGT-52 250-253	-	-	-	Granite	9.4	-	-	0.005	-	0.28	9.0	-	0.25	154	0.2	0.054	-	4	570	3	-	-	0.025
MGT-52 257-260	-	-	-	Granite	9.4	-	-	0.005	-	0.29	9.0	-	0.25	144	0.3	0.056	-	4	160	3	-	-	0.025
MGT-54 240-243	-	-	-	Granite	9.3	-	-	0.005	-	0.22	6.0	-	0.23	155	0.2	0.063	-	4	340	5	-	-	0.025
MGT-54 247-250	-	-	-	Granite	9.4	-	-	0.005	-	0.27	6.0	-	0.23	164	0.1	0.063	-	3	210	3	-	-	0.025
MDC-4 64.69	-	-	-	Granite	9.4	-	-	5	-	2.9	-	-	0.93	260	3.0	2.5	-	37	810	24	-	-	0.09
MS G 420 19 1A	-	-	-	Granite	9.0	-	-	5	-	2.2	-	-	0.19	125	0.5	3.0	-	6	300	20	-	-	0.005
MS G 420 19 1B	-	-	-	Granite	8.8	-	-	5	-	2.1	-	-	0.18	120	0.5	3.0	-	5	370	22	-	-	0.005
MS G 410 03 1A	-	-	-	Granite	9.0	-	-	10	-	2.3	-	-	1.4	395	3.0	2.0	-	67	650	10	-	-	0.10
MS G 410 03 1B	-	-	-	Granite	8.9	-	-	10	-	2.3	-	-	1.5	450	1.0	1.9	-	68	460	10	-	-	0.11
MS/G-410-27 1A	-	-	-	Granite	8.9	-	-	5	-	2.3	-	-	1.7	330	0.5	1.6	-	82	510	12	-	-	0.12
MS/G-410-27 2A	-	-	-	Granite	8.8	-	-	5	-	2.4	-	-	1.7	385	0.5	1.5	-	88	490	6	-	-	0.13

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	Ge	Hf	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
					unit	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																							
Misery (continued)																							
MS 400-38 1a	-	-	-	Granite	9.5	-	-	5	-	2.9	-	-	2.2	675	2.0	1.5	-	71	820	22	-	-	0.17
MS 400-38 2a	-	-	-	Granite	9.6	-	-	5	-	2.9	-	-	1.5	390	1.0	1.7	-	57	770	16	-	-	0.10
MGT-49 171.23-173.14	-	-	-	Granite	9.4	-	-	0.005	-	0.14	2.0	-	0.07	37	0.2	0.030	-	9	360	4	-	-	0.08
MGT-51 184-187	-	-	-	Granite	9.6	-	-	0.005	-	0.24	10	-	0.18	96	0.4	0.038	-	4	360	7	-	-	0.025
MGT-52 125.26-126.8	-	-	-	Granite	9.4	-	-	0.005	-	0.21	4.0	-	0.13	91	0.2	0.034	-	4	570	4	-	-	0.025
MGT-52 137.8-139.3	-	-	-	Granite	9.6	-	-	0.005	-	0.15	2.0	-	0.03	63	0.2	0.034	-	4	230	2	-	-	0.025
MGT-56 38-41	-	-	-	Granite	8.9	-	-	0.005	-	0.24	19	-	0.84	256	0.5	0.017	-	33	830	2	-	-	0.025
		Median			9.1	-	-	5	-	2.0	10	-	0.29	165.5	0.5	2.9	-	7	410	16	-	-	0.02
		Minimum			6.5	-	-	0.005	-	0.10	2.0	-	0.03	37	0.1	0.017	-	1	130	1	-	-	0.005
		Maximum			10.1	-	-	20	-	4.7	34	-	5.2	1,325	7.0	5.5	-	397	1,930	42	-	-	0.24
		Count			370	0	0	130	0	130	41	0	130	130	130	130	0	130	130	130	0	0	117
Panda																							
PG-210-12-1	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PG-210-12-2	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PG-210-08-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PG-210-08-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-210-06-1	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-210-06-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-195-10-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-195-10-2	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Panda-UG-Granite	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
		Median			9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
		Minimum			9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
		Maximum			9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
		Count			9	0	0	0	0	0	0	0	0	0	0	0	0	-	-	0	0	0	0
Pigeon																							
97-54	97-54	188.69	189.09	Granite	9.7	-	-	-	-	1.0	-	-	0.97	225	4.0	0.06	-	19	1,110	8	-	-	-
97-54	97-54	373.1	373.38	Granite	9.7	-	-	-	-	1.6	-	-	1.4	270	2.0	0.11	-	34	550	6	-	-	-
97-55	97-55	295.01	295.75	Granite	9.8	-	-	-	-	0.93	-	-	0.75	205	6.0	0.06	-	16	440	6	-	-	-
97-55	97-55	56	56.59	Granite	9.5	-	-	-	-	1.8	-	-	1.8	300	4.0	0.05	-	56	650	8	-	-	-
HC-Pdef-6	-	-	-	Granite	9.6	0.18	3.6	-	0.021	1.8	42	49	1.0	255	5.3	2.5	4.4	36	350	20	66.3	0.001	0.01
HC-Pdef-7	-	-	-	Granite	9.0	0.22	4.3	-	0.038	2.8	28	86	1.9	418	1.8	2.1	9.6	92	600	19	92.7	0.001	0.005
HC-Pdef-12	-	-	-	Granite	9.0	0.15	2.2	-	0.020	2.2	23	34	1.0	219	1.5	1.8	4.3	44	480	12	71.4	0.001	0.02
HC-PDef-17	-	-	-	Granite	9.5	0.23	3.5	-	0.039	2.3	23	83	1.5	340	2.7	1.6	7.0	74	350	19	92.7	0.001	0.02
HC-PDef-24	-	-	-	Granite	9.2	0.19	2.7	-	0.064	2.5	19	70	1.5	324	2.3	1.6	5.2	58	270	16	67.8	0.001	0.06
HC-PDef-25	-	-	-	Granite	9.3	0.31	3.4	-	0.026	2.0	25	88	1.6	371	3.8	2.4	7.8	74	760	16	63.4	0.002	0.02
HC-PDef-27	-	-	-	Granite	9.9	0.30	2.9	-	0.033	2.5	25	88	1.3	319	1.9	2.3	8.0	47	760	23	104	0.001	0.005
HC-PDef-29	-	-	-	Granite	10.0	0.22	4.9	-	0.048	3.9	32	118	2.2	585	5.8	1.9	14	87	300	20	103.5	0.002	0.01

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																							
Pigeon (continued)																							
HC-PDef-30	-	-	-	Granite	9.7	0.20	3.7	-	0.030	2.0	34	61	1.5	373	4.2	2.4	8.7	55	570	18	87.9	0.001	0.02
HC-PDef-33	-	-	-	Granite	9.3	0.19	2.6	-	0.029	2.1	23	61	1.4	315	3.4	1.5	6.5	61	200	12	94	0.001	0.02
HC-PDef-34	-	-	-	Granite	9.0	0.17	1.7	-	0.022	1.4	15	32	0.78	174	1.3	1.7	2.8	34	720	17	46.3	0.001	0.10
Median					9.5	0.20	3.4	-	0.030	2.0	25	70	1.4	315	3.4	1.7	7.0	55	550	16	87.9	0.001	0.02
Minimum					9.0	0.15	1.7	-	0.020	0.93	15	32	0.75	174	1.3	0.05	2.8	16	200	6	46.3	0.001	0.005
Maximum					10.0	0.31	4.9	-	0.064	3.9	42	118	2.2	585	6.0	2.5	14	92	1,110	23	104	0.002	0.10
Count					15	11	11	0	11	15	11	11	15	15	15	11	15	15	15	15	11	11	11
Sable																							
SDC-07	SDC-07	152.3	152.73	Granite	7.5	-	-	-	-	1.3	-	-	0.96	335	2	0.07	-	15	1,800	10	-	-	-
SDC-02	SDC-02	48.58	49.28	Granite	9.1	-	-	-	-	0.05	-	-	0.07	45	8	0.01	-	5	20	2	-	-	-
SDC-05	SDC-05	152	152.5	Granite	9.8	-	-	-	-	0.25	-	-	0.16	85	2	0.05	-	5	460	10	-	-	-
SDC-07	SDC-07	150.37	150.6	Granite	9.7	-	-	-	-	0.31	-	-	0.03	25	4	0.05	-	5	300	4	-	-	-
SDC-07	SDC-07	91.35	91.8	Granite	9.7	-	-	-	-	0.31	-	-	0.22	150	2	0.05	-	3	1,380	4	-	-	-
SDC-04	SDC-04	47.5	47.5	Granite	9.6	-	-	-	-	0.16	-	-	0.07	50	4	0.05	-	3	140	4	-	-	-
SDC-12	SDC-12	11.28	11.68	Granite	9.3	-	-	-	-	0.16	-	-	0.05	35	4	0.04	-	4	220	4	-	-	-
SDC-07	SDC-07	113	113.3	Granite	9.6	-	-	-	-	0.19	-	-	0.10	75	4	0.04	-	4	200	10	-	-	-
SDC-04	SDC-04	47	47.3	Granite	9.7	-	-	-	-	0.28	-	-	0.27	150	4	0.07	-	5	140	6	-	-	-
SDC-02	SDC-02	56	56.3	Granite	9.5	-	-	-	-	0.16	-	-	0.10	55	4	0.04	-	2	170	1	-	-	-
SDC-11	SDC-11	52	52	Granite	9.7	-	-	-	-	0.13	-	-	0.13	65	4	0.05	-	5	710	2	-	-	-
SDC-12	SDC-12	88.89	89.259	Granite	9.7	-	-	-	-	0.26	-	-	0.28	145	4	0.07	-	5	200	8	-	-	-
SDC-13	SDC-13	37.52	37.79	Granite	9.7	-	-	-	-	0.34	-	-	0.22	120	4	0.05	-	4	260	6	-	-	-
SDC-12	SDC-12	186.64	187.04	Granite	9.4	-	-	-	-	0.14	-	-	0.19	90	2	0.05	-	3	760	6	-	-	-
SDC-02	SDC-02	20.5	20.5	Granite	9.2	-	-	-	-	0.21	-	-	0.14	110	4	0.05	-	6	810	8	-	-	-
SDC-03	SDC-03	26	26.3	Granite	9.7	-	-	-	-	0.34	-	-	0.27	115	4	0.06	-	4	730	6	-	-	-
SDC-13	SDC-13	154.64	154.89	Granite	9.2	-	-	-	-	0.22	-	-	0.15	90	4	0.04	-	4	480	2	-	-	-
SDC-12	SDC-12	303.89	304.39	Granite	9.8	-	-	-	-	0.25	-	-	0.15	110	4	0.05	-	4	1,350	4	-	-	-
SDC-08	SDC-08	54.1	54.43	Granite	9.4	-	-	-	-	0.19	-	-	1.0	220	2	0.06	-	9	930	4	-	-	-
SDC-13	SDC-13	106.58	1069.89	Granite	10.0	-	-	-	-	1.8	-	-	1.5	435	14	0.06	-	70	410	4	-	-	-
SDC-05	SDC-05	233.9	234.17	Granite	9.5	-	-	-	-	0.60	-	-	0.47	245	2	0.08	-	9	1,020	10	-	-	-
SDC-05	SDC-05	224	224.23	Granite	9.8	-	-	-	-	0.48	-	-	0.36	170	4	0.07	-	8	500	6	-	-	-
SDC-07	SDC-07	114.32	144.68	Granite	9.2	-	-	-	-	1.1	-	-	0.84	320	2	0.06	-	16	1,810	16	-	-	-
SDC-12	SDC-12	386.18	386.58	Granite	9.6	-	-	-	-	1.1	-	-	2.9	485	2	0.06	-	28	1,270	4	-	-	-
SDC-07	SDC-07	157.03	157.42	Granite	9.8	-	-	-	-	1.2	-	-	0.89	430	2	0.06	-	9	1,960	8	-	-	-
SDC-06	SDC-06	117.93	118.36	Granite	9.8	-	-	-	-	1.2	-	-	1.0	305	4	0.10	-	13	1,220	6	-	-	-
SDC-04	SDC-04	77	77.42	Granite	9.4	-	-	-	-	0.16	-	-	0.03	20	2	0.03	-	3	230	6	-	-	-
SDC-13	SDC-13	30.14	30.45	Granite	9.4	-	-	-	-	1.6	-	-	1.5	340	2	0.09	-	30	1,190	4	-	-	-
SDC-13	SDC-13	96.97	97.23	Granite	9.5	-	-	-	-	1.6	-	-	1.7	415	4	0.09	-	33	1,300	4	-	-	-
SDC-05	SDC-05	98.73	98.88	Granite	9.5	-	-	-	-	0.20	-	-	0.11	100	4	0.05	-	4	340	6	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																							
Sable (continued)																							
SDC-11	SDC-11	36.95	37.27	Granite	9.9	-	-	-	-	0.20	-	-	0.13	75	4	0.05	-	5	620	6	-	-	-
SDC-05	SDC-05	17	17.31	Granite	9.8	-	-	-	-	0.48	-	-	0.30	170	4	0.06	-	5	980	6	-	-	-
SDC-13	SDC-13	199.96	200.25	Granite	9.8	-	-	-	-	0.81	-	-	0.60	290	4	0.08	-	8	920	8	-	-	-
SDC-08	SDC-08	88.38	89	Granite	9.2	-	-	-	-	0.08	-	-	2.9	240	2	0.08	-	16	1,540	2	-	-	-
SDC-04	SDC-04	83	83.35	Granite	10.1	-	-	-	-	3.8	-	-	2.9	820	1	0.07	-	113	300	6	-	-	-
SDC-08	SDC-08	90.78	91.39	Granite	9.2	-	-	-	-	0.06	-	-	5.9	350	10	0.06	-	43	790	4	-	-	-
SDC-07	SDC-07	114.7	115.6	Granite	9.5	-	-	-	-	1.2	-	-	0.92	305	2	0.07	-	15	1,780	10	-	-	-
SDC-01	SDC-01	68.5	68.9	Granite	9.0	-	-	-	-	0.71	-	-	0.47	180	4	0.11	-	14	560	6	-	-	-
SDC-06	SDC-06	36.7	37.32	Granite	9.5	-	-	-	-	0.15	-	-	0.06	40	4	0.05	-	3	260	4	-	-	-
SCD-05	SCD-05	151.23	151.75	Granite	10.0	-	-	-	-	2.6	-	-	1.9	565	2	0.08	-	88	410	14	-	-	-
SDC-11	SDC-11	55.6	56	Granite	9.6	-	-	-	-	0.21	-	-	0.03	35	4	0.03	-	3	1,410	2	-	-	-
		Median			9.6	-	-	-	-	0.28	-	-	0.27	150	4	0.06	-	5	710	6	-	-	-
		Minimum			7.5	-	-	-	-	0.05	-	-	0.03	20	1	0.01	-	2	20	1	-	-	-
		Maximum			10.1	-	-	-	-	3.8	-	-	5.9	820	14	0.11	-	113	1,960	16	-	-	-
		Count			41	0	0	0	0	41	0	0	41	41	41	41	0	41	41	41	0	0	0
Jay																							
2014-DD-003	JGT-04	53	57.25	Granite	8.59	0.05	0.06	0.005	0.01	0.17	1.2	12	0.14	35	5.26	0.03	0.15	7	490	0.9	8.5	-	0.005
2014-DD-004	JGT-04	61	71	Granite	8.08	0.05	0.52	0.005	0.05	1.86	24.4	127	2.14	329	3.71	0.05	0.39	90	440	8.7	76.1	-	0.1
2014-DD-021	JGT-04	275	285	Granite	9.45	0.05	0.44	0.005	0.01	0.31	13.1	34	0.15	120	5.05	0.05	1.39	4	760	7.8	39.9	-	0.005
2014-DD-023	JGT-05	16.44	20.77	Granite	8.49	0.05	0.16	0.005	0.01	0.18	4.5	12	0.22	81	5.01	0.04	0.06	13	270	3.3	10.6	-	0.005
2014-DD-024	JGT-05	35.74	44.77	Granite	9.21	0.05	0.35	0.005	0.01	0.37	13.2	34	0.33	125	5.07	0.05	0.65	13	720	5.1	36.4	-	0.005
2014-DD-025	JGT-05	71.79	79.86	Granite	9.32	0.05	0.32	0.005	0.01	0.28	10.7	25	0.17	95	5.1	0.05	0.92	5	580	6.2	24.7	-	0.005
2014-DD-026	JGT-05	101.77	110.98	Granite	9.30	0.05	0.35	0.005	0.01	0.24	10.8	17	0.15	99	5.21	0.04	0.73	6	820	7.3	22.6	-	0.005
2014-DD-027	JGT-05	131	139.1	Granite	9.47	0.05	0.39	0.005	0.01	0.3	15.6	23	0.19	97	6.08	0.06	0.7	6	640	5.7	22.9	-	0.005
2014-DD-028	JGT-05	161.34	172.88	Granite	9.49	0.05	0.4	0.005	0.01	0.39	15.4	25	0.21	102	5.92	0.06	1	6	870	5.5	30.4	-	0.005
2014-DD-029	JGT-05	198.88	206.77	Granite	9.46	0.05	0.26	0.005	0.01	0.26	10.2	20	0.16	61	6.24	0.04	0.64	6	210	4.4	20.8	-	0.005
2014-DD-030	JGT-05	233.04	241.73	Granite	9.54	0.05	0.31	0.005	0.01	0.31	14.2	27	0.19	73	5.46	0.05	0.99	4	250	5.2	27.1	-	0.005
2014-DD-031	JGT-05	259.49	268.27	Granite	9.51	0.05	0.31	0.005	0.01	0.38	15.2	32	0.22	96	5.05	0.05	1.36	13	560	4.8	36.8	-	0.02
2014-DD-032	JGT-05	276.96	281.55	Granite	9.50	0.05	0.26	0.005	0.03	1.06	14.5	58	0.93	321	4.31	0.08	1.05	16	1,200	5.1	99.2	-	0.13
2014-DD-038	JGT-03	433.32	441.89	Granite	9.23	0.05	0.3	0.005	0.01	0.18	13	12	0.19	69	5.42	0.05	0.31	6	520	6.1	14.7	-	0.005
2014-DD-039	JGT-03	404.73	413.48	Granite	9.08	0.05	0.39	0.005	0.01	0.13	18.7	7	0.19	64	5.61	0.05	0.3	5	680	7.6	7.6	-	0.005
2014-DD-041	JGT-03	290.1	298.57	Granite	9.17	0.05	0.3	0.005	0.01	0.21	12.6	12	0.26	109	4.51	0.06	0.54	7	600	7	21.8	-	0.03
2014-DD-045	JGT-03	89.48	98.08	Granite	9.14	0.05	0.28	0.005	0.01	0.13	10.8	8	0.17	88	4.39	0.05	0.08	4	750	4.4	10.3	-	0.005
2014-DD-046	JGT-03	239.48	248.11	Granite	9.19	0.05	0.41	0.005	0.01	0.17	14.5	9	0.21	86	5.6	0.05	0.33	5	940	6.6	13	-	0.01
2014-DD-047	JGT-03	205.53	214.19	Granite	9.28	0.05	0.43	0.005	0.01	0.14	17.6	10	0.19	91	5.75	0.04	0.27	5	660	6.4	11	-	0.005
2014-DD-048	JGT-03	154.51	163.19	Granite	9.36	0.05	0.46	0.005	0.01	0.16	15.4	13	0.19	105	5.46	0.05	0.41	5	750	6.2	17.2	-	0.005
2014-DD-050	JGT-02	279	287	Granite	9.20	0.05	0.37	0.005	0.01	0.19	18.1	10	0.2	73	4.88	0.05	0.38	4	620	5.7	18	-	0.005
2014-DD-051	JGT-02	200	207.55	Granite	8.76	0.05	0.37	0.005	0.01	0.13	11.2	9	0.24	79	5.63	0.05	0.025	6	680	2.6	7.9	-	0.03

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035	
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S	
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Granite (continued)																								
Jay (continued)																								
2014-DD-052	JGT-02	125.42	134.04	Granite	8.54	0.05	0.61	0.005	0.01	0.4	21.2	22	0.28	111	5.55	0.04	0.96	27	630	6.2	46.6	-	0.005	
2014-DD-053	JGT-02	64.04	74	Granite	8.60	0.05	0.33	0.005	0.01	0.26	15.4	16	0.2	85	5.73	0.04	0.87	63	640	4.5	29.7	-	0.005	
2014-DD-055	JGT-02	60.16	65.55	Granite	8.44	0.05	0.26	0.005	0.01	0.25	14.7	14	0.19	76	5.7	0.04	0.8	67	380	5.9	32.4	-	0.005	
2014-DD-056	JGT-02	29.89	38.2	Granite	9.07	0.05	0.3	0.005	0.01	0.27	15	15	0.17	71	5.22	0.04	0.97	7	630	4.4	31.9	-	0.005	
2014-DD-057	JGT-02	451.14	459.98	Granite	9.50	0.05	0.45	0.005	0.02	0.46	21.9	28	0.23	113	5.84	0.05	1.81	6	730	6.8	52.1	-	0.005	
2014-DD-058	JGT-02	244.19	252.39	Granite	9.55	0.05	0.21	0.005	0.01	0.2	7.9	23	0.13	51	5.51	0.05	0.43	4	260	5.6	17.3	-	0.005	
2014-DD-059	JGT-02	377.69	383.33	Granite	9.50	0.05	0.25	0.005	0.01	0.25	11.9	28	0.15	55	5.36	0.05	0.7	4	230	5.2	24.6	-	0.005	
2014-DD-060	JGT-02	307	313.09	Granite	9.48	0.05	0.65	0.005	0.01	0.43	20.3	29	0.29	80	5.72	0.04	0.98	8	540	6.6	46.9	-	0.01	
Median					9.3	0.05	0.34	0.005	0.01	0.26	14.5	18.5	0.19	87	5	0.05	0.675	6	630	6	23.75	-	0.005	
Minimum					8.1	0.05	0.06	0.005	0.01	0.13	1.2	7	0.13	35	4	0.03	0.025	4	210	1	7.6	-	0.005	
Maximum					9.6	0.05	0.65	0.005	0.05	1.9	24.4	127	2.1	329	6	0.08	1.81	90	1,200	9	99.2	-	0.13	
Count					30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	0	30
Kimberlite																								
Beartooth																								
64	BCD-01	49m	49	Kimberlite	8.1	-	-	-	-	0.35	-	-	15.01	740	2	0.02	-	1,568	520	10	-	-	-	
64	BCD-01	49m	49	Kimberlite	-	-	-	-	-	0.35	-	-	15.01	720	2	0.04	-	1,187	640	8	-	-	-	
65	BCD-01	186m	186	Kimberlite	8.6	-	-	-	-	0.51	-	-	15.01	780	2	0.03	-	736	1,110	12	-	-	-	
66	BCD-04	100m	100	Kimberlite	8.3	-	-	-	-	0.76	-	-	15	585	2	0.03	-	1,332	680	8	-	-	-	
67	BCD-04	190m	190	Kimberlite	8.5	-	-	-	-	0.51	-	-	15.01	775	2	0.02	-	1,537	520	10	-	-	-	
Median					8.4	-	-	-	-	0.51	-	-	15	740	2	0.03	-	1,332	640	10	-	-	-	
Minimum					8.1	-	-	-	-	0.35	-	-	15	585	2	0.02	-	736	520	8	-	-	-	
Maximum					8.6	-	-	-	-	0.76	-	-	15	780	2	0.04	-	1,568	1,110	12	-	-	-	
Count					4	0	0	0	0	5	0	0	5	5	5	5	0	5	5	5	0	0	0	
Fox																								
FUC 3-3 - 30	FUC 3-3	30	30.3	Kimberlite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 35	FUC 3-3	35	35.3	Kimberlite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 40	FUC 3-3	40	40.3	Kimberlite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 66.1	F1-1	66.1	66.2	Kimberlite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 66.2	F1-1	66.2	66.3	Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 72	F1-1	72	74	Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 94	F1-1	94	96	Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 110	F1-1	110	112	Kimberlite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 116	F1-1	116	118	Kimberlite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 122	F1-1	122	124	Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 158	F1-1	158	160	Kimberlite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 160	F1-1	160	162	Kimberlite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 184	F1-1	184	186	Kimberlite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 186	F1-1	186	188	Kimberlite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035	
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S	
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Kimberlite (continued)																								
Fox (continued)																								
F1-1 - 196	F1-1	196	198	Kimberlite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
F1-1 - 210	F1-1	210	212	Kimberlite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
F1-1 - 216	F1-1	216	218	Kimberlite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 4-3 - 151.5	FUC 4-3	151.5	155.2	Kimberlite	8.8	-	-	10	-	1.9	-	-	11	765	5.0	1.1	-	686	1,370	14	-	-	-	-
F19 - 176	F19	176	177	Kimberlite	8.9	-	-	5	-	1.6	-	-	12	680	5.0	1.1	-	858	880	10	-	-	-	-
F19 - 122	F19	122	123	Kimberlite	8.6	-	-	10	-	2.2	-	-	9.8	615	0.5	0.60	-	677	1,020	14	-	-	-	-
F17 - 200	F17	200	201	Kimberlite	8.6	-	-	5	-	1.7	-	-	14	750	0.5	0.73	-	986	1,040	12	-	-	-	-
F17 - 100	F17	100	101	Kimberlite	8.3	-	-	30	-	3.3	-	-	6.1	580	1.0	0.28	-	301	910	16	-	-	-	-
FWK405-13-1	-	-	-	Kimberlite	7.4	-	-	50	-	2.6	-	-	5.1	480	4.0	0.28	-	356	930	14	-	-	-	-
FWK405-13-2	-	-	-	Kimberlite	7.5	-	-	60	-	2.9	-	-	5.7	580	7.0	0.24	-	404	950	16	-	-	-	-
FK-390-20-1	-	-	-	Kimberlite	8.0	-	-	0.02	-	2.1	-	-	10	705	2.0	0.26	-	624	1,270	10	-	-	-	-
FK-390-20-2	-	-	-	Kimberlite	8.0	-	-	0.02	-	2.0	-	-	10	673	2.0	0.26	-	663	1,320	10	-	-	-	-
FK-375-09R1-1	-	-	-	Kimberlite	8.3	-	-	0.01	-	1.9	-	-	10	722	1.0	0.24	-	664	1,310	11	-	-	-	-
FK-375-09R1-2	-	-	-	Kimberlite	8.3	-	-	0.01	-	1.7	-	-	10	753	0.5	0.23	-	690	1,320	6	-	-	-	-
FK-375-13-1	-	-	-	Kimberlite	8.4	-	-	0.01	-	2.4	-	-	7.1	556	2.0	0.68	-	434	1,100	9	-	-	-	-
FK-375-13-2	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.1	-	-	9.6	660	1.0	0.35	-	590	1,220	11	-	-	-	-
FK-375-21-1	-	-	-	Kimberlite	8.2	-	-	0.03	-	2.8	-	-	6.9	548	5.0	0.39	-	408	1,120	8	-	-	-	-
FK-375-21-2	-	-	-	Kimberlite	8.1	-	-	0.04	-	2.7	-	-	7.3	602	4.0	0.30	-	421	1,220	14	-	-	-	-
FK-375-23-1	-	-	-	Kimberlite	8.3	-	-	0.03	-	3.0	-	-	8.1	597	1.0	0.28	-	511	1,310	13	-	-	-	-
FK-375-23-2	-	-	-	Kimberlite	8.1	-	-	0.02	-	2.4	-	-	9.0	659	2.0	0.29	-	576	1,420	11	-	-	-	-
FK-375-23-3	-	-	-	Kimberlite	8.3	-	-	0.03	-	2.3	-	-	8.8	650	2.0	0.32	-	531	1,380	13	-	-	-	-
FK-375-23-4	-	-	-	Kimberlite	8.4	-	-	0.03	-	1.8	-	-	9.2	644	1.0	0.28	-	578	1,440	9	-	-	-	-
FK-375-29-1	-	-	-	Kimberlite	8.2	-	-	0.02	-	2.1	-	-	8.0	633	4.0	0.32	-	503	1,170	9	-	-	-	-
FK-375-29-2	-	-	-	Kimberlite	8.2	-	-	0.02	-	2.1	-	-	9.4	715	7.0	0.35	-	579	1,270	9	-	-	-	-
FK-375-29-3	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.2	-	-	9.1	658	1.0	0.34	-	556	1,400	12	-	-	-	-
FK-375-29-4	-	-	-	Kimberlite	8.2	-	-	0.02	-	2.2	-	-	8.6	611	1.0	0.34	-	552	1,400	10	-	-	-	-
FK-375-34-1	-	-	-	Kimberlite	8.3	-	-	0.04	-	2.9	-	-	7.6	592	4.0	0.40	-	482	1,200	11	-	-	-	-
FK-375-34-2	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.7	-	-	8.9	662	2.0	0.41	-	529	1,360	12	-	-	-	-
FK-375-34-3	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.3	-	-	8.1	607	1.0	0.68	-	471	1,220	10	-	-	-	-
FK-375-34-4	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.2	-	-	8.2	608	3.0	0.38	-	501	1,150	13	-	-	-	-
FK-375-35-1	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.4	-	-	9.0	655	3.0	0.39	-	583	1,200	9	-	-	-	-
FK-375-35-2	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.2	-	-	8.3	596	9.0	0.38	-	536	1,080	7	-	-	-	-
FK-375-35-3	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.3	-	-	8.9	643	3.0	0.43	-	565	1,160	10	-	-	-	-
FK-375-35-4	-	-	-	Kimberlite	8.4	-	-	0.02	-	2.2	-	-	8.3	608	3.0	0.52	-	506	1,150	7	-	-	-	-
FWK-375-12-01	-	-	-	Kimberlite	8.1	-	-	0.02	-	1.9	-	-	8.6	617	1.0	0.54	-	514	1,180	7	-	-	-	-
FWK-375-12-02	-	-	-	Kimberlite	8.4	-	-	0.01	-	1.2	-	-	11	743	1.0	0.29	-	615	1,380	7	-	-	-	-
FWK-375-14KB1-	-	-	-	Kimberlite	8.6	-	-	0.02	-	2.0	-	-	9.6	620	1.0	0.28	-	615	1,200	8	-	-	-	-
FWK-375-14KB2-	-	-	-	Kimberlite	8.4	-	-	0.01	-	2.1	-	-	10	726	2.0	0.43	-	660	1,340	12	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Kimberlite (continued)																							
Fox (continued)																							
FWK-375-14KB3-	-	-	-	Kimberlite	8.4	-	-	0.01	-	2.0	-	-	9.6	693	2.0	0.31	-	650	1,320	7	-	-	-
FWK-375-14KB4-	-	-	-	Kimberlite	8.5	-	-	0.02	-	2.6	-	-	8.7	622	2.0	0.33	-	510	1,130	9	-	-	-
FWK-375-15kb-1	-	-	-	Kimberlite	8.4	-	-	0.03	-	2.0	-	-	9.4	686	4.0	0.33	-	622	1,400	13	-	-	-
FWK-375-15kb-2	-	-	-	Kimberlite	8.5	-	-	0.03	-	1.9	-	-	10	716	1.0	0.28	-	663	1,430	12	-	-	-
FWK-375-15kb-3	-	-	-	Kimberlite	8.3	-	-	0.03	-	2.3	-	-	9.3	671	4.0	0.28	-	605	1,300	15	-	-	-
FWK-375-15kb-4	-	-	-	Kimberlite	8.3	-	-	0.03	-	2.4	-	-	9.2	655	2.0	0.26	-	577	1,360	15	-	-	-
FWK-375-38-1	-	-	-	Kimberlite	8.7	-	-	0.02	-	1.9	-	-	10	684	1.0	0.43	-	633	1,350	11	-	-	-
FWK-375-38-2	-	-	-	Kimberlite	8.6	-	-	0.01	-	1.5	-	-	10	684	1.0	0.41	-	649	1,310	13	-	-	-
FWK-375-38-3	-	-	-	Kimberlite	8.7	-	-	0.02	-	1.6	-	-	10	721	1.0	0.36	-	669	1,300	8	-	-	-
FWK-375-38-4	-	-	-	Kimberlite	8.4	-	-	0.02	-	1.7	-	-	10	692	1.0	0.44	-	669	1,320	9	-	-	-
FWK-375-36-04 6-OCT-04	-	-	-	Kimberlite	7.4	-	-	0.02	-	2.2	-	-	9.0	658	3.0	0.55	-	585	1,200	12	-	-	-
FWK-375-36-03 6-OCT-04	-	-	-	Kimberlite	7.5	-	-	0.02	-	1.9	-	-	10	725	7.0	0.41	-	665	1,340	8	-	-	-
FWK-375-36-02 6-OCT-04	-	-	-	Kimberlite	8.0	-	-	0.02	-	2.1	-	-	10	727	2.0	0.38	-	614	1,300	11	-	-	-
FWK-375-36-01 6-OCT-04	-	-	-	Kimberlite	7.8	-	-	0.02	-	1.5	-	-	11	761	0.5	0.42	-	764	1,400	11	-	-	-
FWK-360-29-02 26-DEC-04	-	-	-	Kimberlite	7.6	-	-	0.03	-	2.2	-	-	7.8	637	2.0	0.24	-	521	1,120	11	-	-	-
FWK-360-29-02 1-JAN-05	-	-	-	Kimberlite	7.8	-	-	0.02	-	2.7	-	-	9.1	679	1.0	0.30	-	613	1,130	11	-	-	-
FWK-360-29-01 26-DEC-04	-	-	-	Kimberlite	7.6	-	-	0.02	-	2.1	-	-	9.0	708	2.0	0.26	-	556	1,320	13	-	-	-
FWK-360-29-01 1-JAN-05	-	-	-	Kimberlite	7.8	-	-	0.02	-	1.6	-	-	10	728	5.0	0.31	-	655	1,380	11	-	-	-
FWK-360-24-04 19-DEC-04	-	-	-	Kimberlite	7.4	-	-	0.02	-	1.6	-	-	11	726	1.0	0.22	-	657	1,340	9	-	-	-
FWK-360-24-03 19-DEC-04	-	-	-	Kimberlite	7.7	-	-	0.02	-	1.7	-	-	10	754	1.0	0.22	-	658	1,480	9	-	-	-
FWK-360-24-02 19-DEC-04	-	-	-	Kimberlite	7.7	-	-	0.02	-	1.6	-	-	10	703	1.0	0.21	-	672	1,310	9	-	-	-
FWK-360-24-01 19-DEC-04	-	-	-	Kimberlite	7.4	-	-	0.02	-	1.6	-	-	11	728	1.0	0.22	-	701	1,360	8	-	-	-
FWK-360-14-04 3-DEC-04	-	-	-	Kimberlite	7.8	-	-	0.03	-	1.5	-	-	11	715	2.0	0.30	-	740	1,360	12	-	-	-
FWK-360-14-03 3-DEC-04	-	-	-	Kimberlite	8.1	-	-	0.03	-	1.3	-	-	10.9	725	1.0	0.31	-	758	1,360	13	-	-	-
FWK-360-14-02 3-DEC-04	-	-	-	Kimberlite	8.0	-	-	0.04	-	2.3	-	-	9.6	689	2.0	0.28	-	595	1,440	12	-	-	-
FWK-360-14-01 3-DEC-04	-	-	-	Kimberlite	7.7	-	-	0.03	-	1.6	-	-	11	688	2.0	0.29	-	691	1,260	9	-	-	-
FWK-360-09-02 22-NOV-04	-	-	-	Kimberlite	8.1	-	-	0.04	-	2.6	-	-	9.0	668	2.0	0.35	-	551	1,340	10	-	-	-
FWK-360-09-01 22-NOV-04	-	-	-	Kimberlite	8.1	-	-	0.03	-	2.3	-	-	9.6	692	3.0	0.34	-	606	1,450	11	-	-	-
FWK-360-07-02 12-NOV-04	-	-	-	Kimberlite	8.3	-	-	0.03	-	2.2	-	-	10	731	1.0	0.37	-	667	1,530	7	-	-	-
FWK-360-07-01 12-NOV-04	-	-	-	Kimberlite	8.0	-	-	0.04	-	3.0	-	-	8.1	659	5.0	0.46	-	416	1,230	12	-	-	-
FWK-360-05-04 29-OCT-04	-	-	-	Kimberlite	7.1	-	-	0.05	-	3.2	-	-	6.5	598	15	0.16	-	437	1,040	11	-	-	-
FWK-360-05-03 29-OCT-04	-	-	-	Kimberlite	7.5	-	-	0.04	-	2.3	-	-	7.6	603	8.0	0.18	-	495	1,120	7	-	-	-
FWK-360-05-02 29-OCT-04	-	-	-	Kimberlite	7.7	-	-	0.02	-	1.9	-	-	9.9	723	1.0	0.23	-	662	1,250	8	-	-	-
FWK-360-05-01 29-OCT-04	-	-	-	Kimberlite	7.7	-	-	0.03	-	2.6	-	-	8.4	653	6.0	0.44	-	542	1,280	10	-	-	-
FWK-345-33-04 8-Apr-05	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.1	-	-	10	704	0.5	0.41	-	683	1,370	5	-	-	-
FWK-345-33-03 8-Apr-05	-	-	-	Kimberlite	8.4	-	-	0.02	-	2.1	-	-	10	698	0.5	0.32	-	658	1,300	8	-	-	-
FWK-345-33-02 8-Apr-05	-	-	-	Kimberlite	8.5	-	-	0.02	-	1.6	-	-	11	740	0.5	0.45	-	719	1,360	13	-	-	-
FWK-345-33-01 8-Apr-05	-	-	-	Kimberlite	8.2	-	-	0.03	-	2.4	-	-	9.5	636	5.0	0.37	-	590	1,180	8	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																							
Fox (continued)																							
FWK-345-29-04- 8-Apr-05	-	-	-	Kimberlite	8.3	-	-	0.03	-	2.3	-	-	10	686	2.0	0.31	-	632	1,260	7	-	-	-
FWK-345-29-03- 8-Apr-05	-	-	-	Kimberlite	8.4	-	-	0.02	-	2.2	-	-	10	673	1.0	0.37	-	589	1,260	1	-	-	-
FWK-345-29-02- 8-Apr-05	-	-	-	Kimberlite	8.3	-	-	0.03	-	2.1	-	-	10	681	1.0	0.30	-	607	1,370	5	-	-	-
FWK-345-29-01- 8-Apr-05	-	-	-	Kimberlite	7.9	-	-	0.04	-	2.8	-	-	8.7	650	6.0	0.31	-	570	1,220	7	-	-	-
FWK-345-24-06-26-Mar-05	-	-	-	Kimberlite	8.6	-	-	0.02	-	1.6	-	-	9.9	678	2.0	0.56	-	655	1,240	12	-	-	-
FWK-345-24-05-26-Mar-05	-	-	-	Kimberlite	8.1	-	-	0.03	-	2.3	-	-	8.6	632	4.0	0.43	-	565	1,120	13	-	-	-
FWK-345-24-04-26-Mar-05	-	-	-	Kimberlite	8.1	-	-	0.04	-	2.5	-	-	8.2	635	10	0.47	-	552	1,250	15	-	-	-
FWK-345-24-03-26-Mar-05	-	-	-	Kimberlite	8.7	-	-	0.03	-	2.3	-	-	9.7	709	3.0	0.47	-	692	1,250	11	-	-	-
FWK-345-24-02-26-Mar-05	-	-	-	Kimberlite	8.5	-	-	0.02	-	2.0	-	-	9.9	689	1.0	0.53	-	677	1,300	9	-	-	-
FWK-345-24-01-26-Mar-05	-	-	-	Kimberlite	8.5	-	-	0.02	-	2.2	-	-	9.1	676	5.0	0.48	-	618	1,340	17	-	-	-
FWK-345-20-04- 8-Mar-05	-	-	-	Kimberlite	8.7	-	-	0.01	-	1.4	-	-	12	715	0.5	0.53	-	791	1,340	11	-	-	-
FWK-345-20-03- 8-Mar-05	-	-	-	Kimberlite	8.3	-	-	0.03	-	2.4	-	-	5.7	487	3.0	0.30	-	314	990	13	-	-	-
FWK-345-20-02- 8-Mar-05	-	-	-	Kimberlite	8.7	-	-	0.02	-	1.5	-	-	12	702	1.0	0.52	-	754	1,200	9	-	-	-
FWK-345-20-01- 8-Mar-05	-	-	-	Kimberlite	8.3	-	-	0.02	-	1.5	-	-	11	717	1.0	0.53	-	758	1,280	15	-	-	-
FWK-345-15-02 9-FEB-05	-	-	-	Kimberlite	8.1	-	-	0.03	-	2.3	-	-	8.8	617	0.5	0.32	-	504	1,190	25	-	-	-
FWK-345-15-01 9-FEB-05	-	-	-	Kimberlite	8.0	-	-	0.03	-	1.9	-	-	11	734	1.0	0.37	-	737	1,460	11	-	-	-
FWK-345-13-02 18-FEB-05	-	-	-	Kimberlite	8.0	-	-	0.03	-	2.6	-	-	7.7	641	5.0	0.45	-	540	1,210	10	-	-	-
FWK-345-13-01 18-FEB-05	-	-	-	Kimberlite	8.0	-	-	0.03	-	2.5	-	-	7.3	569	6.0	0.38	-	450	1,100	10	-	-	-
FWK-345-08-04 7-FEB-05	-	-	-	Kimberlite	8.1	-	-	0.03	-	2.5	-	-	8.7	616	1.0	0.38	-	479	1,260	11	-	-	-
FWK-345-08-03 7-FEB-05	-	-	-	Kimberlite	7.9	-	-	0.05	-	2.4	-	-	7.7	589	4.0	0.62	-	459	1,130	11	-	-	-
FWK-345-08-02 7-FEB-05	-	-	-	Kimberlite	8.0	-	-	0.03	-	2.3	-	-	8.1	580	3.0	0.50	-	464	1,200	14	-	-	-
FWK-345-08-01 7-FEB-05	-	-	-	Kimberlite	8.1	-	-	0.05	-	2.7	-	-	7.6	579	3.0	0.36	-	487	1,120	13	-	-	-
FWK-345-07-02 4-FEB-05	-	-	-	Kimberlite	8.2	-	-	0.03	-	1.8	-	-	9.0	643	0.5	0.32	-	511	1,280	9	-	-	-
FWK-345-07-01 4-FEB-05	-	-	-	Kimberlite	8.0	-	-	0.05	-	2.1	-	-	8.9	628	2.0	0.32	-	592	1,320	13	-	-	-
FWK-345-06-02 1-FEB-05	-	-	-	Kimberlite	7.9	-	-	0.04	-	2.4	-	-	7.1	534	5.0	0.24	-	404	1,050	13	-	-	-
FWK-345-06-01 1-FEB-05	-	-	-	Kimberlite	8.0	-	-	0.04	-	2.5	-	-	7.6	575	3.0	0.27	-	473	1,260	17	-	-	-
FWK-345-04-02 30-JAN-05	-	-	-	Kimberlite	8.2	-	-	0.03	-	1.8	-	-	9.9	695	2.0	0.34	-	607	1,390	10	-	-	-
FWK-345-04-01 30-JAN-05	-	-	-	Kimberlite	8.1	-	-	0.03	-	2.2	-	-	9.3	669	4.0	0.42	-	571	1,290	10	-	-	-
FWK-345-03-04 28-JAN-05	-	-	-	Kimberlite	7.8	-	-	0.01	-	1.5	-	-	9.9	833	2.0	0.47	-	623	1,290	8	-	-	-
FWK-345-03-03 28-JAN-05	-	-	-	Kimberlite	7.8	-	-	0.02	-	1.5	-	-	11	735	2.0	0.18	-	665	1,380	9	-	-	-
FWK-345-03-02 24-JAN-05	-	-	-	Kimberlite	8.1	-	-	0.02	-	2.2	-	-	9.5	696	2.0	0.30	-	638	1,360	9	-	-	-
FWK-345-03-01 24-JAN-05	-	-	-	Kimberlite	8.0	-	-	0.02	-	2.7	-	-	7.0	648	4.0	0.83	-	740	1,440	11	-	-	-
FWK-345-02-02 20-JAN-05	-	-	-	Kimberlite	8.1	-	-	0.02	-	1.8	-	-	11	742	1.0	0.27	-	694	1,270	9	-	-	-
FWK-345-02-01 20-JAN-05	-	-	-	Kimberlite	8.2	-	-	0.01	-	1.7	-	-	9.1	678	3.0	0.66	-	573	1,210	10	-	-	-
FWK-345-01-04 14-JAN-05	-	-	-	Kimberlite	7.8	-	-	0.02	-	2.4	-	-	8.7	673	3.0	0.54	-	582	1,230	10	-	-	-
FWK-345-01-03 14-JAN-05	-	-	-	Kimberlite	7.8	-	-	0.02	-	2.4	-	-	7.4	578	3.0	1.6	-	521	1,280	6	-	-	-
FWK-345-01-02 14-JAN-05	-	-	-	Kimberlite	7.6	-	-	0.04	-	2.8	-	-	8.7	653	4.0	0.22	-	555	1,180	9	-	-	-
FWK-345-01-01 14-JAN-05	-	-	-	Kimberlite	7.8	-	-	0.03	-	2.6	-	-	7.9	576	4.0	1.0	-	443	990	8	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Kimberlite (continued)																							
Fox (continued)																							
FWK-330-14-08 18-May-05	-	-	-	Kimberlite	8.3	-	-	0.03	-	2.5	-	-	8.9	641	4.0	0.43	-	508	1,260	11	-	-	-
FWK-330-14-07 18-May-05	-	-	-	Kimberlite	8.2	-	-	0.04	-	2.5	-	-	9.0	643	7.0	0.42	-	521	1,270	10	-	-	-
FWK-330-14-06 18-May-05	-	-	-	Kimberlite	8.4	-	-	0.03	-	2.3	-	-	9.7	666	2.0	0.48	-	614	1,330	9	-	-	-
FWK-330-14-05 18-May-05	-	-	-	Kimberlite	8.5	-	-	0.03	-	2.5	-	-	9.0	657	2.0	0.42	-	573	1,380	12	-	-	-
FWK-330-14-04 17-May-05	-	-	-	Kimberlite	8.5	-	-	0.03	-	2.2	-	-	9.0	642	1.0	0.45	-	526	1,300	13	-	-	-
FWK-330-14-03 17-May-05	-	-	-	Kimberlite	8.3	-	-	0.04	-	2.3	-	-	8.2	589	2.0	0.43	-	514	1,200	12	-	-	-
FWK-330-14-02 17-May-05	-	-	-	Kimberlite	8.5	-	-	0.04	-	2.4	-	-	8.6	632	7.0	0.44	-	537	1,330	13	-	-	-
FWK-330-14-01 17-May-05	-	-	-	Kimberlite	8.4	-	-	0.03	-	1.9	-	-	9.6	692	3.0	0.52	-	615	1,360	14	-	-	-
FWK-330-05-04 11-May-05	-	-	-	Kimberlite	8.4	-	-	0.02	-	2.5	-	-	7.2	576	2.0	0.71	-	466	1,140	9	-	-	-
FWK-330-05-04 10-May-05	-	-	-	Kimberlite	8.3	-	-	0.03	-	2.1	-	-	9.5	662	1.0	0.48	-	592	1,360	10	-	-	-
FWK-330-05-03 11-May-05	-	-	-	Kimberlite	8.4	-	-	0.02	-	2.2	-	-	9.1	697	2.0	0.62	-	598	1,290	12	-	-	-
FWK-330-05-03 10-May-05	-	-	-	Kimberlite	8.3	-	-	0.04	-	2.5	-	-	8.5	623	5.0	0.43	-	603	1,220	12	-	-	-
FWK-330-05-02 11-May-05	-	-	-	Kimberlite	8.5	-	-	0.02	-	1.9	-	-	9.7	727	0.5	0.60	-	670	1,320	10	-	-	-
FWK-330-05-02 10-May-05	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.0	-	-	10	703	1.0	0.46	-	713	1,360	11	-	-	-
FWK-330-05-01 11-May-05	-	-	-	Kimberlite	8.5	-	-	0.02	-	2.1	-	-	9.9	697	1.0	0.61	-	676	1,410	9	-	-	-
FWK-330-05-01 10-May-05	-	-	-	Kimberlite	8.3	-	-	0.04	-	2.5	-	-	8.9	612	2.0	0.48	-	500	1,220	11	-	-	-
FWK-330-01-04- 10-Apr-05	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.2	-	-	9.8	682	5.0	0.42	-	588	1,360	7	-	-	-
FWK-330-01-03- 10-Apr-05	-	-	-	Kimberlite	8.4	-	-	0.03	-	1.9	-	-	9.9	715	9.0	0.44	-	632	1,380	5	-	-	-
FWK-330-01-02-17-Apr-05	-	-	-	Kimberlite	8.4	-	-	0.04	-	2.6	-	-	7.3	507	2.0	0.37	-	452	1,010	7	-	-	-
FWK-330-01-02- 10-Apr-05	-	-	-	Kimberlite	8.3	-	-	0.03	-	2.4	-	-	8.7	607	5.0	0.47	-	585	1,180	12	-	-	-
FWK-330-01-01-17-Apr-05	-	-	-	Kimberlite	8.4	-	-	0.03	-	2.4	-	-	8.4	624	3.0	0.47	-	580	1,300	7	-	-	-
FWK-330-01-01- 10-Apr-05	-	-	-	Kimberlite	8.5	-	-	0.02	-	1.9	-	-	10	697	2.0	0.44	-	639	1,460	11	-	-	-
FWK-315-02-06 15-Jun-05	-	-	-	Kimberlite	8.6	-	-	0.02	-	1.7	-	-	9.4	749	5.0	0.76	-	593	1,300	12	-	-	-
FWK-315-02-05 15-Jun-05	-	-	-	Kimberlite	8.4	-	-	0.02	-	2.1	-	-	8.4	623	8.0	0.94	-	548	1,220	12	-	-	-
FWK-315-02-04 15-Jun-05	-	-	-	Kimberlite	8.6	-	-	0.02	-	2.0	-	-	8.9	676	6.0	0.94	-	582	1,280	9	-	-	-
FWK-315-02-03 15-Jun-05	-	-	-	Kimberlite	8.8	-	-	0.02	-	2.0	-	-	9.6	663	13	0.78	-	633	1,240	8	-	-	-
FWK-315-02-02 15-Jun-05	-	-	-	Kimberlite	8.6	-	-	0.02	-	1.6	-	-	9.7	649	5.0	0.67	-	665	1,200	9	-	-	-
FWK-315-02-01 15-Jun-05	-	-	-	Kimberlite	8.5	-	-	0.02	-	1.5	-	-	10	682	6.0	0.60	-	694	1,280	9	-	-	-
FWK-315-01-04 8-Jun-05	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.1	-	-	9.5	666	2.0	0.50	-	613	1,400	11	-	-	-
FWK-315-01-03 8-Jun-05	-	-	-	Kimberlite	8.2	-	-	0.03	-	2.0	-	-	10	703	2.0	0.49	-	667	1,290	7	-	-	-
FWK-315-01-02 8-Jun-05	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.1	-	-	10	676	1.0	0.50	-	676	1,280	12	-	-	-
FWK-315-01-01 8-Jun-05	-	-	-	Kimberlite	8.3	-	-	0.02	-	2.0	-	-	10	711	2.0	0.50	-	689	1,380	12	-	-	-
FWK-285-35-01	-	-	-	Kimberlite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FWK-285-36-01 15-MAY-06	-	-	-	Kimberlite	7.9	-	-	0.02	-	2.0	-	-	9.7	664	0.5	0.51	-	593	1,330	111	-	-	-
FWK-285-36-02 15 MAY-06	-	-	-	Kimberlite	8.1	-	-	0.02	-	2.1	-	-	9.5	639	0.5	0.55	-	567	1,250	17	-	-	-
FWK-285-36-03 15 MAY-06	-	-	-	Kimberlite	7.8	-	-	0.02	-	3.1	-	-	9.3	602	1.0	0.45	-	471	1,130	29	-	-	-
FWK-285-36-04 15-MAY-06	-	-	-	Kimberlite	8.1	-	-	0.03	-	2.7	-	-	8.8	565	0.5	0.39	-	466	1,100	16	-	-	-
Fox-260-WK-3a 26-Jan-09	-	-	-	Kimberlite	8.8	-	-	20	-	1.5	80	-	10	737	2.0	0.26	-	563	1,370	12	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Kimberlite (continued)																							
Fox (continued)																							
				Kimberlite	8.9	-	-	20	-	2.0	50	-	4.4	472	2.0	1.4	-	214	1,110	12	-	-	-
				Kimberlite	9.2	-	-	5	-	2.0	20	-	2.0	425	0.5	2.4	-	77	1,020	10	-	-	-
				Median	8.3	-	-	0.02	-	2.2	50	-	9.3	665	2.0	0.41	-	590	1,280	11	-	-	-
				Minimum	7.1	-	-	0.01	-	1.2	20	-	2.0	425	0.5	0.16	-	77	880	1	-	-	-
				Maximum	9.8	-	-	60	-	3.3	80	-	14	833	15	2.4	-	986	1,530	111	-	-	-
				Count	168	0	0	150	0	150	3	0	150	150	150	150	0	150	150	150	0	0	0
Koala																							
				Kimberlite	7.9	-	-	5	-	0.32	-	-	15.01	835	0.5	0.05	-	1,660	410	12	-	-	0.26
				Kimberlite	7.7	-	-	5	-	0.38	-	-	15.01	870	1.0	0.14	-	1,555	460	14	-	-	0.47
				Kimberlite	8.0	-	-	5	-	0.34	-	-	15.01	890	0.5	0.06	-	1,765	440	14	-	-	0.30
				Kimberlite	8.0	-	-	5	-	0.32	-	-	15.01	830	0.5	0.05	-	1,650	410	12	-	-	0.28
				Kimberlite	7.8	-	-	10	-	0.34	-	-	15.01	935	0.5	0.05	-	1,665	410	12	-	-	0.28
				Kimberlite	7.3	-	-	10	-	0.42	-	-	12	520	3.0	0.03	-	1,265	540	20	-	-	0.42
				Kimberlite	8.2	-	-	5	-	1.5	-	-	11	651	5.0	0.45	-	668	950	16	-	-	0.15
				Kimberlite	8.3	-	-	5	-	1.0	-	-	>15	697	2.0	0.12	-	1,290	1,040	11	-	-	0.08
				Kimberlite	8.0	-	-	10	-	0.35	-	-	13	564	3.0	0.07	-	1,090	450	6	-	-	0.15
				Kimberlite	8.1	-	-	10	-	0.35	-	-	14	575	2.0	0.06	-	1,130	460	9	-	-	0.14
				Kimberlite	7.7	-	-	10	-	0.32	-	-	15	663	2.0	0.10	-	1,340	350	6	-	-	0.21
				Kimberlite	7.7	-	-	10	-	0.34	-	-	15	629	2.0	0.17	-	1,230	370	4	-	-	0.23
				Kimberlite	8.0	-	-	10	-	0.36	-	-	14	582	1.0	0.05	-	1,150	460	6	-	-	0.13
				Kimberlite	8.0	-	-	10	-	0.31	-	-	>15	697	3.0	0.08	-	1,495	360	5	-	-	0.19
				Kimberlite	7.9	-	-	10	-	0.37	-	-	14	579	2.0	0.05	-	1,165	460	8	-	-	0.16
				Kimberlite	8.0	-	-	10	-	0.37	-	-	15	599	2.0	0.07	-	1,170	440	6	-	-	0.24
				Kimberlite	8.0	-	-	10	-	0.37	-	-	15	634	4.0	0.05	-	1,215	440	3	-	-	0.29
				Kimberlite	7.8	-	-	10	-	0.36	-	-	14	616	1.0	0.05	-	1,190	460	6	-	-	0.14
				Kimberlite	7.9	-	-	10	-	0.36	-	-	14	596	3.0	0.07	-	1,180	430	3	-	-	0.13
				Kimberlite	8.0	-	-	10	-	0.38	-	-	14	602	2.0	0.12	-	1,155	460	8	-	-	0.15
				Kimberlite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
				Kimberlite	7.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
				Median	7.9	-	-	10	-	0.36	-	-	14	631.5	2.0	0.07	-	1,223	445	8	-	-	0.20
				Minimum	7.3	-	-	5	-	0.31	-	-	11	520	0.5	0.03	-	668	350	3	-	-	0.08
				Maximum	8.3	-	-	10	-	1.5	-	-	15	935	5.0	0.45	-	1,765	1,040	20	-	-	0.47
				Count	22	0	0	20	0	20	0	0	18	20	20	20	0	20	20	20	0	0	20
Misery																							
				Kimberlite	9.3	-	-	10	-	0.24	-	-	14	1,140	1.0	0.34	-	1,365	1,390	16	-	-	0.12
				Kimberlite	7.8	-	-	30	-	1.8	-	-	5.4	395	10.0	0.66	-	454	900	12	-	-	1.3
				Kimberlite	8.2	-	-	20	-	0.80	-	-	9.9	645	5.0	0.14	-	826	900	14	-	-	0.79
				Kimberlite	9.1	-	-	5	-	1.2	-	-	13	895	1.0	0.25	-	1,095	1,720	16	-	-	0.05

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035	
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %	
Kimberlite (continued)																								
Misery (continued)																								
MK- 430-04-1A	-	-	-	Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK- 430-04-2A	-	-	-	Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK- 430-06-A1	-	-	-	Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK- 430-06-A2	-	-	-	Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK- 430-06-A3	-	-	-	Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK-400-52T-1a	-	-	-	Kimberlite	8.3	-	-	10	-	0.55	-	-	13	720	2.0	0.12	-	997	850	24	-	-	-	0.38
MWKB-380-20-1a	-	-	-	Kimberlite	8.5	-	-	120	-	3.0	-	-	6.6	290	5.0	0.080	-	511	780	36	-	-	-	0.26
MWKB-380-20-2a	-	-	-	Kimberlite	8.5	-	-	5	-	0.44	-	-	10	415	0.5	0.47	-	840	270	12	-	-	-	0.13
MGT-60 143.42-145.0	-	-	-	Kimberlite	5.1	-	-	0.07	-	0.48	20	-	1.5	196	22	0.013	-	132	590	13	-	-	-	1.7
MGT-60 308.0-309.85	-	-	-	Kimberlite	8.6	-	-	0.02	-	1.1	55	-	12	694	1.9	0.15	-	1,164	1,150	8	-	-	-	0.35
MGT-53 245-248	-	-	-	Kimberlite	8.2	-	-	0.02	-	0.49	41	-	13	658	2.9	0.061	-	1,079	820	8	-	-	-	0.29
MGT-54 297-300	-	-	-	Kimberlite	8.6	-	-	0.03	-	0.76	35	-	14	598	2.1	0.11	-	1,190	610	9	-	-	-	0.39
MGT-51 98.0-99.59	-	-	-	Kimberlite	8.5	-	-	0.005	-	1.3	131	-	15	997	1.6	0.043	-	1,293	2,530	11	-	-	-	0.06
MGT-51 113-116	-	-	-	Kimberlite	8.7	-	-	0.005	-	1.6	141	-	16	948	0.8	0.040	-	1,302	2,560	11	-	-	-	0.025
MGT-51 116-119	-	-	-	Kimberlite	8.8	-	-	0.005	-	1.6	138	-	17	984	0.9	0.034	-	1,347	2,510	10	-	-	-	0.025
MGT-51 119-122	-	-	-	Kimberlite	8.8	-	-	0.005	-	1.5	134	-	17	989	1.4	0.5	-	1,252	2,440	11	-	-	-	0.025
MGT-51 122-125	-	-	-	Kimberlite	8.5	-	-	0.005	-	1.3	136	-	16	1,045	0.6	0.034	-	1,249	2,400	10	-	-	-	0.025
MGT-64 255-258	-	-	-	Kimberlite	9.1	-	-	0.005	-	0.59	92	-	20	1,041	0.2	0.033	-	1,540	2,390	10	-	-	-	0.025
MGT-64 258-261	-	-	-	Kimberlite	8.9	-	-	0.005	-	0.26	70	-	19	1,078	0.2	0.060	-	1,435	2,020	8	-	-	-	0.025
MGT-64 261-264	-	-	-	Kimberlite	9.0	-	-	0.005	-	0.27	96	-	19	1,123	0.4	0.062	-	1,647	1,590	8	-	-	-	0.025
MGT-64 264-267	-	-	-	Kimberlite	8.9	-	-	0.005	-	0.50	93	-	20	1,154	0.3	0.061	-	1,705	2,000	10	-	-	-	0.025
MGT-64 267-270	-	-	-	Kimberlite	8.8	-	-	0.005	-	0.40	94	-	19	1,099	0.3	0.060	-	1,596	2,740	14	-	-	-	0.025
MGT-51 100-103	-	-	-	Kimberlite	8.4	-	-	0.005	-	1.2	115	-	17	925	1.9	0.047	-	1,365	2,060	13	-	-	-	0.025
MGT-51 103-106	-	-	-	Kimberlite	8.4	-	-	0.005	-	1.4	123	-	16	1,156	0.9	0.039	-	1,335	2,190	13	-	-	-	0.025
MGT-51 106-109	-	-	-	Kimberlite	8.4	-	-	0.005	-	2.0	127	-	16	1,020	0.3	0.044	-	1,245	2,280	17	-	-	-	0.05
MGT-52 283-285	-	-	-	Kimberlite	8.9	-	-	0.005	-	0.48	102	-	13	990	1.7	0.080	-	1,239	1,830	9	-	-	-	0.10
MGT-52 287-290	-	-	-	Kimberlite	8.6	-	-	0.02	-	1.0	65	-	13	762	1.9	0.23	-	865	1,290	11	-	-	-	0.55
MGT-54 294-296	-	-	-	Kimberlite	8.5	-	-	0.03	-	0.65	33	-	13	637	2.7	0.11	-	1,203	560	14	-	-	-	0.39
			Median		8.5	-	-	0.005	-	0.80	95	-	14	948	1.4	0.061	-	1,245	1,720	11	-	-	-	0.06
			Minimum		5.1	-	-	0.005	-	0.24	20	-	1.5	196	0.2	0.5	-	132	270	8	-	-	-	0.025
			Maximum		9.3	-	-	120	-	3.0	141	-	20	1,156	22	0.66	-	1,705	2,740	36	-	-	-	1.7
			Count		32	0	0	27	0	27	20	0	27	27	27	27	0	27	27	27	0	0	-	27
Pigeon																								
97-54	97-54	113	113	Kimberlite	8.8	-	-	-	-	2.7	-	-	11	1,390	1.0	0.09	-	293	5,220	32	-	-	-	-
97-54	97-54	117	117	Kimberlite	8.7	-	-	-	-	2.2	-	-	11	1,235	1.0	0.09	-	292	5,440	34	-	-	-	-
97-54	97-54	145	150	Kimberlite	8.7	-	-	-	-	4.2	-	-	9.6	1,155	1.0	0.10	-	265	5,070	32	-	-	-	-
97-54	97-54	172	174	Kimberlite	8.4	-	-	-	-	0.69	-	-	14	1,065	1.0	0.04	-	1,191	920	8	-	-	-	-
97-54	97-54	210	215	Kimberlite	8.9	-	-	-	-	2.7	-	-	15.01	850	2.0	0.06	-	1,327	1,410	14	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Kimberlite (continued)																							
Pigeon (continued)																							
97-54	97-54	310	310	Kimberlite	8.8	-	-	-	-	2.8	-	-	15.01	875	1.0	0.04	-	1,034	1,710	14	-	-	-
97-55	97-55	79	83	Kimberlite	7.6	-	-	-	-	2.8	-	-	15.01	880	1.0	0.04	-	1,040	1,720	16	-	-	-
97-55	97-55	137	137	Kimberlite	7.8	-	-	-	-	0.49	-	-	12	690	2.0	0.03	-	683	1,330	14	-	-	-
97-55	97-55	198	198	Kimberlite	8.2	-	-	-	-	1.3	-	-	15.01	605	1.0	0.05	-	1,307	1,190	8	-	-	-
94-07	94-07	120	120	Kimberlite	8.0	-	-	-	-	0.52	-	-	9.6	705	6.0	0.04	-	546	1,200	14	-	-	-
94-07	94-07	170	170	Kimberlite	8.1	-	-	-	-	0.87	-	-	15.01	705	1.0	0.04	-	1,268	1,110	10	-	-	-
94-07	94-07	225	225	Kimberlite	8.9	-	-	-	-	3.0	-	-	15.01	950	1.0	0.06	-	1,142	1,840	14	-	-	-
97-55	97-55	205	210	Kimberlite	8.9	-	-	-	-	2.3	-	-	15.01	835	1.0	0.05	-	1,206	1,390	12	-	-	-
97-55	97-55	250	250	Kimberlite	8.6	-	-	-	-	2.5	-	-	15.01	885	1.0	0.03	-	1,150	1,670	14	-	-	-
94-7 72-77	94-7	72	77	Kimberlite	-	-	-	5	-	2.6	-	-	1.7	420	3.0	1.6	-	78	350	20	-	-	0.12
94-7 77-80.2	94-7	77	80.2	Kimberlite	8.9	-	-	5	-	2.4	-	-	1.7	415	3.0	1.8	-	67	520	26	-	-	0.09
Median					8.7	-	-	5	-	2.4	-	-	15	862.5	1.0	0.05	-	1,037	1,400	14	-	-	0.11
Minimum					7.6	-	-	5	-	0.49	-	-	1.7	415	1.0	0.03	-	67	350	8	-	-	0.09
Maximum					8.9	-	-	5	-	4.2	-	-	15	1,390	6.0	1.8	-	1,327	5,440	34	-	-	0.12
Count					15	0	0	2	0	16	0	0	16	16	16	16	0	16	16	16	0	0	2
Sable																							
95-25	95-25	138	138	Kimberlite	8.1	-	-	-	-	0.38	-	-	15.01	630	2.0	0.04	-	1,234	720	10	-	-	-
95-25	95-25	297	297	Kimberlite	8.4	-	-	-	-	0.74	-	-	15.01	660	1.0	0.11	-	1,215	830	8	-	-	-
SDC-01	SDC-01	126	126	Kimberlite	8.0	-	-	-	-	0.41	-	-	15.01	740	2.0	0.04	-	1,198	1,210	12	-	-	-
SDC-03	SDC-03	132	132	Kimberlite	7.8	-	-	-	-	0.55	-	-	15.01	815	1.0	0.05	-	1,180	1,640	12	-	-	-
SDC-03	SDC-03	132	132	Kimberlite	7.8	-	-	-	-	0.56	-	-	15.01	830	1.0	0.05	-	1,197	1,700	12	-	-	-
SDC-03	SDC-03	266	266	Kimberlite	8.8	-	-	-	-	1.8	-	-	15.01	695	2.0	0.27	-	1,383	980	6	-	-	-
SDC-04	SDC-04	130	130	Kimberlite	8.1	-	-	-	-	0.40	-	-	15.01	740	1.0	0.04	-	1,357	1,050	14	-	-	-
SDC-06	SDC-06	155	155	Kimberlite	8.0	-	-	-	-	0.60	-	-	15.01	1,810	1.0	0.05	-	1,073	1,560	14	-	-	-
SDC-06	SDC-06	290	290	Kimberlite	8.9	-	-	-	-	1.7	-	-	13	645	1.0	0.32	-	752	1,580	12	-	-	-
SDC-08	SDC-08	126	126	Kimberlite	8.2	-	-	-	-	0.38	-	-	15.01	770	1.0	0.04	-	1,080	1,260	12	-	-	-
SDC-10	SDC-10	207	207	Kimberlite	8.7	-	-	-	-	0.70	-	-	15.01	730	1.0	0.14	-	1,190	1,070	8	-	-	-
SDC-12	SDC-12	423	423	Kimberlite	9.6	-	-	-	-	1.6	-	-	15.01	715	2.0	0.43	-	1,258	1,160	12	-	-	-
SDC-13	SDC-13	236	236	Kimberlite	8.8	-	-	-	-	0.77	-	-	15.01	900	2.0	0.10	-	1,269	1,430	14	-	-	-
SDC-08	SDC-08	16	126	Kimberlite	-	-	-	-	-	0.36	-	-	15.01	760	1.0	0.04	-	1,056	1,240	10	-	-	-
Median					8.2	-	-	-	-	0.58	-	-	15	740	1.0	0.05	-	1,198	1,225	12	-	-	-
Minimum					7.8	-	-	-	-	0.36	-	-	13	630	1.0	0.04	-	752	720	6	-	-	-
Maximum					9.6	-	-	-	-	1.8	-	-	15	1,810	2.0	0.43	-	1,383	1,700	14	-	-	-
Count					13	0	0	0	0	14	0	0	14	14	14	14	0	14	14	14	0	0	0

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035	
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %	
Kimberlite (continued)																								
Jay																								
2014-DD-042	JGT-03	40.8	47.22	Kimberlite	7.72	0.05	0.48	0.06	0.02	0.43	46.5	26	10.9	589	6.32	0.06	6.15	687	840	8.5	30.9	-	-	0.78
2014-DD-054	JGT-02	63.4	64.04	Kimberlite	7.81	0.05	0.4	0.005	0.01	0.19	77.2	6	0.77	233	6.98	0.02	3.05	1,580	280	11.8	18.2	-	-	0.005
Median					7.8	0.05	0.44	0.325	0.015	0.31	61.85	16	6	411	6.7	0.04	4.6	1,134	560	10	24.55	-	-	0.3925
Minimum					7.7	0.05	0.4	0.005	0.01	0.19	46.5	6	1	233	6.3	0.02	3.05	687	280	9	18.2	-	-	0.005
Maximum					7.8	0.05	0.48	0.06	0.02	0.4	77.2	26	11	589	7.0	0.06	6.15	1,580	840	12	30.9	-	-	0.78
Count					2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	0	-	2
Coarse Processed Kimberlite																								
TP-SRK-0-0.7m	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-01-4m	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-02-0.07m	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-02-1.8m	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-02B-2.5m	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-04-0-0.5m	-	-	-	Coarse Processed Kimberlite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-04-3.0m	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-05-0m	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-06-0-0.6m	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-09-0-10	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-09-10-20m	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-09B-0-15m	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-10-0-5m	-	-	-	Coarse Processed Kimberlite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-10-0-0.05	-	-	-	Coarse Processed Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-10-DARKm	-	-	-	Coarse Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-13-10-15m	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-14-0-10m	-	-	-	Coarse Processed Kimberlite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-CK-OCT/02	-	-	-	Coarse Processed Kimberlite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.7	-	-	10	-	1.1	-	-	13	755	0.5	0.84	-	966	950	12	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	10	-	1.2	-	-	12	780	0.5	1.1	-	841	990	10	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.6	-	-	20	-	1.0	-	-	14	715	0.5	0.68	-	1,085	850	10	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	-	-	5	-	0.81	-	-	12	695	0.5	0.71	-	913	790	6	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.8	-	-	5	-	0.47	-	-	15.01	745	0.5	0.15	-	1,400	670	2	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.8	-	-	10	-	0.49	-	-	15	735	1.0	0.23	-	1,175	790	4	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	10	-	0.56	-	-	15	705	2.0	0.25	-	1,170	770	6	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.8	-	-	10	-	0.89	-	-	14	725	0.5	0.49	-	1,135	880	8	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	5	-	1.2	-	-	6.9	655	0.5	1.7	-	489	770	6	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	10	-	1.0	-	-	15.01	720	0.5	0.64	-	1,230	730	2	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035	
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S	
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Kimberlite (continued)																								
Coarse Processed Kimberlite (continued)																								
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	-	-	10	-	0.85	-	-	14	845	0.5	0.36	-	1,175	670	10	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	20	-	1.1	-	-	12	780	1.0	0.44	-	1,000	860	10	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	20	-	1.2	-	-	11	765	0.5	0.89	-	878	900	10	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	10	-	1.1	-	-	13	815	1.0	0.49	-	1,040	880	8	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	-	-	10	-	0.94	-	-	14	790	1.0	0.53	-	1,145	750	6	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.8	-	-	10	-	1.0	-	-	13	845	1.0	0.54	-	1,105	780	8	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	10	-	0.83	-	-	15	810	0.5	0.57	-	1,220	680	8	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	-	-	10	-	0.78	-	-	15.01	855	0.5	0.53	-	1,285	740	8	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	-	-	10	-	1.2	-	-	12	820	0.5	0.92	-	915	830	8	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	-	-	10	-	1.2	-	-	10	770	0.5	0.93	-	782	930	8	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	10	-	1.3	-	-	12	820	0.5	0.81	-	890	1,000	10	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	1.1	-	-	13	710	1.0	0.50	-	1,030	980	10	-	-	-	0.45
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	10	-	1.2	-	-	12	820	2.0	0.61	-	943	980	10	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	10	-	1.1	-	-	11	680	1.0	0.55	-	871	980	8	-	-	-	0.42
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	10	-	1.0	-	-	13	670	4.0	0.44	-	1,030	870	8	-	-	-	0.46
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	10	-	1.0	-	-	11	655	1.0	0.85	-	821	910	8	-	-	-	0.41
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	-	-	10	-	1.1	-	-	9.7	625	1.0	0.77	-	703	970	1	-	-	-	0.37
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	1.1	-	-	11	665	2.0	0.63	-	824	800	1	-	-	-	0.40
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	10	-	1.3	-	-	9.2	695	1.0	1.2	-	653	890	1	-	-	-	0.39
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	10	-	1.1	-	-	11	670	0.5	0.60	-	735	900	12	-	-	-	0.45
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	-	-	10	-	1.1	-	-	15.01	880	5.0	0.30	-	1,210	920	28	-	-	-	0.69
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	-	-	10	-	1.1	-	-	14	730	2.0	0.34	-	1,070	750	18	-	-	-	0.63
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	-	-	10	-	1.1	-	-	12	670	3.0	0.67	-	842	870	16	-	-	-	0.40
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	5	-	0.74	-	-	15.01	630	0.5	0.45	-	1,260	530	14	-	-	-	0.24
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	20	-	1.0	-	-	13	765	10.0	0.20	-	1,005	800	16	-	-	-	0.60
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	10	-	1.2	-	-	11	815	3.0	0.66	-	799	930	26	-	-	-	0.51
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	1.0	-	-	15.01	870	3.0	0.40	-	1,395	670	18	-	-	-	0.44
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	10	-	0.88	-	-	15.01	780	11.0	0.28	-	1,200	740	18	-	-	-	0.46
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	10	-	1.1	-	-	11	655	8.0	0.85	-	776	800	14	-	-	-	0.40
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	10	-	1.1	-	-	12	670	2.0	0.70	-	834	740	16	-	-	-	0.40

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																							
Coarse Processed Kimberlite (continued)																							
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	10	-	1.1	-	-	11	625	5.0	0.88	-	750	720	10	-	-	0.34
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	-	-	10	-	0.92	-	-	14	720	7.0	0.43	-	1,085	660	14	-	-	0.48
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	5	-	0.62	-	-	11	500	0.5	0.19	-	843	510	12	-	-	0.29
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	50	-	0.83	-	-	15.01	745	1.0	0.28	-	1,190	740	20	-	-	0.39
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	10	-	1.1	-	-	13	740	8.0	0.32	-	917	770	10	-	-	0.57
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	10	-	1.1	-	-	13	825	4.0	0.46	-	968	770	22	-	-	0.60
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	10	-	0.86	-	-	14	820	6.0	0.53	-	1,025	670	20	-	-	0.37
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	10	-	1.1	-	-	12	760	6.0	0.52	-	879	860	26	-	-	0.49
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	10	-	1.1	-	-	11	735	7.0	0.58	-	769	1,040	30	-	-	0.41
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	10	-	1.1	-	-	9.5	600	3.0	1.2	-	679	700	14	-	-	0.27
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	10	-	0.85	-	-	15	775	2.0	0.55	-	1,080	880	6	-	-	0.22
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	-	-	10	-	1.4	-	-	13	769	4.0	0.65	-	893	880	8	-	-	0.67
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.7	-	-	10	-	1.7	-	-	8.6	636	2.0	1.7	-	555	960	8	-	-	0.33
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	10	-	0.85	-	-	14	726	1.0	0.63	-	1,045	750	6	-	-	0.18
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	10	-	1.4	-	-	12	694	6.0	0.79	-	799	930	9	-	-	0.53
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	-	-	10	-	1.2	-	-	12	692	4.0	0.64	-	830	820	5	-	-	0.51
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	10	-	0.58	-	-	>15	751	1.0	0.25	-	1,440	600	3	-	-	0.12
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	0.63	-	-	>15	774	1.0	0.26	-	1,470	640	1	-	-	0.20
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	-	-	10	-	1.6	-	-	6.4	532	3.0	2.3	-	410	850	7	-	-	0.26
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	10	-	1.0	-	-	14	755	2.0	0.86	-	1,005	890	5	-	-	0.16
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	1.4	-	-	13	780	3.0	0.97	-	942	930	6	-	-	0.55
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	10	-	0.58	-	-	>15	767	2.0	0.12	-	1,530	530	4	-	-	0.24
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.6	-	-	10	-	1.2	-	-	11	630	6.0	1.3	-	802	830	4	-	-	0.31
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	10	-	1.3	-	-	11	666	4.0	1.3	-	806	830	12	-	-	0.33
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	10	-	0.58	-	-	>15	751	1.0	0.25	-	1,440	600	3	-	-	0.12
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	10	-	0.85	-	-	15	775	2.0	0.55	-	1,080	880	6	-	-	0.22
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	10	-	0.92	-	-	13	636	3.0	0.98	-	970	660	5	-	-	0.16
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	10	-	1.1	-	-	10	562	1.0	1.3	-	749	760	4	-	-	0.22
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	1.1	-	-	11	614	3.0	0.69	-	785	850	8	-	-	0.35
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	-	-	10	-	0.93	-	-	11	581	2.0	0.46	-	767	740	6	-	-	0.32
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	1.0	-	-	9.8	598	2.0	0.74	-	677	800	6	-	-	0.26
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	-	-	10	-	1.1	-	-	12	674	3.0	0.49	-	842	860	11	-	-	0.38
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	0.82	-	-	12	609	2.0	0.39	-	888	660	5	-	-	0.29
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	5	-	1.1	-	-	12	574	1.0	0.85	-	821	620	3	-	-	0.25
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	20	-	1.0	-	-	13	649	3.0	0.53	-	875	700	9	-	-	0.38
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	0.86	-	-	13	607	2.0	0.59	-	902	670	7	-	-	0.24
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	0.73	-	-	15	682	1.0	0.60	-	1,100	580	4	-	-	0.14
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	5	-	0.72	-	-	13	647	1.0	0.75	-	993	590	2	-	-	0.12

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																							
Coarse Processed Kimberlite (continued)																							
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	1.0	-	-	12	624	2.0	0.82	-	814	760	4	-	-	0.24
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	20	-	1.4	-	-	10	561	4.0	0.81	-	602	740	10	-	-	0.35
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.6	-	-	10	-	0.70	-	-	11	559	2.0	0.62	-	771	600	7	-	-	0.34
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.7	-	-	10	-	1.1	-	-	11	583	2.0	0.64	-	806	670	2	-	-	0.23
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.4	-	-	10	-	1.1	-	-	11	604	2.0	0.65	-	830	700	5	-	-	0.30
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	-	-	10	-	1.0	-	-	11	637	3.0	0.63	-	852	740	3	-	-	0.32
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	-	-	10	-	1.1	-	-	11	620	2.0	0.36	-	838	850	9	-	-	0.35
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	10	-	1.2	-	-	10	582	2.0	0.86	-	759	660	6	-	-	0.21
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	10	-	0.91	-	-	13	663	2.0	0.40	-	1,015	690	7	-	-	0.33
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	10	-	1.2	-	-	10	573	1.0	1.0	-	781	710	7	-	-	0.20
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	10	-	1.1	-	-	12	606	2.0	0.85	-	878	670	5	-	-	0.30
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	10	-	1.1	-	-	12	629	1.0	1.0	-	853	790	5	-	-	0.20
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	10	-	1.0	-	-	13	610	2.0	0.53	-	984	620	7	-	-	0.32
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	0.74	-	-	13	597	2.0	0.23	-	1,005	590	9	-	-	0.33
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	20	-	1.1	-	-	11	555	3.0	0.42	-	818	650	10	-	-	0.40
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	5	-	0.73	-	-	15	720	1.0	0.29	-	1,155	840	9	-	-	0.14
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	20	-	1.0	-	-	13	598	2.0	0.48	-	976	620	8	-	-	0.37
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	20	-	1.1	-	-	14	675	3.0	0.39	-	1,000	750	8	-	-	0.43
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	0.67	-	-	16	693	1.0	0.20	-	1,215	680	8	-	-	0.24
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	0.92	-	-	13	617	1.0	0.66	-	976	640	7	-	-	0.19
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	20	-	1.1	-	-	13	633	3.0	0.51	-	976	660	9	-	-	0.37
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	10	-	1.0	-	-	13	608	1.0	0.65	-	909	660	8	-	-	0.27
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	-	-	5	-	1.4	-	-	13	697	1.0	0.66	-	771	1,180	10	-	-	0.13
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	-	-	5	-	1.4	-	-	13	719	1.0	0.70	-	806	1,240	12	-	-	0.14
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	-	-	10	-	1.2	-	-	12	661	1.0	0.87	-	861	890	19	-	-	0.22
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	-	-	10	-	1.2	-	-	13	672	2.0	0.76	-	880	890	8	-	-	0.26
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.7	-	-	5	-	1.7	-	-	9.2	576	0.5	1.4	-	606	950	47	-	-	0.14
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	-	-	5	-	1.7	-	-	9.8	577	0.5	1.4	-	650	950	15	-	-	0.14
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.4	-	-	10	-	1.4	-	-	13	779	0.5	1.1	-	861	920	9	-	-	0.22
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.8	-	-	10	-	1.4	-	-	12	692	0.5	1.1	-	858	900	11	-	-	0.23
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.0	-	-	5	-	1.4	-	-	12	667	2.0	1.0	-	842	900	12	-	-	0.18
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.2	-	-	5	-	1.4	-	-	12	669	2.0	1.0	-	834	910	10	-	-	0.20
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.2	-	-	5	-	1.4	-	-	11	598	2.0	1.3	-	777	880	7	-	-	0.16
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	6.5	-	-	5	-	1.4	-	-	11	607	1.0	1.1	-	763	810	8	-	-	0.15
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	-	-	20	-	1.3	-	-	12	683	2.0	0.83	-	844	860	11	-	-	0.27
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.8	-	-	10	-	1.3	-	-	13	677	2.0	0.83	-	840	890	10	-	-	0.26
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	-	-	10	-	1.6	-	-	11	710	2.0	1.5	-	844	1,040	16	-	-	0.21
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	-	-	10	-	1.6	-	-	12	711	1.0	1.4	-	898	1,000	9	-	-	0.18

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																							
Coarse Processed Kimberlite (continued)																							
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	-	-	10	-	1.6	-	-	12	714	2.0	1.2	-	912	940	13	-	-	0.27
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	-	-	10	-	1.4	-	-	11	642	2.0	1.1	-	777	890	11	-	-	0.26
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.6	-	-	10	-	1.6	-	-	12	698	2.0	1.3	-	897	1,020	7	-	-	0.20
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.7	-	-	5	-	1.6	-	-	12	712	2.0	1.4	-	882	1,050	4	-	-	0.19
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	-	-	10	-	1.4	-	-	13	735	1.0	0.96	-	800	950	7	-	-	0.25
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	-	-	5	-	1.4	-	-	13	721	0.5	1.1	-	800	960	6	-	-	0.22
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.5	-	-	5	-	1.5	-	-	14	728	1.0	1.1	-	869	980	6	-	-	0.19
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	-	-	5	-	1.5	-	-	13	702	0.5	1.1	-	807	970	7	-	-	0.17
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.5	-	-	10	-	1.4	-	-	13	673	1.0	1.0	-	743	930	8	-	-	0.23
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	-	-	10	-	1.5	-	-	13	742	0.5	1.1	-	778	1,020	6	-	-	0.23
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.4	-	-	5	-	1.5	-	-	13	702	0.5	1.1	-	794	1,020	7	-	-	0.20
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	-	-	5	-	1.6	-	-	14	721	0.5	1.1	-	817	1,030	10	-	-	0.21
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	-	-	10	-	1.1	-	-	16	765	2.1	0.48	-	1,215	710	7	-	-	0.29
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	-	-	30	-	1.1	-	-	16	735	1.9	0.50	-	1,210	710	6	-	-	0.26
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.4	-	-	10	-	1.4	-	-	12	657	1.0	0.91	-	782	950	7	-	-	0.17
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	-	-	10	-	1.4	-	-	13	669	1.0	0.76	-	823	960	9	-	-	0.20
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	5	-	1.5	-	-	13	722	1.0	1.3	-	827	1,010	16	-	-	0.10
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	-	-	20	-	1.5	-	-	12	647	0.5	1.4	-	806	940	11	-	-	0.07
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	-	-	5	-	1.7	-	-	12	708	1.0	1.5	-	834	1,050	4	-	-	0.12
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	-	-	5	-	1.7	-	-	13	706	1.0	1.4	-	858	1,030	7	-	-	0.13
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	-	-	50	-	1.6	-	-	14	744	0.5	0.95	-	775	1,090	5	-	-	0.15
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.7	-	-	50	-	1.6	-	-	14	744	1.0	0.97	-	776	1,040	5	-	-	0.15
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	-	-	10	-	1.6	-	-	14	741	1.0	1.2	-	962	1,000	4	-	-	0.15
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	-	-	5	-	1.5	-	-	14	733	1.0	1.2	-	951	1,000	1	-	-	0.12
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	-	-	5	-	1.6	-	-	13	738	1.0	1.1	-	958	1,060	6	-	-	0.10
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	-	-	5	-	1.6	-	-	13	720	1.0	1.1	-	930	1,050	4	-	-	0.10
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	-	-	-	-	1.6	-	-	12	664	1.0	1.7	-	786	1,050	6	-	-	0.07
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.5	-	-	-	-	1.6	-	-	12	634	1.0	1.6	-	759	970	6	-	-	0.06
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.6	-	-	-	-	1.6	-	-	13	720	0.5	1.4	-	870	970	9	-	-	0.06
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.7	-	-	-	-	1.5	-	-	13	682	0.5	1.4	-	839	930	10	-	-	0.05
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	-	-	-	-	1.7	-	-	12	690	2.0	1.5	-	804	1,040	12	-	-	0.11
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	-	-	-	-	1.7	-	-	12	692	1.0	1.4	-	827	950	12	-	-	0.10
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	-	-	-	-	1.5	-	-	12	678	0.5	1.3	-	812	1,010	7	-	-	0.08
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	-	-	-	-	1.5	-	-	12	671	0.5	1.3	-	815	1,000	4	-	-	0.08
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.6	-	-	-	-	1.6	-	-	14	716	0.5	1.3	-	874	1,040	11	-	-	0.07
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	-	-	0.02	-	1.4	-	-	12	640	1.0	0.99	-	909	1,150	22	-	-	0.15
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	-	-	0.05	-	1.5	-	-	12	666	0.5	1.1	-	817	1,090	7	-	-	0.08
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.6	-	-	0.05	-	1.7	-	-	11	650	0.5	1.5	-	742	1,020	2	-	-	0.06

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	Price Crustal Abundances																			
		From	To		Paste pH	Ge	Hf	0.08	In	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035	
					unit	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																								
Coarse Processed Kimberlite (continued)																								
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	-	-	0.05	-	1.7	-	-	12	668	1.0	1.1	-	813	1,110	6	-	-	0.07	
CK 00-11-20	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
CK 00-11-21	-	-	-	Coarse Processed Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
CK 00-11-24	-	-	-	Coarse Processed Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
CK 00-11-25	-	-	-	Coarse Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
CKC 3SS 11- 26 3	-	-	-	Coarse Processed Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Median					8.4	-	-	10	-	1.1	-	-	12	692	1.0	0.77	-	861	860	8	-	-	0.24	
Minimum					6.5	-	-	0.02	-	0.47	-	-	6.4	500	0.5	0.12	-	410	510	1	-	-	0.05	
Maximum					9.8	-	-	50	-	1.7	-	-	16	880	11.0	2.3	-	1,530	1,240	47	-	-	0.69	
Count					189	0	0	146	0	155	0	0	151	155	155	155	0	155	155	155	0	0	133	
Fine Processed Kimberlite																								
FK 13-SEP-04	-	-	-	Fine Processed Kimberlite	8.1	-	-	0.01	-	0.32	-	-	18	742	2.0	0.06	-	1,655	470	3	-	-	0.15	
FK 3-JAN-04	-	-	-	Fine Processed Kimberlite	8.1	-	-	0.01	-	0.51	-	-	19	782	2.0	0.16	-	1,700	550	7	-	-	0.18	
FK 7-FEB-04	-	-	-	Fine Processed Kimberlite	8.1	-	-	0.01	-	0.25	-	-	21	763	1.0	0.04	-	1,870	330	3	-	-	0.10	
FK 4-APR-04	-	-	-	Fine Processed Kimberlite	8.1	-	-	0.01	-	0.34	-	-	20	768	1.0	0.09	-	1,765	370	4	-	-	0.17	
FK 7-JUN-04	-	-	-	Fine Processed Kimberlite	8.1	-	-	0.01	-	0.35	-	-	19	747	1.0	0.09	-	1,695	410	6	-	-	0.15	
FK 5-JUL-04	-	-	-	Fine Processed Kimberlite	8.1	-	-	0.01	-	0.56	-	-	18	770	2.0	0.12	-	1,600	600	8	-	-	0.28	
FK 6-AUG-04	-	-	-	Fine Processed Kimberlite	7.9	-	-	0.02	-	0.94	-	-	12	679	5.0	0.14	-	1,045	970	11	-	-	0.57	
FK 8-AUG-04	-	-	-	Fine Processed Kimberlite	8.2	-	-	0.01	-	0.37	-	-	17	711	1.0	0.07	-	1,465	650	7	-	-	0.13	
FK 11-AUG-04	-	-	-	Fine Processed Kimberlite	7.9	-	-	0.02	-	0.93	-	-	12	654	4.0	0.13	-	1,010	970	14	-	-	0.49	
FK 12-AUG-04	-	-	-	Fine Processed Kimberlite	8.2	-	-	0.01	-	0.43	-	-	14	635	2.0	0.07	-	1,190	530	8	-	-	0.35	
FK 15-AUG-04	-	-	-	Fine Processed Kimberlite	8.0	-	-	0.02	-	0.82	-	-	15	725	4.0	0.11	-	1,270	840	13	-	-	0.41	
FK 16-AUG-04	-	-	-	Fine Processed Kimberlite	8.1	-	-	0.02	-	0.72	-	-	14	685	3.0	0.09	-	1,200	740	12	-	-	0.35	
FK 23-AUG-04	-	-	-	Fine Processed Kimberlite	8.1	-	-	0.02	-	0.60	-	-	16	651	2.0	0.10	-	1,400	520	4	-	-	0.60	
FK 28-AUG-04	-	-	-	Fine Processed Kimberlite	8.2	-	-	0.01	-	0.58	-	-	17	730	3.0	0.09	-	1,490	610	5	-	-	0.30	
FK 31-AUG-04	-	-	-	Fine Processed Kimberlite	8.3	-	-	0.01	-	0.44	-	-	16	737	2.0	0.51	-	1,350	480	5	-	-	0.19	
FK 12-SEP-04	-	-	-	Fine Processed Kimberlite	8.2	-	-	0.01	-	0.30	-	-	18	715	1.0	0.06	-	1,535	420	8	-	-	0.12	
FK 20-SEP-04	-	-	-	Fine Processed Kimberlite	8.3	-	-	0.01	-	0.35	-	-	19	753	1.0	0.07	-	1,685	410	4	-	-	0.15	
FK 1-OCT-04	-	-	-	Fine Processed Kimberlite	8.1	-	-	0.03	-	0.85	-	-	15	695	4.0	0.10	-	1,245	830	12	-	-	0.47	
FK 18-OCT-04	-	-	-	Fine Processed Kimberlite	8.2	-	-	0.02	-	0.66	-	-	15	688	3.0	0.12	-	1,315	680	11	-	-	0.37	
FK 25-OCT-04	-	-	-	Fine Processed Kimberlite	8.1	-	-	0.01	-	0.75	-	-	15	753	2.0	0.19	-	1,295	700	13	-	-	0.29	
FINE KIMBERLITE 30-OCT-04	-	-	-	Fine Processed Kimberlite	8.1	-	-	0.01	-	0.59	-	-	14	580	2.0	0.13	-	1,175	490	7	-	-	0.32	
FINE KIMBERLITE 25-DEC-04	-	-	-	Fine Processed Kimberlite	8.2	-	-	0.02	-	0.66	-	-	13	604	2.0	0.12	-	1,105	610	3	-	-	0.55	
FINE KIMBERLITE 23-JAN-05	-	-	-	Fine Processed Kimberlite	8.2	-	-	0.01	-	0.68	-	-	14	648	2.0	0.14	-	1,145	630	10	-	-	0.30	
FINE KIMBERLITE 25-FEB-05	-	-	-	Fine Processed Kimberlite	8.2	-	-	0.01	-	0.61	-	-	14	609	2.0	0.11	-	1,185	510	7	-	-	0.34	
FINE KIMBERLITE 24-MAR-05	-	-	-	Fine Processed Kimberlite	8.3	-	-	0.02	-	0.73	-	-	11	568	6.0	0.19	-	937	600	6	-	-	0.36	
FINE KIMBERLITE 24-APR-05	-	-	-	Fine Processed Kimberlite	7.9	-	-	0.02	-	0.89	-	-	12	613	4.0	0.12	-	975	680	4	-	-	0.37	
FINE KIMBERLITE 25-MAY-05	-	-	-	Fine Processed Kimberlite	8.2	-	-	0.01	-	0.63	-	-	14	628	2.0	0.14	-	1,185	560	5	-	-	0.29	

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																							
<i>Fine Processed Kimberlite (continued)</i>																							
FINE KIMBERLITE 23-JUN-05	-	-	-	Fine Processed Kimberlite	8.3	-	-	0.01	-	0.43	-	-	17	678	2.0	0.08	-	1,410	460	2	-	-	0.21
FINE KIMBERLITE 24-JUL-05	-	-	-	Fine Processed Kimberlite	8.3	-	-	0.01	-	0.42	-	-	18	752	2.0	0.07	-	1,505	550	2	-	-	0.18
FINE KIMBERLITE 23-AUG-05	-	-	-	Fine Processed Kimberlite	8.2	-	-	0.01	-	0.60	-	-	17	722	4.0	0.10	-	1,415	600	4	-	-	0.33
FINE KIMBERLITE 28-SEP-05A	-	-	-	Fine Processed Kimberlite	8.4	-	-	0.01	-	0.69	-	-	16	672	3.0	0.24	-	1,310	530	3	-	-	0.29
FINE KIMBERLITE 28-SEP-05B	-	-	-	Fine Processed Kimberlite	8.5	-	-	0.01	-	0.80	-	-	16	718	2.0	0.35	-	1,380	590	5	-	-	0.32
FINE KIMBERLITE 24-OCT-05	-	-	-	Fine Processed Kimberlite	8.0	-	-	0.01	-	0.67	-	-	14	644	3.0	0.12	-	1,110	560	2	-	-	0.32
FINE KIMBERLITE 28-NOV-05A	-	-	-	Fine Processed Kimberlite	8.5	-	-	0.01	-	1.1	-	-	13	681	4.0	0.40	-	1,115	920	4	-	-	0.30
FINE KIMBERLITE 28-NOV-05B	-	-	-	Fine Processed Kimberlite	8.3	-	-	0.01	-	1.1	-	-	13	676	3.0	0.40	-	1,115	910	7	-	-	0.30
FINE KIMBERLITE 23-DEC-05	-	-	-	Fine Processed Kimberlite	8.4	-	-	0.01	-	0.88	-	-	15	702	2.0	0.23	-	1,200	740	5	-	-	0.33
FINE KIMBERLITE PPD	-	-	-	Fine Processed Kimberlite	8.2	-	-	0.01	-	0.33	-	-	19	703	2.0	0.06	-	1,655	410	2	-	-	0.12
FK 00-11- 09 15	-	-	-	Fine Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FK 00-11- 20 27	-	-	-	Fine Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Median					8.2	-	-	0.01	-	0.61	-	-	15	695	2.0	0.12	-	1,310	590	5	-	-	0.30
Minimum					7.9	-	-	0.01	-	0.25	-	-	11	568	1.0	0.04	-	937	330	2	-	-	0.10
Maximum					8.5	-	-	0.03	-	1.1	-	-	21	782	6.0	0.51	-	1,870	970	14	-	-	0.60
Count					39	0	0	37	0	37	0	0	37	37	37	37	0	37	37	37	0	0	37
Metasediment																							
<i>Beartooth</i>																							
13	BDC-05	48.01	48.44	Metasediment	9.9	-	-	-	-	2.4	-	-	2.2	250	4.0	0.10	-	70	210	6	-	-	-
BDC 2-41.76	BDC 2	41.76	46.16	Metasediment	-	-	-	5	-	1.9	-	-	2.4	530	1.0	2.2	-	109	280	20	-	-	0.17
BDC 2-50.9	BDC 2	50.9	56	Metasediment	-	-	-	5	-	3.1	-	-	2.4	525	1.0	2.5	-	102	80	14	-	-	0.20
BDC 5-41.76	BDC 5	41.76	47.85	Metasediment	-	-	-	5	-	1.8	-	-	2.2	475	2.0	2.0	-	104	310	18	-	-	0.23
BDC 5-49.47	BDC 5	49.47	55.04	Metasediment	-	-	-	5	-	1.8	-	-	2.1	410	7.0	2.5	-	89	560	12	-	-	0.48
BDC 5-55.04	BDC 5	55.04	58.9	Metasediment	-	-	-	5	-	2.0	-	-	3.1	525	3.0	2.2	-	147	460	4	-	-	0.31
Median					9.9	-	-	5	-	1.9	-	-	2.3	500	2.5	2.2	-	103	295	13	-	-	0.23
Minimum					9.9	-	-	5	-	1.8	-	-	2.1	250	1.0	0.10	-	70	80	4	-	-	0.17
Maximum					9.9	-	-	5	-	3.1	-	-	3.1	530	7.0	2.5	-	147	560	20	-	-	0.48
Count					1	0	0	5	0	6	0	0	6	6	6	6	0	6	6	6	0	0	5
Koala																							
KS 390-25 1a	-	-	-	Metasediment	9.7	-	-	5	-	1.7	-	-	1.8	420	0.5	3.0	-	46	1,000	8	-	-	0.01
KS 390-25 2a	-	-	-	Metasediment	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-23 1a	-	-	-	Metasediment	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-23 2a	-	-	-	Metasediment	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-24-1a	-	-	-	Metasediment	9.6	-	-	5	-	2.3	-	-	2.1	415	0.5	3.0	-	50	1,110	8	-	-	0.03
KS-390-24-1a	-	-	-	Metasediment	9.3	-	-	5	-	1.7	-	-	1.8	380	1.0	2.9	-	45	1,000	8	-	-	0.04
KS-390-24-2a	-	-	-	Metasediment	9.6	-	-	5	-	2.1	-	-	1.7	365	0.5	3.1	-	42	900	10	-	-	0.04
KS-390-24-2a	-	-	-	Metasediment	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-26T-1a	-	-	-	Metasediment	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Metasediment (continued)																							
Koala (continued)																							
KS-390-26T-2a	-	-	-	Metasediment	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-27-1a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-27-2a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-37-1a	-	-	-	Metasediment	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-37-2a	-	-	-	Metasediment	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-38-1a	-	-	-	Metasediment	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-38-2a	-	-	-	Metasediment	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS 375-03 1a	-	-	-	Metasediment	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS 375-03 2a	-	-	-	Metasediment	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS 375-05 1a	-	-	-	Metasediment	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS 375-05 2a	-	-	-	Metasediment	9.4	-	-	5	-	1.8	-	-	1.3	205	1.0	4.0	-	27	600	6	-	-	0.04
KS-375-09-1a	-	-	-	Metasediment	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-09-2a	-	-	-	Metasediment	8.8	-	-	5	-	1.8	-	-	1.8	245	1.0	3.5	-	80	540	10	-	-	0.04
KS-375-10-1a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-10-2a	-	-	-	Metasediment	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-11-1a	-	-	-	Metasediment	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-11-2a	-	-	-	Metasediment	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-12-1a	-	-	-	Metasediment	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-12-2a	-	-	-	Metasediment	9.5	-	-	5	-	1.7	-	-	1.0	225	1.0	4.1	-	22	620	12	-	-	0.01
KS-375-14-1a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-14-1a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-14-2a	-	-	-	Metasediment	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-14-2a	-	-	-	Metasediment	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-20-1A	-	-	-	Metasediment	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-20-2A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-22REV1-1A	-	-	-	Metasediment	8.9	-	-	5	-	1.6	-	-	1.1	250	0.5	2.5	-	27	680	8	-	-	0.01
KS-375-22REV1-2A	-	-	-	Metasediment	8.2	-	-	5	-	2.0	-	-	1.4	295	0.5	3.2	-	37	760	10	-	-	0.03
KS-360-05-1A	-	-	-	Metasediment	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-360-05-2A	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Median					9.5	-	-	5	-	1.8	-	-	1.7	295	0.5	3.1	-	42	760	8	-	-	0.03
Minimum					8.2	-	-	5	-	1.6	-	-	1.0	205	0.5	2.5	-	22	540	6	-	-	0.01
Maximum					9.8	-	-	5	-	2.3	-	-	2.1	420	1.0	4.1	-	80	1,110	12	-	-	0.04
Count					38	0	0	9	0	9	0	0	9	9	9	9	0	9	9	9	0	0	9
Misery																							
MGT-66 45-48	-	-	-	Metasediment	9.2	-	-	0.005	-	1.3	17	-	1.8	387	1.5	0.028	-	98	0	3	-	-	0.15
MGT-66 50-53	-	-	-	Metasediment	9.4	-	-	0.005	-	1.5	16	-	1.8	476	1.7	0.026	-	97	0	3	-	-	0.15
MGT-66 81.03-82.28	-	-	-	Metasediment	9.4	-	-	0.005	-	1.4	19	-	1.4	383	1.4	0.035	-	67	0	4	-	-	0.13
MGT-66 100.58-102.04	-	-	-	Metasediment	9.1	-	-	0.005	-	1.0	14	-	2.2	403	2.2	0.025	-	90	0	4	-	-	0.31

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
					unit	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	
Metasediment (continued)																							
Misery (continued)																							
MGT-49 273-276	-	-	-	Metasediment	9.2	-	-	0.005	-	1.8	13	-	2.0	514	1.8	0.039	-	94	0	4	-	-	0.15
MDC-4 15.02	-	-	-	Metasediment	7.4	-	-	5	-	2.7	-	-	1.8	375	3.0	1.7	-	81	580	18	-	-	0.15
MDC-4 26.4	-	-	-	Metasediment	8.7	-	-	5	-	2.6	-	-	1.8	405	4.0	1.9	-	83	570	14	-	-	0.16
MDC-4 31.5	-	-	-	Metasediment	9.1	-	-	5	-	2.0	-	-	1.5	360	3.0	2.2	-	72	640	18	-	-	0.16
MDC-4 37.06	-	-	-	Metasediment	8.9	-	-	5	-	2.7	-	-	1.9	405	3.0	1.9	-	88	620	18	-	-	0.15
MDC-4 46.8	-	-	-	Metasediment	8.4	-	-	5	-	2.9	-	-	2.0	435	3.0	1.8	-	90	600	18	-	-	0.17
MDC-4 53.4	-	-	-	Metasediment	8.3	-	-	5	-	2.5	-	-	1.3	310	3.0	2.4	-	57	770	18	-	-	0.12
MDC-4 59.04	-	-	-	Metasediment	8.9	-	-	30	-	2.7	-	-	1.9	385	5.0	1.6	-	90	520	20	-	-	0.29
MDC-4 70.78	-	-	-	Metasediment	9.2	-	-	30	-	2.7	-	-	1.6	375	4.0	2.2	-	71	560	24	-	-	0.19
MDC-6 14.32	-	-	-	Metasediment	9.6	-	-	5	-	2.8	-	-	1.4	485	3.0	2.1	-	63	960	16	-	-	0.13
MDC-6 75.69	-	-	-	Metasediment	9.4	-	-	5	-	2.5	-	-	0.96	360	2.0	2.2	-	45	670	18	-	-	0.10
MDC-6 104.66	-	-	-	Metasediment	9.0	-	-	5	-	2.4	-	-	1.0	330	1.0	1.9	-	46	550	20	-	-	0.11
MDC-6 144.7	-	-	-	Metasediment	9.1	-	-	5	-	2.1	-	-	1.3	410	1.0	2.2	-	69	610	22	-	-	0.23
MDC-6 190	-	-	-	Metasediment	9.1	-	-	5	-	2.2	-	-	1.4	420	3.0	1.9	-	66	400	12	-	-	0.17
MDC-8 18.85	-	-	-	Metasediment	8.3	-	-	5	-	1.3	-	-	1.3	490	3.0	1.1	-	67	520	18	-	-	0.33
MDC-8 46.48	-	-	-	Metasediment	9.3	-	-	5	-	1.8	-	-	1.4	405	3.0	1.1	-	61	490	18	-	-	0.20
MDC-8 157.28	-	-	-	Metasediment	8.8	-	-	5	-	1.9	-	-	1.5	390	2.0	2.0	-	72	530	16	-	-	0.15
MDC-4 25.7	-	-	-	Metasediment	9.1	-	-	5	-	2.8	-	-	1.2	365	3.0	2.2	-	49	790	22	-	-	0.06
MDC-4 87.47	-	-	-	Metasediment	9.3	-	-	5	-	2.5	-	-	1.5	405	2.0	2.1	-	62	830	20	-	-	0.14
MS 450-30 A	-	-	-	Metasediment	9.3	-	-	5	-	1.8	-	-	0.24	140	0.5	4.0	-	1	240	18	-	-	-
MS 450-30 B	-	-	-	Metasediment	9.1	-	-	5	-	2.0	-	-	0.23	140	0.5	3.7	-	3	220	18	-	-	-
MS 450-34-1A	-	-	-	Metasediment	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 450-34-2A	-	-	-	Metasediment	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 450-35-2A	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS-440-E-01	-	-	-	Metasediment	9.3	-	-	0.005	-	2.4	20	-	1.7	412	1.0	1.8	-	79	830	6	-	-	0.20
MS-440-E-02	-	-	-	Metasediment	9.2	-	-	0.005	-	2.2	30	-	1.6	420	1.0	2.3	-	72	590	15	-	-	0.19
MS-440-SE-01	-	-	-	Metasediment	8.7	-	-	0.005	-	2.7	20	-	1.7	428	1.0	1.9	-	78	600	8	-	-	0.23
MPS 440-01 A	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A1	-	-	-	Metasediment	8.1	-	-	5	-	2.7	-	-	1.5	410	0.5	1.4	-	68	500	12	-	-	-
MPS 440-01-05 A2	-	-	-	Metasediment	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A3	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A4	-	-	-	Metasediment	8.3	-	-	5	-	2.4	-	-	1.4	350	0.5	1.7	-	62	460	22	-	-	-
MPS 440-01-05 A5	-	-	-	Metasediment	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A6	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A7	-	-	-	Metasediment	8.6	-	-	5	-	2.1	-	-	1.4	405	0.5	2.1	-	65	460	16	-	-	-
MPS 440-01-05 A8	-	-	-	Metasediment	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-06 A	-	-	-	Metasediment	8.5	-	-	5	-	3.1	-	-	1.4	340	0.5	1.8	-	62	470	16	-	-	-
MPS 440-06 AA	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Metasediment (continued)																							
Misery (continued)																							
MPS 440-06 AAA	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-01 1A	-	-	-	Metasediment	8.4	-	-	5	-	2.6	-	-	0.99	315	1.0	2.0	-	42	660	12	-	-	-
MS 440-01 2A	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-01 2AA	-	-	-	Metasediment	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-10 1A	-	-	-	Metasediment	8.5	-	-	5	-	2.3	-	-	0.89	270	0.5	2.3	-	38	510	16	-	-	-
MS 440-10 2A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-13 1A	-	-	-	Metasediment	7.8	-	-	5	-	2.7	-	-	1.3	335	0.5	2.0	-	50	590	20	-	-	-
MS 440-13 2A	-	-	-	Metasediment	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-16 A	-	-	-	Metasediment	9.3	-	-	5	-	2.4	-	-	1.1	350	1.0	2.1	-	58	1,000	12	-	-	-
MS 440-16 B	-	-	-	Metasediment	8.7	-	-	5	-	2.6	-	-	1.6	425	0.5	1.8	-	70	550	6	-	-	-
MS 440-18 1A	-	-	-	Metasediment	8.4	-	-	5	-	1.4	-	-	1.8	380	0.5	1.7	-	78	610	10	-	-	-
MS 440-19 1A	-	-	-	Metasediment	7.6	-	-	5	-	2.0	-	-	1.6	380	1.0	1.9	-	74	530	10	-	-	-
MS 440-19 2A	-	-	-	Metasediment	7.7	-	-	5	-	3.0	-	-	1.7	320	0.5	1.0	-	76	470	4	-	-	-
MS 440-21 1A	-	-	-	Metasediment	7.1	-	-	5	-	2.2	-	-	1.1	315	1.0	2.2	-	46	550	14	-	-	-
MS 440-21 2A	-	-	-	Metasediment	7.2	-	-	5	-	2.2	-	-	0.97	285	1.0	2.5	-	43	530	14	-	-	-
MS 440-23 1A	-	-	-	Metasediment	8.7	-	-	5	-	2.5	-	-	1.4	345	1.0	1.9	-	62	540	16	-	-	-
MS 440-27 28-1A	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-27 28-2A	-	-	-	Metasediment	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-27-1A	-	-	-	Metasediment	7.8	-	-	5	-	1.9	-	-	2.8	550	2.0	0.73	-	113	1,270	12	-	-	-
MS 440-27-2A	-	-	-	Metasediment	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-29-1A	-	-	-	Metasediment	8.2	-	-	5	-	2.4	-	-	1.6	410	1.0	1.8	-	82	540	16	-	-	-
MS 440-29-2A	-	-	-	Metasediment	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-30-1A	-	-	-	Metasediment	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-30-2A	-	-	-	Metasediment	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-31-1A	-	-	-	Metasediment	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-31-2A	-	-	-	Metasediment	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-33-1A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-33-2A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-35-1A	-	-	-	Metasediment	8.5	-	-	5	-	2.1	-	-	0.96	590	1.0	3.4	-	20	480	14	-	-	-
MS 440-36-1A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-36-2A	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 440-38-1A	-	-	-	Metasediment	8.7	-	-	5	-	3.1	-	-	1.4	360	2.0	2.6	-	45	670	38	-	-	-
MS- 440-38-2A	-	-	-	Metasediment	7.7	-	-	5	-	3.6	-	-	0.49	215	0.5	2.8	-	14	890	20	-	-	-
MS- 440-43-1A	-	-	-	Metasediment	8.3	-	-	5	-	3.0	-	-	1.8	515	1.0	2.9	-	88	700	16	-	-	-
MS- 440-43-2A	-	-	-	Metasediment	7.3	-	-	5	-	3.0	-	-	0.84	320	3.0	2.3	-	29	820	14	-	-	-
MS K 440 46 1A	-	-	-	Metasediment	8.2	-	-	5	-	2.0	-	-	1.8	395	2.0	1.6	-	78	640	10	-	-	0.15
MS K 440 46 1B	-	-	-	Metasediment	8.3	-	-	5	-	2.0	-	-	1.6	395	0.5	1.6	-	66	540	10	-	-	0.19
MS- 440-49-1A	-	-	-	Metasediment	7.3	-	-	5	-	2.1	-	-	1.3	355	0.5	1.9	-	61	470	12	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																							
Misery (continued)																							
MS- 440-49-2A	-	-	-	Metasediment	7.8	-	-	5	-	2.7	-	-	1.5	410	1.0	2.5	-	70	760	14	-	-	-
MS- 440-52-1A	-	-	-	Metasediment	7.6	-	-	5	-	2.3	-	-	0.84	285	0.5	3.3	-	29	600	12	-	-	-
MS- 440-52-2A	-	-	-	Metasediment	7.8	-	-	5	-	2.2	-	-	0.84	280	0.5	3.4	-	28	480	10	-	-	-
MS- 440-64-1A	-	-	-	Metasediment	8.7	-	-	5	-	2.8	-	-	1.6	460	1.0	2.9	-	77	630	20	-	-	0.14
MS- 440-64-2A	-	-	-	Metasediment	8.6	-	-	5	-	2.5	-	-	1.4	370	0.5	1.9	-	68	540	12	-	-	0.07
MS- 440-69-1A	-	-	-	Metasediment	8.0	-	-	5	-	2.9	-	-	1.8	450	1.0	1.5	-	75	550	12	-	-	0.14
MS- 440-69-2A	-	-	-	Metasediment	7.9	-	-	5	-	2.5	-	-	1.8	465	0.5	1.9	-	88	620	16	-	-	0.18
MS-440-71-1A	-	-	-	Metasediment	8.4	-	-	5	-	2.1	-	-	1.5	465	5.0	1.7	-	68	520	18	-	-	0.11
MS-440-71-2A	-	-	-	Metasediment	8.5	-	-	5	-	2.4	-	-	1.6	365	6.0	1.6	-	73	520	14	-	-	0.17
MS-440-74-1A	-	-	-	Metasediment	8.0	-	-	5	-	3.5	-	-	1.7	315	7.0	0.75	-	52	480	20	-	-	0.03
MS-440-74-2A	-	-	-	Metasediment	7.9	-	-	5	-	2.4	-	-	1.4	380	4.0	1.5	-	60	490	14	-	-	0.08
MS-440-75-1A	-	-	-	Metasediment	7.7	-	-	5	-	2.3	-	-	1.0	330	2.0	2.4	-	40	500	16	-	-	0.02
MS-440-75-2A	-	-	-	Metasediment	7.5	-	-	5	-	1.9	-	-	1.3	330	4.0	1.9	-	49	410	10	-	-	0.06
MS-430-NW-01	-	-	-	Metasediment	8.3	-	-	0.005	-	3.0	20	-	1.6	423	0.5	1.8	-	70	670	9	-	-	0.18
MS-430-NW-02	-	-	-	Metasediment	8.2	-	-	0.005	-	3.1	30	-	1.5	421	1.0	1.8	-	70	720	11	-	-	0.20
MS-430-NW-03	-	-	-	Metasediment	8.3	-	-	0.005	-	3.0	20	-	1.6	435	1.0	1.9	-	72	670	9	-	-	0.18
MS- 430-01-1A	-	-	-	Metasediment	7.7	-	-	5	-	3.4	-	-	1.9	265	2.0	0.69	-	45	400	6	-	-	-
MS- 430-01-2A	-	-	-	Metasediment	7.8	-	-	5	-	3.4	-	-	2.4	260	1.0	1.4	-	76	540	8	-	-	-
MS- 430-02-1A	-	-	-	Metasediment	7.8	-	-	5	-	1.4	-	-	13	855	0.5	0.05	-	963	1,520	10	-	-	-
MS- 430-02-2A	-	-	-	Metasediment	8.2	-	-	5	-	2.9	-	-	2.8	440	1.0	1.5	-	141	520	14	-	-	-
MS- 430-03-1A	-	-	-	Metasediment	8.1	-	-	5	-	2.5	-	-	1.8	405	0.5	2.6	-	80	560	14	-	-	-
MS- 430-03-2A	-	-	-	Metasediment	8.3	-	-	5	-	2.4	-	-	3.0	440	2.0	2.3	-	181	710	12	-	-	-
MS- 430-04-1A	-	-	-	Metasediment	8.3	-	-	5	-	2.1	-	-	7.8	700	1.0	1.5	-	572	1,270	14	-	-	-
MS- 430-04-2A	-	-	-	Metasediment	8.4	-	-	5	-	2.5	-	-	1.8	460	0.5	1.6	-	73	600	12	-	-	-
MS- 430-05-1A	-	-	-	Metasediment	8.3	-	-	5	-	2.1	-	-	7.7	725	0.5	1.7	-	567	1,240	12	-	-	-
MS- 430-05-2A	-	-	-	Metasediment	8.0	-	-	5	-	2.5	-	-	1.7	415	1.0	1.6	-	69	530	12	-	-	-
MS- 430-06-1A	-	-	-	Metasediment	8.1	-	-	5	-	2.8	-	-	1.9	410	1.0	1.7	-	88	520	12	-	-	-
MS- 430-06-2A	-	-	-	Metasediment	8.1	-	-	5	-	3.0	-	-	2.1	405	4.0	1.9	-	85	540	12	-	-	-
MS- 430-07-1A	-	-	-	Metasediment	8.6	-	-	5	-	2.9	-	-	2.1	450	0.5	1.8	-	81	520	12	-	-	-
MS- 430-07-2A	-	-	-	Metasediment	8.4	-	-	5	-	2.0	-	-	1.7	400	0.5	1.8	-	65	560	14	-	-	-
MS- 430-08-1A	-	-	-	Metasediment	8.5	-	-	5	-	2.9	-	-	2.0	465	1.0	2.0	-	86	580	14	-	-	-
MS- 430-08-2A	-	-	-	Metasediment	8.6	-	-	5	-	2.4	-	-	1.9	420	0.5	2.2	-	80	530	12	-	-	-
MS- 430-09-1A	-	-	-	Metasediment	8.5	-	-	5	-	2.6	-	-	1.8	435	1.0	2.7	-	63	620	14	-	-	-
MS- 430-09-2A	-	-	-	Metasediment	8.6	-	-	5	-	3.3	-	-	1.6	365	0.5	2.6	-	70	670	18	-	-	-
MS 430 10 1A	-	-	-	Metasediment	9.2	-	-	5	-	1.7	-	-	1.1	330	4.0	2.6	-	53	440	18	-	-	0.18
MS 430 10 2A	-	-	-	Metasediment	9.4	-	-	5	-	1.7	-	-	1.4	360	3.0	2.5	-	67	620	18	-	-	0.22
MS 430 12 1A	-	-	-	Metasediment	9.0	-	-	5	-	1.7	-	-	1.5	350	3.0	2.4	-	72	520	12	-	-	0.17
MS 430 12 2A	-	-	-	Metasediment	9.0	-	-	5	-	2.1	-	-	1.6	405	1.0	2.2	-	76	510	28	-	-	0.13

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Metasediment (continued)																							
Misery (continued)																							
MS 430 14 1A	-	-	-	Metasediment	8.5	-	-	5	-	3.3	-	-	1.9	465	1.0	1.2	-	86	530	24	-	-	0.11
MS 430 14 2A	-	-	-	Metasediment	8.7	-	-	5	-	2.7	-	-	1.8	360	1.0	1.6	-	71	500	16	-	-	0.10
MS 430 16 1A	-	-	-	Metasediment	8.7	-	-	5	-	2.1	-	-	1.6	355	2.0	2.0	-	73	500	18	-	-	0.11
MS 430 16 2A	-	-	-	Metasediment	8.4	-	-	5	-	3.2	-	-	1.6	315	3.0	0.90	-	77	470	10	-	-	0.04
MS 430 17 1A	-	-	-	Metasediment	9.0	-	-	5	-	1.5	-	-	2.1	990	4.0	2.2	-	63	700	6	-	-	0.13
MS 430 17 2A	-	-	-	Metasediment	9.0	-	-	5	-	1.6	-	-	2.0	810	4.0	2.1	-	60	630	8	-	-	0.08
MS 430 22 1A	-	-	-	Metasediment	7.9	-	-	5	-	2.5	-	-	1.3	355	3.0	1.4	-	78	450	16	-	-	0.25
MS 430 22 2A	-	-	-	Metasediment	9.0	-	-	5	-	1.3	-	-	1.5	390	4.0	2.2	-	72	590	14	-	-	0.09
MS 430 24 1A	-	-	-	Metasediment	8.7	-	-	5	-	2.8	-	-	1.6	435	4.0	1.9	-	80	610	10	-	-	0.30
MS 430 24 2A	-	-	-	Metasediment	8.7	-	-	5	-	2.6	-	-	1.6	425	3.0	2.0	-	73	600	18	-	-	0.26
MS 430 26 1A	-	-	-	Metasediment	8.6	-	-	5	-	2.2	-	-	1.9	750	4.0	1.9	-	59	780	12	-	-	0.10
MS 430 26 2A	-	-	-	Metasediment	8.5	-	-	5	-	2.5	-	-	1.3	360	2.0	1.9	-	51	600	10	-	-	0.10
MS 430 32 1A	-	-	-	Metasediment	9.1	-	-	5	-	2.5	-	-	1.6	405	3.0	2.2	-	69	600	14	-	-	0.16
MS 430 32 2A	-	-	-	Metasediment	8.8	-	-	5	-	2.8	-	-	1.6	380	4.0	1.9	-	75	630	12	-	-	0.15
MS- 430-38-1A	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 430-38-2A	-	-	-	Metasediment	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 430-39-1A	-	-	-	Metasediment	7.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 430-39-2A	-	-	-	Metasediment	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 430-40-1A	-	-	-	Metasediment	8.2	-	-	5	-	4.0	-	-	5.2	725	3.0	0.36	-	207	770	12	-	-	0.05
MS- 430-40-2A	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG/S-430-44-1A	-	-	-	Metasediment	8.7	-	-	5	-	2.5	-	-	1.9	385	3.0	1.7	-	76	540	12	-	-	0.17
MS-430-38-1A	-	-	-	Metasediment	8.8	-	-	5	-	2.3	-	-	1.3	425	6.0	1.7	-	55	570	6	-	-	0.07
MS-430-38-2A	-	-	-	Metasediment	9.0	-	-	5	-	2.1	-	-	2.4	665	1.0	1.9	-	100	690	22	-	-	0.14
MS-430-43-1A	-	-	-	Metasediment	8.8	-	-	5	-	2.4	-	-	1.6	405	4.0	1.7	-	79	630	26	-	-	0.11
MS-430-43-2A	-	-	-	Metasediment	8.6	-	-	5	-	3.9	-	-	0.46	160	1.0	1.8	-	20	990	16	-	-	0.05
MS-430-49-1A	-	-	-	Metasediment	8.2	-	-	5	-	2.5	-	-	2.0	515	3.0	1.8	-	84	440	8	-	-	0.24
MS-430-49-2A	-	-	-	Metasediment	8.4	-	-	5	-	1.7	-	-	1.2	315	2.0	2.0	-	64	560	8	-	-	0.13
MS-430-50-1A	-	-	-	Metasediment	8.6	-	-	5	-	2.0	-	-	0.77	290	0.5	2.5	-	37	400	12	-	-	0.07
MS-430-50-2A	-	-	-	Metasediment	8.5	-	-	5	-	2.1	-	-	1.4	360	4.0	1.8	-	71	450	16	-	-	0.17
MS-430-52-1A	-	-	-	Metasediment	8.8	-	-	5	-	0.83	-	-	3.0	1,695	0.5	1.9	-	61	870	4	-	-	0.08
MS-430-52-2A	-	-	-	Metasediment	9.4	-	-	5	-	2.6	-	-	0.80	395	0.5	2.4	-	34	980	16	-	-	0.04
MS-430-53-1A	-	-	-	Metasediment	8.8	-	-	5	-	2.3	-	-	0.71	240	3.0	2.4	-	28	590	20	-	-	0.07
MS-430-53-2A	-	-	-	Metasediment	8.5	-	-	5	-	2.3	-	-	1.3	355	1.0	2.2	-	60	470	22	-	-	0.11
MS-430-54-1A	-	-	-	Metasediment	8.3	-	-	5	-	2.4	-	-	2.0	435	0.5	1.7	-	75	580	14	-	-	0.17
MS-430-54-2A	-	-	-	Metasediment	8.2	-	-	5	-	2.9	-	-	1.9	270	2.0	1.1	-	68	560	2	-	-	0.21
MS-430-57-1A	-	-	-	Metasediment	8.4	-	-	5	-	2.0	-	-	1.5	445	5.0	1.5	-	78	490	12	-	-	0.21
MS-430-57-2A	-	-	-	Metasediment	8.5	-	-	5	-	1.9	-	-	1.4	410	0.5	1.7	-	64	720	16	-	-	0.10
MS-430-59-1A	-	-	-	Metasediment	8.7	-	-	5	-	2.1	-	-	1.5	365	2.0	1.8	-	75	570	20	-	-	0.21

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	Ge	Hf	0.08	In	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
					unit	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																							
Misery (continued)																							
MS-430-59-2A	-	-	-	Metasediment	9.1	-	-	5	-	2.3	-	-	1.8	470	8.0	2.3	-	81	540	22	-	-	0.28
MS-420-18-01	-	-	-	Metasediment	9.4	-	-	0.005	-	2.1	30	-	1.7	429	1.9	2.3	-	79	520	15	-	-	0.17
MS-420-20-01	-	-	-	Metasediment	9.3	-	-	0.005	-	2.6	29	-	1.7	414	1.6	2.2	-	75	590	14	-	-	0.13
MS-420-24-01	-	-	-	Metasediment	8.3	-	-	0.005	-	2.5	25	-	1.6	398	2.0	1.7	-	76	580	15	-	-	0.16
MS-420-24-02	-	-	-	Metasediment	8.2	-	-	0.005	-	2.3	25	-	1.4	368	1.8	2.3	-	66	570	18	-	-	0.16
MS-420-25-01	-	-	-	Metasediment	8.8	-	-	0.005	-	2.7	36	-	1.7	437	1.6	1.8	-	74	620	15	-	-	0.13
MS-420-25-02	-	-	-	Metasediment	8.8	-	-	0.005	-	3.4	42	-	1.8	477	1.7	1.6	-	66	660	10	-	-	0.07
MS- 420-01-1A	-	-	-	Metasediment	8.4	-	-	5	-	1.1	-	-	13	955	0.5	0.10	-	991	1,840	2	-	-	0.09
MS- 420-01-2A	-	-	-	Metasediment	8.4	-	-	5	-	2.7	-	-	1.6	385	1.0	2.0	-	77	670	16	-	-	0.24
MS- 420-05-1A	-	-	-	Metasediment	8.6	-	-	5	-	1.4	-	-	1.6	435	1.0	2.2	-	71	700	14	-	-	0.12
MS- 420-05-2A	-	-	-	Metasediment	9.1	-	-	5	-	2.0	-	-	0.19	130	1.0	3.9	-	6	430	26	-	-	0.005
MS- 420-06-1A	-	-	-	Metasediment	8.5	-	-	5	-	1.6	-	-	1.4	410	1.0	2.2	-	72	660	16	-	-	0.17
MS- 420-06-2A	-	-	-	Metasediment	8.6	-	-	5	-	2.2	-	-	1.4	330	2.0	2.7	-	61	650	16	-	-	0.13
MS- 420-08-1A	-	-	-	Metasediment	8.8	-	-	5	-	2.0	-	-	1.5	460	2.0	2.4	-	68	610	14	-	-	0.12
MS- 420-08-2A	-	-	-	Metasediment	8.9	-	-	5	-	2.1	-	-	1.7	555	3.0	2.5	-	71	700	12	-	-	0.12
MS- 420-09-1A	-	-	-	Metasediment	8.3	-	-	5	-	2.0	-	-	1.2	345	2.0	2.2	-	62	760	16	-	-	0.18
MS- 420-09-2A	-	-	-	Metasediment	8.5	-	-	5	-	2.1	-	-	1.4	390	1.0	1.9	-	73	570	14	-	-	0.15
MS- 420-12-1B	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 420-12-2B	-	-	-	Metasediment	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 420-16-1B	-	-	-	Metasediment	8.4	-	-	5	-	3.2	-	-	1.6	445	3.0	1.4	-	88	520	16	-	-	0.18
MS- 420-16-2B	-	-	-	Metasediment	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 420 22 1A	-	-	-	Metasediment	8.4	-	-	5	-	2.1	-	-	1.9	445	1.0	1.9	-	70	510	20	-	-	0.19
MS 420 22 1A	-	-	-	Metasediment	9.1	-	-	10	-	3.2	-	-	0.60	155	1.0	1.9	-	31	960	14	-	-	0.01
MS 420 22 1B	-	-	-	Metasediment	8.7	-	-	5	-	2.1	-	-	1.7	425	0.5	2.1	-	71	540	6	-	-	0.12
MS 420 22 1B	-	-	-	Metasediment	8.3	-	-	5	-	2.6	-	-	6.4	655	0.5	1.1	-	550	1,570	8	-	-	0.07
MS-420-32-1A	-	-	-	Metasediment	8.2	-	-	5	-	1.7	-	-	1.4	345	2.0	1.2	-	73	440	18	-	-	0.33
MS-420-32-2A	-	-	-	Metasediment	8.3	-	-	5	-	1.8	-	-	1.7	455	8.0	0.72	-	75	510	16	-	-	0.28
MS-420-33-1A	-	-	-	Metasediment	8.7	-	-	5	-	1.7	-	-	1.6	365	1.0	2.0	-	78	530	14	-	-	0.21
MS-420-33-2A	-	-	-	Metasediment	8.6	-	-	5	-	1.6	-	-	1.4	305	4.0	2.4	-	68	550	12	-	-	0.17
MS-420-34-1A	-	-	-	Metasediment	8.6	-	-	5	-	2.4	-	-	1.6	405	2.0	1.6	-	76	500	12	-	-	0.13
MS-420-34-2A	-	-	-	Metasediment	8.8	-	-	5	-	2.3	-	-	1.6	415	1.0	1.9	-	77	510	20	-	-	0.11
MS-420-35-1A	-	-	-	Metasediment	8.5	-	-	5	-	2.5	-	-	2.0	380	5.0	1.6	-	80	520	24	-	-	0.18
MS-420-35-2A	-	-	-	Metasediment	8.7	-	-	5	-	2.1	-	-	1.7	315	1.0	1.7	-	71	420	12	-	-	0.14
MS-420-37-1A	-	-	-	Metasediment	8.5	-	-	5	-	2.5	-	-	1.8	435	5.0	1.8	-	81	540	14	-	-	0.18
MS-420-37-2A	-	-	-	Metasediment	8.5	-	-	5	-	2.2	-	-	1.5	385	0.5	1.7	-	80	500	18	-	-	0.24
MS-420-39 1A	-	-	-	Metasediment	9.1	-	-	5	-	2.5	-	-	0.95	315	2.0	1.4	-	50	980	14	-	-	0.13
MS-420-39 2A	-	-	-	Metasediment	8.7	-	-	5	-	2.7	-	-	1.4	330	1.0	1.5	-	67	590	16	-	-	0.17
MS-420-40 2A	-	-	-	Metasediment	9.1	-	-	5	-	2.6	-	-	1.5	420	0.5	1.7	-	70	560	10	-	-	0.16

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Metasediment (continued)																							
Misery (continued)																							
MS-420-40 1A	-	-	-	Metasediment	8.8	-	-	5	-	2.8	-	-	1.8	455	2.0	1.7	-	85	550	6	-	-	0.17
MS-420-40B 1B	-	-	-	Metasediment	9.3	-	-	5	-	1.9	-	-	1.6	540	0.5	1.9	-	74	590	12	-	-	0.19
MS-420-40B 2B	-	-	-	Metasediment	9.3	-	-	5	-	2.1	-	-	1.6	540	3.0	2.0	-	72	590	10	-	-	0.16
MS-420-41 1B	-	-	-	Metasediment	8.1	-	-	10	-	1.0	-	-	11	570	7.0	0.22	-	755	810	10	-	-	1.0
MS-420-41 2B	-	-	-	Metasediment	9.0	-	-	5	-	2.5	-	-	1.3	345	0.5	1.9	-	63	700	18	-	-	0.21
MS-420-43 1A	-	-	-	Metasediment	9.1	-	-	5	-	2.3	-	-	1.6	395	0.5	1.7	-	77	620	16	-	-	0.16
MS-420-43 2A	-	-	-	Metasediment	9.1	-	-	5	-	1.8	-	-	1.5	345	1.0	1.8	-	73	450	16	-	-	0.20
MS-420-44-1a	-	-	-	Metasediment	9.1	-	-	5	-	2.4	-	-	1.7	435	3.0	2.1	-	81	610	16	-	-	0.23
MS-420-44-2a	-	-	-	Metasediment	8.8	-	-	5	-	2.1	-	-	1.5	360	3.0	1.9	-	68	560	22	-	-	0.17
MS-410-01-01	-	-	-	Metasediment	9.1	-	-	0.005	-	3.1	32	-	1.8	465	1.8	1.4	-	88	550	10	-	-	0.08
MS-410-01-02	-	-	-	Metasediment	8.8	-	-	0.005	-	3.4	27	-	1.9	477	2.2	1.3	-	93	550	10	-	-	0.14
MS 410 02 1A	-	-	-	Metasediment	8.7	-	-	5	-	2.2	-	-	1.6	390	0.5	1.6	-	77	630	12	-	-	0.20
MS 410 02 1B	-	-	-	Metasediment	8.7	-	-	5	-	2.1	-	-	1.7	350	0.5	1.5	-	70	660	8	-	-	0.19
MS 410 08 1A	-	-	-	Metasediment	8.9	-	-	10	-	2.3	-	-	0.87	285	1.0	2.0	-	39	540	18	-	-	0.12
MS 410 08 1B	-	-	-	Metasediment	8.8	-	-	5	-	1.9	-	-	0.65	250	0.5	2.5	-	23	400	20	-	-	0.03
MS 410 11 1A	-	-	-	Metasediment	8.3	-	-	5	-	2.5	-	-	1.7	325	0.5	1.3	-	76	660	8	-	-	0.15
MS 410 11 1B	-	-	-	Metasediment	8.4	-	-	5	-	2.7	-	-	1.7	335	2.0	1.4	-	77	610	6	-	-	0.15
MS-410-29 1B	-	-	-	Metasediment	8.7	-	-	5	-	2.3	-	-	2.0	400	1.0	1.8	-	111	720	12	-	-	0.17
MS-410-29 2B	-	-	-	Metasediment	8.2	-	-	5	-	0.89	-	-	12	680	1.0	0.11	-	876	1,130	10	-	-	0.18
MS-410-30B 1B	-	-	-	Metasediment	9.2	-	-	5	-	2.2	-	-	1.7	395	1.0	1.4	-	102	590	12	-	-	0.35
MS-410-30B 2B	-	-	-	Metasediment	8.9	-	-	5	-	2.2	-	-	4.3	530	1.0	1.0	-	330	880	16	-	-	0.32
MS-410-33 1A	-	-	-	Metasediment	8.7	-	-	5	-	2.4	-	-	1.3	390	1.0	1.8	-	68	460	14	-	-	0.13
MS-410-33 2B	-	-	-	Metasediment	8.6	-	-	5	-	2.0	-	-	2.9	355	1.0	1.6	-	199	580	12	-	-	0.21
MS-410-34 1A	-	-	-	Metasediment	8.8	-	-	5	-	2.3	-	-	1.5	400	0.5	1.5	-	73	600	12	-	-	0.20
MS-410-34 2A	-	-	-	Metasediment	8.7	-	-	5	-	1.9	-	-	2.0	340	0.5	1.6	-	74	430	14	-	-	0.18
MS-410-35 1A	-	-	-	Metasediment	8.4	-	-	10	-	1.0	-	-	13	550	4.0	0.10	-	923	1,280	10	-	-	0.27
MS-410-35 2A	-	-	-	Metasediment	8.5	-	-	5	-	2.0	-	-	1.4	370	0.5	1.5	-	71	550	10	-	-	0.14
MS-410-37 1A	-	-	-	Metasediment	9.1	-	-	5	-	2.2	-	-	1.6	370	3.0	2.1	-	81	510	14	-	-	0.11
MS-410-37 2A	-	-	-	Metasediment	9.0	-	-	5	-	2.9	-	-	1.8	340	1.0	1.4	-	85	550	10	-	-	0.15
MS-410-39 1A	-	-	-	Metasediment	9.3	-	-	5	-	2.0	-	-	1.4	355	7.0	1.7	-	75	530	12	-	-	0.15
MS-410-39 2A	-	-	-	Metasediment	9.2	-	-	5	-	2.7	-	-	1.5	300	0.5	1.9	-	91	620	18	-	-	0.11
MS-410-42 1A	-	-	-	Metasediment	9.2	-	-	5	-	2.4	-	-	1.5	375	1.0	1.7	-	71	590	16	-	-	0.18
MS-410-42 2A	-	-	-	Metasediment	9.0	-	-	5	-	1.2	-	-	2.7	1,395	4.0	1.7	-	68	810	1	-	-	0.15
MS-410-43 1A	-	-	-	Metasediment	9.2	-	-	5	-	1.9	-	-	1.4	340	0.5	2.1	-	67	490	18	-	-	0.17
MS-410-43 2A	-	-	-	Metasediment	9.2	-	-	5	-	1.7	-	-	1.4	295	0.5	2.1	-	67	510	10	-	-	0.16
MS-410-45-1A	-	-	-	Metasediment	9.0	-	-	5	-	1.9	-	-	1.5	445	9.0	2.0	-	73	550	16	-	-	0.20
MS-410-45-2A	-	-	-	Metasediment	9.1	-	-	5	-	2.1	-	-	1.9	800	7.0	2.0	-	75	570	16	-	-	0.09
MS-410-46 1A	-	-	-	Metasediment	9.1	-	-	5	-	2.1	-	-	1.4	295	0.5	1.6	-	70	350	20	-	-	0.13

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																							
Misery (continued)																							
MS-410-46 2A	-	-	-	Metasediment	9.2	-	-	5	-	1.8	-	-	2.3	490	0.5	2.1	-	76	710	16	-	-	0.26
MS-410-47-1A	-	-	-	Metasediment	9.2	-	-	5	-	2.4	-	-	1.4	385	6.0	2.4	-	64	520	14	-	-	0.07
MS-410-47-1A	-	-	-	Metasediment	9.3	-	-	5	-	2.3	-	-	1.4	405	3.0	2.5	-	70	550	30	-	-	0.17
MS-410-47-2A	-	-	-	Metasediment	8.9	-	-	5	-	2.4	-	-	1.5	435	6.0	2.3	-	73	580	18	-	-	0.15
MS-410-48-1A	-	-	-	Metasediment	8.7	-	-	5	-	2.0	-	-	1.8	445	14	1.5	-	99	530	20	-	-	0.16
MS-410-48-2A	-	-	-	Metasediment	8.7	-	-	5	-	2.0	-	-	1.5	405	4.0	1.7	-	82	600	22	-	-	0.18
MS-410-52-1A	-	-	-	Metasediment	8.7	-	-	5	-	2.3	-	-	1.6	405	3.0	1.9	-	81	520	20	-	-	0.14
MS-410-52-2A	-	-	-	Metasediment	8.7	-	-	5	-	2.7	-	-	1.3	420	3.0	1.8	-	57	760	26	-	-	0.09
MS-410-53-1A	-	-	-	Metasediment	8.7	-	-	5	-	2.2	-	-	1.5	420	4.0	1.8	-	77	550	18	-	-	0.18
MS-410-53-2A	-	-	-	Metasediment	8.9	-	-	5	-	1.8	-	-	1.3	375	6.0	2.1	-	70	630	16	-	-	0.35
MS-410-54-1A	-	-	-	Metasediment	9.1	-	-	5	-	2.5	-	-	1.6	430	1.0	2.6	-	78	560	14	-	-	0.22
MS-410-54-2A	-	-	-	Metasediment	9.1	-	-	5	-	2.0	-	-	1.4	405	8.0	2.1	-	73	540	18	-	-	0.20
MS-410-55-1A	-	-	-	Metasediment	9.0	-	-	5	-	2.1	-	-	1.7	390	6.0	2.1	-	95	630	18	-	-	0.18
MS-410-55-2A	-	-	-	Metasediment	8.8	-	-	5	-	2.4	-	-	1.7	340	5.0	1.5	-	77	550	8	-	-	0.28
MS-410-58-1A	-	-	-	Metasediment	8.5	-	-	5	-	2.5	-	-	1.9	465	2.0	2.1	-	85	620	18	-	-	0.25
MS-410-58-2A	-	-	-	Metasediment	8.7	-	-	5	-	2.1	-	-	1.8	520	1.0	2.3	-	79	620	16	-	-	0.25
MS 400-38-1a	-	-	-	Metasediment	9.3	-	-	5	-	2.1	-	-	1.9	460	2.0	2.1	-	85	680	20	-	-	0.22
MS 400-38-2a	-	-	-	Metasediment	9.5	-	-	5	-	2.2	-	-	1.8	465	2.0	1.9	-	75	570	18	-	-	0.15
MS 400-41 2a	-	-	-	Metasediment	9.5	-	-	5	-	2.5	-	-	1.5	385	3.0	2.4	-	74	670	16	-	-	0.13
MS 400-42-2a	-	-	-	Metasediment	9.2	-	-	5	-	1.8	-	-	2.4	860	3.0	2.6	-	83	790	14	-	-	0.17
MS 400-43 1a	-	-	-	Metasediment	9.7	-	-	5	-	2.0	-	-	1.5	440	3.0	2.4	-	77	610	16	-	-	0.20
MS 400-43 2a	-	-	-	Metasediment	9.3	-	-	5	-	2.5	-	-	1.8	445	10	1.9	-	114	560	16	-	-	0.14
MS 400-45-1a	-	-	-	Metasediment	8.7	-	-	5	-	2.1	-	-	3.3	405	2.0	1.8	-	193	750	22	-	-	0.20
MS 400-45-2a	-	-	-	Metasediment	9.3	-	-	5	-	2.6	-	-	1.5	390	3.0	2.0	-	71	590	14	-	-	0.10
MS-400-12-1A	-	-	-	Metasediment	8.5	-	-	5	-	1.8	-	-	6.7	540	5.0	1.4	-	468	730	26	-	-	0.16
MS-400-12-2A	-	-	-	Metasediment	8.5	-	-	5	-	1.7	-	-	3.1	375	4.0	2.2	-	205	700	22	-	-	0.19
MS-400-13-1A	-	-	-	Metasediment	8.3	-	-	5	-	2.2	-	-	2.0	330	2.0	2.0	-	118	580	16	-	-	0.10
MS-400-13-2A	-	-	-	Metasediment	8.4	-	-	5	-	2.4	-	-	1.5	420	13	1.9	-	90	550	18	-	-	0.20
MS-400-14-1A	-	-	-	Metasediment	8.7	-	-	5	-	3.0	-	-	1.5	555	7.0	1.4	-	74	540	6	-	-	0.07
MS-400-14-2A	-	-	-	Metasediment	8.4	-	-	5	-	2.6	-	-	1.5	310	3.0	1.7	-	76	600	16	-	-	0.19
MS-400-16-1A	-	-	-	Metasediment	8.8	-	-	5	-	3.1	-	-	1.7	455	4.0	1.9	-	69	680	16	-	-	0.15
MS-400-16-2A	-	-	-	Metasediment	8.8	-	-	5	-	2.4	-	-	1.4	400	3.0	1.8	-	67	560	18	-	-	0.11
MS-400-18-1A	-	-	-	Metasediment	8.8	-	-	5	-	2.2	-	-	2.1	465	4.0	0.99	-	70	680	16	-	-	0.22
MS-400-18-2A	-	-	-	Metasediment	9.1	-	-	5	-	2.0	-	-	1.2	380	6.0	1.8	-	56	530	18	-	-	0.17
MS-400-20-1A	-	-	-	Metasediment	9.1	-	-	5	-	2.2	-	-	1.4	435	5.0	2.4	-	73	500	16	-	-	0.14
MS-400-20-2A	-	-	-	Metasediment	8.6	-	-	5	-	1.9	-	-	1.4	285	6.0	2.2	-	73	510	10	-	-	0.09
MS-400-23-1A	-	-	-	Metasediment	8.2	-	-	5	-	2.5	-	-	2.9	410	8.0	2.0	-	196	730	20	-	-	0.05
MS-400-23-2A	-	-	-	Metasediment	8.1	-	-	5	-	1.8	-	-	1.6	415	8.0	2.1	-	69	580	20	-	-	0.19

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price	Crustal Abundances																		
		From	To	General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
					Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
unit	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
Metasediment (continued)																							
Misery (continued)																							
MS-400-28-1A	-	-	-	Metasediment	9.2	-	-	5	-	2.5	-	-	1.3	390	3.0	2.1	-	60	740	18	-	-	0.10
MS-400-28-2A	-	-	-	Metasediment	9.3	-	-	5	-	2.0	-	-	1.4	435	13	2.4	-	97	560	20	-	-	0.11
MS-400-35-1A	-	-	-	Metasediment	8.3	-	-	5	-	2.6	-	-	1.5	375	9.0	1.5	-	73	620	18	-	-	0.13
MS-400-35-2A	-	-	-	Metasediment	8.4	-	-	5	-	2.6	-	-	1.6	430	6.0	1.6	-	77	690	18	-	-	0.19
MS-400-46-1a	-	-	-	Metasediment	9.5	-	-	5	-	1.8	-	-	1.6	400	3.0	2.7	-	69	550	22	-	-	0.21
MS-400-46-2a	-	-	-	Metasediment	9.2	-	-	5	-	2.0	-	-	1.8	485	3.0	2.6	-	80	650	20	-	-	0.20
MS-400-47-2A	-	-	-	Metasediment	9.4	-	-	5	-	2.3	-	-	1.6	485	5.0	2.4	-	67	690	26	-	-	0.24
MS-400-48-1a	-	-	-	Metasediment	9.1	-	-	5	-	3.3	-	-	2.0	530	1.0	1.4	-	92	480	18	-	-	0.22
MS-400-48-2a	-	-	-	Metasediment	9.3	-	-	5	-	2.2	-	-	1.7	505	4.0	2.3	-	80	520	22	-	-	0.26
MS-400-49-1a	-	-	-	Metasediment	9.4	-	-	5	-	2.3	-	-	2.0	545	3.0	2.8	-	62	610	14	-	-	0.11
MS-400-51-1a	-	-	-	Metasediment	9.5	-	-	5	-	2.0	-	-	0.88	230	1.0	2.3	-	39	680	18	-	-	0.12
MS-400-51-2a	-	-	-	Metasediment	8.9	-	-	5	-	2.4	-	-	1.7	380	0.5	2.2	-	81	510	16	-	-	0.27
MS-400-52T-2a	-	-	-	Metasediment	9.3	-	-	5	-	2.4	-	-	1.7	360	1.0	1.9	-	87	570	12	-	-	0.11
MS-400-53-1a	-	-	-	Metasediment	9.2	-	-	5	-	2.0	-	-	1.6	355	0.5	2.0	-	74	510	12	-	-	0.17
MS-400-53-2a	-	-	-	Metasediment	9.1	-	-	5	-	2.4	-	-	1.5	370	0.5	1.8	-	68	750	14	-	-	0.14
MS-400-54-1a	-	-	-	Metasediment	9.4	-	-	5	-	2.2	-	-	1.4	365	1.0	2.0	-	69	580	18	-	-	0.18
MS-400-54-2a	-	-	-	Metasediment	9.3	-	-	5	-	2.3	-	-	1.5	380	1.0	1.4	-	60	880	14	-	-	0.15
MS 390-13-1a	-	-	-	Metasediment	9.1	-	-	5	-	2.5	-	-	1.6	450	2.0	2.2	-	78	560	16	-	-	0.14
MS 390-13-2a	-	-	-	Metasediment	9.0	-	-	5	-	2.2	-	-	1.7	415	3.0	1.8	-	75	530	16	-	-	0.16
MS-390-01-1A	-	-	-	Metasediment	8.4	-	-	5	-	2.3	-	-	1.7	430	9.0	1.9	-	87	590	8	-	-	0.13
MS-390-01-2A	-	-	-	Metasediment	8.3	-	-	5	-	2.1	-	-	1.5	355	6.0	1.9	-	71	550	12	-	-	0.07
MS 390-12T 1a	-	-	-	Metasediment	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 390-12T 2a	-	-	-	Metasediment	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS-390-21-1a	-	-	-	Metasediment	9.4	-	-	5	-	2.6	-	-	1.9	425	1.0	1.8	-	85	650	22	-	-	0.19
MS-390-21-2a	-	-	-	Metasediment	9.3	-	-	5	-	2.4	-	-	1.7	385	3.0	2.1	-	84	590	16	-	-	0.17
MS-390-25-1a	-	-	-	Metasediment	9.7	-	-	5	-	2.4	-	-	0.32	165	0.5	3.6	-	11	560	24	-	-	0.02
MS-390-25-2a	-	-	-	Metasediment	9.0	-	-	5	-	2.1	-	-	1.5	390	2.0	2.4	-	68	580	14	-	-	0.17
MS-390-27-1a	-	-	-	Metasediment	9.1	-	-	5	-	2.2	-	-	2.2	470	0.5	2.2	-	98	800	12	-	-	0.34
MS-390-27-2a	-	-	-	Metasediment	9.0	-	-	5	-	2.7	-	-	2.2	495	2.0	1.8	-	95	670	6	-	-	0.16
MS-390-28-1a	-	-	-	Metasediment	9.0	-	-	5	-	2.3	-	-	2.4	380	0.5	2.0	-	141	710	16	-	-	0.14
MS-390-28-2a	-	-	-	Metasediment	9.7	-	-	5	-	2.4	-	-	0.23	190	0.5	3.8	-	5	380	20	-	-	0.005
MS-390-30-1a	-	-	-	Metasediment	8.2	-	-	5	-	3.2	-	-	1.7	415	2.0	1.9	-	99	640	22	-	-	0.59
MS-390-30-2a	-	-	-	Metasediment	9.4	-	-	5	-	2.5	-	-	1.1	325	0.5	2.5	-	49	540	12	-	-	0.14
MS-390-31-1a	-	-	-	Metasediment	9.2	-	-	5	-	2.8	-	-	1.4	340	0.5	2.3	-	61	610	16	-	-	0.14
MS-390-31-2a	-	-	-	Metasediment	9.5	-	-	5	-	2.6	-	-	1.4	385	1.0	2.5	-	67	710	18	-	-	0.18
MS-390-32-1a	-	-	-	Metasediment	9.3	-	-	10	-	2.9	-	-	1.7	370	1.0	2.1	-	73	660	16	-	-	0.17
MS-390-32-2a	-	-	-	Metasediment	9.2	-	-	5	-	2.9	-	-	2.1	460	2.0	2.0	-	98	600	16	-	-	0.24
MS-390-33-1a	-	-	-	Metasediment	9.3	-	-	10	-	2.5	-	-	1.5	455	2.0	2.4	-	70	600	16	-	-	0.19

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Metasediment (continued)																							
Misery (continued)																							
MS-390-33-1a	-	-	-	Metasediment	9.2	-	-	5	-	1.9	-	-	1.5	400	1.0	2.7	-	75	650	16	-	-	0.25
MS-390-34-1a	-	-	-	Metasediment	9.2	-	-	5	-	2.6	-	-	1.7	555	1.0	2.2	-	67	730	14	-	-	0.15
MS-390-34-2a	-	-	-	Metasediment	9.7	-	-	5	-	2.5	-	-	1.6	410	1.0	2.7	-	71	550	14	-	-	0.15
MS-390-36-1a	-	-	-	Metasediment	9.2	-	-	5	-	0.90	-	-	3.2	1,865	0.5	2.0	-	65	1,020	14	-	-	0.12
MS-390-36-2a	-	-	-	Metasediment	9.2	-	-	5	-	2.0	-	-	1.6	475	2.0	2.7	-	71	600	18	-	-	0.22
MS-390-37-1A	-	-	-	Metasediment	8.9	-	-	5	-	3.0	-	-	1.8	480	1.0	2.3	-	80	660	20	-	-	0.20
MS-390-37-2A	-	-	-	Metasediment	8.7	-	-	5	-	2.0	-	-	1.6	455	0.5	2.2	-	64	650	18	-	-	0.16
MS-390-38-1A	-	-	-	Metasediment	9.3	-	-	5	-	2.7	-	-	1.9	500	2.0	2.0	-	84	560	14	-	-	0.15
MS-390-39-1A	-	-	-	Metasediment	8.8	-	-	5	-	2.3	-	-	1.6	445	1.0	2.1	-	77	650	16	-	-	0.24
MS-390-39-2A	-	-	-	Metasediment	8.9	-	-	5	-	2.6	-	-	2.1	480	2.0	2.4	-	102	650	20	-	-	0.18
MS-390-40-1A	-	-	-	Metasediment	8.6	-	-	5	-	3.5	-	-	2.0	485	3.0	1.7	-	83	600	16	-	-	0.13
MS-390-40-2A	-	-	-	Metasediment	8.7	-	-	5	-	2.4	-	-	1.2	315	2.0	1.8	-	64	470	16	-	-	0.10
MS-380-32-2A	-	-	-	Metasediment	8.8	-	-	5	-	3.2	-	-	2.1	540	2.0	1.8	-	91	550	18	-	-	0.15
MS-380-60-1	-	-	-	Metasediment	8.9	-	-	0.01	-	2.6	-	-	1.6	435	2.0	2.2	-	90	700	15	-	-	0.34
MS-380-60-2	-	-	-	Metasediment	8.9	-	-	0.01	-	2.8	-	-	1.7	423	4.0	2.1	-	79	520	10	-	-	0.13
MS-380-58-1	-	-	-	Metasediment	8.8	-	-	0.01	-	1.9	-	-	1.6	354	6.0	2.5	-	75	620	10	-	-	0.2
MS-380-58-2	-	-	-	Metasediment	8.6	-	-	0.01	-	1.9	-	-	1.6	341	4.0	2.4	-	71	520	11	-	-	0.17
MS-370-18-2	-	-	-	Metasediment	8.7	-	-	0.005	-	2.5	-	-	1.8	431	3.0	2.2	-	86	550	14	-	-	0.20
MS-360-22T-1	-	-	-	Metasediment	8.8	-	-	0.01	-	1.8	-	-	1.6	400	2.0	1.7	-	83	580	18	-	-	0.18
MS-360-22T-2	-	-	-	Metasediment	8.5	-	-	0.005	-	3.0	-	-	0.35	164	3.0	1.7	-	9	1,030	23	-	-	0.01
MS-360-22T-3	-	-	-	Metasediment	8.7	-	-	0.005	-	2.9	-	-	0.92	299	2.0	1.7	-	42	1,000	21	-	-	0.11
MS-360-22T-4	-	-	-	Metasediment	8.6	-	-	0.005	-	3.1	-	-	0.24	141	2.0	2.4	-	4	1,180	23	-	-	0.01
MS-360-26-1	-	-	-	Metasediment	8.7	-	-	0.005	-	2.3	-	-	1.9	389	3.0	1.9	-	81	530	12	-	-	0.20
MS-360-26-2	-	-	-	Metasediment	8.7	-	-	0.005	-	2.3	-	-	1.8	396	2.0	1.8	-	81	590	13	-	-	0.19
MS-360-26-3	-	-	-	Metasediment	8.7	-	-	0.005	-	2.4	-	-	1.7	393	3.0	1.9	-	82	670	17	-	-	0.19
MS-360-26-4	-	-	-	Metasediment	8.4	-	-	0.005	-	2.5	-	-	1.8	367	2.0	2.0	-	81	610	10	-	-	0.32
MS-360-26-5	-	-	-	Metasediment	8.7	-	-	0.005	-	2.1	-	-	1.6	330	2.0	2.3	-	69	610	9	-	-	0.32
MS-360-26-6	-	-	-	Metasediment	8.7	-	-	0.005	-	2.1	-	-	1.5	384	2.0	2.2	-	68	530	13	-	-	0.24
MS-320-19-02 14-DEC-04	-	-	-	Metasediment	8.9	-	-	0.005	-	2.2	-	-	3.2	421	2.0	2.1	-	195	760	9	-	-	0.15
MS-320-19-01 14-DEC-04	-	-	-	Metasediment	8.5	-	-	0.005	-	2.2	-	-	1.5	343	3.0	2.0	-	69	540	9	-	-	0.16
MS-310-10-02 20-FEB-05	-	-	-	Metasediment	8.1	-	-	0.01	-	1.6	-	-	8.7	634	3.0	0.67	-	708	950	10	-	-	0.45
MS-310-10-01 20-FEB-05	-	-	-	Metasediment	8.3	-	-	0.005	-	0.50	-	-	16	676	1.0	0.07	-	1,360	630	9	-	-	0.15
MS-290-12-04- 3-Apr-05	-	-	-	Metasediment	9.3	-	-	0.01	-	1.9	-	-	2.7	327	1.0	2.4	-	162	620	11	-	-	0.19
MS-290-12-03- 3-Apr-05	-	-	-	Metasediment	9.1	-	-	0.01	-	1.9	-	-	3.0	361	1.0	1.8	-	224	710	12	-	-	0.21
MS-290-12-02- 3-Apr-05	-	-	-	Metasediment	9.2	-	-	0.005	-	2.2	-	-	2.2	383	1.0	2.1	-	142	600	13	-	-	0.21
MS-290-12-01- 3-Apr-05	-	-	-	Metasediment	8.7	-	-	0.005	-	2.0	-	-	2.5	362	1.0	1.9	-	200	720	9	-	-	0.18
MGT-49 70-73	-	-	-	Metasediment	9.4	-	-	0.005	-	1.9	11	-	1.6	375	1.2	0.105	-	76	520	6	-	-	0.18
MGT-49 125-128	-	-	-	Metasediment	9.4	-	-	0.005	-	1.7	11	-	1.8	402	1.6	0.05	-	72	620	5	-	-	0.18

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																			0.035
		From	To		Paste pH	Ge	Hf	0.08	In	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035	
					unit	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																								
Misery (continued)																								
MGT-49 200-203	-	-	-	Metasediment	9.2	-	-	0.005	-	1.7	13	-	1.5	393	1.6	0.04	-	72	510	4	-	-	0.19	
MGT-49 264-267	-	-	-	Metasediment	9.2	-	-	0.005	-	1.4	14	-	1.5	376	1.3	0.034	-	68	400	3	-	-	0.21	
MGT-51 169-172	-	-	-	Metasediment	9.2	-	-	0.005	-	1.8	10	-	1.7	413	1.3	0.04	-	78	450	2	-	-	0.18	
MGT-56 230-233	-	-	-	Metasediment	9.2	-	-	0.005	-	1.5	13	-	1.4	376	1.5	0.039	-	66	460	4	-	-	0.16	
MGT-56 290-293	-	-	-	Metasediment	9.4	-	-	0.005	-	1.5	13	-	1.3	392	1.0	0.05	-	65	460	2	-	-	0.19	
MGT-66 9-12	-	-	-	Metasediment	9.0	-	-	0.005	-	0.28	6.0	-	0.27	151	0.3	0.027	-	13	1,270	2	-	-	0.025	
MGT-66 21-24	-	-	-	Metasediment	9.6	-	-	0.005	-	1.4	18	-	1.4	339	1.4	0.046	-	72	290	4	-	-	0.14	
MGT-66 33-36	-	-	-	Metasediment	9.4	-	-	0.005	-	1.8	14	-	1.8	426	1.7	0.044	-	89	440	3	-	-	0.15	
MGT-66 41-44	-	-	-	Metasediment	9.8	-	-	0.005	-	1.3	15	-	1.3	471	1.7	0.048	-	74	390	5	-	-	0.26	
MGT-66 52-65	-	-	-	Metasediment	9.6	-	-	0.005	-	1.6	21	-	1.5	378	1.9	0.04	-	78	420	4	-	-	0.08	
MGT-66 72.47-74.64	-	-	-	Metasediment	10.0	-	-	0.005	-	1.8	18	-	1.6	461	1.5	0.038	-	84	350	5	-	-	0.10	
MGT-66 83-86	-	-	-	Metasediment	9.5	-	-	0.005	-	1.3	17	-	1.3	322	1.6	0.034	-	66	490	4	-	-	0.10	
MGT-66 95-98	-	-	-	Metasediment	9.7	-	-	0.005	-	1.4	13	-	1.6	382	1.6	0.041	-	78	360	4	-	-	0.20	
MGT-44 45-48	-	-	-	Metasediment	8.6	-	-	0.005	-	0.71	15	-	1.9	384	2.0	0.018	-	89	540	4	-	-	0.44	
MGT-44 52-55	-	-	-	Metasediment	8.7	-	-	0.005	-	1.6	11	-	1.9	446	1.5	0.03	-	79	480	4	-	-	0.12	
MGT-44 70.5-73.5	-	-	-	Metasediment	8.5	-	-	0.005	-	1.7	10	-	1.7	447	2.5	0.038	-	84	450	6	-	-	0.31	
MGT-51 72-75	-	-	-	Metasediment	9.3	-	-	0.005	-	1.7	14	-	2.0	434	1.6	0.056	-	81	610	6	-	-	0.16	
MGT-51 79-82	-	-	-	Metasediment	9.1	-	-	0.005	-	1.3	12	-	1.6	402	1.4	0.049	-	75	720	6	-	-	0.25	
MGT-51 220-223	-	-	-	Metasediment	9.3	-	-	0.005	-	0.60	22	-	0.49	205	0.8	0.033	-	18	640	8	-	-	0.07	
MGT-51 250-253	-	-	-	Metasediment	9.0	-	-	0.005	-	1.2	18	-	1.6	429	1.5	0.028	-	77	560	4	-	-	0.22	
MGT-51 257-260	-	-	-	Metasediment	9.0	-	-	0.005	-	1.4	19	-	1.8	464	1.7	0.029	-	82	600	4	-	-	0.23	
MGT-51 328-330	-	-	-	Metasediment	8.7	-	-	0.02	-	0.76	29	-	15.0	612	1.8	0.151	-	1,363	600	7	-	-	0.31	
MS K 430 45 1A	-	-	-	Metasediment	8.3	-	-	5	-	1.1	-	-	11.5	790	0.5	0.31	-	1,010	1,140	1	-	-	0.13	
MS K 430 45 1B	-	-	-	Metasediment	8.3	-	-	5	-	1.1	-	-	13.0	840	0.5	0.19	-	939	1,350	2	-	-	0.15	
Median					8.7	-	-	5	-	2.3	18	-	1.6	400	1.8	1.9	-	74	580	14	-	-	0.16	
Minimum					7.1	-	-	0.005	-	0.28	6.0	-	0.19	130	0.3	0.018	-	1	0	1	-	-	0.005	
Maximum					10.0	-	-	30	-	4.0	42.4	-	15.8	1,865	14.0	4.0	-	1,363	1,840	38	-	-	1.0	
Count					370	0	0	333	0	333	43	0	333	333	333	333	0	333	333	333	0	0	287	
Pigeon																								
97-54	97-54	29.57	30	Metasediment	8.4	-	-	-	-	0.39	-	-	2.0	170	2.0	0.02	-	88	590	4	-	-	-	
94-7 6.71-10	94-7	6.71	10	Metasediment	8.2	-	-	5	-	2.2	-	-	1.6	400	4.0	1.4	-	79	350	22	-	-	0.15	
94-7 10-15	94-7	10	15	Metasediment	-	-	-	5	-	2.4	-	-	1.5	380	0.5	1.4	-	82	410	18	-	-	0.13	
94-7 15-19.3	94-7	15	19.3	Metasediment	-	-	-	5	-	2.5	-	-	2.1	550	1.0	1.6	-	116	320	18	-	-	0.08	
94-7 19.3-22	94-7	19.3	22	Metasediment	-	-	-	5	-	2.4	-	-	1.8	430	1.0	1.8	-	69	500	20	-	-	0.12	
94-7 22-27	94-7	22	27	Metasediment	-	-	-	5	-	2.3	-	-	1.6	460	0.5	1.4	-	69	470	16	-	-	0.15	
94-7 27-32	94-7	27	32	Metasediment	8.4	-	-	5	-	2.5	-	-	1.5	420	0.5	1.0	-	86	400	12	-	-	0.13	
94-7 32-37	94-7	32	37	Metasediment	-	-	-	5	-	2.6	-	-	1.7	410	2.0	1.2	-	85	400	18	-	-	0.11	
94-7 37-42	94-7	37	42	Metasediment	-	-	-	5	-	2.3	-	-	1.4	355	1.0	1.8	-	69	460	24	-	-	0.08	

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Metasediment (continued)																							
Pigeon (continued)																							
94-7 42-47	94-7	42	47	Metasediment	-	-	-	5	-	2.8	-	-	1.8	455	1.0	1.3	-	92	390	24	-	-	0.13
94-7 47-52	94-7	47	52	Metasediment	-	-	-	5	-	2.8	-	-	1.5	385	1.0	1.5	-	71	380	20	-	-	0.11
94-7 52-57	94-7	52	57	Metasediment	8.8	-	-	5	-	2.5	-	-	1.8	470	3.0	1.9	-	77	550	24	-	-	0.08
94-7 57-62	94-7	57	62	Metasediment	-	-	-	5	-	3.1	-	-	2.0	495	3.0	1.7	-	100	400	24	-	-	0.11
94-7 62-67	94-7	62	67	Metasediment	-	-	-	5	-	2.5	-	-	1.9	455	1.0	1.9	-	92	560	22	-	-	0.10
94-7 67-72	94-7	67	72	Metasediment	-	-	-	5	-	2.4	-	-	1.6	395	2.0	1.8	-	68	410	22	-	-	0.11
HC-Pdef-2	-	-	-	Metasediment	8.8	0.16	3.3	-	0.051	2.9	20	67	1.9	373	2.0	0.80	7.5	103	180	11	55.8	0.001	0.04
HC-Pdef-3	-	-	-	Metasediment	9.5	0.17	3.6	-	0.054	2.9	25	88	2.0	431	3.6	1.9	7.9	99	450	20	93.7	0.002	0.21
HC-Pdef-4	-	-	-	Metasediment	9.6	0.18	3.2	-	0.056	2.5	20	101	2.8	513	1.2	1.8	6.5	113	540	14	52.5	0.001	0.13
HC-Pdef-5	-	-	-	Metasediment	9.6	0.17	2.7	-	0.053	2.4	14	81	2.5	594	0.4	1.0	5.1	21	2,090	10	59.2	0.001	0.41
HC-Pdef-8	-	-	-	Metasediment	9.4	0.22	4.2	-	0.049	2.6	28	77	2.1	588	1.8	1.6	9.0	108	370	13	72.9	0.001	0.12
HC-Pdef-9	-	-	-	Metasediment	9.4	0.20	3.9	-	0.039	2.4	28	69	1.7	383	3.9	1.6	7.5	81	410	18	81.4	0.001	0.01
HC-Pdef-10	-	-	-	Metasediment	9.7	0.28	2.9	-	0.192	2.1	35	63	8.8	1,160	0.4	0.23	4.8	374	1,870	3	155	0.001	0.26
HC-Pdef-11	-	-	-	Metasediment	9.2	0.19	3.5	-	0.035	2.3	28	55	1.7	377	2.1	1.3	6.4	82	480	11	80.6	0.002	0.25
HC-Pdef-13	-	-	-	Metasediment	9.5	0.22	3.9	-	0.036	2.7	35	55	1.7	453	3.1	1.8	7.6	79	350	15	111.5	0.001	0.04
HC-Pdef-14	-	-	-	Metasediment	9.5	0.20	4.3	-	0.029	2.2	30	44	1.6	374	2.4	2.2	7.3	80	380	16	88.1	0.002	0.03
HC-Pdef-15	-	-	-	Metasediment	9.4	0.21	4.2	-	0.039	2.3	28	74	1.6	406	1.9	1.7	7.0	87	290	15	79	0.001	0.02
HC-Pdef-16	-	-	-	Metasediment	8.0	0.23	3.4	-	0.046	2.8	30	59	1.8	381	2.3	1.4	8.5	95	310	13	80.2	0.001	0.18
HC-PDef-18	-	-	-	Metasediment	9.2	0.24	3.8	-	0.039	2.0	27	88	1.6	342	2.4	1.6	5.8	72	390	17	79.7	0.001	0.10
HC-PDef-19	-	-	-	Metasediment	9.8	0.27	3.6	-	0.047	2.4	19	98	1.7	433	2.9	1.6	7.8	94	320	17	64.6	0.001	0.01
HC-PDef-20	-	-	-	Metasediment	9.3	0.27	3.7	-	0.041	2.6	21	92	1.9	470	2.5	0.97	7.1	93	370	10	88	0.002	0.13
HC-PDef-21	-	-	-	Metasediment	9.6	0.30	3.8	-	0.057	2.8	19	144	2.2	485	2.3	2.6	8.6	112	390	23	69.2	0.001	0.02
HC-PDef-22	-	-	-	Metasediment	9.8	0.29	3.0	-	0.032	2.2	30	59	1.2	291	3.0	1.9	6.5	53	420	20	89.1	0.002	0.01
HC-PDef-23	-	-	-	Metasediment	9.5	0.25	3.3	-	0.035	2.2	26	83	1.6	346	2.4	1.7	6.0	68	430	17	91.6	0.001	0.12
HC-PDef-26	-	-	-	Metasediment	9.3	0.25	3.0	-	0.042	2.6	21	78	1.9	390	2.2	1.2	6.2	84	490	11	66.7	0.001	0.14
HC-PDef-28	-	-	-	Metasediment	9.8	0.29	2.2	-	0.021	1.5	19	52	0.93	264	2.5	3.0	4.9	28	1,010	23	56.9	0.001	0.01
HC-PDef-31	-	-	-	Metasediment	9.2	0.20	2.8	-	0.042	2.4	22	54	1.6	352	3.1	1.4	7.3	78	300	13	74.4	0.002	0.01
HC-PDef-32	-	-	-	Metasediment	9.0	0.19	3.2	-	0.034	2.2	15	61	1.9	456	3.2	2.7	9.7	57	430	12	93	0.001	0.01
HC-PDef-35	-	-	-	Metasediment	9.4	0.20	2.9	-	0.026	2.0	27	43	1.3	350	2.6	2.0	6.0	45	300	16	60.9	0.001	0.005
Median					9.4	0.22	3.4	5	0.041	2.4	26	69	1.7	408	2.2	1.6	7.1	82	405	17	79.7	0.001	0.11
Minimum					8.0	0.16	2.2	5	0.021	0.39	14	43	0.93	170	0.4	0.02	4.8	21	180	3	52.5	0.001	0.005
Maximum					9.8	0.30	4.3	5	0.192	3.1	35	144	8.8	1,160	4.0	3.0	9.7	374	2,090	24	155	0.002	0.41
Count					27	23	23	14	23	38	23	23	38	38	38	38	23	38	38	38	23	23	37
Jay																							
2014-DD-001	JGT-04	35.58	41.58	Metasediment	8.30	0.05	0.53	0.01	0.04	1.6	20.5	96	2.11	345	4.16	0.04	0.42	66	460	3	65.9	-	0.15
2014-DD-002	JGT-04	41.58	48.98	Metasediment	7.94	0.05	0.5	0.005	0.04	1.81	23.7	112	1.99	352	3.06	0.04	0.48	71	470	2.9	94.6	-	0.05
2014-DD-005	JGT-04	74.58	83.58	Metasediment	9.05	0.05	0.05	0.005	0.01	0.13	0.6	6	0.08	32	5.53	0.04	0.11	5	340	2	5.3	-	0.005
2014-DD-006	JGT-04	86.17	95.58	Metasediment	8.29	0.05	0.38	0.005	0.05	1.73	22.5	124	2.26	358	4.23	0.06	0.39	89	490	5.8	77.1	-	0.18

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035	
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %	
Metasediment (continued)																								
Jay (continued)																								
2014-DD-007	JGT-04	100	107.7	Metasediment	8.58	0.05	0.19	0.005	0.05	1.77	24.7	106	2.15	312	5.48	0.07	0.52	136	2,720	5.5	75.2	-	0.27	
2014-DD-008	JGT-04	114.12	122.54	Metasediment	8.26	0.05	0.46	0.005	0.05	1.88	22.6	89	2.36	364	4.14	0.05	0.46	92	410	3.9	73.7	-	0.16	
2014-DD-009	JGT-04	125.58	135.9	Metasediment	8.69	0.05	0.38	0.005	0.04	1.51	21.7	93	1.95	465	5.11	0.06	0.47	71	660	3.6	90.5	-	0.1	
2014-DD-010	JGT-04	142.21	147.1	Metasediment	8.24	0.05	0.32	0.005	0.05	2.23	27.8	96	2.52	452	4.03	0.06	0.42	91	400	5.7	120	-	0.14	
2014-DD-011	JGT-04	147.1	152.58	Metasediment	8.01	0.1	0.27	0.005	0.05	2.25	29.8	88	2.33	403	3.7	0.06	0.49	96	340	4	95.2	-	0.11	
2014-DD-012	JGT-04	155.58	163.58	Metasediment	8.14	0.05	0.42	0.005	0.05	2.16	26.5	104	2.25	364	3.51	0.06	0.48	83	300	3.2	84	-	0.1	
2014-DD-013	JGT-04	163.38	171.69	Metasediment	8.48	0.05	0.35	0.005	0.04	1.82	26.8	85	2.29	406	4.12	0.11	0.38	69	660	3.7	67.8	-	0.13	
2014-DD-014	JGT-04	174.5	180	Metasediment	8.88	0.05	0.34	0.005	0.04	1.58	22.3	58	1.78	426	3.89	0.06	0.55	35	610	4.7	74.3	-	0.13	
2014-DD-015	JGT-04	188	196.2	Metasediment	8.38	0.1	0.38	0.005	0.06	2.24	30.1	89	2.38	440	3.32	0.1	0.41	92	560	5.3	94.5	-	0.13	
2014-DD-016	JGT-04	199	206.58	Metasediment	8.17	0.05	0.35	0.005	0.05	1.98	30.6	104	2.23	350	4.28	0.05	0.42	92	400	4.6	82	-	0.16	
2014-DD-017	JGT-04	221	230	Metasediment	8.57	0.05	0.38	0.005	0.04	1.41	26.6	136	1.87	370	5.68	0.04	0.42	77	560	8.4	83.3	-	0.19	
2014-DD-018	JGT-04	231.28	241	Metasediment	8.64	0.05	0.34	0.005	0.03	1.66	24.5	120	1.69	444	6.24	0.04	0.77	71	360	6.6	111	-	0.26	
2014-DD-019	JGT-04	241	251	Metasediment	9.10	0.05	0.32	0.005	0.03	1.55	25	122	1.53	435	7.01	0.05	0.75	67	620	9.2	118	-	0.17	
2014-DD-020	JGT-04	251	260	Metasediment	9.51	0.05	0.35	0.03	0.01	0.75	18.7	81	1	296	6.36	0.05	0.39	43	590	3.6	83.7	-	0.02	
2014-DD-022	JGT-05	15.2	16.44	Metasediment	8.99	0.05	0.45	0.005	0.07	1.57	16	114	1.15	330	5.47	0.05	1.33	45	300	5.6	179	-	0.1	
2014-DD-033	JGT-05	281.55	287.77	Metasediment	9.12	0.05	0.15	0.005	0.07	2.38	20.8	84	2	515	5.29	0.07	0.74	98	640	3.2	270	-	0.19	
2014-DD-034	JGT-05	287.77	292.77	Metasediment	9.48	0.05	0.15	0.005	0.11	2.17	25.7	69	1.76	414	5.44	0.07	0.94	83	250	3.2	246	-	0.08	
2014-DD-035	JGT-05	299.18	308.77	Metasediment	9.13	0.05	0.17	0.005	0.1	2.35	21.8	79	2.07	518	4.81	0.07	1.05	95	450	3.6	190	-	0.26	
2014-DD-036	JGT-05	308.77	317	Metasediment	9.29	0.05	0.25	0.005	0.09	1.7	21.9	68	1.37	339	4.89	0.05	1.49	68	980	4.3	180	-	0.13	
2014-DD-037	JGT-05	336	346	Metasediment	9.87	0.05	0.36	0.005	0.04	1.69	26.3	79	1.43	409	5.28	0.06	1.15	66	210	3.7	172	-	0.26	
Median					8.6	0.05	0.35	0.005	0.05	1.8	24.1	91	2.0	386.5	4.9	0.06	0.48	74	465	4	92.5	-	0.135	
Minimum					7.9	0.05	0.05	0.005	0.01	0.1	0.6	6	0.1	32	3.1	0.04	0.11	5	210	2	5.3	-	0.005	
Maximum					9.9	0.1	0.53	0.03	0.11	2.4	30.6	136	2.5	518	7.0	0.11	1.49	136	2,720	9	270	-	0.27	
Count					24	24	24	24	24	24	24	24	24	24	24	24	24	24	24	24	24	0	24	
Waste Rock																								
Fox																								
SRK FOX 2	SRK FOX 2	0	0.3	Mixed Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SRK FOX 4	SRK FOX 4	0	0.3	Mixed Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SRK FOX 1	SRK FOX 1	0	0.3	Mixed Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SRK FOX 3	SRK FOX 3	0	0.3	Mixed Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SRK FOX 5	SRK FOX 5	0	0.3	Mixed Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Median					9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Minimum					8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Maximum					9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Count					5	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Koala																							
KNW 420 06+07 1A	-	-	-	Waste Rock	8.0	-	-	10	-	0.74	-	-	12	1,110	0.5	0.41	-	918	760	10	-	-	-
KNW 420 06+07 2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 465-1 2-1A	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 465-1 2-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-16 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450- 18+21 1	-	-	-	Waste Rock	9.6	-	-	5	-	2.0	-	-	1.8	295	0.5	2.9	-	39	1,080	6	-	-	-
KSW 450- 18+21 2	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-20 1A	-	-	-	Waste Rock	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-20 2A	-	-	-	Waste Rock	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-22 2A	-	-	-	Waste Rock	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-22 2AA	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-23 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-23 2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-25-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-25-2A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-28-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-28-2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-29-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-29-2A	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-31-1A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-31-2A	-	-	-	Waste Rock	9.0	-	-	5	-	1.9	-	-	1.9	390	1.0	3.1	-	47	1,010	4	-	-	-
KSW- 450-34-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 450-34-2A	-	-	-	Waste Rock	9.1	-	-	5	-	1.8	-	-	1.9	445	0.5	3.6	-	51	920	8	-	-	-
KSW- 450-35-1A	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 450-35-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 450-36-1A	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 450-36-2A	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 450-38-1A	-	-	-	Waste Rock	8.5	-	-	5	-	2.5	-	-	1.7	370	0.5	3.3	-	51	880	12	-	-	-
KSW- 450-38-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450 39 1A	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450 39 2A	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-27 1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-27 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-28 1A	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-28 2A	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-32-1A	-	-	-	Waste Rock	9.3	-	-	5	-	2.5	-	-	2.1	300	5.0	2.9	-	52	1,320	4	-	-	-
KSW 443-32-1AA	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-32-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Koala (continued)																							
KSW 443-32-2AA	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-33-1A	-	-	-	Waste Rock	9.4	-	-	5	-	1.8	-	-	1.6	350	0.5	3.2	-	45	900	4	-	-	-
KSW 443-33-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-34-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-34-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-35-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-35-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-36-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-36-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-38-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-38-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 445-40-2A	-	-	-	Waste Rock	8.7	-	-	5	-	2.2	-	-	2.1	450	1.0	3.9	-	48	970	8	-	-	-
KSW- 445-40-1A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-41-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-41-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-42-1A	-	-	-	Waste Rock	7.4	-	-	5	-	3.1	-	-	0.98	290	2.0	2.6	-	41	960	16	-	-	-
KSW- 443-42-2A	-	-	-	Waste Rock	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-43-1A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-43-2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443+450 2A	-	-	-	Waste Rock	9.6	-	-	5	-	1.9	-	-	1.8	430	0.5	2.9	-	45	880	10	-	-	-
KSW 443+450 1A	-	-	-	Waste Rock	9.4	-	-	5	-	1.9	-	-	1.8	420	0.5	2.7	-	45	920	12	-	-	-
KSW 443 46 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443 46 2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-6 1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-6 2A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-7 1A	-	-	-	Waste Rock	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-7 2A	-	-	-	Waste Rock	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-10-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-10-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-15-1A	-	-	-	Waste Rock	9.1	-	-	5	-	2.9	-	-	0.89	290	0.5	2.2	-	29	840	12	-	-	-
KSW 435-15-2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-16-1A	-	-	-	Waste Rock	8.7	-	-	5	-	1.6	-	-	1.4	335	0.5	4.0	-	40	730	10	-	-	-
KSW- 435-16-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-23-1A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-23-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 24 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 24 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-25 1A	-	-	-	Waste Rock	9.3	-	-	5	-	2.2	-	-	0.8	220	0.5	1.8	-	30	630	12	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Koala (continued)																							
KSW 435 26 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 26 2A	-	-	-	Waste Rock	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 27 1A	-	-	-	Waste Rock	9.7	-	-	5	-	1.9	-	-	1.8	340	3.0	3.2	-	45	990	14	-	-	0.04
KSW 435 27 2A	-	-	-	Waste Rock	9.6	-	-	5	-	1.8	-	-	2.3	415	2.0	3.1	-	88	970	14	-	-	0.08
KSW 435 30 1A	-	-	-	Waste Rock	8.4	-	-	5	-	2.7	-	-	0.72	245	3.0	2.3	-	28	800	16	-	-	0.04
KSW 435 30 2A	-	-	-	Waste Rock	9.4	-	-	5	-	2.3	-	-	1.1	505	3.0	3.0	-	34	1,060	14	-	-	0.01
KSW 435 31 1A	-	-	-	Waste Rock	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 31 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 34 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 34 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 42 1A	-	-	-	Waste Rock	9.2	-	-	5	-	2.5	-	-	1.4	315	3.0	2.4	-	48	980	8	-	-	0.07
KSW 435 42 2A	-	-	-	Waste Rock	9.5	-	-	5	-	2.4	-	-	1.6	295	2.0	2.4	-	65	390	10	-	-	0.13
KSW 435 51 1A	-	-	-	Waste Rock	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 51 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 52 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 52 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 53 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 53 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 54 1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 54 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 55 1A	-	-	-	Waste Rock	9.8	-	-	5	-	2.3	-	-	1.7	280	2.0	2.8	-	45	760	4	-	-	0.02
KSW 435 55 2A	-	-	-	Waste Rock	9.7	-	-	5	-	2.2	-	-	1.6	275	3.0	2.6	-	49	230	10	-	-	0.05
KSW 435 60 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 60 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 66 1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 66 2A	-	-	-	Waste Rock	7.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-59-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-59-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-77-1A	-	-	-	Waste Rock	9.3	-	-	5	-	1.7	-	-	1.7	385	1.0	3.3	-	42	1,060	10	-	-	0.01
KSW- 435-77-2A	-	-	-	Waste Rock	9.3	-	-	5	-	1.6	-	-	1.6	365	1.0	3.3	-	42	1,050	12	-	-	0.03
KSW- 435-81-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-81-2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-07-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-07-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-09-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-09-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-14-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-14-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Waste Rock (continued)																							
Koala (continued)																							
KSW 420 34 1A	-	-	-	Waste Rock	9.0	-	-	20	-	1.6	-	-	1.8	440	0.5	2.5	-	50	1,140	1	-	-	0.005
KSW 420 34 2A	-	-	-	Waste Rock	9.0	-	-	30	-	1.6	-	-	1.9	435	0.5	2.3	-	51	1,120	2	-	-	0.005
KSW 420 36 1A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 36 2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 37 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 37 2A	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 39 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 39 2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-30-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-30-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-38-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-38-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-38A-1A	-	-	-	Waste Rock	9.7	-	-	5	-	1.8	-	-	1.9	395	4.0	3.0	-	47	930	1	-	-	0.01
KSW-420-38A-2A	-	-	-	Waste Rock	9.5	-	-	5	-	1.9	-	-	1.9	345	4.0	3.1	-	33	810	8	-	-	0.06
KSW-420-40-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-40-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-41-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-41-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-46 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-46 2A	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405 04 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405 04 2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405 05 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405 05 2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405-25 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-06-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-06-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-10-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-10-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-11-1A	-	-	-	Waste Rock	8.8	-	-	5	-	2.2	-	-	2.0	320	2.0	2.7	-	47	710	4	-	-	0.04
KSW-405-11-2A	-	-	-	Waste Rock	8.7	-	-	5	-	1.6	-	-	1.5	270	3.0	2.9	-	43	400	2	-	-	0.09
KSW-405-13-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-13-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-17-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-17-2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-19-1A	-	-	-	Waste Rock	8.9	-	-	5	-	1.9	-	-	1.8	345	1.0	2.7	-	55	950	14	-	-	0.06
KSW-405-19-2A	-	-	-	Waste Rock	8.7	-	-	5	-	1.6	-	-	1.8	425	4.0	2.6	-	80	2,080	16	-	-	0.09
KSW-405-25 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Koala (continued)																							
KSW-405-38 1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-38 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-40 1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-40 2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-45 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-45 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-49 1A	-	-	-	Waste Rock	9.3	-	-	5	-	1.8	-	-	1.6	340	2.0	2.4	-	53	810	8	-	-	0.01
KSW-405-49 2A	-	-	-	Waste Rock	9.6	-	-	5	-	2.0	-	-	1.7	390	9.0	2.5	-	92	770	6	-	-	0.01
KSW-405-52-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-52-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-57-1A	-	-	-	Waste Rock	9.2	-	-	5	-	1.8	-	-	1.8	450	6.0	2.8	-	48	920	10	-	-	0.01
KSW-405-57-2A	-	-	-	Waste Rock	9.3	-	-	5	-	1.8	-	-	1.5	375	5.0	3.0	-	41	990	16	-	-	0.04
KSW-405-63-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-63-2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 390-21 1a	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 390-21 2a	-	-	-	Waste Rock	9.8	-	-	5	-	1.8	-	-	1.6	350	0.5	3.0	-	39	910	10	-	-	0.01
KSW-390-03-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-03-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-05-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-05-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-06-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-06-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-08-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-08-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-09-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-09-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-10-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-10-2A	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-11-1A	-	-	-	Waste Rock	8.5	-	-	5	-	2.6	-	-	2.0	375	7.0	2.6	-	48	900	8	-	-	0.02
KSW-390-11-2A	-	-	-	Waste Rock	8.8	-	-	5	-	1.8	-	-	1.7	355	8.0	3.0	-	46	940	6	-	-	0.02
KSW-390-12-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-12-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-24-1a	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-24-2a	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 375-03 1a	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 375-03 2a	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 375-06 1a	-	-	-	Waste Rock	9.6	-	-	5	-	1.6	-	-	1.3	280	1.0	4.1	-	26	700	8	-	-	0.03
KSW 375-06 2a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Waste Rock (continued)																							
Koala (continued)																							
KSW-375-13-1a	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-375-13-2a	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
				Median	9.2	-	-	5	-	1.9	-	-	1.7	352.5	2.0	2.9	-	47	920	10	-	-	0.03
				Minimum	7.2	-	-	5	-	0.74	-	-	0.72	220	0.5	0.41	-	26	230	1	-	-	0.005
				Maximum	10.1	-	-	30	-	3.1	-	-	12	1,110	9.0	4.1	-	918	2,080	16	-	-	0.13
				Count	192	0	0	40	0	40	0	0	40	40	40	40	0	40	40	40	0	0	26
Panda																							
PPW 360-76 1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-76 2A	-	-	-	Waste Rock	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-76-1B	-	-	-	Waste Rock	9.7	-	-	5	-	2.0	-	-	1.9	435	0.5	3.3	-	47	1,030	14	-	-	-
PPW- 360-76-2B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-77 1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-77 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-77-1B	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-77-2B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-78 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-78 2A	-	-	-	Waste Rock	9.5	-	-	5	-	1.9	-	-	1.9	365	0.5	2.9	-	55	960	8	-	-	-
PPW- 360-78-1B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-78-2B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-79 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-79 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-79-1B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-79-2B	-	-	-	Waste Rock	9.8	-	-	5	-	2.1	-	-	1.9	375	0.5	3.0	-	50	880	12	-	-	-
PPW 360-80 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-80 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-80-1B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-80-2B	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-82 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-82 2A	-	-	-	Waste Rock	9.4	-	-	5	-	1.8	-	-	1.9	380	0.5	3.0	-	47	1,020	10	-	-	-
PPW- 360-82-1B	-	-	-	Waste Rock	9.6	-	-	5	-	1.9	-	-	1.9	395	0.5	3.1	-	44	1,080	12	-	-	-
PPW- 360-82-2B	-	-	-	Waste Rock	9.7	-	-	5	-	1.8	-	-	1.8	365	0.5	3.2	-	42	1,030	14	-	-	-
PPW 360-89 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-89 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-29 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-29-1B	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-33 1A	-	-	-	Waste Rock	9.5	-	-	5	-	1.4	-	-	1.9	380	0.5	3.1	-	57	1,040	8	-	-	-
PPW 345-33 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-33-1B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Panda (continued)																							
PPW- 345-33-2B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-34 1A	-	-	-	Waste Rock	12.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-34 2A	-	-	-	Waste Rock	10.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-34-1B	-	-	-	Waste Rock	11.8	-	-	5	-	1.8	-	-	1.9	375	0.5	3.0	-	48	920	12	-	-	-
PPW- 345-34-2B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-35 1A	-	-	-	Waste Rock	10.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-35 2A	-	-	-	Waste Rock	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-35-1B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-35-2B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-36 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-36 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-36-1B	-	-	-	Waste Rock	9.3	-	-	5	-	2.1	-	-	2.3	320	0.5	3.0	-	103	740	16	-	-	-
PPW- 345-36-2B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-37 1A	-	-	-	Waste Rock	9.8	-	-	5	-	1.8	-	-	1.8	395	0.5	2.9	-	46	970	8	-	-	-
PPW 345-37 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-37-1B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-37-2B	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-41-1	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-42 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-42 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-42-1	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-42-2	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-43 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-43 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-43-1	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-43-2	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-48 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-49 1A	-	-	-	Waste Rock	9.6	-	-	5	-	1.8	-	-	2.0	370	0.5	3.1	-	64	910	10	-	-	-
PPW 345-49 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-50-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-50-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-52 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-52 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-55 1A	-	-	-	Waste Rock	9.5	-	-	5	-	1.8	-	-	1.9	330	0.5	3.1	-	44	950	10	-	-	-
PPW 345-55 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-56 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-56 2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-13 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Panda (continued)																							
PPW- 330-13-1B	-	-	-	Waste Rock	9.0	-	-	5	-	2.0	-	-	1.8	385	0.5	3.3	-	44	860	70	-	-	-
PPW- 330-16-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-16-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-17 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-17 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-17-1B	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-17-2B	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-18 1A	-	-	-	Waste Rock	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-18 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-18-1B	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-18-2B	-	-	-	Waste Rock	9.5	-	-	5	-	1.9	-	-	1.8	375	0.5	3.0	-	42	1,010	12	-	-	-
PPW 330-20 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-20 2A	-	-	-	Waste Rock	9.4	-	-	5	-	2.3	-	-	2.2	430	0.5	2.7	-	50	980	6	-	-	-
PPW- 330-20-1B	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-20-2B	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-28 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-28 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-28-1B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-28-2B	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-30 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-30 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-32-1A	-	-	-	Waste Rock	9.3	-	-	5	-	1.9	-	-	2.3	435	1.0	3.1	-	83	990	12	-	-	-
PPW 330-32-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-37-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-37-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-38 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-38 2A	-	-	-	Waste Rock	9.6	-	-	5	-	1.8	-	-	2.0	410	0.5	3.3	-	48	1,060	12	-	-	-
PPW 330-41-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-41-1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-41-2	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-41-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-44 1A	-	-	-	Waste Rock	9.7	-	-	5	-	1.9	-	-	2.0	400	0.5	3.1	-	52	990	12	-	-	-
PPW 330-44 1AA	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-44 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-44 2AA	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-47 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-47 2A	-	-	-	Waste Rock	9.6	-	-	5	-	1.8	-	-	2.0	345	0.5	3.0	-	68	870	12	-	-	-
PPW 330-48 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Panda (continued)																							
PPW 330-49 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-49 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-50 1A	-	-	-	Waste Rock	9.5	-	-	5	-	1.9	-	-	1.7	350	0.5	3.3	-	42	820	10	-	-	-
PPW 330-50 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-56 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-56 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-59 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-59 2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-61 1A	-	-	-	Waste Rock	9.5	-	-	5	-	2.2	-	-	1.9	360	0.5	3.1	-	51	1,010	6	-	-	-
PPW 330-61 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-62 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-62 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-63 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-63 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-64 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-64 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-65-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-65-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-66-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-66-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-70-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-70-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-71-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-71-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-72-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-72-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-73-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-73-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 332-75-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 332-75-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-76-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-77-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-77-2A	-	-	-	Waste Rock	9.2	-	-	5	-	1.9	-	-	2.0	460	0.5	3.5	-	69	900	6	-	-	-
PWP- 330-80-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-80-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-82-1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-03 1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-03 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Panda (continued)																							
PPW 315-04 1A	-	-	-	Waste Rock	9.5	-	-	5	-	1.7	-	-	2.2	460	0.5	2.9	-	68	990	8	-	-	-
PPW 315-04 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-05 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-05 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-06 1A	-	-	-	Waste Rock	9.8	-	-	5	-	1.6	-	-	1.6	330	0.5	3.1	-	40	850	10	-	-	-
PPW 315-06 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-10-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-10-2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-11-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-11-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-13-1A	-	-	-	Waste Rock	9.2	-	-	5	-	2.0	-	-	1.7	365	0.5	3.1	-	42	880	12	-	-	-
PPW 315-13-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-14-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-14-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-16-1A	-	-	-	Waste Rock	9.2	-	-	5	-	1.9	-	-	2.0	435	1.0	3.3	-	53	1,000	10	-	-	-
PPW 315-16-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-17-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 317-17-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-18-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-18-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-19-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-19-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-20-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-20-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-22-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-22-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-23-1A	-	-	-	Waste Rock	9.0	-	-	5	-	1.2	-	-	0.63	140	1.0	4.4	-	31	280	12	-	-	-
PPW 315-23-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-24-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-24-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-25-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-25-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-28-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-28-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-26-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-26-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-27-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-27-2A	-	-	-	Waste Rock	9.3	-	-	5	-	1.8	-	-	1.8	395	0.5	3.4	-	45	800	8	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Panda (continued)																							
PWP- 315-28-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-28-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-31-1A	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-31-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-31-2A	-	-	-	Waste Rock	8.4	-	-	5	-	4.3	-	-	5.3	370	0.5	0.45	-	50	810	1	-	-	-
PWP- 315-31-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-33-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-33-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-34-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-34-2A	-	-	-	Waste Rock	9.1	-	-	5	-	1.7	-	-	2.0	365	0.5	3.7	-	43	880	6	-	-	-
PWP- 315-35-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-35-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-36-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-36-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-42-1A	-	-	-	Waste Rock	9.4	-	-	5	-	1.8	-	-	2.3	520	0.5	4.1	-	57	1,080	8	-	-	-
PWP- 315-42-2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-43-1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-43-2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-44-1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-44-2A	-	-	-	Waste Rock	9.7	-	-	5	-	2.0	-	-	1.8	410	1.0	4.0	-	45	850	10	-	-	-
PWP- 315-45-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-45-2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-46-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-46-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315 48 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315 48 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-76-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-22-1A	-	-	-	Waste Rock	8.8	-	-	5	-	1.9	-	-	2.2	480	2.0	3.8	-	57	1,060	8	-	-	-
PWP- 300-22-2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-24-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-24-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-35-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-35-2A	-	-	-	Waste Rock	9.4	-	-	5	-	1.9	-	-	2.2	510	0.5	3.9	-	55	1,010	10	-	-	-
PWP- 300-36-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-36-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-38-1A	-	-	-	Waste Rock	9.8	-	-	5	-	2.0	-	-	2.1	415	0.5	3.9	-	52	970	8	-	-	-
PWP- 300-38-2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-42-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Panda (continued)																							
PWP- 300-42-2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-48-1A	-	-	-	Waste Rock	9.7	-	-	5	-	1.9	-	-	2.0	450	2.0	4.0	-	44	940	8	-	-	-
PWP- 300-48-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 50 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 50 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 53 1A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 53 1A	-	-	-	Waste Rock	9.6	-	-	5	-	1.7	-	-	2.1	425	3.0	3.0	-	58	1,200	10	-	-	0.01
PPW 300 53 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 53 2A	-	-	-	Waste Rock	9.7	-	-	5	-	1.7	-	-	1.9	340	4.0	2.9	-	47	1,010	8	-	-	0.01
PPW 300 54 1A	-	-	-	Waste Rock	9.7	-	-	5	-	1.8	-	-	1.9	445	0.5	3.1	-	54	1,010	10	-	-	0.005
PPW 300 54 2A	-	-	-	Waste Rock	9.3	-	-	5	-	1.6	-	-	2.0	395	3.0	2.9	-	59	980	12	-	-	0.05
PPW 300 55 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 55 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 57 1A	-	-	-	Waste Rock	9.5	-	-	5	-	1.6	-	-	2.0	390	3.0	2.9	-	60	1,020	8	-	-	0.02
PPW 300 57 2A	-	-	-	Waste Rock	9.7	-	-	5	-	1.5	-	-	1.8	360	2.0	2.8	-	54	1,000	6	-	-	0.01
PPW 300 61 1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 61 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 63 1A	-	-	-	Waste Rock	9.7	-	-	5	-	1.8	-	-	1.9	375	4.0	2.8	-	53	740	8	-	-	0.04
PPW 300 63 2A	-	-	-	Waste Rock	9.6	-	-	5	-	1.7	-	-	1.8	360	4.0	3.2	-	44	910	8	-	-	0.02
PPW 300 65 1A	-	-	-	Waste Rock	9.8	-	-	5	-	1.8	-	-	1.9	385	3.0	2.7	-	48	920	12	-	-	0.01
PPW 300 65 2A	-	-	-	Waste Rock	9.8	-	-	5	-	1.9	-	-	1.7	355	3.0	2.8	-	41	960	2	-	-	0.01
PPW 300 66 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 66 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 68 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 68 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 69 1A	-	-	-	Waste Rock	8.6	-	-	5	-	1.5	-	-	2.8	350	1.0	2.1	-	149	850	1	-	-	0.10
PPW 300 69 2A	-	-	-	Waste Rock	9.9	-	-	5	-	1.8	-	-	1.7	320	2.0	2.6	-	44	880	8	-	-	0.005
PPW- 300-71-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-71-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-72-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-72-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-73-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-73-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-75-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-75-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 02 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 02 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 03 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Panda (continued)																							
PPW 285 03 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 04 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 04 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 05 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 05 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 06 1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 06 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 10 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 10 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 23 1	-	-	-	Waste Rock	8.9	-	-	20	-	1.7	-	-	2.1	295	0.5	2.7	-	95	710	6	-	-	0.08
PPW 285 23 1A	-	-	-	Waste Rock	9.3	-	-	30	-	1.4	-	-	1.3	250	0.5	2.9	-	36	580	1	-	-	0.03
PPW 285 27 1	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 27 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 28 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 28 1B	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 30 1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 30 1B	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 32 1	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 32 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 33 1	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 33 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-07-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-07-1A	-	-	-	Waste Rock	9.4	-	-	5	-	1.6	-	-	1.7	390	1.0	3.1	-	46	990	12	-	-	0.01
PPW- 285-07-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-07-2A	-	-	-	Waste Rock	9.2	-	-	5	-	1.5	-	-	1.6	360	0.5	3.2	-	41	960	8	-	-	0.01
PPW- 285-08-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-08-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-10-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-10-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-12-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-12-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-15-1A	-	-	-	Waste Rock	9.1	-	-	5	-	1.7	-	-	1.7	375	0.5	3.1	-	45	1,010	14	-	-	0.01
PPW- 285-15-2A	-	-	-	Waste Rock	9.2	-	-	5	-	1.6	-	-	1.6	355	1.0	3.1	-	43	930	10	-	-	0.01
PPW- 285-16-1A	-	-	-	Waste Rock	9.3	-	-	5	-	1.6	-	-	1.5	280	0.5	2.7	-	48	610	10	-	-	0.05
PPW- 285-16-2A	-	-	-	Waste Rock	9.4	-	-	5	-	2.0	-	-	1.8	315	1.0	2.7	-	80	300	10	-	-	0.17
PPW- 285-19-1A	-	-	-	Waste Rock	9.3	-	-	5	-	1.8	-	-	1.8	370	1.0	2.8	-	65	910	10	-	-	0.02
PPW- 285-19-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-24-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Panda (continued)																							
PPW- 285-24-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 270-02-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 270-02-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 03 1	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 03 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 04 1	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 04 1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 05 1	-	-	-	Waste Rock	9.3	-	-	10	-	1.5	-	-	1.7	365	0.5	2.2	-	47	890	2	-	-	0.005
PPW 270 05 1A	-	-	-	Waste Rock	9.4	-	-	30	-	1.8	-	-	1.9	410	0.5	2.3	-	59	1,050	6	-	-	0.01
PPW 270 07 1	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 07 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 10 1	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 10 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 13 1	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 13 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 14 1	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 14 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PG-270-27 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PG-270-27 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-07-1A	-	-	-	Waste Rock	9.4	-	-	5	-	1.6	-	-	2.1	535	1.0	2.8	-	45	970	1	-	-	0.01
PPW-270-07-2A	-	-	-	Waste Rock	9.4	-	-	5	-	1.6	-	-	2.0	510	0.5	2.8	-	44	930	6	-	-	0.01
PPW-270-16-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-16-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-17-1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-17-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-18-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-18-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-21-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-21-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-22-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-22-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-24-1A	-	-	-	Waste Rock	9.6	-	-	5	-	1.8	-	-	1.6	400	0.5	2.7	-	47	840	8	-	-	0.01
PPW-270-24-2A	-	-	-	Waste Rock	9.3	-	-	5	-	1.7	-	-	2.1	320	5.0	2.5	-	82	1,120	1	-	-	0.03
PPW-270-25-1A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-25-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-29 1A	-	-	-	Waste Rock	9.8	-	-	5	-	1.4	-	-	0.76	205	4.0	3.1	-	21	410	10	-	-	0.01
PPW-270-29 2A	-	-	-	Waste Rock	9.5	-	-	5	-	1.7	-	-	1.8	375	3.0	2.5	-	52	860	6	-	-	0.02
PG-255-11 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035	
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S	
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
Waste Rock (continued)																								
Panda (continued)																								
PG-255-11 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-03-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-03-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-04-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-04-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-05-1A	-	-	-	Waste Rock	9.4	-	-	5	-	1.6	-	-	1.4	360	3.0	2.7	-	40	690	6	-	-	0.01	-
PPW-255-05-2A	-	-	-	Waste Rock	9.5	-	-	5	-	1.9	-	-	1.6	470	0.5	2.5	-	46	830	12	-	-	0.01	-
PPW-255-07 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-07 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-08-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-08-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-13 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-13 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-15 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-15 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-17 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-17 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-19 1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-19 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-21 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-21 2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-24-1A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-24-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-26-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-26-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-27-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-27-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-29-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-29-2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-32-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-32-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-33-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-33-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-02-240-28-1a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-02-240-28-2a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-02-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-02-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-03-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
		From	To		Paste pH	Ge	Hf	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
					unit	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Panda (continued)																							
PPW-240-03-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-240-15-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-240-15-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-240-31-1a	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-240-31-2a	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-240-32-1a	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-240-32-2a	-	-	-	Waste Rock	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-240-38-1a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-240-38-2a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-240-39-1a	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-240-39-2a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PP-225-09-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PP-225-14-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PP-225-14-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-225-07-1a	-	-	-	Waste Rock	9.4	-	-	5	-	1.9	-	-	1.7	355	0.5	2.9	-	43	810	12	-	-	0.01
PPW-225-07-2a	-	-	-	Waste Rock	9.6	-	-	5	-	1.7	-	-	1.7	385	0.5	2.8	-	40	820	8	-	-	0.005
SRK-ROAD-18B	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
SRK-PPWR-18B	-	-	-	Waste Rock	9.0	-	-	0.005	-	1.9	-	-	2.1	403	2.0	3.1	-	85	1,090	10	-	-	0.07
			Median		9.5	-	-	5	-	1.8	-	-	1.9	375	0.5	3.0	-	48	935	10	-	-	0.01
			Minimum		8.4	-	-	0.005	-	1.2	-	-	0.63	140	0.5	0.45	-	21	280	1	-	-	0.005
			Maximum		12.1	-	-	30	-	4.3	-	-	5.3	535	5.0	4.4	-	149	1,200	70	-	-	0.17
			Count		391	0	0	70	0	70	0	0	70	70	70	70	0	70	70	70	0	0	34
Waste Rock Dump																							
BH-00-01 0-2	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 2-4	-	-	-	Waste Rock	8.9	-	-	10	-	1.9	-	-	2.0	415	0.5	3.0	-	71	970	46	-	-	-
BH-00-01 4-6	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 6-8	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 8-10	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 10-12	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 12-14	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 14-16	-	-	-	Waste Rock	9.4	-	-	5	-	1.7	-	-	1.4	545	1.0	3.3	-	42	810	764	-	-	-
BH-00-01 16-18	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 18-19	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 0-2	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 2-4	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 4-6	-	-	-	Waste Rock	9.0	-	-	5	-	2.0	-	-	1.8	380	0.5	3.3	-	48	950	28	-	-	-
BH-00-02 6-8	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 8-10	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb	Rb	Re	S
		unit	ppm		ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																							
Waste Rock Dump (continued)																							
BH-00-02 10-12	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 12-14	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 14-16	-	-	-	Waste Rock	9.6	-	-	5	-	2.2	-	-	1.9	440	0.5	3.3	-	49	900	288	-	-	-
BH-00-02 16-18	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 18-19	-	-	-	Waste Rock	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 0-2	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 2-4	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 4-6	-	-	-	Waste Rock	8.3	-	-	5	-	2.1	-	-	1.8	410	3.0	3.0	-	56	870	116	-	-	-
BH-00-02A 6-8	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 8-10	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 10-12	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 12-14	-	-	-	Waste Rock	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 16-18	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 18-19	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03 0-2	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03 2-4	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03 4-6	-	-	-	Waste Rock	9.5	-	-	5	-	1.9	-	-	1.8	400	0.5	3.0	-	45	900	24	-	-	-
BH-00-03 6-8	-	-	-	Waste Rock	7.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03A 0-2	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03A 2-4	-	-	-	Waste Rock	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03A 4-6	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03A 6-8	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 0-2	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 2-4	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 4-6	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 6-8	-	-	-	Waste Rock	9.2	-	-	5	-	2.0	-	-	2.0	400	1.0	3.2	-	57	870	38	-	-	-
BH-00-06 8-10	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 10-12	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 12-14	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 14-16	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 16-18	-	-	-	Waste Rock	8.9	-	-	5	-	1.8	-	-	3.4	445	0.5	2.9	-	193	1,020	28	-	-	-
BH-00-06 18-20	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 20-22	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 22-24	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 24-26	-	-	-	Waste Rock	9.6	-	-	5	-	2.1	-	-	2.1	430	0.5	3.0	-	64	750	168	-	-	-
BH-00-06 26-28	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part B**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	-	-	0.08	-	2.085	39	20	2.33	950	1.3	2.355	-	84	1,050	19	-	-	0.035
		From	To		Paste pH unit	Ge ppm	Hf ppm	Hg ppm	In ppm	K %	La ppm	Li ppm	Mg %	Mn ppm	Mo ppm	Na %	Nb ppm	Ni ppm	P ppm	Pb ppm	Rb ppm	Re ppm	S %
Waste Rock (continued)																							
Waste Rock Dump (continued)																							
	BH-00-06	28-30	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
	BH-00-06	30-32	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
				Median	9.2	-	-	5	-	2.0	-	-	1.9	415	0.5	3.0	-	56	900	46	-	-	-
				Minimum	7.4	-	-	5	-	1.7	-	-	1.4	380	0.5	2.9	-	42	750	24	-	-	-
				Maximum	9.7	-	-	10	-	2.2	-	-	3.4	545	3.0	3.3	-	193	1,020	764	-	-	-
				Count	53	0	0	9	0	9	0	0	9	9	9	9	0	9	9	9	0	0	0

Note:

a) Typical crustal abundance for continental rocks taken from Price WL. 1997. Draft Guidelines and Recommended Methods for the Prediction of Metal Leaching and Acid Rock Drainage at Mine sites in British Columbia. British Columbia Ministry of Employment and Investment, Energy and Minerals Division: Victoria, BC, Canada.

- >1 x = Concentration greater than typical crustal abundance.
- >5 x = Concentration greater than 5 x the typical crustal abundance.
- >10 x = Concentration greater than 10 x the typical crustal abundance.
- 0.1 Below detection limit, given half detection limit value.
- 15.01 Above upper detection, given value of detection limit +0.01.

No. = number; - = not available; % = percent; pH = potential of hydrogen, provides measure of the acidity or alkalinity of a solution on a scale of 0 to 14; ppm = parts per million; > = greater than.

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-	
																							Paste pH
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Overburden																							
Koala Black Clay																							
KBC-405-1	-	-	-	Black Clay	7.7	2.5	-	-	-	1,020	-	-	-	0.30	-	-	-	99	5.0	-	80	-	
KBC-405-2	-	-	-	Black Clay	7.8	2.5	-	-	-	905	-	-	-	0.30	-	-	-	83	5.0	-	68	-	
KBC-405-3	-	-	-	Black Clay	7.7	2.5	-	-	-	1,055	-	-	-	0.28	-	-	-	104	5.0	-	80	-	
KBC-405-4	-	-	-	Black Clay	7.7	2.5	-	-	-	1,025	-	-	-	0.26	-	-	-	94	5.0	-	68	-	
KBC-405-5	-	-	-	Black Clay	7.7	2.5	-	-	-	878	-	-	-	0.32	-	-	-	100	5.0	-	80	-	
KBC-405-6	-	-	-	Black Clay	7.7	2.5	-	-	-	941	-	-	-	0.32	-	-	-	95	5.0	-	74	-	
KBC-405-7	-	-	-	Black Clay	7.8	2.5	-	-	-	960	-	-	-	0.28	-	-	-	110	5.0	-	76	-	
KBC-405-8	-	-	-	Black Clay	7.9	2.5	-	-	-	915	-	-	-	0.27	-	-	-	95	5.0	-	66	-	
KBC-405-46-1A	-	-	-	Black Clay	7.4	2.5	-	-	-	931	-	-	-	0.39	-	-	-	111	5.0	-	80	-	
KBC-408	-	-	-	Black Clay	7.2	2.5	-	-	-	567	-	-	-	0.24	-	-	-	72	5.0	-	44	-	
KBC-DUMP-1A	-	-	-	Black Clay	7.7	2.5	-	-	-	1,025	-	-	-	0.37	-	-	-	111	5.0	-	80	-	
KBC-DUMP-2A	-	-	-	Black Clay	7.5	2.5	-	-	-	751	-	-	-	0.31	-	-	-	109	5.0	-	90	-	
KBC-DUMP-3A	-	-	-	Black Clay	7.4	5.0	-	-	-	625	-	-	-	0.28	-	-	-	118	5.0	-	86	-	
KBC-DUMP-4A	-	-	-	Black Clay	7.8	2.5	-	-	-	897	-	-	-	0.33	-	-	-	97	5.0	-	78	-	
KBC-DUMP-5A	-	-	-	Black Clay	7.2	5.0	-	-	-	1,010	-	-	-	0.36	-	-	-	107	5.0	-	78	-	
KBC-DUMP-6A	-	-	-	Black Clay	7.3	2.5	-	-	-	993	-	-	-	0.37	-	-	-	108	5.0	-	80	-	
KBC-DUMP-7A	-	-	-	Black Clay	7.3	5.0	-	-	-	804	-	-	-	0.35	-	-	-	99	5.0	-	80	-	
KBC-DUMP-8A	-	-	-	Black Clay	7.4	2.5	-	-	-	536	-	-	-	0.27	-	-	-	107	5.0	-	72	-	
KBC-DUMP-9A	-	-	-	Black Clay	7.3	2.5	-	-	-	610	-	-	-	0.27	-	-	-	93	5.0	-	80	-	
KBC-DUMP-10A	-	-	-	Black Clay	7.4	2.5	-	-	-	867	-	-	-	0.33	-	-	-	100	5.0	-	74	-	
Median					7.6	2.5	-	-	-	910	-	-	-	0.31	-	-	-	100	5.0	-	79	-	
Minimum					7.2	2.5	-	-	-	536	-	-	-	0.24	-	-	-	72	5.0	-	44	-	
Maximum					7.9	5.0	-	-	-	1,055	-	-	-	0.39	-	-	-	118	5.0	-	90	-	
Count					20	20	0	0	0	20	0	0	0	20	0	0	0	20	20	0	20	0	
Koala Till																							
KT-420-47 1A	-	-	-	Till	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KT-420-47 2A	-	-	-	Till	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Median					8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Minimum					8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Maximum					8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Count					2	0	0	0	0	-	0	0	0	0	0	0	0	0	0	0	0	0	

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	General Rock Type																		
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-	
		From	To	unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U (ICP)	U (XRF)	V	W	Y	Zn	Zr		
Diabase																							
Beartooth																							
60	96-35	36.98	37.43	Diabase	9.6	2.5	3.0	-	5.0	41	-	-	-	0.14	-	-	-	38	5.0	19	50	-	
61	96-35	42.02	42.63	Diabase	9.7	2.5	2.0	-	5.0	31	-	-	-	0.21	-	-	-	54	5.0	8.0	57	-	
Median					9.6	2.5	2.5	-	5.0	36	-	-	-	0.18	-	-	-	46	5.0	14	54	-	
Minimum					9.6	2.5	2.0	-	5.0	31	-	-	-	0.14	-	-	-	38	5.0	8.0	50	-	
Maximum					9.7	2.5	3.0	-	5.0	41	-	-	-	0.21	-	-	-	54	5.0	19	57	-	
Count					2	2	2	0	2	2	0	0	0	2	0	0	0	2	2	2	2	0	
Fox																							
FUC 3-3 - 65	FUC 3-3	65	65.3	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 66	FUC 3-3	66	66.3	Diabase	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 67	FUC 3-3	67	67.3	Diabase	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 70	FUC 3-3	70	70.3	Diabase	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 75	FUC 3-3	75	75.3	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 80	FUC 3-3	80	80.3	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 85	FUC 3-3	85	85.3	Diabase	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 90	FUC 3-3	90	90.3	Diabase	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 95	FUC 3-3	95	95.3	Diabase	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 712	Decline	712	712.1	Diabase	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Decline - 1202.2	Decline	1,202.2	1,202.3	Diabase	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 1-2 - 87.78	FUC 1-2	87.78	93.72	Diabase	8.2	0.2	-	-	-	178	-	-	-	0.87	-	-	-	342	5.0	-	12	-	
FUC 1-2 - 93.72	FUC 1-2	93.72	99.61	Diabase	8.1	0.2	-	-	-	166	-	-	-	0.83	-	-	-	325	5.0	-	86	-	
FUC 1-2 - 99.61	FUC 1-2	99.61	108.66	Diabase	8.1	0.1	-	-	-	199	-	-	-	0.91	-	-	-	338	5.0	-	74	-	
FUC 1-2 - 108.66	FUC 1-2	108.66	113.03	Diabase	8.3	0.1	-	-	-	181	-	-	-	0.91	-	-	-	352	5.0	-	54	-	
FGT-05 - 11.4	FGT-05	11.4	14.3	Diabase	-	2.5	-	-	-	314	-	-	-	0.68	-	-	-	279	5.0	-	84	-	
FGT-05 - 134.9	FGT-05	134.9	142	Diabase	8.5	2.5	-	-	-	175	-	-	-	0.90	-	-	-	364	5.0	-	98	-	
FGT-05 - 142	FGT-05	142	149.5	Diabase	-	2.5	-	-	-	172	-	-	-	0.81	-	-	-	337	5.0	-	88	-	
FGT-05 - 149.5	FGT-05	149.5	157	Diabase	-	2.5	-	-	-	193	-	-	-	0.93	-	-	-	342	5.0	-	96	-	
FGT-05 - 157	FGT-05	157	164.5	Diabase	-	2.5	-	-	-	174	-	-	-	0.86	-	-	-	347	5.0	-	92	-	
FGT-05 - 164.5	FGT-05	164.5	172	Diabase	-	5.0	-	-	-	160	-	-	-	0.86	-	-	-	353	5.0	-	98	-	
FGT-05 - 172	FGT-05	172	175.36	Diabase	-	2.5	-	-	-	177	-	-	-	0.88	-	-	-	359	5.0	-	96	-	
Fox-250-Diabase 8-Oct-09	-	-	-	Diabase	9.0	12	34	-	-	267	-	-	10	0.92	5.0	5.0	-	327	5.0	-	104	-	
Median					8.6	2.5	34	-	-	178	-	-	10	0.88	5.0	5.0	-	342	5.0	-	90	-	
Minimum					8.1	0.1	34	-	-	160	-	-	10	0.68	5.0	5.0	-	279	5.0	-	12	-	
Maximum					9.3	12	34	-	-	314	-	-	10	0.93	5.0	5.0	-	364	5.0	-	104	-	
Count					17	12	1	0	0	12	0	0	1	12	1	1	0	12	12	0	12	0	
Misery																							
MDC-10 142.36	-	-	-	Diabase	9.4	2.5	-	-	-	200	-	-	-	1.1	-	-	-	363	5.0	-	142	-	
MDC-10 159.49	-	-	-	Diabase	9.3	2.5	-	-	-	203	-	-	-	0.95	-	-	-	285	5.0	-	126	-	
MDC-10 171.12	-	-	-	Diabase	9.2	2.5	-	-	-	200	-	-	-	1.2	-	-	-	381	5.0	-	158	-	

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-																	
					General Rock Type	Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70
		From	To	unit		Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr
Diabase (continued)																						
Misery (continued)																						
MD 450-26 1A	-	-	-	Diabase	8.8	0.1	-	-	-	206	-	-	-	0.99	-	-	-	365	5.0	-	110	-
MD 430 21 1A	-	-	-	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD 430 21 2A	-	-	-	Diabase	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD 430 25 1A	-	-	-	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD 430 25 2A	-	-	-	Diabase	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD- 430-33-1A	-	-	-	Diabase	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD- 430-34-2A	-	-	-	Diabase	8.8	2.5	-	-	-	217	-	-	-	1.1	-	-	-	368	5.0	-	118	-
MD-430-91-01	-	-	-	Diabase	8.7	0.08	42	2.0	-	203	-	0.025	2.6	1.1	0.18	0.7	-	366	0.3	-	116	-
MD-430-91-02	-	-	-	Diabase	9.5	0.025	15	1.0	-	229	-	0.025	5.7	0.40	1.1	3.0	-	121	1.1	-	132	-
MD- 420-04-1A	-	-	-	Diabase	8.3	2.5	-	-	-	184	-	-	-	1.0	-	-	-	347	5.0	-	116	-
MD- 420-04-2A	-	-	-	Diabase	8.3	2.5	-	-	-	194	-	-	-	0.95	-	-	-	347	5.0	-	128	-
MD-420-12-01	-	-	-	Diabase	9.1	0.05	45	2.0	-	248	-	0.025	2.1	1.2	0.28	0.5	-	420	0.2	-	158	-
MD-410-08-01	-	-	-	Diabase	8.8	0.08	38	3.0	-	251	-	0.07	2.3	1.0	0.26	1.0	-	323	0.3	-	132	-
MD-410-08-02	-	-	-	Diabase	8.9	0.06	36	3.0	-	262	-	0.025	2.3	1.0	0.29	0.9	-	328	0.3	-	124	-
MD-410-07-01	-	-	-	Diabase	9.4	0.07	40	3.0	-	234	-	0.07	2.5	1.1	0.41	0.6	-	381	0.3	-	162	-
MD-410-07-02	-	-	-	Diabase	9.1	0.05	38	3.0	-	213	-	0.025	2.5	1.2	0.23	0.6	-	384	0.3	-	143	-
MD 400-42-1a	-	-	-	Diabase	8.7	2.5	-	-	-	177	-	-	-	1.1	-	-	-	366	5.0	-	138	-
MD-400-49-2a	-	-	-	Diabase	8.7	2.5	-	-	-	168	-	-	-	0.93	-	-	-	322	5.0	-	142	-
MD-390-38-2A	-	-	-	Diabase	9.2	5.0	-	-	-	209	-	-	-	0.96	-	-	-	435	5.0	-	134	-
MD-380-32-1A	-	-	-	Diabase	8.8	2.5	-	-	-	206	-	-	-	0.92	-	-	-	336	5.0	-	164	-
MD-370-22-1	-	-	-	Diabase	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MD-370-22-2	-	-	-	Diabase	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MDC-28 3.9-7	-	-	-	Diabase	9.0	0.05	2.0	0.25	-	20	-	0.1	1.5	0.30	0.05	0.4	-	168	0.05	-	78	-
MDC-28 7-10	-	-	-	Diabase	9.2	0.05	1.9	0.6	-	21	-	0.1	1.4	0.27	0.05	0.3	-	180	0.05	-	78	-
MDC-28 10-13	-	-	-	Diabase	9.4	0.05	1.6	0.8	-	19	-	0.1	1.2	0.21	0.05	0.2	-	244	0.05	-	70	-
MDC-28 13-16	-	-	-	Diabase	9.3	0.05	1.7	0.8	-	18	-	0.1	1.3	0.22	0.05	0.2	-	171	0.05	-	75	-
MDC-28 16-19	-	-	-	Diabase	9.2	0.05	1.8	0.6	-	19	-	0.1	1.5	0.27	0.1	0.2	-	168	0.05	-	77	-
MDC-28 19-22	-	-	-	Diabase	9.1	0.05	1.9	0.6	-	16	-	0.1	1.4	0.23	0.1	0.2	-	117	0.05	-	57	-
MDC-28 23-26.07	-	-	-	Diabase	9.1	0.05	2.9	0.25	-	32	-	0.1	1.5	0.23	0.05	0.8	-	130	0.05	-	81	-
MGT-57 28.7-32	-	-	-	Diabase	9.1	0.05	0.3	0.25	-	12	-	0.1	4.2	0.027	0.05	2.4	-	4.0	0.05	-	22	-
MGT-57 40-43	-	-	-	Diabase	9.2	0.05	1.7	0.25	-	15	-	0.1	1.4	0.21	0.1	0.2	-	151	0.05	-	72	-
MGT-57 51-54	-	-	-	Diabase	9.4	0.05	1.9	0.7	-	24	-	0.1	1.3	0.24	0.1	0.2	-	131	0.05	-	63	-
MGT-57 62-65	-	-	-	Diabase	9.4	0.05	2.0	1.0	-	16	-	0.1	1.2	0.23	0.05	0.2	-	167	0.05	-	78	-
MGT-57 74-77	-	-	-	Diabase	8.3	0.05	2.0	0.8	-	18	-	0.1	1.4	0.23	0.1	0.5	-	149	0.05	-	66	-
MGT-66 16-19	-	-	-	Diabase	9.8	0.05	0.6	0.25	-	7	-	0.1	25	0.085	0.2	5.4	-	8.0	0.05	-	46	-
MGT-43 286-289	-	-	-	Diabase	9.0	0.05	2.4	0.25	-	18	-	0.1	1.6	0.23	0.1	0.3	-	157	0.05	-	95	-
MGT-43 289-292	-	-	-	Diabase	8.9	0.05	3.6	0.25	-	20	-	0.1	1.8	0.25	0.2	0.2	-	164	0.2	-	106	-
MGT-43 292-295	-	-	-	Diabase	8.9	0.05	3.1	0.25	-	16	-	0.1	1.6	0.27	0.1	0.2	-	153	0.1	-	87	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval From To		Price Crustal Abundances General Rock Type	Price Crustal Abundances																		
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-	
					unit	Sb ppm	Sc ppm	Se ppm	Sn ppm	Sr ppm	Ta ppm	Te ppm	Th ppm	Ti %	Tl ppm	U (ICP) ppm	U (XRF) ppm	V ppm	W ppm	Y ppm	Zn ppm	Zr ppm	
Diabase (continued)																							
Misery (continued)																							
MGT-43 300-303	-	-	-	Diabase	8.9	0.05	2.8	0.25	-	20	-	0.1	1.4	0.26	0.05	0.2	-	151	0.1	-	146	-	
MGT-43 303-306	-	-	-	Diabase	8.8	0.05	3.5	0.25	-	21	-	0.1	1.9	0.25	0.05	0.5	-	107	0.1	-	88	-	
MGT-43 306-309	-	-	-	Diabase	9.1	0.05	2.2	0.25	-	20	-	0.1	1.6	0.23	0.1	0.2	-	143	0.05	-	93	-	
MGT-43 309-311.13	-	-	-	Diabase	9.0	0.05	2.8	0.25	-	15	-	0.1	1.5	0.25	0.05	0.2	-	138	0.05	-	99	-	
MGT-54 211-213.47	-	-	-	Diabase	9.2	0.05	2.6	0.25	-	19	-	0.1	1.5	0.27	0.1	0.2	-	167	0.05	-	92	-	
MGT-54 208-211	-	-	-	Diabase	9.1	0.05	2.5	0.25	-	22	-	0.1	1.6	0.24	0.1	0.2	-	127	0.05	-	98	-	
97-54	97-54	126.14	126.46	Diabase	9.1	2.5	4.0	-	5.0	57	-	-	-	0.40	-	-	-	284	5.0	16	143	-	
97-54	97-54	18.88	19.08	Diabase	9.1	2.5	3.0	-	5.0	51	-	-	-	0.43	-	-	-	293	5.0	17	127	-	
97-54	97-54	20.54	20.65	Diabase	8.2	2.5	18	-	5.0	36	-	-	-	0.57	-	-	-	337	5.0	21	114	-	
97-54	97-54	41.3	42.03	Diabase	8.6	2.5	9.0	-	5.0	51	-	-	-	0.37	-	-	-	333	5.0	17	115	-	
97-54	97-54	52.75	53.29	Diabase	9.5	2.5	3.0	-	5.0	70	-	-	-	0.42	-	-	-	284	5.0	11	86	-	
97-54	97-54	81.07	81.38	Diabase	9.4	2.5	3.0	-	5.0	44	-	-	-	0.42	-	-	-	314	5.0	15	111	-	
HC-Pdef-1	-	-	-	Diabase	8.7	0.07	44	2.0	1.2	168	0.32	0.025	0.6	0.94	0.06	0.2	-	369	0.2	26	108	82	
Median					9.0	0.05	2.9	0.6	5.0	44	0.32	0.1	1.6	0.40	0.1	0.25	-	284	0.2	17	110	82	
Minimum					8.2	0.025	0.3	0.25	1.2	7	0.32	0.025	0.6	0.027	0.05	0.2	-	4.0	0.05	11	22	82	
Maximum					9.8	5.0	45	3.0	5.0	262	0.32	0.1	25	1.2	1.1	5.4	-	435	5.0	26	164	82	
Count					54	47	36	30	7	47	1	30	30	47	30	30	0	47	47	7	47	1	
Sable																							
SDC-13	SDC-13	164.64	164.91	Diabase	8.9	2.5	3.0	-	5.0	37	-	-	-	0.55	-	-	-	291	5.0	16	136	-	
Median					8.9	2.5	3.0	-	5.0	37	-	-	-	0.55	-	-	-	291	5.0	16	136	-	
Minimum					8.9	2.5	3.0	-	5.0	37	-	-	-	0.55	-	-	-	291	5.0	16	136	-	
Maximum					8.9	2.5	3.0	-	5.0	37	-	-	-	0.55	-	-	-	291	5.0	16	136	-	
Count					1	1	1	0	1	1	0	0	0	1	0	0	0	1	1	1	1	0	
Jay																							
2014-DD-040	JGT-03	349.4	356.81	Diabase	9.10	0.025	4.8	0.5	0.3	29	0.025	0.025	0.8	0.28	0.15	0.16	-	159	0.05	12	65	10.9	
2014-DD-043	JGT-03	47.22	57.11	Diabase	9.05	0.025	3.4	0.5	0.4	18	0.025	0.025	1	0.31	0.23	0.52	-	112	0.05	10.6	65	11.3	
2014-DD-044	JGT-03	57.95	65.48	Diabase	9.05	0.025	2.9	0.5	0.3	21	0.025	0.025	0.5	0.36	0.25	0.17	-	129	0.05	12.1	64	9.7	
2014-DD-049	JGT-02	413.02	421.45	Diabase	9.02	0.025	2.9	0.5	0.15	25	0.025	0.025	0.9	0.25	0.13	0.24	-	149	0.05	10.3	57	8.6	
Median					9.1	0.0	3.2	0.5	0.3	23	0.025	0.025	0.85	0.3	0.19	0.205	-	139	0.1	11	65	10.3	
Minimum					9.0	0.0	2.9	0.5	0.2	18	0.025	0.025	0.5	0.25	0.13	0.16	-	112	0.1	10	57	8.6	
Maximum					9.1	0.0	4.8	0.5	0.4	29	0.025	0.025	1	0.36	0.25	0.52	-	159	0.1	12	65	11.3	
Count					4	4	4	4	4	4	4	4	4	4	4	4	0	4	4	4	4	4	
Granite																							
Beartooth																							
58	96-35	13.5	13.95	Granite	9.8	2.5	5.0	-	5.0	60	-	-	-	0.28	-	-	-	82	5.0	6.0	76	-	
59	96-35	30	30.62	Granite	9.8	2.5	4.0	-	5.0	33	-	-	-	0.26	-	-	-	73	5.0	6.0	71	-	
62	96-35	30.14	46.78	Granite	9.8	2.5	3.0	-	5.0	45	-	-	-	0.27	-	-	-	81	5.0	6.0	80	-	
63	96-35	221.27	221.83	Granite	9.1	2.5	3.0	-	5.0	38	-	-	-	0.27	-	-	-	75	5.0	5.0	85	-	

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-																	
					-																	
		From	To	General Rock Type	Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
			unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr		
Granite (continued)																						
Beartooth (continued)																						
12	BDC-05	40.2	40.53	Granite	9.8	5.0	3.0	-	5.0	36	-	-	-	0.28	-	-	-	68	5.0	2.0	54	-
14	BDC-05	63.74	64.07	Granite	9.5	5.0	4.0	-	5.0	49	-	-	-	0.27	-	-	-	72	5.0	6.0	110	-
15	BDC-07	224.63	225.02	Granite	9.9	5.0	3.0	-	5.0	41	-	-	-	0.28	-	-	-	78	5.0	5.0	69	-
BDC 4-54.64	BDC 4	54.64	60.21	Granite	-	2.5	-	-	-	637	-	-	-	0.35	-	-	-	87	5.0	-	74	-
BGT 01-108	BGT 01	108	112.35	Granite	-	2.5	-	-	-	568	-	-	-	0.36	-	-	-	83	5.0	-	70	-
BGT 01-125.34	BGT 01	125.34	129.61	Granite	-	2.5	-	-	-	561	-	-	-	0.30	-	-	-	80	5.0	-	58	-
BGT 02-60.12	BGT 02	60.12	64.52	Granite	-	2.5	-	-	-	527	-	-	-	0.34	-	-	-	109	5.0	-	64	-
BGT 03-18.28	BGT 03	18.28	22.62	Granite	-	2.5	-	-	-	628	-	-	-	0.32	-	-	-	83	5.0	-	68	-
BGT 03-64.95	BGT 03	64.95	69.2	Granite	-	2.5	-	-	-	676	-	-	-	0.35	-	-	-	92	5.0	-	72	-
BGT 03-107.6	BGT 03	107.6	111.82	Granite	-	2.5	-	-	-	643	-	-	-	0.34	-	-	-	90	5.0	-	70	-
BGT 04-70.03	BGT 04	70.03	74.32	Granite	-	2.5	-	-	-	666	-	-	-	0.34	-	-	-	89	5.0	-	72	-
BGT 05-104.77	BGT 05	104.77	109.66	Granite	-	2.5	-	-	-	698	-	-	-	0.34	-	-	-	83	5.0	-	72	-
BGT 05-135.31	BGT 05	135.31	139.58	Granite	-	2.5	-	-	-	687	-	-	-	0.33	-	-	-	84	5.0	-	86	-
DDH 96-35-64.19	DDH 96-35	64.19	70.65	Granite	-	2.5	-	-	-	571	-	-	-	0.43	-	-	-	165	5.0	-	90	-
BDC 2-88.19	BDC 2	88.19	90.86	Granite	-	2.5	-	-	-	337	-	-	-	0.56	-	-	-	198	5.0	-	112	-
BDC 3-38	BDC 3	38	42	Granite	-	2.5	-	-	-	653	-	-	-	0.43	-	-	-	118	10	-	94	-
BGT 01-99.36	BGT 01	99.36	103.64	Granite	-	2.5	-	-	-	516	-	-	-	0.29	-	-	-	80	5.0	-	62	-
BGT 04-48.38	BGT 04	48.38	52.7	Granite	-	2.5	-	-	-	606	-	-	-	0.37	-	-	-	106	5.0	-	82	-
BGT 05-78.58	BGT 05	78.58	81.93	Granite	-	2.5	-	-	-	524	-	-	-	0.44	-	-	-	134	10	-	80	-
BDC 5-17	BDC 5	17	18	Granite	-	2.5	-	-	-	130	-	-	-	0.13	-	-	-	41	5.0	-	28	-
BDC 3-42	BDC 3	42	57	Granite	-	2.5	-	-	-	417	-	-	-	0.28	-	-	-	109	5.0	-	80	-
BDC 4-38.7	BDC 4	38.7	42	Granite	-	2.5	-	-	-	588	-	-	-	0.36	-	-	-	112	5.0	-	80	-
BDC 5-20.96	BDC 5	20.96	26.65	Granite	-	2.5	-	-	-	614	-	-	-	0.33	-	-	-	82	5.0	-	68	-
BDC 7-20.28	BDC 7	20.28	26.93	Granite	-	2.5	-	-	-	508	-	-	-	0.42	-	-	-	155	5.0	-	90	-
BDC 7-32.42	BDC 7	32.42	36.9	Granite	-	2.5	-	-	-	624	-	-	-	0.34	-	-	-	81	5.0	-	70	-
BDC 7-36.9	BDC 7	36.9	42	Granite	-	2.5	-	-	-	490	-	-	-	0.41	-	-	-	143	5.0	-	74	-
BDC 7-53.95	BDC 7	53.95	58.98	Granite	-	2.5	-	-	-	574	-	-	-	0.29	-	-	-	85	5.0	-	68	-
BDC 7-64.09	BDC 7	64.09	69.29	Granite	-	2.5	-	-	-	413	-	-	-	0.35	-	-	-	159	5.0	-	76	-
BGT 01-65.18	BGT 01	65.18	69.43	Granite	-	2.5	-	-	-	653	-	-	-	0.38	-	-	-	97	10	-	78	-
BGT 01-82.23	BGT 01	82.23	86.35	Granite	-	2.5	-	-	-	557	-	-	-	0.37	-	-	-	82	5.0	-	68	-
BGT 02-107.4	BGT 02	107.4	111.73	Granite	-	2.5	-	-	-	668	-	-	-	0.33	-	-	-	78	5.0	-	70	-
BGT 02-146.12	BGT 02	146.12	150.45	Granite	-	2.5	-	-	-	583	-	-	-	0.43	-	-	-	125	5.0	-	76	-
BGT 03-39.31	BGT 03	39.31	43.66	Granite	-	2.5	-	-	-	608	-	-	-	0.37	-	-	-	93	5.0	-	70	-
BGT 04-35.95	BGT 04	35.95	41	Granite	-	2.5	-	-	-	932	-	-	-	0.34	-	-	-	113	5.0	-	114	-
BGT 04-91.65	BGT 04	91.65	95.95	Granite	-	2.5	-	-	-	631	-	-	-	0.33	-	-	-	86	5.0	-	74	-
BGT 04-130.5	BGT 04	130.5	134.87	Granite	-	2.5	-	-	-	642	-	-	-	0.36	-	-	-	99	5.0	-	74	-
BGT 05-25.9	BGT 05	25.9	30.95	Granite	-	2.5	-	-	-	623	-	-	-	0.43	-	-	-	155	5.0	-	90	-
BGT 05-56.78	BGT 05	56.78	61.17	Granite	-	2.5	-	-	-	660	-	-	-	0.39	-	-	-	89	5.0	-	78	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-																		
					-																		
		From	To	General Rock Type	Paste pH	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U (ICP)	U (XRF)	V	W	Y	Zn	Zr	
		unit																					
Granite (continued)																							
Beartooth (continued)																							
BGT 05-165.49	BGT 05	165.49	169.74	Granite	-	2.5	-	-	-	588	-	-	-	0.27	-	-	-	74	5.0	-	56	-	
BTG-460-25-01	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BTG-460-25-02	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-04-02	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-03-01	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-03-02	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-10-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-10-2	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-10-3	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-10-4	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-10-5	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-10-6	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-10-7	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-10-8	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-10-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-10-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BTGS-440-09-1	-	-	-	Granite	9.5	2.5	-	-	-	661	-	-	-	0.32	-	-	-	86	5.0	-	62	-	
BTGS-440-09-2	-	-	-	Granite	9.7	2.5	-	-	-	635	-	-	-	0.38	-	-	-	100	10	-	80	-	
BTGS-440-09-3	-	-	-	Granite	9.3	2.5	-	-	-	615	-	-	-	0.30	-	-	-	77	5.0	-	60	-	
BTGS-440-09-4	-	-	-	Granite	9.8	2.5	-	-	-	644	-	-	-	0.32	-	-	-	88	5.0	-	61	-	
BG-440-11-1	-	-	-	Granite	9.0	2.5	-	-	-	554	-	-	-	0.39	-	-	-	98	5.0	-	79	-	
BG-440-11-2	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-11-3	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-11-4	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-12-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-12-2	-	-	-	Granite	8.8	2.5	-	-	-	567	-	-	-	0.35	-	-	-	83	5.0	-	70	-	
BG-440-12-3	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-12-4	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-13-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-13-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-15-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-15-2	-	-	-	Granite	8.8	2.5	-	-	-	631	-	-	-	0.32	-	-	-	85	5.0	-	68	-	
BG-440-20-04	-	-	-	Granite	9.7	2.5	-	-	-	613	-	-	-	0.32	-	-	-	77	5.0	-	65	-	
BG-440-20-03	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-20-02	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-20-01	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-22-04	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
BG-440-22-03	-	-	-	Granite	9.6	2.5	-	-	-	651	-	-	-	0.31	-	-	-	77	5.0	-	68	-	

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Beartooth (continued)																						
BG-440-22-02	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-440-22-01	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-440-26-1	-	-	-	Granite	9.2	2.5	-	-	-	606	-	-	-	0.36	-	-	-	107	5.0	-	77	-
BTG-440-26-2	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-440-26-3	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-440-26-4	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-21-02	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-21-01	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-19-04	-	-	-	Granite	7.9	2.5	-	-	-	464	-	-	-	0.39	-	-	-	128	5.0	-	77	-
BG-430-19-03	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-19-02	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-19-01	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-18-04	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-18-03	-	-	-	Granite	9.6	2.5	-	-	-	608	-	-	-	0.35	-	-	-	77	5.0	-	64	-
BG-430-18-02	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-18-01	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-17-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-17-03	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-17-02	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-17-01	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-05-02	-	-	-	Granite	9.6	2.5	-	-	-	586	-	-	-	0.28	-	-	-	76	5.0	-	62	-
BG-430-05-01	-	-	-	Granite	9.6	2.5	-	-	-	561	-	-	-	0.27	-	-	-	74	5.0	-	63	-
BG-430-04-01	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-02-02	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-430-02-01	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-04	-	-	-	Granite	8.2	2.5	-	-	-	430	-	-	-	0.34	-	-	-	103	5.0	-	61	-
BG-420-04-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-03	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-03	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-02	-	-	-	Granite	8.8	2.5	-	-	-	473	-	-	-	0.43	-	-	-	128	5.0	-	78	-
BG-420-04-02	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-01	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BG-420-04-01	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BTG-410-05-01	-	-	-	Granite	9.9	2.5	-	-	-	617	-	-	-	0.31	-	-	-	75	5.0	-	67	-
BTG-410-05-02	-	-	-	Granite	9.5	2.5	-	-	-	634	-	-	-	0.32	-	-	-	75	5.0	-	68	-
BT-310-Granite-3	-	-	-	Granite	9.5	2.5	8.0	-	-	645	-	-	10	0.34	5.0	5.0	-	82	5.0	-	82	-
BT-310-Granite-2	-	-	-	Granite	9.7	5.0	8.0	-	-	619	-	-	10	0.34	5.0	5.0	-	95	5.0	-	80	-
BT-310-Granite-1	-	-	-	Granite	9.8	2.5	7.0	-	-	608	-	-	10	0.32	5.0	5.0	-	77	5.0	-	74	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Beartooth (continued)																						
BT-300-Granite-3	-	-	-	Granite	8.9	2.5	12	-	-	624	-	-	10	0.31	5.0	5.0	-	79	5.0	-	75	-
BT-300-Granite-2	-	-	-	Granite	9.1	2.5	8.0	-	-	614	-	-	10	0.27	5.0	5.0	-	70	5.0	-	65	-
BT-300-Granite-1	-	-	-	Granite	10.1	2.5	7.0	-	-	631	-	-	10	0.33	5.0	5.0	-	83	5.0	-	72	-
BT-290-Granite-2	-	-	-	Granite	10.1	2.5	7.0	-	-	660	-	-	10	0.32	5.0	5.0	-	82	5.0	-	70	-
BT-290-Granite-1	-	-	-	Granite	9.2	2.5	8.0	-	-	607	-	-	10	0.31	5.0	5.0	-	81	5.0	-	70	-
BT-290-Granite-3	-	-	-	Granite	9.8	2.5	7.0	-	-	664	-	-	10	0.34	5.0	5.0	-	85	5.0	-	71	-
BT-280-Granite-2	-	-	-	Granite	10.0	2.5	6.0	-	-	672	-	-	10	0.31	5.0	5.0	-	78	5.0	-	67	-
BT-280-Granite-1	-	-	-	Granite	9.9	2.5	7.0	-	-	675	-	-	10	0.31	5.0	5.0	-	81	5.0	-	70	-
Median					9.3	2.5	7.0	-	5.0	608	-	-	10	0.34	5.0	5.0	-	84	5.0	6.0	72	-
Minimum					7.8	2.5	3.0	-	5.0	33	-	-	10	0.13	5.0	5.0	-	41	5.0	2.0	28	-
Maximum					10.1	5.0	12	-	5.0	932	-	-	10	0.56	5.0	5.0	-	198	10	6.0	114	-
Count					90	72	18	0	7	72	0	0	11	72	11	11	0	72	72	7	72	0
Fox																						
FUC-2B - 56	FUC-2B	56	56.3	Granite	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 45	FUC 3-3	45	45.3	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 50	FUC 3-3	50	50.3	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 55	FUC 3-3	55	55.3	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 3-3 - 60	FUC 3-3	60	60.3	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 4-3 - 144	FUC 4-3	144	144.3	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 4-4 - 144	FUC 4-4	144	144.3	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 4-5 - 128	FUC 4-5	128	128.3	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FX 4-1 - 188	FX 4-1	188	188.3	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - -	Decline	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - -	Decline	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 69	Decline	69	69.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 200	Decline	200	200.1	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 245	Decline	245	245.1	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 296	Decline	296	296.1	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 365	Decline	365	365.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 372	Decline	372	372.1	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 377	Decline	377	377.1	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 447	Decline	447	447.1	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 500	Decline	500	500.1	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 552	Decline	552	552.1	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 610	Decline	610	610.1	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 660	Decline	660	660.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Decline - 764	Decline	764	764.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-	
					unit	Sb ppm	Sc ppm	Se ppm	Sn ppm	Sr ppm	Ta ppm	Te ppm	Th ppm	Ti %	Tl ppm	U (ICP) ppm	U (XRF) ppm	V ppm	W ppm	Y ppm	Zn ppm	Zr ppm	
Granite (continued)																							
Fox (continued)																							
Decline - 809	Decline	809	809.1	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
Decline - 822	Decline	822	822.1	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
Decline - 851	Decline	851	851.1	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
Decline - 901	Decline	901	901.1	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
Decline - 951	Decline	951	951.1	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
Decline - 1001	Decline	1,001	1,001.1	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
Decline - 1055.9	Decline	1,055.9	1,056	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
Decline - 1106.2	Decline	1,106.2	1,106.3	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
Decline - 1168.8	Decline	1,168.8	1,168.9	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
Decline - 1276.1	Decline	1,276.1	1,276.2	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
Decline - 1326.1	Decline	1,326.1	1,326.2	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FUC 1-2 - 70.15	FUC 1-2	70.15	76.02	Granite	8.2	0.4	-	-	-	601	-	-	-	0.33	-	-	-	88	5.0	-	52		
FUC 1-2 - 76.02	FUC 1-2	76.02	80.38	Granite	8.6	0.1	-	-	-	562	-	-	-	0.31	-	-	-	87	5.0	-	48		
FUC 1-2 - 80.38	FUC 1-2	80.38	87.78	Granite	8.4	0.2	-	-	-	185	-	-	-	0.90	-	-	-	381	5.0	-	80		
FUC 1-2 - 113.03	FUC 1-2	113.03	116.91	Granite	8.5	0.1	-	-	-	637	-	-	-	0.35	-	-	-	92	5.0	-	52		
FUC 1-2 - 116.91	FUC 1-2	116.91	122.67	Granite	8.6	0.2	-	-	-	700	-	-	-	0.33	-	-	-	90	5.0	-	60		
FUC 4-3 - 146.96	FUC 4-3	146.96	151.5	Granite	8.8	0.2	-	-	-	650	-	-	-	0.31	-	-	-	77	5.0	-	58		
FUC 4-3 - 155.2	FUC 4-3	155.2	163.4	Granite	8.3	0.2	-	-	-	676	-	-	-	0.30	-	-	-	77	5.0	-	60		
FDC 11 - 108.25	FDC 11	108.25	118.8	Granite	8.5	0.2	-	-	-	562	-	-	-	0.29	-	-	-	74	5.0	-	46		
FDC 11 - 118.8	FDC 11	118.8	123	Granite	8.6	0.1	-	-	-	537	-	-	-	0.25	-	-	-	69	5.0	-	38		
FDC 11 - 122.5	FDC 11	122.5	128.02	Granite	8.2	0.4	-	-	-	396	-	-	-	0.24	-	-	-	68	5.0	-	50		
FGT-03 - 1.52	FGT-03	1.52	10.82	Granite	9.1	2.5	-	-	-	611	-	-	-	0.33	-	-	-	82	5.0	-	86		
FGT-03 - 10.82	FGT-03	10.82	18.32	Granite	-	2.5	-	-	-	625	-	-	-	0.35	-	-	-	89	5.0	-	84		
FGT-03 - 18.32	FGT-03	18.32	25.82	Granite	-	2.5	-	-	-	515	-	-	-	0.31	-	-	-	79	5.0	-	68		
FGT-03 - 25.82	FGT-03	25.82	30.24	Granite	-	2.5	-	-	-	563	-	-	-	0.28	-	-	-	69	5.0	-	68		
FGT-03 - 30.24	FGT-03	30.24	37.74	Granite	-	2.5	-	-	-	599	-	-	-	0.31	-	-	-	79	5.0	-	72		
FGT-03 - 37.74	FGT-03	37.74	45.24	Granite	-	2.5	-	-	-	607	-	-	-	0.30	-	-	-	78	5.0	-	78		
FGT-03 - 45.24	FGT-03	45.24	52.74	Granite	-	5.0	-	-	-	583	-	-	-	0.32	-	-	-	77	5.0	-	76		
FGT-03 - 52.74	FGT-03	52.74	58.29	Granite	-	5.0	-	-	-	594	-	-	-	0.32	-	-	-	80	5.0	-	76		
FGT-03 - 58.29	FGT-03	58.29	65.79	Granite	-	2.5	-	-	-	621	-	-	-	0.31	-	-	-	78	5.0	-	72		
FGT-03 - 65.79	FGT-03	65.79	73.29	Granite	-	2.5	-	-	-	625	-	-	-	0.32	-	-	-	78	5.0	-	72		
FGT-03 - 73.29	FGT-03	73.29	80.79	Granite	9.6	5.0	-	-	-	654	-	-	-	0.35	-	-	-	87	5.0	-	76		
FGT-03 - 80.79	FGT-03	80.79	83.82	Granite	-	2.5	-	-	-	617	-	-	-	0.31	-	-	-	76	5.0	-	68		
FGT-03 - 83.82	FGT-03	83.82	90.22	Granite	-	2.5	-	-	-	603	-	-	-	0.32	-	-	-	78	5.0	-	70		
FGT-03 - 90.22	FGT-03	90.22	97.72	Granite	-	5.0	-	-	-	681	-	-	-	0.34	-	-	-	86	5.0	-	74		
FGT-03 - 97.72	FGT-03	97.72	105.22	Granite	-	2.5	-	-	-	572	-	-	-	0.29	-	-	-	74	5.0	-	66		
FGT-03 - 105.22	FGT-03	105.22	112.72	Granite	-	2.5	-	-	-	655	-	-	-	0.33	-	-	-	85	5.0	-	74		
FGT-03 - 112.72	FGT-03	112.72	115.5	Granite	-	2.5	-	-	-	673	-	-	-	0.32	-	-	-	79	5.0	-	74		

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-																		
					General Rock Type																		
		From	To	Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-		
		unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr				
Granite (continued)																							
Fox (continued)																							
FGT-03 - 115.5	FGT-03	115.5	123	Granite	-	5.0	-	-	-	649	-	-	-	0.33	-	-	-	85	5.0	-	80	-	
FGT-03 - 123	FGT-03	123	130.5	Granite	-	15	-	-	-	599	-	-	-	0.33	-	-	-	81	5.0	-	70	-	
FGT-03 - 130.5	FGT-03	130.5	138	Granite	-	2.5	-	-	-	561	-	-	-	0.33	-	-	-	83	5.0	-	68	-	
FGT-03 - 138	FGT-03	138	148.68	Granite	8.9	5.0	-	-	-	489	-	-	-	0.32	-	-	-	81	5.0	-	68	-	
FGT-03 - 148.68	FGT-03	148.68	153.11	Granite	-	5.0	-	-	-	627	-	-	-	0.33	-	-	-	85	5.0	-	74	-	
FGT-03 - 153.11	FGT-03	153.11	160.61	Granite	-	2.5	-	-	-	476	-	-	-	0.29	-	-	-	71	5.0	-	62	-	
FGT-03 - 160.61	FGT-03	160.61	168.11	Granite	-	2.5	-	-	-	663	-	-	-	0.33	-	-	-	82	5.0	-	72	-	
FGT-03 - 168.11	FGT-03	168.11	172.05	Granite	-	5.0	-	-	-	626	-	-	-	0.34	-	-	-	85	5.0	-	72	-	
FGT-03 - 172.05	FGT-03	172.05	179.55	Granite	-	5.0	-	-	-	648	-	-	-	0.33	-	-	-	81	5.0	-	72	-	
FGT-03 - 179.55	FGT-03	179.55	187.05	Granite	-	2.5	-	-	-	660	-	-	-	0.33	-	-	-	83	5.0	-	72	-	
FGT-03 - 187.05	FGT-03	187.05	193.21	Granite	-	2.5	-	-	-	701	-	-	-	0.37	-	-	-	93	5.0	-	78	-	
FGT-03 - 193.21	FGT-03	193.21	198.77	Granite	-	2.5	-	-	-	674	-	-	-	0.35	-	-	-	86	5.0	-	72	-	
FGT-03 - 198.77	FGT-03	198.77	206.27	Granite	-	2.5	-	-	-	679	-	-	-	0.34	-	-	-	84	5.0	-	74	-	
FGT-03 - 206.27	FGT-03	206.27	213.77	Granite	9.6	2.5	-	-	-	640	-	-	-	0.34	-	-	-	85	5.0	-	76	-	
FGT-03 - 213.77	FGT-03	213.77	221.27	Granite	-	2.5	-	-	-	653	-	-	-	0.33	-	-	-	81	5.0	-	70	-	
FGT-03 - 221.27	FGT-03	221.27	228.77	Granite	-	10	-	-	-	648	-	-	-	0.33	-	-	-	80	5.0	-	72	-	
FGT-03 - 228.77	FGT-03	228.77	235.73	Granite	-	2.5	-	-	-	659	-	-	-	0.34	-	-	-	84	5.0	-	76	-	
FGT-03 - 235.73	FGT-03	235.73	243.23	Granite	-	5.0	-	-	-	599	-	-	-	0.31	-	-	-	77	5.0	-	72	-	
FGT-03 - 243.23	FGT-03	243.23	251.46	Granite	-	2.5	-	-	-	652	-	-	-	0.33	-	-	-	78	5.0	-	72	-	
FGT-05 - 1.1	FGT-05	1.1	5.5	Granite	8.9	2.5	-	-	-	654	-	-	-	0.28	-	-	-	82	5.0	-	68	-	
FGT-05 - 5.5	FGT-05	5.5	11.4	Granite	-	2.5	-	-	-	590	-	-	-	0.26	-	-	-	75	5.0	-	58	-	
FGT-05 - 14.3	FGT-05	14.3	20.34	Granite	-	2.5	-	-	-	609	-	-	-	0.27	-	-	-	78	5.0	-	60	-	
FGT-05 - 20.34	FGT-05	20.34	26	Granite	-	2.5	-	-	-	630	-	-	-	0.29	-	-	-	82	5.0	-	64	-	
FGT-05 - 26	FGT-05	26	30.8	Granite	-	2.5	-	-	-	609	-	-	-	0.30	-	-	-	80	5.0	-	62	-	
FGT-05 - 30.8	FGT-05	30.8	37.7	Granite	-	2.5	-	-	-	506	-	-	-	0.26	-	-	-	74	5.0	-	62	-	
FGT-05 - 37.7	FGT-05	37.7	45	Granite	-	2.5	-	-	-	635	-	-	-	0.29	-	-	-	81	5.0	-	66	-	
FGT-05 - 45	FGT-05	45	52.5	Granite	-	2.5	-	-	-	613	-	-	-	0.28	-	-	-	77	5.0	-	64	-	
FGT-05 - 52.5	FGT-05	52.5	60	Granite	-	2.5	-	-	-	641	-	-	-	0.28	-	-	-	78	5.0	-	62	-	
FGT-05 - 60	FGT-05	60	67.5	Granite	9.5	2.5	-	-	-	664	-	-	-	0.29	-	-	-	81	5.0	-	64	-	
FGT-05 - 67.5	FGT-05	67.5	75	Granite	-	2.5	-	-	-	641	-	-	-	0.28	-	-	-	77	5.0	-	62	-	
FGT-05 - 75	FGT-05	75	82.5	Granite	-	2.5	-	-	-	614	-	-	-	0.29	-	-	-	85	5.0	-	68	-	
FGT-05 - 82.5	FGT-05	82.5	90	Granite	-	2.5	-	-	-	644	-	-	-	0.28	-	-	-	78	5.0	-	62	-	
FGT-05 - 90	FGT-05	90	97.5	Granite	-	2.5	-	-	-	663	-	-	-	0.29	-	-	-	81	5.0	-	64	-	
FGT-05 - 97.5	FGT-05	97.5	105	Granite	-	2.5	-	-	-	632	-	-	-	0.29	-	-	-	78	5.0	-	66	-	
FGT-05 - 105	FGT-05	105	112.5	Granite	-	2.5	-	-	-	649	-	-	-	0.32	-	-	-	82	5.0	-	66	-	
FGT-05 - 112.5	FGT-05	112.5	120	Granite	-	2.5	-	-	-	668	-	-	-	0.33	-	-	-	93	5.0	-	68	-	
FGT-05 - 120	FGT-05	120	128	Granite	-	2.5	-	-	-	609	-	-	-	0.29	-	-	-	79	5.0	-	62	-	
FGT-05 - 128	FGT-05	128	134.9	Granite	-	2.5	-	-	-	579	-	-	-	0.29	-	-	-	81	5.0	-	62	-	

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-																		
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-	
		From	To	General Rock Type	unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr	
Granite (continued)																							
Fox (continued)																							
FGT-05 - 175.36	FGT-05	175.36	183	Granite	-	2.5	-	-	-	602	-	-	-	0.31	-	-	-	86	5.0	-	64	-	
FGT-05 - 183	FGT-05	183	190.5	Granite	-	2.5	-	-	-	658	-	-	-	0.30	-	-	-	85	5.0	-	64	-	
FGT-05 - 190.5	FGT-05	190.5	198	Granite	-	2.5	-	-	-	660	-	-	-	0.32	-	-	-	85	5.0	-	68	-	
FGT-05 - 198	FGT-05	198	205.5	Granite	-	2.5	-	-	-	629	-	-	-	0.30	-	-	-	80	5.0	-	64	-	
FGT-05 - 205.5	FGT-05	205.5	213	Granite	9.4	2.5	-	-	-	626	-	-	-	0.30	-	-	-	86	5.0	-	68	-	
FGT-05 - 213	FGT-05	213	220.5	Granite	-	2.5	-	-	-	629	-	-	-	0.30	-	-	-	83	5.0	-	64	-	
FGT-05 - 220.5	FGT-05	220.5	228	Granite	-	2.5	-	-	-	621	-	-	-	0.28	-	-	-	80	5.0	-	62	-	
FGT-05 - 228	FGT-05	228	235.5	Granite	-	2.5	-	-	-	590	-	-	-	0.29	-	-	-	78	5.0	-	62	-	
FGT-05 - 235.5	FGT-05	235.5	243	Granite	-	2.5	-	-	-	628	-	-	-	0.30	-	-	-	80	5.0	-	62	-	
FGT-05 - 243	FGT-05	243	250.5	Granite	-	2.5	-	-	-	607	-	-	-	0.30	-	-	-	80	5.0	-	64	-	
FGT-05 - 250.5	FGT-05	250.5	258	Granite	-	2.5	-	-	-	621	-	-	-	0.29	-	-	-	78	5.0	-	64	-	
FGT-05 - 258	FGT-05	258	265.5	Granite	-	2.5	-	-	-	638	-	-	-	0.31	-	-	-	84	5.0	-	70	-	
FGT-05 - 265.5	FGT-05	265.5	273	Granite	-	2.5	-	-	-	627	-	-	-	0.29	-	-	-	81	5.0	-	64	-	
FGT-05 - 273	FGT-05	273	280.5	Granite	-	2.5	-	-	-	669	-	-	-	0.31	-	-	-	87	5.0	-	68	-	
FGT-05 - 280.5	FGT-05	280.5	288	Granite	9.3	2.5	-	-	-	652	-	-	-	0.30	-	-	-	82	5.0	-	66	-	
FGT-05 - 288	FGT-05	288	295	Granite	-	2.5	-	-	-	614	-	-	-	0.31	-	-	-	81	5.0	-	68	-	
FGT-05 - 295	FGT-05	295	EOH	Granite	-	2.5	-	-	-	641	-	-	-	0.31	-	-	-	85	5.0	-	66	-	
FGT-07 - 4	FGT-07	4	14.21	Granite	9.1	2.5	-	-	-	489	-	-	-	0.20	-	-	-	49	5.0	-	46	-	
FGT-07 - 14.21	FGT-07	14.21	20.12	Granite	-	2.5	-	-	-	464	-	-	-	0.20	-	-	-	47	5.0	-	44	-	
FGT-07 - 20.12	FGT-07	20.12	31.45	Granite	-	2.5	-	-	-	551	-	-	-	0.22	-	-	-	54	5.0	-	48	-	
FGT-07 - 31.45	FGT-07	31.45	39	Granite	-	2.5	-	-	-	501	-	-	-	0.21	-	-	-	54	5.0	-	50	-	
FGT-07 - 39	FGT-07	39	46.5	Granite	-	2.5	-	-	-	489	-	-	-	0.21	-	-	-	56	5.0	-	52	-	
FGT-07 - 46.5	FGT-07	46.5	54	Granite	-	2.5	-	-	-	429	-	-	-	0.21	-	-	-	55	5.0	-	50	-	
FGT-07 - 54	FGT-07	54	61.5	Granite	-	2.5	-	-	-	362	-	-	-	0.18	-	-	-	49	5.0	-	44	-	
FGT-07 - 61.5	FGT-07	61.5	69	Granite	-	2.5	-	-	-	373	-	-	-	0.18	-	-	-	44	5.0	-	42	-	
FGT-07 - 69	FGT-07	69	76.5	Granite	-	2.5	-	-	-	526	-	-	-	0.24	-	-	-	56	5.0	-	48	-	
FGT-07 - 76.5	FGT-07	76.5	86.23	Granite	-	2.5	-	-	-	611	-	-	-	0.30	-	-	-	81	5.0	-	62	-	
FGT-07 - 86.23	FGT-07	86.23	94	Granite	9.3	2.5	-	-	-	610	-	-	-	0.30	-	-	-	84	5.0	-	64	-	
FGT-07 - 94	FGT-07	94	101.5	Granite	-	2.5	-	-	-	613	-	-	-	0.30	-	-	-	84	5.0	-	64	-	
FGT-07 - 101.5	FGT-07	101.5	109	Granite	-	2.5	-	-	-	623	-	-	-	0.31	-	-	-	86	5.0	-	64	-	
FGT-07 - 109	FGT-07	109	116.5	Granite	-	2.5	-	-	-	644	-	-	-	0.34	-	-	-	93	5.0	-	68	-	
FGT-07 - 116.5	FGT-07	116.5	124	Granite	-	2.5	-	-	-	672	-	-	-	0.34	-	-	-	93	5.0	-	70	-	
FGT-07 - 124	FGT-07	124	131.78	Granite	-	2.5	-	-	-	652	-	-	-	0.31	-	-	-	88	5.0	-	66	-	
FGT-07 - 131.78	FGT-07	131.78	135.64	Granite	-	2.5	-	-	-	693	-	-	-	0.32	-	-	-	90	5.0	-	68	-	
FGT-07 - 135.64	FGT-07	135.64	143	Granite	-	2.5	-	-	-	649	-	-	-	0.32	-	-	-	89	5.0	-	66	-	
FGT-07 - 143	FGT-07	143	149	Granite	-	2.5	-	-	-	55	-	-	-	0.03	-	-	-	8.0	5.0	-	6.0	-	
FGT-07 - 149	FGT-07	149	156.5	Granite	-	2.5	-	-	-	82	-	-	-	0.04	-	-	-	12	5.0	-	8.0	-	
FGT-07 - 156.5	FGT-07	156.5	162.63	Granite	9.1	2.5	-	-	-	629	-	-	-	0.29	-	-	-	86	5.0	-	64	-	

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	Price Crustal Abundances																	
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr
Granite (continued)																						
Fox (continued)																						
FGT-07 - 162.63	FGT-07	162.63	170	Granite	-	2.5	-	-	-	588	-	-	-	0.28	-	-	-	82	5.0	-	62	-
FGT-07 - 170	FGT-07	170	177.5	Granite	-	2.5	-	-	-	629	-	-	-	0.31	-	-	-	94	5.0	-	68	-
FGT-07 - 177.5	FGT-07	177.5	188.55	Granite	-	2.5	-	-	-	617	-	-	-	0.31	-	-	-	94	5.0	-	66	-
FGT-07 - 188.55	FGT-07	188.55	193.27	Granite	-	2.5	-	-	-	608	-	-	-	0.30	-	-	-	87	5.0	-	66	-
FGT-07 - 193.27	FGT-07	193.27	199.62	Granite	-	2.5	-	-	-	680	-	-	-	0.29	-	-	-	89	5.0	-	62	-
FGT-07 - 199.62	FGT-07	199.62	204.78	Granite	-	2.5	-	-	-	737	-	-	-	0.30	-	-	-	114	5.0	-	70	-
FGT-07 - 204.78	FGT-07	204.78	212.28	Granite	-	2.5	-	-	-	776	-	-	-	0.30	-	-	-	87	5.0	-	66	-
FGT-07 - 212.28	FGT-07	212.28	219.78	Granite	-	2.5	-	-	-	672	-	-	-	0.30	-	-	-	86	5.0	-	66	-
FGT-07 - 219.78	FGT-07	219.78	227.28	Granite	-	2.5	-	-	-	650	-	-	-	0.29	-	-	-	84	5.0	-	62	-
FGT-07 - 227.28	FGT-07	227.28	234.78	Granite	9.3	2.5	-	-	-	579	-	-	-	0.29	-	-	-	87	5.0	-	62	-
FGT-07 - 234.78	FGT-07	234.78	242.28	Granite	-	2.5	-	-	-	630	-	-	-	0.31	-	-	-	85	5.0	-	66	-
FGT-07 - 242.28	FGT-07	242.28	249.78	Granite	-	2.5	-	-	-	651	-	-	-	0.29	-	-	-	83	5.0	-	62	-
FGT-07 - 249.78	FGT-07	249.78	257.28	Granite	-	2.5	-	-	-	657	-	-	-	0.29	-	-	-	87	5.0	-	66	-
FGT-07 - 257.28	FGT-07	257.28	267.52	Granite	-	2.5	-	-	-	688	-	-	-	0.30	-	-	-	88	5.0	-	64	-
FG-470-01-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-470-01-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-450-23-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-450-23-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-24-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-24-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-25-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-25-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-26-1	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-26-2	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-31-1	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-447-31-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-03-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-03-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-03-1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-03-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-04-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-04-2	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-06-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-06-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-07-1	-	-	-	Granite	9.5	2.5	-	-	-	731	-	-	-	0.33	-	-	-	74	5.0	-	68	-
FG-435-07-2	-	-	-	Granite	9.6	2.5	-	-	-	690	-	-	-	0.32	-	-	-	75	5.0	-	68	-
FG-435-08-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-435-08-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-																		
					General Rock Type																		
		From	To	Paste pH	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U (ICP)	U (XRF)	V	W	Y	Zn	Zr		
		unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm			
Granite (continued)																							
Fox (continued)																							
FG-435-13-1	-	-	-	Granite	9.4	2.5	-	-	-	739	-	-	-	0.33	-	-	-	73	5.0	-	70	-	
FG-435-13-2	-	-	-	Granite	9.5	2.5	-	-	-	741	-	-	-	0.31	-	-	-	72	20	-	65	-	
FG-435-18-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-18-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-27-1a	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-27-1b	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-34-1a	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-34-1b	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-30-1a	-	-	-	Granite	9.3	2.5	-	-	-	693	-	-	-	0.32	-	-	-	80	5.0	-	74	-	
FG-435-30-2a	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-31-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-31-2	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-38-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-38-2	-	-	-	Granite	9.1	2.5	-	-	-	716	-	-	-	0.30	-	-	-	76	5.0	-	65	-	
FG-435-44-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-44-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-48-1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-435-48-1b	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-420-06-1	-	-	-	Granite	9.4	2.5	-	-	-	661	-	-	-	0.32	-	-	-	85	5.0	-	65	-	
FG-420-06-2	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-420-14-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-420-14-2	-	-	-	Granite	9.4	2.5	-	-	-	647	-	-	-	0.31	-	-	-	75	5.0	-	62	-	
FG-420-21-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-420-21-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-420-25-1	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-420-25-2	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-420-27-1	-	-	-	Granite	9.4	2.5	-	-	-	725	-	-	-	0.31	-	-	-	77	5.0	-	62	-	
FG-420-27-2	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-420-36-1	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-420-36-2	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-420-38-1	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-420-38-2	-	-	-	Granite	9.3	2.5	-	-	-	535	-	-	-	0.30	-	-	-	77	5.0	-	59	-	
F420	-	-	-	Granite	9.3	2.5	-	-	-	535	-	-	-	0.30	-	-	-	77	5.0	-	59	-	
F420	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F420	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F420	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-420-25-1	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FG-420-25-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Fox (continued)																						
FG-420-27-1	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-27-2	-	-	-	Granite	9.4	2.5	-	-	-	725	-	-	-	0.31	-	-	-	77	5.0	-	62	-
FG-420-51-A	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-420-51-B	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-05-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-05-2	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-05-1	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-05-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-09-A	-	-	-	Granite	9.3	2.5	-	-	-	675	-	-	-	0.31	-	-	-	83	5.0	-	62	-
FG-405-09-B	-	-	-	Granite	9.4	2.5	-	-	-	645	-	-	-	0.30	-	-	-	80	5.0	-	65	-
FG-405-48-1	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-48-2	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-53-1	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-405-53-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
F-390-25-1A	-	-	-	Granite	9.6	2.5	-	-	-	649	-	-	-	0.30	-	-	-	82	5.0	-	66	-
F-390-25-1B	-	-	-	Granite	9.4	2.5	-	-	-	622	-	-	-	0.28	-	-	-	73	5.0	-	59	-
FG-390-20-1	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-20-2	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-25-1A	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-25-1B	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-37-1	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-37-2	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-38-1	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-38-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-42-1	-	-	-	Granite	9.6	2.5	-	-	-	664	-	-	-	0.30	-	-	-	76	10	-	62	-
FG-390-42-2	-	-	-	Granite	9.6	2.5	-	-	-	635	-	-	-	0.28	-	-	-	76	5.0	-	58	-
FG-390-43-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-43-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-43-3	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-43-4	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-44-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-44-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-45-1	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-45-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-45-3	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-45-4	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-46-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-46-2	-	-	-	Granite	8.9	2.5	-	-	-	688	-	-	-	0.31	-	-	-	77	5.0	-	65	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Fox (continued)																						
FG-390-46-3	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-46-4	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-48-1	-	-	-	Granite	9.1	2.5	-	-	-	591	-	-	-	0.27	-	-	-	72	5.0	-	58	-
FG-390-48-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-48-3	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-48-4	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-49-1	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-49-2	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-50-1	-	-	-	Granite	9.2	2.5	-	-	-	662	-	-	-	0.30	-	-	-	82	5.0	-	66	-
FG-390-50-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-50-3	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-390-50-4	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-08-1	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-08-1	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-08-2	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-08-2	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-09R1-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-09R1-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-12-01	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-12-02	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-18-1	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-18-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-18-3	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-18-4	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-22-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-22-2	-	-	-	Granite	8.6	2.5	-	-	-	632	-	-	-	0.32	-	-	-	85	5.0	-	62	-
FG-375-24-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-24-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-24-3	-	-	-	Granite	9.5	2.5	-	-	-	657	-	-	-	0.28	-	-	-	78	5.0	-	62	-
FG-375-24-4	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-28-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-28-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-28-3	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-28-4	-	-	-	Granite	9.4	2.5	-	-	-	715	-	-	-	0.31	-	-	-	86	5.0	-	67	-
FG-375-30-1	-	-	-	Granite	9.3	2.5	-	-	-	689	-	-	-	0.33	-	-	-	90	5.0	-	69	-
FG-375-30-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-30-3	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-30-4	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval From To		Price Crustal Abundances General Rock Type	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
					Paste pH	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr
					unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Fox (continued)																						
FG-375-31-1	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-31-2	-	-	-	Granite	8.5	2.5	-	-	-	757	-	-	-	0.32	-	-	-	92	5.0	-	73	-
FG-375-31-3	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-31-4	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-37-1	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-37-2	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-37-3	-	-	-	Granite	8.3	2.5	-	-	-	586	-	-	-	0.27	-	-	-	74	5.0	-	54	-
FG-375-37-4	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-1	-	-	-	Granite	9.8	2.5	-	-	-	659	-	-	-	0.30	-	-	-	79	5.0	-	62	-
FG-375-40-2	-	-	-	Granite	9.6	2.5	-	-	-	583	-	-	-	0.28	-	-	-	74	5.0	-	59	-
FOX-375-07-1A	-	-	-	Granite	9.8	2.5	-	-	-	730	-	-	-	0.30	-	-	-	84	5.0	-	65	-
FOX-375-07-1B	-	-	-	Granite	9.7	2.5	-	-	-	697	-	-	-	0.30	-	-	-	81	5.0	-	64	-
FG-375-52-02 22-NOV-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-52-01 22-NOV-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-45-04 29-OCT-04	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-45-03 29-OCT-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-45-02 29-OCT-04	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-45-01 29-OCT-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-04 24-OCT-04	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-04 20-OCT-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-03 24-OCT-04	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-03 20-OCT-04	-	-	-	Granite	9.3	2.5	-	-	-	718	-	-	-	0.31	-	-	-	81	5.0	-	67	-
FG-375-42-02 24-OCT-04	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-02 20-OCT-04	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-42-01 24-OCT-04	-	-	-	Granite	8.6	2.5	-	-	-	598	-	-	-	0.31	-	-	-	84	5.0	-	66	-
FG-375-42-01 20-OCT-04	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-41-04 13-OCT-04	-	-	-	Granite	8.8	2.5	-	-	-	593	-	-	-	0.28	-	-	-	74	10	-	57	-
FG-375-41-03 13-OCT-04	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-41-02 13-OCT-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-41-01 13-OCT-04	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-04 12-OCT-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-03 12-OCT-04	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-02 12-OCT-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-40-01 12-OCT-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-39-04 6-SEP-04	-	-	-	Granite	8.1	2.5	-	-	-	619	-	-	-	0.28	-	-	-	76	5.0	-	64	-
FG-375-39-03 6-SEP-04	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-39-02 6-SEP-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-39-01 6-SEP-04	-	-	-	Granite	7.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Fox (continued)																						
FG-375-33-04 6-OCT-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-33-03 6-OCT-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-33-02 6-OCT-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-375-33-01 6-OCT-04	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-370-06-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-01-01	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-01-02	-	-	-	Granite	9.6	2.5	-	-	-	668	-	-	-	0.30	-	-	-	80	5.0	-	62	-
FG-360-01-03	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-01-04	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-52-04 8-Apr-05	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-52-03 8-Apr-05	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-52-02 8-Apr-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-52-01 8-Apr-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-06 8-Apr-05	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-05 8-Apr-05	-	-	-	Granite	8.3	2.5	-	-	-	599	-	-	-	0.30	-	-	-	84	10	-	63	-
FG-360-51-04 23-Mar-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-03 23-Mar-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-02 23-Mar-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-51-01 23-Mar-05	-	-	-	Granite	9.3	2.5	-	-	-	606	-	-	-	0.29	-	-	-	74	5.0	-	60	-
FG-360-47-06 8-Mar-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-47-05 8-Mar-05	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-47-04 8-Mar-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-47-03 8-Mar-05	-	-	-	Granite	9.6	2.5	-	-	-	649	-	-	-	0.31	-	-	-	80	5.0	-	64	-
FG-360-47-02 8-Mar-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-47-01 8-Mar-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-46-04 28-FEB-05	-	-	-	Granite	9.5	2.5	-	-	-	640	-	-	-	0.29	-	-	-	74	5.0	-	62	-
FG-360-46-03 28-FEB-05	-	-	-	Granite	9.5	2.5	-	-	-	664	-	-	-	0.30	-	-	-	77	5.0	-	66	-
FG-360-46-02 28-FEB-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-46-01 28-FEB-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-44-04 18-FEB-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-44-03 18-FEB-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-44-02 18-FEB-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-44-01 18-FEB-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-42-06 1-FEB-05	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-42-05 1-FEB-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-42-04 30-JAN-05	-	-	-	Granite	8.9	2.5	-	-	-	585	-	-	-	0.28	-	-	-	75	5.0	-	64	-
FG-360-42-03 30-JAN-05	-	-	-	Granite	8.8	2.5	-	-	-	589	-	-	-	0.28	-	-	-	77	5.0	-	62	-
FG-360-42-02 28-JAN-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Fox (continued)																						
FG-360-42-01	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-41-04	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-41-03	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-41-02	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-41-01	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-40-04	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-40-03	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-40-02	-	-	-	Granite	9.7	2.5	-	-	-	684	-	-	-	0.30	-	-	-	77	5.0	-	66	-
FG-360-40-01	-	-	-	Granite	9.6	2.5	-	-	-	656	-	-	-	0.30	-	-	-	78	5.0	-	67	-
FG-360-39-06	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-05	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-04	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-04	-	-	-	Granite	9.5	2.5	-	-	-	623	-	-	-	0.28	-	-	-	72	5.0	-	61	-
FG-360-39-03	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-03	-	-	-	Granite	9.2	2.5	-	-	-	447	-	-	-	0.27	-	-	-	71	5.0	-	59	-
FG-360-39-02	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-02	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-01	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-39-01	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-38-04	-	-	-	Granite	9.8	2.5	-	-	-	650	-	-	-	0.28	-	-	-	74	5.0	-	64	-
FG-360-38-03	-	-	-	Granite	9.0	2.5	-	-	-	693	-	-	-	0.29	-	-	-	82	5.0	-	71	-
FG-360-38-02	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-38-01	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-36-02	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-36-01	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-35-04	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-35-03	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-35-02	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-35-01	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-04	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-03	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-02	-	-	-	Granite	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-02	-	-	-	Granite	9.3	2.5	-	-	-	687	-	-	-	0.24	-	-	-	64	5.0	-	57	-
FG-360-30-01	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-30-01	-	-	-	Granite	9.4	2.5	-	-	-	663	-	-	-	0.28	-	-	-	75	5.0	-	64	-
FG-360-29-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-29-03	-	-	-	Granite	8.0	2.5	-	-	-	775	-	-	-	0.28	-	-	-	85	5.0	-	65	-
FG-360-29-02	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Fox (continued)																						
FG-360-29-01 1-JAN-05	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-28-02 26-DEC-04	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-28-01 26-DEC-04	-	-	-	Granite	8.1	2.5	-	-	-	373	-	-	-	0.75	-	-	-	280	5.0	-	92	-
FG-360-25-02 11-JAN-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-25-01 11-JAN-05	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-22-04 13-DEC-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-22-03 13-DEC-04	-	-	-	Granite	8.8	2.5	-	-	-	634	-	-	-	0.32	-	-	-	84	5.0	-	65	-
FG-360-22-02 13-DEC-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-22-01 13-DEC-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-18-02 1-JAN-05	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-18-01 1-JAN-05	-	-	-	Granite	8.5	2.5	-	-	-	719	-	-	-	0.29	-	-	-	78	5.0	-	64	-
FG-360-11-04 26-FEB-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-11-03 26-FEB-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-11-02 3-DEC-04	-	-	-	Granite	8.2	2.5	-	-	-	460	-	-	-	0.31	-	-	-	84	5.0	-	53	-
FG-360-11-02 26-FEB-05	-	-	-	Granite	8.9	2.5	-	-	-	594	-	-	-	0.41	-	-	-	129	5.0	-	69	-
FG-360-11-01 3-DEC-04	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-11-01 26-FEB-05	-	-	-	Granite	9.2	2.5	-	-	-	604	-	-	-	0.50	-	-	-	161	5.0	-	77	-
FG-360-03-04 13-OCT-04	-	-	-	Granite	8.3	2.5	-	-	-	649	-	-	-	0.31	-	-	-	80	5.0	-	68	-
FG-360-03-03 13-OCT-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-03-02 13-OCT-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-03-01 13-OCT-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-02-04 6-OCT-04	-	-	-	Granite	8.2	2.5	-	-	-	598	-	-	-	0.29	-	-	-	79	5.0	-	60	-
FG-360-02-03 6-OCT-04	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-02-02 6-OCT-04	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-360-02-01 6-OCT-04	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-4 17-May-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-3 17-May-05	-	-	-	Granite	9.1	2.5	-	-	-	392	-	-	-	0.68	-	-	-	254	5.0	-	88	-
FG-345-42-2 17-May-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-1 17-May-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-08 11-May-05	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-07 11-May-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-06 11-May-05	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-05 11-May-05	-	-	-	Granite	8.9	2.5	-	-	-	286	-	-	-	0.82	-	-	-	317	5.0	-	97	-
FG-345-42-04 10-May-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-03 10-May-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-02 10-May-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-42-01 10-May-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-41-04 4-May-05	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval From To		Price Crustal Abundances General Rock Type	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
					Paste pH	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr
					unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Fox (continued)																						
FG-345-41-03 4-May-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-41-02 4-May-05	-	-	-	Granite	9.2	2.5	-	-	-	553	-	-	-	0.30	-	-	-	83	5.0	-	56	-
FG-345-41-01 4-May-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-40-04 4-May-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-40-03 4-May-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-40-02 4-May-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-40-01 4-May-05	-	-	-	Granite	9.3	2.5	-	-	-	604	-	-	-	0.33	-	-	-	94	5.0	-	70	-
FG-345-38-06 24-Apr-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-05 24-Apr-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-04 24-Apr-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-03 24-Apr-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-02 24-Apr-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-38-01 24-Apr-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-37-04 18-Apr-05	-	-	-	Granite	9.3	2.5	-	-	-	642	-	-	-	0.29	-	-	-	77	5.0	-	61	-
FG-345-37-03 18-Apr-05	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-37-02 18-Apr-05	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-37-01 18-Apr-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-36-04 18-Apr-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-36-03 18-Apr-05	-	-	-	Granite	9.2	2.5	-	-	-	661	-	-	-	0.31	-	-	-	83	5.0	-	66	-
FG-345-36-02 18-Apr-05	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-36-01 18-Apr-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-35-04 17-Apr-05	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-35-03 17-Apr-05	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-35-02 17-Apr-05	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-35-01 17-Apr-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-34-04 10-Apr-05	-	-	-	Granite	9.8	2.5	-	-	-	671	-	-	-	0.28	-	-	-	72	5.0	-	61	-
FG-345-34-03 10-Apr-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-34-02 10-Apr-05	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-34-01 10-Apr-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-06 1-Apr-05	-	-	-	Granite	9.3	2.5	-	-	-	584	-	-	-	0.31	-	-	-	77	10	-	64	-
FG-345-27-05 1-Apr-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-04 1-Apr-05	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-03 1-Apr-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-02 1-Apr-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-27-01 1-Apr-05	-	-	-	Granite	9.4	2.5	-	-	-	596	-	-	-	0.31	-	-	-	83	5.0	-	62	-
FG-345-21-04 24-Mar-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-21-03 24-Mar-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-345-21-02 24-Mar-05	-	-	-	Granite	9.4	2.5	-	-	-	668	-	-	-	0.30	-	-	-	78	5.0	-	62	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	General Rock Type																		
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-	
		unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U (ICP)	U (XRF)	V	W	Y	Zn	Zr				
Granite (continued)																							
Fox (continued)																							
FG-345-21-01	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-16-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-16-03	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-16-02	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-16-01	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-14-02	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-14-01	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-12-06	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-12-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-12-04	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-12-03	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-12-02	-	-	-	Granite	8.3	2.5	-	-	-	465	-	-	-	0.31	-	-	-	84	10	-	60		
FG-345-12-01	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-10-04	-	-	-	Granite	9.9	2.5	-	-	-	761	-	-	-	0.31	-	-	-	84	5.0	-	70		
FG-345-10-03	-	-	-	Granite	9.7	2.5	-	-	-	693	-	-	-	0.31	-	-	-	88	5.0	-	73		
FG-345-10-02	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-10-01	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-09-04	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-09-03	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-09-02	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-09-01	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-07-04	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-07-03	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-07-02	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-345-07-01	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-25-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-25-03	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-25-02	-	-	-	Granite	9.6	2.5	-	-	-	696	-	-	-	0.30	-	-	-	76	5.0	-	65		
FG-330-25-01	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-24-04	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-24-03	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-24-02	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-24-01	-	-	-	Granite	9.8	2.5	-	-	-	660	-	-	-	0.33	-	-	-	79	5.0	-	67		
FG-330-23-04	-	-	-	Granite	9.0	2.5	-	-	-	498	-	-	-	0.29	-	-	-	70	5.0	-	60		
FG-330-23-03	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-23-02	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-23-01	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-22-08	-	-	-	Granite	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	General Rock Type																		
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-	
		From	To	unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U (ICP)	U (XRF)	V	W	Y	Zn	Zr		
Granite (continued)																							
Fox (continued)																							
FG-330-22-07	-	-	-	Granite	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-22-06	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-22-05	-	-	-	Granite	9.7	2.5	-	-	665	-	-	-	0.32	-	-	-	83	5.0	-	70	-		
FG-330-22-04	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-22-03	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-22-02	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-22-01	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-20-04	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-20-03	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-20-02	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-20-01	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-18-02	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-18-01	-	-	-	Granite	8.9	2.5	-	-	647	-	-	-	0.30	-	-	-	78	5.0	-	64	-		
FG-330-15-04	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-15-03	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-15-02	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-15-01	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-13-04	-	-	-	Granite	9.3	2.5	-	-	624	-	-	-	0.30	-	-	-	69	5.0	-	57	-		
FG-330-13-03	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-13-02	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-13-01	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-09-08	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-09-07	-	-	-	Granite	9.6	2.5	-	-	688	-	-	-	0.31	-	-	-	75	5.0	-	63	-		
FG-330-09-06	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-09-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-09-04	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-09-03	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-09-02	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-330-09-01	-	-	-	Granite	9.4	2.5	-	-	658	-	-	-	0.37	-	-	-	100	5.0	-	68	-		
FG-315-13-02	-	-	-	Granite	8.9	2.5	-	-	528	-	-	-	0.29	-	-	-	75	10	-	63	-		
FG-315-13-03	-	-	-	Granite	9.4	2.5	-	-	643	-	-	-	0.33	-	-	-	83	5.0	-	68	-		
FG-315-13-04	-	-	-	Granite	9.2	2.5	-	-	585	-	-	-	0.31	-	-	-	81	5.0	-	67	-		
FG-315-16-01	-	-	-	Granite	9.7	2.5	-	-	606	-	-	-	0.30	-	-	-	78	5.0	-	65	-		
FG-315-16-02	-	-	-	Granite	9.5	2.5	-	-	655	-	-	-	0.31	-	-	-	78	5.0	-	65	-		
FG-315-16-03	-	-	-	Granite	9.6	2.5	-	-	625	-	-	-	0.30	-	-	-	77	5.0	-	66	-		
FG-315-16-04	-	-	-	Granite	9.5	2.5	-	-	638	-	-	-	0.31	-	-	-	79	5.0	-	66	-		
FG-275-20-1	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
FG-275-20-2	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Fox (continued)																						
FG-275-20-3	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-275-20-4	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FG-270-16-01	-	-	-	Granite	9.8	2.5	-	-	-	545	-	-	-	0.32	-	-	-	77	5.0	-	67	-
Fox-260-Granite-2 31-Mar-09	-	-	-	Granite	9.3	2.5	2.0	-	-	202	-	-	10	0.09	5.0	5.0	-	13	5.0	-	12	-
Fox-260-Granite-1 31-Mar-09	-	-	-	Granite	9.4	2.5	7.0	-	-	471	-	-	10	0.29	5.0	5.0	-	73	5.0	-	47	-
Fox-250-Granite-2 26-Jan-09	-	-	-	Granite	9.4	2.5	7.0	-	-	708	-	-	10	0.28	5.0	5.0	-	76	5.0	-	63	-
Fox-250-Granite-1 26-Jan-09	-	-	-	Granite	9.9	2.5	8.0	-	-	664	-	-	10	0.33	5.0	5.0	-	80	5.0	-	67	-
Fox-250-Gr.Xenolith 8-Oct-09	-	-	-	Granite	9.9	6.0	9.0	-	-	668	-	-	10	0.32	5.0	10	-	85	5.0	-	67	-
Fox-250-Granite-3 8-Oct-09	-	-	-	Granite	9.7	2.5	10	-	-	547	-	-	10	0.32	5.0	5.0	-	85	5.0	-	69	-
Fox-250-Granite-4 8-Oct-09	-	-	-	Granite	9.6	5.0	8.0	-	-	625	-	-	10	0.30	5.0	10	-	78	5.0	-	63	-
Fox-240-Granite-3a 26-Jan-09	-	-	-	Granite	9.8	2.5	7.0	-	-	656	-	-	10	0.31	5.0	5.0	-	79	5.0	-	66	-
Fox-240-Granite-2a 26-Jan-09	-	-	-	Granite	9.9	2.5	7.0	-	-	679	-	-	10	0.31	5.0	5.0	-	82	5.0	-	67	-
Fox-240-Granite-1a 26-Jan-09	-	-	-	Granite	9.6	2.5	8.0	-	-	631	-	-	10	0.29	5.0	5.0	-	73	5.0	-	62	-
Fox-240-Granite-2 31-Mar-09	-	-	-	Granite	9.5	2.5	8.0	-	-	598	-	-	10	0.32	5.0	5.0	-	77	5.0	-	66	-
Fox-240-Granite-1 31-Mar-09	-	-	-	Granite	9.8	2.5	9.0	-	-	652	-	-	10	0.32	5.0	5.0	-	87	5.0	-	69	-
Median					9.3	2.5	8.0	-	-	632	-	-	10	0.30	5.0	5.0	-	80	5.0	-	65	-
Minimum					7.5	0.1	2.0	-	-	55	-	-	10	0.03	5.0	5.0	-	8.0	5.0	-	6.0	-
Maximum					10.0	15	10	-	-	776	-	-	10	0.90	5.0	10	-	381	20	-	97	-
Count					475	218	12	0	0	218	0	0	12	218	12	12	0	218	218	0	218	0
Koala																						
KG-345-27-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-27-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-28-1	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-28-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-30-1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-30-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-33-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-33-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-36-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-36-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-28-1	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-345-28-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-13-2	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-05-1A	-	-	-	Granite	9.0	2.5	-	-	-	577	-	-	-	0.30	-	-	-	66	10	-	63	-
KG-330-05-2A	-	-	-	Granite	8.6	2.5	-	-	-	498	-	-	-	0.29	-	-	-	69	10	-	65	-
KG-330-15-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-15-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-13-1	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Koala (continued)																						
KG-330-13-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-26-1	-	-	-	Granite	8.8	2.5	-	-	-	366	-	-	-	0.28	-	-	-	75	10	-	62	-
KG-330-26-2	-	-	-	Granite	9.2	2.5	-	-	-	140	-	-	-	0.13	-	-	-	29	10	-	19	-
KG-330-17-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-17-2	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-10-1	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-10-2	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-21-1	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-330-21-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-12-1	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-12-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-27-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-27-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-05-1A	-	-	-	Granite	9.5	2.5	-	-	-	678	-	-	-	0.28	-	-	-	70	10	-	67	-
KG-315-05-2A	-	-	-	Granite	9.3	2.5	-	-	-	636	-	-	-	0.29	-	-	-	69	10	-	61	-
KG-315-28-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-315-28-2	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-17-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-17-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-20-1	-	-	-	Granite	9.0	2.5	-	-	-	760	-	-	-	0.29	-	-	-	71	5.0	-	61	-
KSG-300-20-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-20-1	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-300-20-2	-	-	-	Granite	9.0	2.5	-	-	-	760	-	-	-	0.29	-	-	-	71	5.0	-	61	-
KSG-290-01-1	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-01-2	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-06-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-06-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-06-1	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSG-290-06-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-290-11-A	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-290-11-B	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-16-1	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-16-2	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-1	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-1	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-2	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-280-18-1	-	-	-	Granite	9.7	2.5	-	-	-	669	-	-	-	0.34	-	-	-	90	5.0	-	72	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Koala (continued)																						
KG-280-18-2	-	-	-	Granite	9.2	2.5	-	-	-	541	-	-	-	0.26	-	-	-	74	5.0	-	61	-
KG-270-08-1	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-270-08-2	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KG-270-08-01	-	-	-	Granite	9.1	2.5	-	-	-	291	-	-	-	0.18	-	-	-	51	5.0	-	37	-
KG-270-08-02	-	-	-	Granite	9.2	2.5	-	-	-	412	-	-	-	0.19	-	-	-	49	5.0	-	34	-
KG-270-17-02	-	-	-	Granite	8.1	2.5	-	-	-	537	-	-	-	0.28	-	-	-	75	5.0	-	58	-
KG-270-17-01	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-290-13-1A	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-290-13-1B	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-280-16-1A	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-280-16-1B	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Koala-UG-Granite	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
			Median		9.1	2.5	-	-	-	541	-	-	-	0.28	-	-	-	70	5.0	-	61	-
			Minimum		7.8	2.5	-	-	-	140	-	-	-	0.13	-	-	-	29	5.0	-	19	-
			Maximum		9.9	2.5	-	-	-	760	-	-	-	0.34	-	-	-	90	10	-	72	-
			Count		68	13	0	0	0	13	0	0	0	13	0	0	0	13	13	0	13	0
Misery																						
MDC-1 31.7	-	-	-	Granite	8.8	2.5	-	-	-	517	-	-	-	0.09	-	-	-	9.0	5.0	-	44	-
MDC-1 61.21	-	-	-	Granite	9.2	2.5	-	-	-	535	-	-	-	0.08	-	-	-	9.0	5.0	-	36	-
MDC-1 90.8	-	-	-	Granite	9.4	2.5	-	-	-	489	-	-	-	0.09	-	-	-	10	5.0	-	44	-
MDC-6 218.2	-	-	-	Granite	9.7	2.5	-	-	-	417	-	-	-	0.07	-	-	-	9.0	5.0	-	34	-
MDC-4 23.6	-	-	-	Granite	8.7	2.5	-	-	-	220	-	-	-	0.11	-	-	-	14	5.0	-	34	-
MDC-4 56	-	-	-	Granite	9.5	2.5	-	-	-	284	-	-	-	0.15	-	-	-	20	5.0	-	42	-
MDC-6 161.4	-	-	-	Granite	9.5	2.5	-	-	-	168	-	-	-	0.08	-	-	-	16	5.0	-	32	-
MDC-8 82	-	-	-	Granite	9.7	2.5	-	-	-	160	-	-	-	0.13	-	-	-	12	5.0	-	36	-
MDC-4 41.14	-	-	-	Granite	8.9	2.5	-	-	-	200	-	-	-	0.12	-	-	-	12	5.0	-	30	-
MDC-4 45.8	-	-	-	Granite	9.4	2.5	-	-	-	195	-	-	-	0.32	-	-	-	44	5.0	-	86	-
MDC-6 54.5	-	-	-	Granite	9.4	2.5	-	-	-	259	-	-	-	0.31	-	-	-	85	5.0	-	86	-
MDC-8 106.45	-	-	-	Granite	9.5	2.5	-	-	-	169	-	-	-	0.23	-	-	-	68	5.0	-	90	-
MPG 450- A	-	-	-	Granite	9.5	0.1	-	-	-	526	-	-	-	0.09	-	-	-	13	5.0	-	36	-
MPG 450- AA	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPG 450-AAA	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-26 2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-27 1A	-	-	-	Granite	9.3	0.1	-	-	-	549	-	-	-	0.07	-	-	-	10	5.0	-	30	-
MG 450-27 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-31 1A	-	-	-	Granite	8.1	0.1	-	-	-	404	-	-	-	0.21	-	-	-	57	5.0	-	36	-
MG 450-34 1A	-	-	-	Granite	9.2	0.1	-	-	-	553	-	-	-	0.09	-	-	-	11	5.0	-	40	-
MG 450-39-1A	-	-	-	Granite	8.6	0.2	-	-	-	609	-	-	-	0.10	-	-	-	15	5.0	-	42	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Misery (continued)																						
MG 450-39-1AA	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-39-1AAA	-	-	-	Granite	8.3	0.2	-	-	-	274	-	-	-	0.90	-	-	-	293	5.0	-	108	-
MG 450-39-2A	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-39-2AA	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-39-2AAA	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-41-1A	-	-	-	Granite	8.9	0.2	-	-	-	635	-	-	-	0.09	-	-	-	12	5.0	-	38	-
MG 450-41-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-45-1A	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 450-45-2A	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-46-1A	-	-	-	Granite	7.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-46-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-48-1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-48-2A	-	-	-	Granite	8.9	0.2	-	-	-	620	-	-	-	0.09	-	-	-	11	5.0	-	48	-
MG- 450-49-1A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-49-2A	-	-	-	Granite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-50-1A	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 450-50-2A	-	-	-	Granite	7.2	0.2	-	-	-	576	-	-	-	0.10	-	-	-	15	10	-	42	-
MG-440-SE-01	-	-	-	Granite	9.9	2.5	2.0	-	-	546	-	-	10	0.09	5.0	10	-	10	5.0	-	45	-
MG-440-SE-02	-	-	-	Granite	9.6	2.5	1.0	-	-	571	-	-	10	0.08	5.0	5.0	-	9.0	5.0	-	40	-
MG-440-SE-03	-	-	-	Granite	9.7	2.5	1.0	-	-	594	-	-	10	0.09	5.0	5.0	-	10	5.0	-	43	-
MG 440-01 1A	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-37-1A	-	-	-	Granite	9.2	2.5	-	-	-	449	-	-	-	0.10	-	-	-	12	10	-	42	-
MG- 440-37-2A	-	-	-	Granite	7.7	2.5	-	-	-	292	-	-	-	0.20	-	-	-	57	10	-	48	-
MG 440-39-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440-39-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-40-1A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-40-2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-44-1A	-	-	-	Granite	8.7	0.8	-	-	-	547	-	-	-	0.12	-	-	-	23	10	-	48	-
MG- 440-44-1A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-44-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-44-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-46-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-46-2A	-	-	-	Granite	8.7	0.8	-	-	-	504	-	-	-	0.11	-	-	-	12	5.0	-	46	-
MG- 440-53-1A	-	-	-	Granite	7.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-53-2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-54-1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-54-2A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-55-1A	-	-	-	Granite	7.6	0.6	-	-	-	625	-	-	-	0.12	-	-	-	17	5.0	-	54	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Misery (continued)																						
MG- 440-55-2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 57 1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 57 1B	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 59 1A	-	-	-	Granite	9.4	2.5	-	-	-	488	-	-	-	0.16	-	-	-	36	5.0	-	50	-
MG 440 59 2A	-	-	-	Granite	9.6	2.5	-	-	-	508	-	-	-	0.14	-	-	-	32	5.0	-	50	-
MG 440 60 1A	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 60 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 61 1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 61 2A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 62 1A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 62 2A	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 65 1A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 65 2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 440 66 1A	-	-	-	Granite	8.5	2.5	-	-	-	439	-	-	-	0.11	-	-	-	16	5.0	-	48	-
MG 440 66 2A	-	-	-	Granite	7.9	2.5	-	-	-	439	-	-	-	0.19	-	-	-	47	5.0	-	56	-
MG- 440-67-1A	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-67-2A	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-68-1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 440-68-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-440-70-1A	-	-	-	Granite	8.9	2.5	-	-	-	257	-	-	-	0.75	-	-	-	251	5.0	-	100	-
MG-440-70-2A	-	-	-	Granite	8.4	5.0	-	-	-	231	-	-	-	0.59	-	-	-	185	5.0	-	82	-
MG-430-W-01	-	-	-	Granite	9.7	2.5	1.0	-	-	538	-	-	10	0.09	5.0	10	-	9.0	5.0	-	40	-
MG-430-W-02	-	-	-	Granite	9.9	2.5	2.0	-	-	527	-	-	10	0.09	5.0	5.0	-	10	5.0	-	40	-
MG-430-W-03	-	-	-	Granite	9.6	2.5	2.0	-	-	497	-	-	10	0.08	5.0	10	-	8.0	5.0	-	35	-
MG- 430-11-1A	-	-	-	Granite	8.7	0.1	-	-	-	246	-	-	-	0.28	-	-	-	108	10	-	68	-
MG- 430-13-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-13-2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-13-3A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 18 1A	-	-	-	Granite	9.3	2.5	-	-	-	475	-	-	-	0.09	-	-	-	15	5.0	-	42	-
MG 430 18 2A	-	-	-	Granite	9.6	2.5	-	-	-	517	-	-	-	0.07	-	-	-	10	5.0	-	38	-
MG 430 19 1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 19 2A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 20 1A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 20 2A	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 27 2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 28 1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 28 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 29 1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Misery (continued)																						
MG 430 29 2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 30 1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 30 2A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 31 1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 31 2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-33-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-34-1A	-	-	-	Granite	9.1	2.5	-	-	-	476	-	-	-	0.08	-	-	-	10	10	-	38	-
MG- 430-35-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-35-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-36-1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-36-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-41-1B	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 430-41-2B	-	-	-	Granite	6.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 47 1A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 47 1B	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 430 27 1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG/S-430-44-2A	-	-	-	Granite	9.1	2.5	-	-	-	540	-	-	-	0.08	-	-	-	11	5.0	-	40	-
MG-430-42-1A	-	-	-	Granite	8.6	2.5	-	-	-	457	-	-	-	0.18	-	-	-	40	5.0	-	50	-
MG-430-42-2A	-	-	-	Granite	7.8	2.5	-	-	-	464	-	-	-	0.12	-	-	-	23	5.0	-	42	-
MG-430-58 1A	-	-	-	Granite	9.0	2.5	-	-	-	446	-	-	-	0.13	-	-	-	24	5.0	-	40	-
MG-430-58 2A	-	-	-	Granite	8.9	2.5	-	-	-	366	-	-	-	0.40	-	-	-	120	5.0	-	74	-
MG-420-SW-01	-	-	-	Granite	9.8	5.0	2.0	-	-	646	-	-	10	0.08	5.0	5.0	-	9.0	5.0	-	39	-
MG-420-SW-02	-	-	-	Granite	10.0	2.5	2.0	-	-	630	-	-	10	0.08	5.0	10	-	9.0	5.0	-	40	-
MG-420-SW-03	-	-	-	Granite	9.9	2.5	1.0	-	-	626	-	-	10	0.08	5.0	5.0	-	9.0	5.0	-	38	-
MG- 420-07-1A	-	-	-	Granite	9.0	2.5	-	-	-	499	-	-	-	0.09	-	-	-	11	10	-	42	-
MG- 420-07-2A	-	-	-	Granite	9.0	2.5	-	-	-	516	-	-	-	0.09	-	-	-	11	10	-	40	-
MG- 420-10-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-10-2A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-13-1A	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-13-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-14-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-14-2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-15-1B	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG- 420-15-2B	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 420 20 1A	-	-	-	Granite	8.4	2.5	-	-	-	402	-	-	-	0.11	-	-	-	19	5.0	-	40	-
MG 420 20 1B	-	-	-	Granite	8.4	2.5	-	-	-	439	-	-	-	0.11	-	-	-	17	5.0	-	42	-
MG/S-420-30-1A	-	-	-	Granite	9.3	2.5	-	-	-	460	-	-	-	0.10	-	-	-	15	5.0	-	34	-
MG/S-420-30-2A	-	-	-	Granite	9.4	2.5	-	-	-	555	-	-	-	0.09	-	-	-	12	5.0	-	42	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Misery (continued)																						
MG-420-18-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-18-2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-24-1A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-24-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-25/26-1A	-	-	-	Granite	9.2	2.5	-	-	-	421	-	-	-	0.24	-	-	-	65	5.0	-	62	-
MG-420-25/26-2A	-	-	-	Granite	8.9	2.5	-	-	-	218	-	-	-	0.26	-	-	-	88	5.0	-	74	-
MG-420-26-1A	-	-	-	Granite	9.1	2.5	-	-	-	351	-	-	-	0.15	-	-	-	40	5.0	-	50	-
MG-420-26-2A	-	-	-	Granite	9.2	5.0	-	-	-	637	-	-	-	0.79	-	-	-	246	5.0	-	126	-
MG-420-27-1A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-27-2A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-28-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-28-2A	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-30-1A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-30-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-31-1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-31-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-36-1A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-420-36-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-02-01	-	-	-	Granite	9.6	0.025	2.5	0.5	-	424	-	0.025	19	0.14	0.73	5.8	-	15	0.5	-	49	-
MG-410-03-01	-	-	-	Granite	9.5	0.025	3.0	0.5	-	531	-	0.025	8.0	0.11	0.41	2.5	-	17	0.6	-	36	-
MG-410-07-01	-	-	-	Granite	8.8	0.025	2.0	1.0	-	446	-	0.05	2.4	0.089	0.28	2.9	-	11	0.3	-	30	-
MG 410 04 1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 04 1B	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 05 1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 05 2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 06 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 06 1B	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 07 1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 07 1B	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 09 1A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 09 1B	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 10 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 410 10 1B	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-12-1A	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-12-2A	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-16-1A	-	-	-	Granite	9.1	2.5	-	-	-	457	-	-	-	0.08	-	-	-	10	5.0	-	36	-
MG-410-16-2A	-	-	-	Granite	8.7	2.5	-	-	-	438	-	-	-	0.09	-	-	-	11	5.0	-	34	-
MG-410-17-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Misery (continued)																						
MG-410-17-2A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-19-1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-19-2A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-20 1A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-20 2A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-24 1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-24 2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-26 1A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-26 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-28 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-28 2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-31 1A	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-31 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-32 1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-32 2A	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-36 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-36 2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-38 1A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-38 2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-40 1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-410-40 2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG/D-410-41 -1A	-	-	-	Granite	9.1	5.0	-	-	-	297	-	-	-	0.08	-	-	-	11	5.0	-	32	-
MG/D-410-41 -2A	-	-	-	Granite	9.4	2.5	-	-	-	337	-	-	-	0.11	-	-	-	20	5.0	-	38	-
MG 400-34 1a	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 400-34 2a	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 400-41 1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-01-1A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-01-2A	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-02 1A	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-02 2A	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-03 1A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-03 2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-05 1A	-	-	-	Granite	9.3	2.5	-	-	-	418	-	-	-	0.10	-	-	-	14	5.0	-	38	-
MG-400-05 2A	-	-	-	Granite	8.9	2.5	-	-	-	402	-	-	-	0.10	-	-	-	16	5.0	-	36	-
MG-400-07 1A	-	-	-	Granite	9.5	2.5	-	-	-	450	-	-	-	0.09	-	-	-	11	5.0	-	42	-
MG-400-07 2A	-	-	-	Granite	9.6	2.5	-	-	-	532	-	-	-	0.09	-	-	-	10	5.0	-	40	-
MG-400-08-1A	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-08-2A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Misery (continued)																						
MG-400-09-1A	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-09-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-11-1A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-11-2A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-15-1A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-15-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-21-1A	-	-	-	Granite	9.4	2.5	-	-	-	499	-	-	-	0.09	-	-	-	11	5.0	-	48	-
MG-400-21-2A	-	-	-	Granite	9.3	2.5	-	-	-	462	-	-	-	0.09	-	-	-	12	5.0	-	46	-
MG-400-24-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-24-2A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-25-1A	-	-	-	Granite	8.8	2.5	-	-	-	269	-	-	-	0.32	-	-	-	106	5.0	-	84	-
MG-400-25-2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-31-1A	-	-	-	Granite	8.9	2.5	-	-	-	321	-	-	-	0.35	-	-	-	110	5.0	-	94	-
MG-400-31-2A	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-32-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-32-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-36-1A	-	-	-	Granite	8.9	2.5	-	-	-	533	-	-	-	0.08	-	-	-	10	5.0	-	50	-
MG-400-36-2A	-	-	-	Granite	9.2	2.5	-	-	-	573	-	-	-	0.09	-	-	-	10	5.0	-	52	-
MG-400-37-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-400-37-2A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-05 1a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-05 2a	-	-	-	Granite	9.9	2.5	-	-	-	582	-	-	-	0.09	-	-	-	12	5.0	-	46	-
MG 390-06 1a	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-06 2a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-09 1a	-	-	-	Granite	9.7	2.5	-	-	-	450	-	-	-	0.10	-	-	-	13	5.0	-	46	-
MG 390-09 1a	-	-	-	Granite	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-09 2a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-09 2a	-	-	-	Granite	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-10 1a	-	-	-	Granite	9.5	2.5	-	-	-	546	-	-	-	0.08	-	-	-	9.0	5.0	-	42	-
MG 390-10 2a	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-11G 1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-11G 2a	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-13 1a	-	-	-	Granite	9.6	2.5	-	-	-	515	-	-	-	0.11	-	-	-	12	5.0	-	54	-
MG 390-13 2a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-14T 1a	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 390-14T 2a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-02-1A	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-02-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Misery (continued)																						
MG-390-03-1A	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-03-2A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-04-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-04-2A	-	-	-	Granite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-17-1a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-17-1a	-	-	-	Granite	8.8	2.5	-	-	-	255	-	-	-	0.08	-	-	-	8.0	5.0	-	22	-
MG-390-17-2a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-17-2a	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-20-1a	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-20-2a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-21-1a	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-21-2a	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-22-1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-22-1a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-22-2a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-22-2a	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-23T-1a	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-390-23T-2a	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 380-10 1a	-	-	-	Granite	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 380-10 2a	-	-	-	Granite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 380-14 1a	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG 380-14 2a	-	-	-	Granite	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-16-1a	-	-	-	Granite	9.8	5.0	-	-	-	539	-	-	-	0.08	-	-	-	9.0	5.0	-	42	-
MG-380-16-2a	-	-	-	Granite	9.9	2.5	-	-	-	496	-	-	-	0.07	-	-	-	8.0	5.0	-	38	-
MG-380-18-1a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-18-2a	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-19-1a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-19-2a	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-23-1A	-	-	-	Granite	8.7	2.5	-	-	-	431	-	-	-	0.07	-	-	-	8.0	5.0	-	28	-
MG-380-23-2A	-	-	-	Granite	9.1	2.5	-	-	-	489	-	-	-	0.08	-	-	-	9.0	5.0	-	36	-
MG-380-26-1A	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-26-2A	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-27-1A	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-27-2A	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-29T-1A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-29T-2A	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-31T-1A	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-380-31T-2A	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Misery (continued)																						
MG-370-06-1	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-370-06-2	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-370-24-B	-	-	-	Granite	6.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-360-28-1	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-360-28-2	-	-	-	Granite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-360-31-1	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-360-31-2	-	-	-	Granite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MGS-360-18-01	-	-	-	Granite	9.2	2.5	-	-	-	231	-	-	-	0.34	-	-	-	106	5.0	-	86	-
MGS-360-18-02	-	-	-	Granite	9.3	2.5	-	-	-	201	-	-	-	0.32	-	-	-	98	5.0	-	76	-
MG-350-35-1	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-350-35-2	-	-	-	Granite	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-340-23-02 10-DEC-04	-	-	-	Granite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-340-23-01 10-DEC-04	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-330-19-02 27-DEC-04	-	-	-	Granite	7.8	2.5	-	-	-	513	-	-	-	0.09	-	-	-	11	5.0	-	37	-
MG-330-19-01 27-DEC-04	-	-	-	Granite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-330-18-02 26-DEC-04	-	-	-	Granite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-330-18-01 26-DEC-04	-	-	-	Granite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-31-02 15-JAN-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-31-01 15-JAN-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-30-02 11-JAN-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-30-01 11-JAN-05	-	-	-	Granite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-29-02 5-FEB-05	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-29-01 5-FEB-05	-	-	-	Granite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-25-04 1-JAN-05	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-25-03 1-JAN-05	-	-	-	Granite	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-25-02 1-JAN-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-25-01 1-JAN-05	-	-	-	Granite	8.6	2.5	-	-	-	589	-	-	-	0.10	-	-	-	19	5.0	-	46	-
MG-320-20-02 18-DEC-04	-	-	-	Granite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-320-20-01 18-DEC-04	-	-	-	Granite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-310-10-02 20-FEB-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-310-10-01 20-FEB-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-310-09-02 20-FEB-05	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-310-09-01 20-FEB-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-310-07-02 15-FEB-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-310-07-01 15-FEB-05	-	-	-	Granite	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-300-13-06 25-Mar-05	-	-	-	Granite	9.0	2.5	-	-	-	491	-	-	-	0.10	-	-	-	19	5.0	-	48	-
MG-300-13-05 25-Mar-05	-	-	-	Granite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-300-13-04 25-Mar-05	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Misery (continued)																						
MG-300-13-03 25-Mar-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-300-13-02 25-Mar-05	-	-	-	Granite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-300-13-01 25-Mar-05	-	-	-	Granite	8.6	2.5	-	-	-	508	-	-	-	0.11	-	-	-	27	5.0	-	41	-
MG-290-10-04 31-Mar-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-290-10-03 31-Mar-05	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-290-10-02 31-Mar-05	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG-290-10-01 31-Mar-05	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MGT-39 100-103	-	-	-	Granite	9.8	0.05	0.5	0.25	-	11	-	0.1	1.7	0.066	0.2	1.2	-	7.0	0.05	-	39	-
MGT-39 200-203	-	-	-	Granite	9.6	0.05	0.5	0.25	-	15	-	0.1	8.0	0.049	0.1	3.1	-	5.0	0.05	-	40	-
MGT-49 58.28-60.08	-	-	-	Granite	9.4	0.05	1.0	0.25	-	6	-	0.1	1.4	0.03	0.1	10	-	10	0.05	-	24	-
MGT-49 65.82-67.00	-	-	-	Granite	9.7	0.05	0.3	0.25	-	4	-	0.1	4.0	0.007	0.05	14	-	1.0	0.05	-	26	-
MGT-69 7.3-9.5	-	-	-	Granite	9.3	0.05	0.5	0.25	-	14	-	0.1	3.1	0.041	0.05	6.7	-	5.0	0.1	-	30	-
MGT-69 166-169	-	-	-	Granite	9.3	0.05	0.5	0.25	-	19	-	0.1	13	0.02	0.05	4.8	-	6.0	0.05	-	29	-
MGT-44 213-216	-	-	-	Granite	9.5	0.05	2.9	0.25	-	5	-	0.1	23	0.14	0.3	5.4	-	26	0.05	-	60	-
MGT-60 35-38	-	-	-	Granite	9.6	0.05	0.7	0.25	-	4	-	0.1	13	0.045	0.2	4.4	-	3.0	0.05	-	30	-
MGT-63 220-223	-	-	-	Granite	9.2	0.05	0.3	0.25	-	11	-	0.1	12	0.003	0.05	4.0	-	1.0	0.05	-	11	-
MGT-66 55-58	-	-	-	Granite	9.8	0.05	0.6	0.25	-	15	-	0.1	27	0.036	0.05	6.7	-	6.0	0.05	-	32	-
MGT-66 76-79	-	-	-	Granite	9.8	0.05	0.6	0.25	-	5	-	0.1	24	0.073	0.2	5.3	-	7.0	0.05	-	43	-
MGT-70 15-18	-	-	-	Granite	9.6	0.05	0.5	0.25	-	9	-	0.1	1.4	0.055	0.1	1.1	-	7.0	0.05	-	36	-
MGT-70 33-36	-	-	-	Granite	9.7	0.05	0.4	0.25	-	10	-	0.1	1.2	0.048	0.1	2.7	-	5.0	0.05	-	36	-
MGT-70 51-54	-	-	-	Granite	9.7	0.05	0.5	0.25	-	10	-	0.1	4.8	0.061	0.2	5.1	-	7.0	0.05	-	42	-
MGT-70 69-72	-	-	-	Granite	9.8	0.05	0.5	0.25	-	10	-	0.1	1.5	0.051	0.1	1.6	-	6.0	0.05	-	36	-
MGT-51 174-177	-	-	-	Granite	9.6	0.05	0.6	0.25	-	7	-	0.1	25	0.065	0.2	6.1	-	5.0	0.05	-	36	-
MGT-52 50-53	-	-	-	Granite	9.3	0.05	0.5	0.25	-	12	-	0.1	2.1	0.065	0.2	1.7	-	7.0	0.05	-	44	-
MGT-52 57-60	-	-	-	Granite	9.3	0.05	0.8	0.25	-	13	-	0.1	2.1	0.081	0.2	2.0	-	8.0	0.05	-	48	-
MGT-52 150-153	-	-	-	Granite	9.6	0.05	0.6	0.25	-	13	-	0.1	1.7	0.074	0.2	1.6	-	7.0	0.05	-	47	-
MGT-52 157-160	-	-	-	Granite	9.5	0.05	0.9	0.25	-	15	-	0.1	3.1	0.086	0.3	1.7	-	8.0	0.05	-	53	-
MGT-52 250-253	-	-	-	Granite	9.4	0.05	0.7	0.25	-	15	-	0.1	2.7	0.074	0.2	1.5	-	7.0	0.05	-	47	-
MGT-52 257-260	-	-	-	Granite	9.4	0.05	0.9	0.25	-	13	-	0.1	2.8	0.09	0.2	1.5	-	9.0	0.05	-	54	-
MGT-54 240-243	-	-	-	Granite	9.3	0.05	0.6	0.25	-	17	-	0.1	1.8	0.072	0.2	2.6	-	7.0	0.05	-	46	-
MGT-54 247-250	-	-	-	Granite	9.4	0.05	0.7	0.25	-	15	-	0.1	1.9	0.083	0.2	1.9	-	8.0	0.05	-	46	-
MDC-4 64.69	-	-	-	Granite	9.4	2.5	-	-	-	239	-	-	-	0.24	-	-	-	61	5.0	-	60	-
MS G 420 19 1A	-	-	-	Granite	9.0	2.5	-	-	-	492	-	-	-	0.07	-	-	-	7.0	5.0	-	34	-
MS G 420 19 1B	-	-	-	Granite	8.8	2.5	-	-	-	464	-	-	-	0.06	-	-	-	8.0	5.0	-	30	-
MS G 410 03 1A	-	-	-	Granite	9.0	2.5	-	-	-	276	-	-	-	0.31	-	-	-	97	5.0	-	86	-
MS G 410 03 1B	-	-	-	Granite	8.9	2.5	-	-	-	258	-	-	-	0.34	-	-	-	95	10	-	92	-
MS/G-410-27 1A	-	-	-	Granite	8.9	2.5	-	-	-	191	-	-	-	0.34	-	-	-	118	5.0	-	72	-
MS/G-410-27 2A	-	-	-	Granite	8.8	2.5	-	-	-	156	-	-	-	0.37	-	-	-	128	5.0	-	70	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-																		
					Paste pH unit	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-	
						Sb ppm	Sc ppm	Se ppm	Sn ppm	Sr ppm	Ta ppm	Te ppm	Th ppm	Ti %	TI ppm	U (ICP) ppm	U (XRF) ppm	V ppm	W ppm	Y ppm	Zn ppm	Zr ppm	
Granite (continued)																							
Misery (continued)																							
MS 400-38 1a	-	-	-	Granite	9.5	2.5	-	-	-	193	-	-	-	0.49	-	-	-	155	5.0	-	104	-	
MS 400-38 2a	-	-	-	Granite	9.6	2.5	-	-	-	187	-	-	-	0.27	-	-	-	88	5.0	-	68	-	
MGT-49 171.23-173.14	-	-	-	Granite	9.4	0.05	0.3	0.25	-	5	-	0.1	1.0	0.004	0.05	17	-	1.0	0.1	-	14	-	
MGT-51 184-187	-	-	-	Granite	9.6	0.05	0.4	0.25	-	7	-	0.1	7.4	0.023	0.05	7.0	-	3.0	0.05	-	15	-	
MGT-52 125.26-126.8	-	-	-	Granite	9.4	0.05	0.4	0.25	-	12	-	0.1	1.3	0.024	0.05	5.2	-	3.0	0.1	-	17	-	
MGT-52 137.8-139.3	-	-	-	Granite	9.6	0.05	0.1	0.25	-	4	-	0.1	0.5	0.002	0.05	3.8	-	1.0	0.05	-	5.0	-	
MGT-56 38-41	-	-	-	Granite	8.9	0.05	1.3	0.25	-	9	-	0.1	5.8	0.005	0.05	1.8	-	17	0.05	-	21	-	
Median					9.1	2.5	0.7	0.25	-	423	-	0.1	5.8	0.09	0.2	5.0	-	11	5.0	-	42	-	
Minimum					6.5	0.025	0.1	0.25	-	4	-	0.025	0.5	0.002	0.05	1.1	-	1.0	0.05	-	5.0	-	
Maximum					10.1	5.0	3.0	1.0	-	646	-	0.1	27	0.90	5.0	17	-	293	10	-	126	-	
Count					370	130	41	32	0	130	0	32	41	129	41	41	0	130	130	0	130	0	
Panda																							
PG-210-12-1	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PG-210-12-2	-	-	-	Granite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PG-210-08-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PG-210-08-2	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-210-06-1	-	-	-	Granite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-210-06-2	-	-	-	Granite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-195-10-1	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW-195-10-2	-	-	-	Granite	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Panda-UG-Granite	-	-	-	Granite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Median					9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Minimum					9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Maximum					9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Count					9	0	0	0	0	-	0	0	0	0	0	0	0	0	0	0	0	0	
Pigeon																							
97-54	97-54	188.69	189.09	Granite	9.7	2.5	5.0	-	5.0	11	-	-	-	0.11	-	-	-	35	5.0	7.0	47	-	
97-54	97-54	373.1	373.38	Granite	9.7	5.0	7.0	-	5.0	19	-	-	-	0.21	-	-	-	72	5.0	6.0	53	-	
97-55	97-55	295.01	295.75	Granite	9.8	2.5	2.0	-	5.0	12	-	-	-	0.10	-	-	-	24	5.0	4.0	37	-	
97-55	97-55	56	56.59	Granite	9.5	5.0	9.0	-	5.0	11	-	-	-	0.20	-	-	-	93	5.0	7.0	73	-	
HC-Pdef-6	-	-	-	Granite	9.6	0.05	9.1	1.0	0.7	338	0.4	0.025	16	0.21	0.41	3.1	-	67	1.6	9.9	43	96	
HC-Pdef-7	-	-	-	Granite	9.0	0.09	19	1.0	1.1	266	0.75	0.025	9.4	0.44	0.68	3.3	-	140	0.9	8.3	80	132	
HC-Pdef-12	-	-	-	Granite	9.0	0.025	11	1.0	0.7	233	0.52	0.025	6.4	0.20	0.29	3.3	-	68	0.8	8.4	42	64	
HC-PDef-17	-	-	-	Granite	9.5	0.08	16	1.0	1.1	205	0.64	0.025	8.5	0.33	0.66	3.9	-	115	0.7	8.1	75	126	
HC-PDef-24	-	-	-	Granite	9.2	0.06	13	1.0	1.4	133	0.56	0.025	5.4	0.32	0.36	2.9	-	110	2.1	6.1	111	103	
HC-PDef-25	-	-	-	Granite	9.3	0.06	16	2.0	0.8	234	0.68	0.025	9.9	0.32	0.48	3.6	-	115	1.2	12	61	121	
HC-PDef-27	-	-	-	Granite	9.9	0.025	13	1.0	1.2	274	0.82	0.025	8.9	0.23	0.59	3.3	-	75	5.1	8.1	62	101	
HC-PDef-29	-	-	-	Granite	10.0	0.025	22	1.0	1.6	238	1.3	0.025	13	0.50	1.1	4.4	-	160	1.8	11	97	175	

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	General Rock Type																	
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U (ICP)	U (XRF)	V	W	Y	Zn	Zr	
Granite (continued)																						
Pigeon (continued)																						
HC-PDef-30	-	-	-	Granite	9.7	0.05	13	1.0	0.7	329	0.65	0.025	14	0.29	0.59	3.7	-	97	0.9	11	58	136
HC-PDef-33	-	-	-	Granite	9.3	0.07	16	1.0	0.8	153	0.72	0.025	7.0	0.29	0.58	3.4	-	96	0.9	8.0	59	100
HC-PDef-34	-	-	-	Granite	9.0	0.06	7.4	1.0	0.6	168	0.37	0.025	4.0	0.13	0.17	2.7	-	49	1.7	6.5	39	61
Median					9.5	0.06	13	1.0	1.1	205	0.65	0.025	8.9	0.23	0.58	3.3	-	93	1.7	8.1	59	103
Minimum					9.0	0.025	2.0	1.0	0.6	11	0.37	0.025	4.0	0.10	0.17	2.7	-	24	0.7	4.0	37	61
Maximum					10.0	5.0	22	2.0	5.0	338	1.3	0.025	16	0.50	1.1	4.4	-	160	5.1	12	111	175
Count					15	15	15	11	15	15	11	11	11	15	11	11	0	15	15	15	15	11
Sable																						
SDC-07	SDC-07	152.3	152.73	Granite	7.5	2.5	4.0	-	5.0	26	-	-	-	0.27	-	-	-	64	5.0	13	130	-
SDC-02	SDC-02	48.58	49.28	Granite	9.1	5.0	0.5	-	5.0	1	-	-	-	0.01	-	-	-	1.0	5.0	0.5	424	-
SDC-05	SDC-05	152	152.5	Granite	9.8	2.5	0.5	-	5.0	7	-	-	-	0.05	-	-	-	5.0	5.0	2.0	47	-
SDC-07	SDC-07	150.37	150.6	Granite	9.7	2.5	0.5	-	5.0	7	-	-	-	0.005	-	-	-	1.0	5.0	1.0	3.0	-
SDC-07	SDC-07	91.35	91.8	Granite	9.7	2.5	1.0	-	5.0	5	-	-	-	0.03	-	-	-	4.0	5.0	6.0	45	-
SDC-04	SDC-04	47.5	47.5	Granite	9.6	5.0	0.5	-	5.0	4	-	-	-	0.01	-	-	-	1.0	5.0	1.0	7.0	-
SDC-12	SDC-12	11.28	11.68	Granite	9.3	2.5	0.5	-	5.0	4	-	-	-	0.005	-	-	-	1.0	5.0	0.5	10	-
SDC-07	SDC-07	113	113.3	Granite	9.6	2.5	0.5	-	5.0	5	-	-	-	0.005	-	-	-	1.0	5.0	1.0	20	-
SDC-04	SDC-04	47	47.3	Granite	9.7	2.5	0.5	-	5.0	5	-	-	-	0.03	-	-	-	3.0	5.0	2.0	52	-
SDC-02	SDC-02	56	56.3	Granite	9.5	5.0	0.5	-	5.0	3	-	-	-	0.005	-	-	-	1.0	5.0	0.5	9.0	-
SDC-11	SDC-11	52	52	Granite	9.7	2.5	0.5	-	5.0	6	-	-	-	0.005	-	-	-	2.0	5.0	3.0	15	-
SDC-12	SDC-12	88.89	89.259	Granite	9.7	2.5	0.5	-	5.0	8	-	-	-	0.03	-	-	-	5.0	5.0	2.0	48	-
SDC-13	SDC-13	37.52	37.79	Granite	9.7	2.5	0.5	-	5.0	8	-	-	-	0.06	-	-	-	5.0	5.0	2.0	42	-
SDC-12	SDC-12	186.64	187.04	Granite	9.4	2.5	0.5	-	5.0	8	-	-	-	0.01	-	-	-	3.0	5.0	3.0	27	-
SDC-02	SDC-02	20.5	20.5	Granite	9.2	5.0	0.5	-	5.0	4	-	-	-	0.01	-	-	-	2.0	5.0	4.0	23	-
SDC-03	SDC-03	26	26.3	Granite	9.7	5.0	0.5	-	5.0	7	-	-	-	0.03	-	-	-	5.0	5.0	5.0	92	-
SDC-13	SDC-13	154.64	154.89	Granite	9.2	2.5	0.5	-	5.0	5	-	-	-	0.01	-	-	-	3.0	5.0	2.0	18	-
SDC-12	SDC-12	303.89	304.39	Granite	9.8	2.5	0.5	-	5.0	10	-	-	-	0.04	-	-	-	3.0	5.0	5.0	28	-
SDC-08	SDC-08	54.1	54.43	Granite	9.4	2.5	1.0	-	5.0	15	-	-	-	0.05	-	-	-	25	5.0	4.0	35	-
SDC-13	SDC-13	106.58	1,069.89	Granite	10.0	2.5	9.0	-	5.0	9	-	-	-	0.31	-	-	-	93	5.0	6.0	99	-
SDC-05	SDC-05	233.9	234.17	Granite	9.5	2.5	1.0	-	5.0	13	-	-	-	0.13	-	-	-	19	5.0	5.0	88	-
SDC-05	SDC-05	224	224.23	Granite	9.8	2.5	1.0	-	5.0	20	-	-	-	0.11	-	-	-	18	5.0	4.0	53	-
SDC-07	SDC-07	114.32	144.68	Granite	9.2	2.5	3.0	-	5.0	25	-	-	-	0.23	-	-	-	52	5.0	11	129	-
SDC-12	SDC-12	386.18	386.58	Granite	9.6	2.5	4.0	-	5.0	26	-	-	-	0.12	-	-	-	61	5.0	7.0	107	-
SDC-07	SDC-07	157.03	157.42	Granite	9.8	2.5	3.0	-	5.0	17	-	-	-	0.26	-	-	-	66	5.0	11	152	-
SDC-06	SDC-06	117.93	118.36	Granite	9.8	2.5	4.0	-	5.0	36	-	-	-	0.26	-	-	-	50	5.0	6.0	99	-
SDC-04	SDC-04	77	77.42	Granite	9.4	2.5	0.5	-	5.0	4	-	-	-	0.005	-	-	-	1.0	5.0	1.0	0.5	-
SDC-13	SDC-13	30.14	30.45	Granite	9.4	2.5	4.0	-	5.0	61	-	-	-	0.29	-	-	-	68	5.0	7.0	79	-
SDC-13	SDC-13	96.97	97.23	Granite	9.5	2.5	3.0	-	5.0	75	-	-	-	0.28	-	-	-	69	5.0	6.0	90	-
SDC-05	SDC-05	98.73	98.88	Granite	9.5	2.5	0.5	-	5.0	4	-	-	-	0.01	-	-	-	1.0	5.0	2.0	30	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Granite (continued)																						
Sable (continued)																						
SDC-11	SDC-11	36.95	37.27	Granite	9.9	5.0	0.5	-	5.0	6	-	-	-	0.005	-	-	-	2.0	5.0	2.0	20	-
SDC-05	SDC-05	17	17.31	Granite	9.8	5.0	1.0	-	5.0	7	-	-	-	0.08	-	-	-	8.0	5.0	5.0	72	-
SDC-13	SDC-13	199.96	200.25	Granite	9.8	2.5	1.0	-	5.0	11	-	-	-	0.16	-	-	-	22	5.0	4.0	121	-
SDC-08	SDC-08	88.38	89	Granite	9.2	2.5	3.0	-	5.0	12	-	-	-	0.005	-	-	-	29	5.0	5.0	43	-
SDC-04	SDC-04	83	83.35	Granite	10.1	5.0	13	-	5.0	14	-	-	-	0.59	-	-	-	158	5.0	3.0	291	-
SDC-08	SDC-08	90.78	91.39	Granite	9.2	2.5	2.0	-	5.0	7	-	-	-	0.01	-	-	-	76	5.0	3.0	54	-
SDC-07	SDC-07	114.7	115.6	Granite	9.5	5.0	3.0	-	5.0	25	-	-	-	0.25	-	-	-	64	5.0	12	127	-
SDC-01	SDC-01	68.5	68.9	Granite	9.0	5.0	2.0	-	5.0	13	-	-	-	0.12	-	-	-	23	5.0	5.0	72	-
SDC-06	SDC-06	36.7	37.32	Granite	9.5	2.5	0.5	-	5.0	3	-	-	-	0.005	-	-	-	1.0	5.0	1.0	14	-
SCD-05	SCD-05	151.23	151.75	Granite	10.0	5.0	9.0	-	5.0	10	-	-	-	0.39	-	-	-	108	5.0	5.0	227	-
SDC-11	SDC-11	55.6	56	Granite	9.6	2.5	0.5	-	5.0	5	-	-	-	0.005	-	-	-	1.0	5.0	6.0	5.0	-
		Median			9.6	2.5	0.5	-	5.0	8	-	-	-	0.03	-	-	-	5.0	5.0	4.0	48	-
		Minimum			7.5	2.5	0.5	-	5.0	1	-	-	-	0.005	-	-	-	1.0	5.0	0.5	0.5	-
		Maximum			10.1	5.0	13	-	5.0	75	-	-	-	0.59	-	-	-	158	5.0	13	424	-
		Count			41	41	41	0	41	41	0	0	0	41	0	0	0	41	41	41	41	0
Jay																						
2014-DD-003	JGT-04	53	57.25	Granite	8.59	0.025	0.3	0.5	0.15	5	0.025	0.025	0.9	0.005	0.05	0.55	-	2	0.2	1.04	4	3
2014-DD-004	JGT-04	61	71	Granite	8.08	0.025	18.6	0.5	1.1	8	0.025	0.025	6.2	0.23	0.55	2.54	-	143	0.3	5.02	139	21.3
2014-DD-021	JGT-04	275	285	Granite	9.45	0.025	0.5	0.5	0.7	5	0.025	0.025	5.3	0.03	0.4	8.33	-	3	0.1	3.46	48	14.2
2014-DD-023	JGT-05	16.44	20.77	Granite	8.49	0.025	0.3	0.5	0.3	5	0.025	0.025	2.3	0.005	0.05	3.4	-	6	0.4	1.12	23	6.7
2014-DD-024	JGT-05	35.74	44.77	Granite	9.21	0.025	1.4	0.5	1	5	0.025	0.025	4.9	0.04	0.32	4.85	-	12	0.1	4.22	49	12.7
2014-DD-025	JGT-05	71.79	79.86	Granite	9.32	0.025	0.6	0.5	0.5	4	0.025	0.025	4.6	0.03	0.22	5.1	-	3	0.05	2.64	46	12.1
2014-DD-026	JGT-05	101.77	110.98	Granite	9.30	0.025	0.3	0.5	0.4	5	0.025	0.025	5.1	0.02	0.19	5.66	-	3	0.1	3.16	42	13
2014-DD-027	JGT-05	131	139.1	Granite	9.47	0.025	0.6	0.5	0.4	5	0.025	0.025	7.4	0.03	0.19	4.59	-	5	0.1	2.87	48	14.8
2014-DD-028	JGT-05	161.34	172.88	Granite	9.49	0.025	0.8	0.5	0.5	5	0.025	0.025	6.9	0.05	0.26	5.21	-	6	0.05	7.09	51	15.1
2014-DD-029	JGT-05	198.88	206.77	Granite	9.46	0.025	0.7	0.5	0.4	4	0.025	0.025	4.5	0.03	0.17	3.93	-	3	0.05	1.72	34	9.3
2014-DD-030	JGT-05	233.04	241.73	Granite	9.54	0.025	1	0.5	0.6	4	0.025	0.025	6.6	0.04	0.25	4.15	-	4	0.05	2.29	46	12.2
2014-DD-031	JGT-05	259.49	268.27	Granite	9.51	0.025	1.2	0.5	0.7	5	0.025	0.025	6.4	0.06	0.35	3.98	-	5	0.05	4.81	48	11.9
2014-DD-032	JGT-05	276.96	281.55	Granite	9.50	0.025	3.5	0.5	1.2	21	0.025	0.025	3.2	0.15	0.96	1.89	-	39	0.2	5.84	149	11.4
2014-DD-038	JGT-03	433.32	441.89	Granite	9.23	0.025	0.5	0.5	0.15	6	0.025	0.025	6.1	0.01	0.11	6.12	-	4	0.05	2.24	36	10.1
2014-DD-039	JGT-03	404.73	413.48	Granite	9.08	0.025	0.4	0.5	0.15	6	0.025	0.025	6.8	0.005	0.05	9.19	-	3	0.05	2.06	24	12.5
2014-DD-041	JGT-03	290.1	298.57	Granite	9.17	0.06	1.2	0.5	0.3	6	0.025	0.025	5.9	0.05	0.21	5.46	-	10	0.05	3.23	44	10.4
2014-DD-045	JGT-03	89.48	98.08	Granite	9.14	0.025	0.4	0.5	0.15	6	0.025	0.025	4	0.005	0.06	3.51	-	3	0.1	3.11	24	9
2014-DD-046	JGT-03	239.48	248.11	Granite	9.19	0.07	0.4	0.5	0.3	5	0.025	0.025	5.8	0.01	0.1	8.33	-	4	0.05	3.5	30	14.4
2014-DD-047	JGT-03	205.53	214.19	Granite	9.28	0.025	0.5	0.5	0.15	4	0.025	0.025	9.5	0.005	0.08	7.84	-	4	0.05	3.27	46	15.1
2014-DD-048	JGT-03	154.51	163.19	Granite	9.36	0.025	0.4	0.5	0.4	5	0.025	0.025	6.1	0.01	0.15	5.94	-	4	0.05	2.67	44	15.6
2014-DD-050	JGT-02	279	287	Granite	9.20	0.025	0.7	0.5	0.15	5	0.025	0.025	9	0.02	0.15	5.26	-	5	0.05	4.08	38	12
2014-DD-051	JGT-02	200	207.55	Granite	8.76	0.025	0.6	0.5	0.15	6	0.025	0.025	5.5	0.005	0.04	3.06	-	4	0.2	2.22	25	12.2

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	General Rock Type																		
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-	
		From	To	unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr		
Granite (continued)																							
Jay (continued)																							
2014-DD-052	JGT-02	125.42	134.04	Granite	8.54	0.025	1.3	0.5	0.4	6	0.025	0.025	16.6	0.05	0.42	5.01	-	8	0.1	5.97	49	20.2	
2014-DD-053	JGT-02	64.04	74	Granite	8.60	0.025	0.9	0.5	0.3	5	0.025	0.025	6.7	0.03	0.24	4.2	-	5	0.05	3.55	47	10.5	
2014-DD-055	JGT-02	60.16	65.55	Granite	8.44	0.025	0.9	0.5	0.15	5	0.025	0.025	6	0.03	0.25	3.87	-	6	0.3	2.66	43	8.1	
2014-DD-056	JGT-02	29.89	38.2	Granite	9.07	0.025	0.7	0.5	0.15	4	0.025	0.025	6.7	0.03	0.27	3.67	-	4	0.05	3.21	38	9.6	
2014-DD-057	JGT-02	451.14	459.98	Granite	9.50	0.025	1.5	0.5	0.9	5	0.025	0.025	9.8	0.08	0.51	7.12	-	6	0.1	4.98	61	14.1	
2014-DD-058	JGT-02	244.19	252.39	Granite	9.55	0.025	0.6	0.5	0.15	4	0.025	0.025	3.4	0.02	0.16	2.8	-	3	0.05	1.23	31	6.9	
2014-DD-059	JGT-02	377.69	383.33	Granite	9.50	0.025	0.7	0.5	0.15	4	0.025	0.025	5.3	0.03	0.23	4.09	-	3	0.05	2.33	32	8.3	
2014-DD-060	JGT-02	307	313.09	Granite	9.48	0.025	1.3	0.5	0.4	5	0.025	0.025	17.8	0.07	0.46	5.3	-	8	0.05	5.35	58	22	
Median					9.3	0.0	0.7	0.5	0.4	5	0.025	0.025	6.05	0.03	0.215	4.72	-	4.0	0.1	3.2	44	12.15	
Minimum					8.1	0.0	0.3	0.5	0.2	4	0.025	0.025	0.9	0.005	0.04	0.55	-	2.0	0.1	1.04	4.0	3	
Maximum					9.6	0.1	19	0.5	1.2	21	0.025	0.025	17.8	0.23	0.96	9.19	-	143	0.4	7	149	22	
Count					30	30	30	30	30	30	30	30	30	30	30	30	0	30	30	30	30	30	
Kimberlite																							
Beartooth																							
64	BCD-01	49m	49	Kimberlite	8.1	5.0	4.0	-	5.0	216	-	-	-	0.05	-	-	-	29	5.0	3.0	53	-	
64	BCD-01	49m	49	Kimberlite	-	5.0	4.0	-	5.0	360	-	-	-	0.03	-	-	-	25	5.0	5.0	45	-	
65	BCD-01	186m	186	Kimberlite	8.6	5.0	6.0	-	5.0	472	-	-	-	0.07	-	-	-	48	5.0	9.0	63	-	
66	BCD-04	100m	100	Kimberlite	8.3	5.0	4.0	-	5.0	324	-	-	-	0.05	-	-	-	29	5.0	4.0	44	-	
67	BCD-04	190m	190	Kimberlite	8.5	5.0	4.0	-	5.0	210	-	-	-	0.05	-	-	-	28	5.0	3.0	52	-	
Median					8.4	5.0	4.0	-	5.0	324	-	-	-	0.05	-	-	-	29	5.0	4.0	52	-	
Minimum					8.1	5.0	4.0	-	5.0	210	-	-	-	0.03	-	-	-	25	5.0	3.0	44	-	
Maximum					8.6	5.0	6.0	-	5.0	472	-	-	-	0.07	-	-	-	48	5.0	9.0	63	-	
Count					4	5	5	0	5	5	0	0	0	5	0	0	0	5	5	5	5	0	
Fox																							
FUC 3-3 - 30	FUC 3-3	30	30.3	Kimberlite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 35	FUC 3-3	35	35.3	Kimberlite	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
FUC 3-3 - 40	FUC 3-3	40	40.3	Kimberlite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 66.1	F1-1	66.1	66.2	Kimberlite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 66.2	F1-1	66.2	66.3	Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 72	F1-1	72	74	Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 94	F1-1	94	96	Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 110	F1-1	110	112	Kimberlite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 116	F1-1	116	118	Kimberlite	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 122	F1-1	122	124	Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 158	F1-1	158	160	Kimberlite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 160	F1-1	160	162	Kimberlite	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 184	F1-1	184	186	Kimberlite	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
F1-1 - 186	F1-1	186	188	Kimberlite	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																						
Fox (continued)																						
F1-1 - 196	F1-1	196	198	Kimberlite	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
F1-1 - 210	F1-1	210	212	Kimberlite	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
F1-1 - 216	F1-1	216	218	Kimberlite	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FUC 4-3 - 151.5	FUC 4-3	151.5	155.2	Kimberlite	8.8	0.6	-	-	-	871	-	-	-	0.30	-	-	-	102	5.0	-	62	-
F19 - 176	F19	176	177	Kimberlite	8.9	0.4	-	-	-	499	-	-	-	0.20	-	-	-	72	5.0	-	54	-
F19 - 122	F19	122	123	Kimberlite	8.6	0.6	-	-	-	743	-	-	-	0.21	-	-	-	80	5.0	-	64	-
F17 - 200	F17	200	201	Kimberlite	8.6	0.2	-	-	-	564	-	-	-	0.22	-	-	-	79	5.0	-	60	-
F17 - 100	F17	100	101	Kimberlite	8.3	1.6	-	-	-	460	-	-	-	0.27	-	-	-	186	5.0	-	118	-
FWK405-13-1	-	-	-	Kimberlite	7.4	2.5	-	-	-	393	-	-	-	0.27	-	-	-	133	5.0	-	98	-
FWK405-13-2	-	-	-	Kimberlite	7.5	2.5	-	-	-	462	-	-	-	0.30	-	-	-	148	5.0	-	108	-
FK-390-20-1	-	-	-	Kimberlite	8.0	2.5	-	-	-	705	-	-	-	0.26	-	-	-	99	5.0	-	69	-
FK-390-20-2	-	-	-	Kimberlite	8.0	2.5	-	-	-	745	-	-	-	0.27	-	-	-	97	5.0	-	66	-
FK-375-09R1-1	-	-	-	Kimberlite	8.3	2.5	-	-	-	743	-	-	-	0.25	-	-	-	92	5.0	-	65	-
FK-375-09R1-2	-	-	-	Kimberlite	8.3	2.5	-	-	-	749	-	-	-	0.25	-	-	-	88	5.0	-	62	-
FK-375-13-1	-	-	-	Kimberlite	8.4	2.5	-	-	-	604	-	-	-	0.25	-	-	-	100	5.0	-	70	-
FK-375-13-2	-	-	-	Kimberlite	8.3	2.5	-	-	-	696	-	-	-	0.27	-	-	-	103	5.0	-	66	-
FK-375-21-1	-	-	-	Kimberlite	8.2	2.5	-	-	-	560	-	-	-	0.26	-	-	-	118	5.0	-	86	-
FK-375-21-2	-	-	-	Kimberlite	8.1	2.5	-	-	-	593	-	-	-	0.26	-	-	-	112	5.0	-	84	-
FK-375-23-1	-	-	-	Kimberlite	8.3	2.5	-	-	-	678	-	-	-	0.30	-	-	-	127	5.0	-	93	-
FK-375-23-2	-	-	-	Kimberlite	8.1	2.5	-	-	-	775	-	-	-	0.28	-	-	-	112	5.0	-	75	-
FK-375-23-3	-	-	-	Kimberlite	8.3	2.5	-	-	-	744	-	-	-	0.28	-	-	-	108	5.0	-	73	-
FK-375-23-4	-	-	-	Kimberlite	8.4	2.5	-	-	-	797	-	-	-	0.27	-	-	-	97	5.0	-	67	-
FK-375-29-1	-	-	-	Kimberlite	8.2	2.5	-	-	-	670	-	-	-	0.23	-	-	-	84	5.0	-	61	-
FK-375-29-2	-	-	-	Kimberlite	8.2	2.5	-	-	-	776	-	-	-	0.27	-	-	-	91	5.0	-	62	-
FK-375-29-3	-	-	-	Kimberlite	8.3	2.5	-	-	-	814	-	-	-	0.27	-	-	-	97	5.0	-	63	-
FK-375-29-4	-	-	-	Kimberlite	8.2	2.5	-	-	-	790	-	-	-	0.28	-	-	-	87	5.0	-	62	-
FK-375-34-1	-	-	-	Kimberlite	8.3	2.5	-	-	-	619	-	-	-	0.26	-	-	-	108	5.0	-	78	-
FK-375-34-2	-	-	-	Kimberlite	8.3	2.5	-	-	-	736	-	-	-	0.28	-	-	-	106	5.0	-	77	-
FK-375-34-3	-	-	-	Kimberlite	8.3	2.5	-	-	-	700	-	-	-	0.27	-	-	-	97	5.0	-	69	-
FK-375-34-4	-	-	-	Kimberlite	8.3	2.5	-	-	-	666	-	-	-	0.24	-	-	-	98	5.0	-	71	-
FK-375-35-1	-	-	-	Kimberlite	8.3	2.5	-	-	-	711	-	-	-	0.25	-	-	-	91	5.0	-	66	-
FK-375-35-2	-	-	-	Kimberlite	8.3	2.5	-	-	-	625	-	-	-	0.23	-	-	-	93	5.0	-	64	-
FK-375-35-3	-	-	-	Kimberlite	8.3	2.5	-	-	-	700	-	-	-	0.24	-	-	-	92	5.0	-	65	-
FK-375-35-4	-	-	-	Kimberlite	8.4	2.5	-	-	-	666	-	-	-	0.25	-	-	-	86	5.0	-	62	-
FWK-375-12-01	-	-	-	Kimberlite	8.1	2.5	-	-	-	706	-	-	-	0.24	-	-	-	87	5.0	-	60	-
FWK-375-12-02	-	-	-	Kimberlite	8.4	2.5	-	-	-	851	-	-	-	0.27	-	-	-	96	5.0	-	61	-
FWK-375-14KB1-	-	-	-	Kimberlite	8.6	2.5	-	-	-	723	-	-	-	0.24	-	-	-	93	5.0	-	66	-
FWK-375-14KB2-	-	-	-	Kimberlite	8.4	2.5	-	-	-	777	-	-	-	0.29	-	-	-	106	5.0	-	73	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																						
Fox (continued)																						
FWK-375-14KB3-	-	-	-	Kimberlite	8.4	2.5	-	-	-	746	-	-	-	0.26	-	-	-	96	5.0	-	68	-
FWK-375-14KB4-	-	-	-	Kimberlite	8.5	2.5	-	-	-	632	-	-	-	0.25	-	-	-	102	5.0	-	72	-
FWK-375-15kb-1	-	-	-	Kimberlite	8.4	2.5	-	-	-	764	-	-	-	0.26	-	-	-	105	5.0	-	75	-
FWK-375-15kb-2	-	-	-	Kimberlite	8.5	2.5	-	-	-	791	-	-	-	0.26	-	-	-	100	5.0	-	73	-
FWK-375-15kb-3	-	-	-	Kimberlite	8.3	2.5	-	-	-	723	-	-	-	0.27	-	-	-	111	10	-	78	-
FWK-375-15kb-4	-	-	-	Kimberlite	8.3	2.5	-	-	-	726	-	-	-	0.27	-	-	-	107	5.0	-	76	-
FWK-375-38-1	-	-	-	Kimberlite	8.7	2.5	-	-	-	815	-	-	-	0.28	-	-	-	90	5.0	-	63	-
FWK-375-38-2	-	-	-	Kimberlite	8.6	2.5	-	-	-	789	-	-	-	0.26	-	-	-	88	5.0	-	62	-
FWK-375-38-3	-	-	-	Kimberlite	8.7	2.5	-	-	-	737	-	-	-	0.29	-	-	-	98	5.0	-	63	-
FWK-375-38-4	-	-	-	Kimberlite	8.4	2.5	-	-	-	822	-	-	-	0.27	-	-	-	91	5.0	-	62	-
FWK-375-36-04 6-OCT-04	-	-	-	Kimberlite	7.4	2.5	-	-	-	694	-	-	-	0.26	-	-	-	99	5.0	-	72	-
FWK-375-36-03 6-OCT-04	-	-	-	Kimberlite	7.5	6.0	-	-	-	768	-	-	-	0.27	-	-	-	99	5.0	-	67	-
FWK-375-36-02 6-OCT-04	-	-	-	Kimberlite	8.0	2.5	-	-	-	736	-	-	-	0.28	-	-	-	104	5.0	-	70	-
FWK-375-36-01 6-OCT-04	-	-	-	Kimberlite	7.8	2.5	-	-	-	840	-	-	-	0.27	-	-	-	95	5.0	-	67	-
FWK-360-29-02 26-DEC-04	-	-	-	Kimberlite	7.6	2.5	-	-	-	574	-	-	-	0.24	-	-	-	97	5.0	-	75	-
FWK-360-29-02 1-JAN-05	-	-	-	Kimberlite	7.8	2.5	-	-	-	666	-	-	-	0.27	-	-	-	100	5.0	-	69	-
FWK-360-29-01 26-DEC-04	-	-	-	Kimberlite	7.6	2.5	-	-	-	697	-	-	-	0.28	-	-	-	112	10	-	81	-
FWK-360-29-01 1-JAN-05	-	-	-	Kimberlite	7.8	2.5	-	-	-	812	-	-	-	0.27	-	-	-	96	5.0	-	65	-
FWK-360-24-04 19-DEC-04	-	-	-	Kimberlite	7.4	2.5	-	-	-	811	-	-	-	0.26	-	-	-	94	5.0	-	63	-
FWK-360-24-03 19-DEC-04	-	-	-	Kimberlite	7.7	2.5	-	-	-	838	-	-	-	0.28	-	-	-	101	5.0	-	67	-
FWK-360-24-02 19-DEC-04	-	-	-	Kimberlite	7.7	2.5	-	-	-	779	-	-	-	0.25	-	-	-	92	5.0	-	63	-
FWK-360-24-01 19-DEC-04	-	-	-	Kimberlite	7.4	2.5	-	-	-	819	-	-	-	0.26	-	-	-	95	5.0	-	64	-
FWK-360-14-04 3-DEC-04	-	-	-	Kimberlite	7.8	2.5	-	-	-	765	-	-	-	0.27	-	-	-	105	5.0	-	74	-
FWK-360-14-03 3-DEC-04	-	-	-	Kimberlite	8.1	2.5	-	-	-	772	-	-	-	0.26	-	-	-	96	5.0	-	70	-
FWK-360-14-02 3-DEC-04	-	-	-	Kimberlite	8.0	2.5	-	-	-	758	-	-	-	0.29	-	-	-	116	5.0	-	83	-
FWK-360-14-01 3-DEC-04	-	-	-	Kimberlite	7.7	2.5	-	-	-	727	-	-	-	0.27	-	-	-	107	5.0	-	74	-
FWK-360-09-02 22-NOV-04	-	-	-	Kimberlite	8.1	2.5	-	-	-	716	-	-	-	0.28	-	-	-	106	5.0	-	78	-
FWK-360-09-01 22-NOV-04	-	-	-	Kimberlite	8.1	2.5	-	-	-	792	-	-	-	0.28	-	-	-	103	5.0	-	75	-
FWK-360-07-02 12-NOV-04	-	-	-	Kimberlite	8.3	2.5	-	-	-	842	-	-	-	0.29	-	-	-	110	5.0	-	78	-
FWK-360-07-01 12-NOV-04	-	-	-	Kimberlite	8.0	2.5	-	-	-	656	-	-	-	0.30	-	-	-	130	5.0	-	95	-
FWK-360-05-04 29-OCT-04	-	-	-	Kimberlite	7.1	5.0	-	-	-	463	-	-	-	0.28	-	-	-	134	5.0	-	100	-
FWK-360-05-03 29-OCT-04	-	-	-	Kimberlite	7.5	2.5	-	-	-	538	-	-	-	0.25	-	-	-	102	5.0	-	77	-
FWK-360-05-02 29-OCT-04	-	-	-	Kimberlite	7.7	2.5	-	-	-	683	-	-	-	0.24	-	-	-	90	5.0	-	67	-
FWK-360-05-01 29-OCT-04	-	-	-	Kimberlite	7.7	2.5	-	-	-	661	-	-	-	0.27	-	-	-	107	5.0	-	79	-
FWK-345-33-04 8-Apr-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	780	-	-	-	0.26	-	-	-	95	10	-	67	-
FWK-345-33-03 8-Apr-05	-	-	-	Kimberlite	8.4	2.5	-	-	-	791	-	-	-	0.27	-	-	-	104	10	-	66	-
FWK-345-33-02 8-Apr-05	-	-	-	Kimberlite	8.5	2.5	-	-	-	801	-	-	-	0.26	-	-	-	90	10	-	62	-
FWK-345-33-01 8-Apr-05	-	-	-	Kimberlite	8.2	2.5	-	-	-	659	-	-	-	0.25	-	-	-	101	5.0	-	74	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	General Rock Type																	
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr	
Kimberlite (continued)																						
Fox (continued)																						
FWK-345-29-04- 8-Apr-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	778	-	-	-	0.27	-	-	-	98	10	-	66	-
FWK-345-29-03- 8-Apr-05	-	-	-	Kimberlite	8.4	2.5	-	-	-	751	-	-	-	0.26	-	-	-	94	10	-	64	-
FWK-345-29-02- 8-Apr-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	750	-	-	-	0.26	-	-	-	95	5.0	-	68	-
FWK-345-29-01- 8-Apr-05	-	-	-	Kimberlite	7.9	2.5	-	-	-	672	-	-	-	0.26	-	-	-	106	5.0	-	80	-
FWK-345-24-06-26-Mar-05	-	-	-	Kimberlite	8.6	2.5	-	-	-	769	-	-	-	0.25	-	-	-	92	5.0	-	65	-
FWK-345-24-05-26-Mar-05	-	-	-	Kimberlite	8.1	2.5	-	-	-	663	-	-	-	0.24	-	-	-	96	5.0	-	70	-
FWK-345-24-04-26-Mar-05	-	-	-	Kimberlite	8.1	2.5	-	-	-	657	-	-	-	0.24	-	-	-	106	5.0	-	80	-
FWK-345-24-03-26-Mar-05	-	-	-	Kimberlite	8.7	2.5	-	-	-	723	-	-	-	0.25	-	-	-	102	5.0	-	76	-
FWK-345-24-02-26-Mar-05	-	-	-	Kimberlite	8.5	2.5	-	-	-	772	-	-	-	0.26	-	-	-	97	5.0	-	72	-
FWK-345-24-01-26-Mar-05	-	-	-	Kimberlite	8.5	2.5	-	-	-	792	-	-	-	0.25	-	-	-	100	5.0	-	75	-
FWK-345-20-04- 8-Mar-05	-	-	-	Kimberlite	8.7	2.5	-	-	-	725	-	-	-	0.24	-	-	-	86	5.0	-	60	-
FWK-345-20-03- 8-Mar-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	416	-	-	-	0.22	-	-	-	116	5.0	-	81	-
FWK-345-20-02- 8-Mar-05	-	-	-	Kimberlite	8.7	2.5	-	-	-	712	-	-	-	0.23	-	-	-	83	5.0	-	62	-
FWK-345-20-01- 8-Mar-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	716	-	-	-	0.23	-	-	-	92	5.0	-	69	-
FWK-345-15-02 9-FEB-05	-	-	-	Kimberlite	8.1	2.5	-	-	-	650	-	-	-	0.28	-	-	-	117	5.0	-	85	-
FWK-345-15-01 9-FEB-05	-	-	-	Kimberlite	8.0	2.5	-	-	-	834	-	-	-	0.29	-	-	-	110	5.0	-	74	-
FWK-345-13-02 18-FEB-05	-	-	-	Kimberlite	8.0	5.0	-	-	-	636	-	-	-	0.29	-	-	-	125	5.0	-	82	-
FWK-345-13-01 18-FEB-05	-	-	-	Kimberlite	8.0	2.5	-	-	-	599	-	-	-	0.25	-	-	-	110	10	-	77	-
FWK-345-08-04 7-FEB-05	-	-	-	Kimberlite	8.1	2.5	-	-	-	662	-	-	-	0.27	-	-	-	113	5.0	-	79	-
FWK-345-08-03 7-FEB-05	-	-	-	Kimberlite	7.9	2.5	-	-	-	606	-	-	-	0.26	-	-	-	100	10	-	77	-
FWK-345-08-02 7-FEB-05	-	-	-	Kimberlite	8.0	2.5	-	-	-	675	-	-	-	0.26	-	-	-	101	5.0	-	96	-
FWK-345-08-01 7-FEB-05	-	-	-	Kimberlite	8.1	2.5	-	-	-	617	-	-	-	0.28	-	-	-	111	5.0	-	83	-
FWK-345-07-02 4-FEB-05	-	-	-	Kimberlite	8.2	2.5	-	-	-	691	-	-	-	0.27	-	-	-	103	10	-	72	-
FWK-345-07-01 4-FEB-05	-	-	-	Kimberlite	8.0	2.5	-	-	-	744	-	-	-	0.28	-	-	-	105	10	-	79	-
FWK-345-06-02 1-FEB-05	-	-	-	Kimberlite	7.9	2.5	-	-	-	540	-	-	-	0.28	-	-	-	127	5.0	-	89	-
FWK-345-06-01 1-FEB-05	-	-	-	Kimberlite	8.0	2.5	-	-	-	629	-	-	-	0.30	-	-	-	134	10	-	92	-
FWK-345-04-02 30-JAN-05	-	-	-	Kimberlite	8.2	2.5	-	-	-	776	-	-	-	0.26	-	-	-	102	5.0	-	73	-
FWK-345-04-01 30-JAN-05	-	-	-	Kimberlite	8.1	2.5	-	-	-	730	-	-	-	0.28	-	-	-	113	5.0	-	78	-
FWK-345-03-04 28-JAN-05	-	-	-	Kimberlite	7.8	2.5	-	-	-	641	-	-	-	0.33	-	-	-	113	5.0	-	67	-
FWK-345-03-03 28-JAN-05	-	-	-	Kimberlite	7.8	2.5	-	-	-	738	-	-	-	0.27	-	-	-	91	5.0	-	63	-
FWK-345-03-02 24-JAN-05	-	-	-	Kimberlite	8.1	2.5	-	-	-	781	-	-	-	0.26	-	-	-	92	5.0	-	68	-
FWK-345-03-01 24-JAN-05	-	-	-	Kimberlite	8.0	2.5	-	-	-	577	-	-	-	0.32	-	-	-	114	5.0	-	82	-
FWK-345-02-02 20-JAN-05	-	-	-	Kimberlite	8.1	2.5	-	-	-	676	-	-	-	0.24	-	-	-	87	5.0	-	63	-
FWK-345-02-01 20-JAN-05	-	-	-	Kimberlite	8.2	2.5	-	-	-	689	-	-	-	0.26	-	-	-	86	5.0	-	59	-
FWK-345-01-04 14-JAN-05	-	-	-	Kimberlite	7.8	2.5	-	-	-	608	-	-	-	0.25	-	-	-	93	5.0	-	72	-
FWK-345-01-03 14-JAN-05	-	-	-	Kimberlite	7.8	2.5	-	-	-	534	-	-	-	0.21	-	-	-	71	5.0	-	58	-
FWK-345-01-02 14-JAN-05	-	-	-	Kimberlite	7.6	2.5	-	-	-	558	-	-	-	0.27	-	-	-	102	5.0	-	80	-
FWK-345-01-01 14-JAN-05	-	-	-	Kimberlite	7.8	2.5	-	-	-	515	-	-	-	0.22	-	-	-	86	5.0	-	63	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																						
Fox (continued)																						
FWK-330-14-08 18-May-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	716	-	-	-	0.27	-	-	-	113	5.0	-	81	-
FWK-330-14-07 18-May-05	-	-	-	Kimberlite	8.2	2.5	-	-	-	750	-	-	-	0.28	-	-	-	122	5.0	-	81	-
FWK-330-14-06 18-May-05	-	-	-	Kimberlite	8.4	2.5	-	-	-	782	-	-	-	0.28	-	-	-	112	5.0	-	76	-
FWK-330-14-05 18-May-05	-	-	-	Kimberlite	8.5	2.5	-	-	-	778	-	-	-	0.28	-	-	-	114	5.0	-	79	-
FWK-330-14-04 17-May-05	-	-	-	Kimberlite	8.5	2.5	-	-	-	753	-	-	-	0.26	-	-	-	104	5.0	-	74	-
FWK-330-14-03 17-May-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	684	-	-	-	0.26	-	-	-	104	5.0	-	78	-
FWK-330-14-02 17-May-05	-	-	-	Kimberlite	8.5	2.5	-	-	-	751	-	-	-	0.28	-	-	-	104	5.0	-	79	-
FWK-330-14-01 17-May-05	-	-	-	Kimberlite	8.4	2.5	-	-	-	784	-	-	-	0.28	-	-	-	98	5.0	-	68	-
FWK-330-05-04 11-May-05	-	-	-	Kimberlite	8.4	2.5	-	-	-	713	-	-	-	0.26	-	-	-	84	5.0	-	59	-
FWK-330-05-04 10-May-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	800	-	-	-	0.26	-	-	-	96	5.0	-	70	-
FWK-330-05-03 11-May-05	-	-	-	Kimberlite	8.4	2.5	-	-	-	786	-	-	-	0.29	-	-	-	101	5.0	-	66	-
FWK-330-05-03 10-May-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	694	-	-	-	0.26	-	-	-	104	5.0	-	81	-
FWK-330-05-02 11-May-05	-	-	-	Kimberlite	8.5	2.5	-	-	-	807	-	-	-	0.30	-	-	-	106	5.0	-	66	-
FWK-330-05-02 10-May-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	844	-	-	-	0.26	-	-	-	89	5.0	-	67	-
FWK-330-05-01 11-May-05	-	-	-	Kimberlite	8.5	2.5	-	-	-	854	-	-	-	0.28	-	-	-	95	5.0	-	66	-
FWK-330-05-01 10-May-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	713	-	-	-	0.27	-	-	-	100	5.0	-	78	-
FWK-330-01-04- 10-Apr-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	779	-	-	-	0.25	-	-	-	101	5.0	-	73	-
FWK-330-01-03- 10-Apr-05	-	-	-	Kimberlite	8.4	2.5	-	-	-	863	-	-	-	0.28	-	-	-	103	5.0	-	69	-
FWK-330-01-02-17-Apr-05	-	-	-	Kimberlite	8.4	2.5	-	-	-	559	-	-	-	0.25	-	-	-	111	5.0	-	81	-
FWK-330-01-02- 10-Apr-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	682	-	-	-	0.27	-	-	-	110	10	-	81	-
FWK-330-01-01-17-Apr-05	-	-	-	Kimberlite	8.4	2.5	-	-	-	740	-	-	-	0.27	-	-	-	110	10	-	78	-
FWK-330-01-01- 10-Apr-05	-	-	-	Kimberlite	8.5	2.5	-	-	-	823	-	-	-	0.27	-	-	-	96	5.0	-	67	-
FWK-315-02-06 15-Jun-05	-	-	-	Kimberlite	8.6	2.5	-	-	-	845	-	-	-	0.31	-	-	-	106	5.0	-	65	-
FWK-315-02-05 15-Jun-05	-	-	-	Kimberlite	8.4	2.5	-	-	-	815	-	-	-	0.29	-	-	-	92	5.0	-	63	-
FWK-315-02-04 15-Jun-05	-	-	-	Kimberlite	8.6	2.5	-	-	-	891	-	-	-	0.29	-	-	-	94	5.0	-	64	-
FWK-315-02-03 15-Jun-05	-	-	-	Kimberlite	8.8	2.5	-	-	-	844	-	-	-	0.28	-	-	-	91	5.0	-	61	-
FWK-315-02-02 15-Jun-05	-	-	-	Kimberlite	8.6	2.5	-	-	-	803	-	-	-	0.25	-	-	-	82	5.0	-	57	-
FWK-315-02-01 15-Jun-05	-	-	-	Kimberlite	8.5	2.5	-	-	-	864	-	-	-	0.26	-	-	-	88	5.0	-	59	-
FWK-315-01-04 8-Jun-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	800	-	-	-	0.27	-	-	-	96	5.0	-	67	-
FWK-315-01-03 8-Jun-05	-	-	-	Kimberlite	8.2	2.5	-	-	-	820	-	-	-	0.26	-	-	-	105	5.0	-	69	-
FWK-315-01-02 8-Jun-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	808	-	-	-	0.25	-	-	-	90	5.0	-	65	-
FWK-315-01-01 8-Jun-05	-	-	-	Kimberlite	8.3	2.5	-	-	-	842	-	-	-	0.28	-	-	-	99	5.0	-	71	-
FWK-285-35-01	-	-	-	Kimberlite	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FWK-285-36-01 15-MAY-06	-	-	-	Kimberlite	7.9	2.5	-	-	-	803	-	-	-	0.28	-	-	-	102	5.0	-	306	-
FWK-285-36-02 15 MAY-06	-	-	-	Kimberlite	8.1	2.5	-	-	-	755	-	-	-	0.25	-	-	-	100	5.0	-	83	-
FWK-285-36-03 15 MAY-06	-	-	-	Kimberlite	7.8	2.5	-	-	-	674	-	-	-	0.27	-	-	-	116	5.0	-	115	-
FWK-285-36-04 15-MAY-06	-	-	-	Kimberlite	8.1	2.5	-	-	-	661	-	-	-	0.24	-	-	-	101	5.0	-	82	-
Fox-260-WK-3a 26-Jan-09	-	-	-	Kimberlite	8.8	2.5	10	-	-	703	-	-	20	0.27	5.0	5.0	-	95	5.0	-	69	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval From To		Price Crustal Abundances General Rock Type	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
					Paste pH	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr
					unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																						
Fox (continued)																						
Fox-260-WK-2a 26-Jan-09	-	-	-	Kimberlite	8.9	2.5	8.0	-	-	639	-	-	10	0.26	5.0	5.0	-	78	5.0	-	58	-
Fox-260-WK-1a 26-Jan-09	-	-	-	Kimberlite	9.2	2.5	9.0	-	-	602	-	-	10	0.29	5.0	5.0	-	76	5.0	-	64	-
Median					8.3	2.5	9.0	-	-	733	-	-	10	0.27	5.0	5.0	-	100	5.0	-	70	-
Minimum					7.1	0.2	8.0	-	-	393	-	-	10	0.20	5.0	5.0	-	71	5.0	-	54	-
Maximum					9.8	6.0	10	-	-	891	-	-	20	0.33	5.0	5.0	-	186	10	-	306	-
Count					168	150	3	0	0	150	0	0	3	150	3	3	0	150	150	0	150	0
Koala																						
KK-DUMP-1A	-	-	-	Kimberlite	7.9	2.5	-	-	-	167	-	-	-	0.08	-	-	-	37	5.0	-	48	-
KK-DUMP-2A	-	-	-	Kimberlite	7.7	2.5	-	-	-	239	-	-	-	0.10	-	-	-	50	5.0	-	52	-
KK-DUMP-3A-1	-	-	-	Kimberlite	8.0	2.5	-	-	-	238	-	-	-	0.10	-	-	-	44	5.0	-	52	-
KK-DUMP-3A-2	-	-	-	Kimberlite	8.0	2.5	-	-	-	223	-	-	-	0.10	-	-	-	41	5.0	-	52	-
KK-DUMP-4A	-	-	-	Kimberlite	7.8	2.5	-	-	-	221	-	-	-	0.09	-	-	-	39	5.0	-	52	-
KK-DUMP-5A	-	-	-	Kimberlite	7.3	2.5	-	-	-	180	-	-	-	0.14	-	-	-	70	5.0	-	56	-
KWK-380-50-1	-	-	-	Kimberlite	8.2	5.0	-	-	-	379	-	-	-	0.22	-	-	-	83	10	-	68	-
KWK-380-50-2	-	-	-	Kimberlite	8.3	5.0	-	-	-	320	-	-	-	0.14	-	-	-	53	10	-	47	-
KWK-360-18-1A	-	-	-	Kimberlite	8.0	5.0	-	-	-	257	-	-	-	0.10	-	-	-	39	10	-	40	-
KWK-360-18-2A	-	-	-	Kimberlite	8.1	5.0	-	-	-	254	-	-	-	0.10	-	-	-	38	10	-	40	-
KWK-360-17-1A	-	-	-	Kimberlite	7.7	5.0	-	-	-	201	-	-	-	0.07	-	-	-	30	10	-	38	-
KWK-360-17-2A	-	-	-	Kimberlite	7.7	5.0	-	-	-	214	-	-	-	0.08	-	-	-	31	10	-	38	-
KWK-345-17-1	-	-	-	Kimberlite	8.0	5.0	-	-	-	267	-	-	-	0.09	-	-	-	38	10	-	39	-
KWK-345-17-2	-	-	-	Kimberlite	8.0	5.0	-	-	-	224	-	-	-	0.08	-	-	-	29	10	-	40	-
KWK-345-17-1A	-	-	-	Kimberlite	7.9	5.0	-	-	-	247	-	-	-	0.10	-	-	-	40	10	-	41	-
KWK-345-17-2A	-	-	-	Kimberlite	8.0	5.0	-	-	-	252	-	-	-	0.10	-	-	-	40	10	-	42	-
KWK-345-17-1A	-	-	-	Kimberlite	8.0	5.0	-	-	-	265	-	-	-	0.09	-	-	-	36	10	-	40	-
KWK-345-17-2A	-	-	-	Kimberlite	7.8	5.0	-	-	-	259	-	-	-	0.10	-	-	-	41	10	-	42	-
KWK-345-21-1A	-	-	-	Kimberlite	7.9	5.0	-	-	-	251	-	-	-	0.10	-	-	-	38	10	-	41	-
KWK-345-21-2A	-	-	-	Kimberlite	8.0	5.0	-	-	-	268	-	-	-	0.10	-	-	-	40	10	-	42	-
KS-280-04-1A	-	-	-	Kimberlite	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-280-04-1B	-	-	-	Kimberlite	7.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Median					7.9	5.0	-	-	-	249	-	-	-	0.10	-	-	-	40	10	-	42	-
Minimum					7.3	2.5	-	-	-	167	-	-	-	0.07	-	-	-	29	5.0	-	38	-
Maximum					8.3	5.0	-	-	-	379	-	-	-	0.22	-	-	-	83	10	-	68	-
Count					22	20	0	0	0	20	0	0	0	20	0	0	0	20	20	0	20	0
Misery																						
MDC-10 149.47	-	-	-	Kimberlite	9.3	2.5	-	-	-	805	-	-	-	0.28	-	-	-	97	5.0	-	54	-
SRK MISERY 1	-	-	-	Kimberlite	7.8	2.5	-	-	-	183	-	-	-	0.24	-	-	-	122	5.0	-	92	-
SRK MISERY 2	-	-	-	Kimberlite	8.2	2.5	-	-	-	355	-	-	-	0.20	-	-	-	97	5.0	-	74	-
SRK MISERY 3	-	-	-	Kimberlite	9.1	2.5	-	-	-	735	-	-	-	0.19	-	-	-	68	5.0	-	48	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																						
Misery (continued)																						
MK- 430-04-1A	-	-	-	Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK- 430-04-2A	-	-	-	Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK- 430-06-A1	-	-	-	Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK- 430-06-A2	-	-	-	Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK- 430-06-A3	-	-	-	Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MK-400-52T-1a	-	-	-	Kimberlite	8.3	2.5	-	-	-	328	-	-	-	0.17	-	-	-	83	5.0	-	58	-
MWKB-380-20-1a	-	-	-	Kimberlite	8.5	2.5	-	-	-	183	-	-	-	0.38	-	-	-	126	5.0	-	44	-
MWKB-380-20-2a	-	-	-	Kimberlite	8.5	2.5	-	-	-	162	-	-	-	0.07	-	-	-	36	5.0	-	38	-
MGT-60 143.42-145.0	-	-	-	Kimberlite	5.1	0.6	2.5	5.5	-	77	-	0.1	6.8	0.013	0.9	8.5	-	58	0.05	-	104	-
MGT-60 308.0-309.85	-	-	-	Kimberlite	8.6	0.05	5.6	1.0	-	495	-	0.1	5.6	0.081	0.2	2.3	-	57	0.05	-	48	-
MGT-53 245-248	-	-	-	Kimberlite	8.2	0.05	3.9	0.25	-	292	-	0.2	3.8	0.035	0.2	1.9	-	47	0.05	-	55	-
MGT-54 297-300	-	-	-	Kimberlite	8.6	0.05	4.5	0.8	-	190	-	0.1	4.8	0.043	0.1	2.4	-	60	0.1	-	54	-
MGT-51 98.0-99.59	-	-	-	Kimberlite	8.5	0.05	8.5	0.25	-	1,067	-	0.1	6.2	0.12	0.2	3.0	-	76	0.1	-	41	-
MGT-51 113-116	-	-	-	Kimberlite	8.7	0.1	8.8	0.25	-	1,102	-	0.1	13	0.15	0.2	3.0	-	78	0.1	-	45	-
MGT-51 116-119	-	-	-	Kimberlite	8.8	0.1	8.2	0.25	-	1,084	-	0.1	13	0.14	0.2	2.9	-	74	0.05	-	43	-
MGT-51 119-122	-	-	-	Kimberlite	8.8	0.1	8.0	0.25	-	1,048	-	0.1	12	0.13	0.2	2.8	-	77	0.1	-	42	-
MGT-51 122-125	-	-	-	Kimberlite	8.5	0.1	8.1	0.25	-	1,009	-	0.1	13	0.13	0.2	2.6	-	71	0.05	-	41	-
MGT-64 255-258	-	-	-	Kimberlite	9.1	0.05	7.2	0.25	-	647	-	0.1	0.6	0.094	0.2	2.6	-	56	0.05	-	40	-
MGT-64 258-261	-	-	-	Kimberlite	8.9	0.05	8.2	0.7	-	985	-	0.1	1.4	0.096	0.1	3.0	-	42	0.1	-	40	-
MGT-64 261-264	-	-	-	Kimberlite	9.0	0.05	9.1	0.25	-	934	-	0.1	2.0	0.10	0.05	3.7	-	42	0.2	-	45	-
MGT-64 264-267	-	-	-	Kimberlite	8.9	0.05	9.1	0.25	-	1,114	-	0.1	1.5	0.099	0.05	3.9	-	67	0.1	-	43	-
MGT-64 267-270	-	-	-	Kimberlite	8.8	0.05	8.8	0.25	-	1,091	-	0.1	0.8	0.087	0.1	4.1	-	84	0.1	-	42	-
MGT-51 100-103	-	-	-	Kimberlite	8.4	0.05	9.6	0.25	-	986	-	0.1	5.9	0.12	0.1	3.4	-	77	0.1	-	50	-
MGT-51 103-106	-	-	-	Kimberlite	8.4	0.05	9.7	0.25	-	933	-	0.1	9.1	0.15	0.2	5.9	-	71	0.2	-	47	-
MGT-51 106-109	-	-	-	Kimberlite	8.4	0.05	10	0.25	-	994	-	0.1	16	0.19	0.3	4.1	-	96	0.05	-	49	-
MGT-52 283-285	-	-	-	Kimberlite	8.9	0.05	7.2	0.25	-	882	-	0.1	3.1	0.10	0.2	2.3	-	54	0.05	-	47	-
MGT-52 287-290	-	-	-	Kimberlite	8.6	0.05	7.0	1.2	-	708	-	0.1	7.4	0.11	0.3	4.5	-	85	0.05	-	69	-
MGT-54 294-296	-	-	-	Kimberlite	8.5	0.05	5.4	0.6	-	179	-	0.1	4.4	0.048	0.1	2.3	-	56	0.2	-	67	-
Median					8.5	0.05	8.2	0.25	-	805	-	0.1	5.8	0.12	0.2	3.0	-	71	0.1	-	47	-
Minimum					5.1	0.05	2.5	0.25	-	77	-	0.1	0.6	0.013	0.05	1.9	-	36	0.05	-	38	-
Maximum					9.3	2.5	10	5.5	-	1,114	-	0.2	16	0.38	0.9	8.5	-	126	5.0	-	104	-
Count					32	27	20	20	0	27	0	20	20	27	20	20	0	27	27	0	27	0
Pigeon																						
97-54	97-54	113	113	Kimberlite	8.8	2.5	18	-	5.0	2,967	-	-	-	0.49	-	-	-	134	5.0	15	65	-
97-54	97-54	117	117	Kimberlite	8.7	2.5	17	-	5.0	2,964	-	-	-	0.45	-	-	-	125	5.0	15	61	-
97-54	97-54	145	150	Kimberlite	8.7	2.5	14	-	5.0	2,662	-	-	-	0.49	-	-	-	137	5.0	13	64	-
97-54	97-54	172	174	Kimberlite	8.4	5.0	4.0	-	5.0	349	-	-	-	0.06	-	-	-	55	5.0	3.0	43	-
97-54	97-54	210	215	Kimberlite	8.9	5.0	8.0	-	5.0	531	-	-	-	0.11	-	-	-	76	5.0	4.0	46	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																						
Pigeon (continued)																						
97-54	97-54	310	310	Kimberlite	8.8	10	9.0	-	5.0	658	-	-	-	0.14	-	-	-	76	5.0	6.0	45	-
97-55	97-55	79	83	Kimberlite	7.6	10	9.0	-	5.0	660	-	-	-	0.15	-	-	-	77	5.0	6.0	46	-
97-55	97-55	137	137	Kimberlite	7.8	2.5	6.0	-	5.0	746	-	-	-	0.09	-	-	-	56	5.0	9.0	55	-
97-55	97-55	198	198	Kimberlite	8.2	5.0	5.0	-	5.0	311	-	-	-	0.10	-	-	-	56	5.0	4.0	46	-
94-07	94-07	120	120	Kimberlite	8.0	5.0	6.0	-	5.0	692	-	-	-	0.08	-	-	-	57	5.0	12	58	-
94-07	94-07	170	170	Kimberlite	8.1	2.5	5.0	-	5.0	361	-	-	-	0.07	-	-	-	47	5.0	4.0	44	-
94-07	94-07	225	225	Kimberlite	8.9	10	10	-	5.0	762	-	-	-	0.14	-	-	-	87	5.0	6.0	46	-
97-55	97-55	205	210	Kimberlite	8.9	10	9.0	-	5.0	369	-	-	-	0.15	-	-	-	76	5.0	5.0	49	-
97-55	97-55	250	250	Kimberlite	8.6	5.0	9.0	-	5.0	411	-	-	-	0.16	-	-	-	84	5.0	5.0	44	-
94-7 72-77	94-7	72	77	Kimberlite	-	2.5	-	-	-	210	-	-	-	0.32	-	-	-	124	10	-	70	-
94-7 77-80.2	94-7	77	80.2	Kimberlite	8.9	2.5	-	-	-	311	-	-	-	0.31	-	-	-	107	10	-	74	-
Median					8.7	5.0	9.0	-	5.0	595	-	-	-	0.15	-	-	-	77	5.0	6.0	48	-
Minimum					7.6	2.5	4.0	-	5.0	210	-	-	-	0.06	-	-	-	47	5.0	3.0	43	-
Maximum					8.9	10	18	-	5.0	2,967	-	-	-	0.49	-	-	-	137	10	15	74	-
Count					15	16	14	0	14	16	0	0	0	16	0	0	0	16	16	14	16	0
Sable																						
95-25	95-25	138	138	Kimberlite	8.1	5.0	3.0	-	5.0	222	-	-	-	0.04	-	-	-	35	5.0	4.0	51	-
95-25	95-25	297	297	Kimberlite	8.4	5.0	4.0	-	5.0	313	-	-	-	0.05	-	-	-	38	5.0	3.0	47	-
SDC-01	SDC-01	126	126	Kimberlite	8.0	2.5	6.0	-	5.0	521	-	-	-	0.06	-	-	-	45	5.0	5.0	54	-
SDC-03	SDC-03	132	132	Kimberlite	7.8	5.0	7.0	-	5.0	794	-	-	-	0.07	-	-	-	46	5.0	4.0	44	-
SDC-03	SDC-03	132	132	Kimberlite	7.8	5.0	7.0	-	5.0	808	-	-	-	0.07	-	-	-	48	5.0	4.0	45	-
SDC-03	SDC-03	266	266	Kimberlite	8.8	5.0	5.0	-	5.0	473	-	-	-	0.04	-	-	-	37	5.0	4.0	51	-
SDC-04	SDC-04	130	130	Kimberlite	8.1	5.0	5.0	-	5.0	443	-	-	-	0.05	-	-	-	41	5.0	4.0	50	-
SDC-06	SDC-06	155	155	Kimberlite	8.0	2.5	7.0	-	5.0	794	-	-	-	0.09	-	-	-	48	5.0	4.0	45	-
SDC-06	SDC-06	290	290	Kimberlite	8.9	2.5	7.0	-	5.0	798	-	-	-	0.09	-	-	-	52	5.0	6.0	50	-
SDC-08	SDC-08	126	126	Kimberlite	8.2	5.0	5.0	-	5.0	421	-	-	-	0.05	-	-	-	40	5.0	5.0	59	-
SDC-10	SDC-10	207	207	Kimberlite	8.7	5.0	5.0	-	5.0	593	-	-	-	0.06	-	-	-	31	5.0	4.0	48	-
SDC-12	SDC-12	423	423	Kimberlite	9.6	5.0	5.0	-	5.0	528	-	-	-	0.05	-	-	-	41	5.0	4.0	51	-
SDC-13	SDC-13	236	236	Kimberlite	8.8	5.0	7.0	-	5.0	489	-	-	-	0.06	-	-	-	49	5.0	4.0	50	-
SDC-08	SDC-08	16	126	Kimberlite	-	5.0	5.0	-	5.0	415	-	-	-	0.05	-	-	-	39	5.0	5.0	58	-
Median					8.2	5.0	5.0	-	5.0	505	-	-	-	0.055	-	-	-	41	5.0	4.0	50	-
Minimum					7.8	2.5	3.0	-	5.0	222	-	-	-	0.04	-	-	-	31	5.0	3.0	44	-
Maximum					9.6	5.0	7.0	-	5.0	808	-	-	-	0.09	-	-	-	52	5.0	6.0	59	-
Count					13	14	14	0	14	14	0	0	0	14	0	0	0	14	14	14	14	0

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-																	
					-																	
		From	To	General Rock Type	Paste pH	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U (ICP)	U (XRF)	V	W	Y	Zn	Zr
						unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	
Kimberlite (continued)																						
Jay																						
2014-DD-042	JGT-03	40.8	47.22	Kimberlite	7.72	0.4	5.8	1	0.5	294	0.025	0.025	6.9	0.05	0.46	3.99	-	72	1	8.92	93	20.8
2014-DD-054	JGT-02	63.4	64.04	Kimberlite	7.81	0.07	6.5	0.5	0.15	22	0.025	0.025	8.9	0.04	0.05	7.31	-	21	0.7	4.53	99	13.8
Median					7.8	0.2	6.2	0.75	0.3	158	0.025	0.025	7.9	0.045	0.255	5.65	-	47	0.9	6.7	96	17.3
Minimum					7.7	0.1	5.8	0.5	0.2	22	0.025	0.025	6.9	0.04	0.05	3.99	-	21	0.7	4.5	93	13.8
Maximum					7.8	0.4	6.5	1	0.5	294	0.025	0.025	8.9	0.05	0.46	7.31	-	72	1.0	8.9	99	20.8
Count					2	2	2	2	2	2	2	2	2	2	2	2	0	2	2	2	2	2
Coarse Processed Kimberlite																						
TP-SRK-0-0.7m	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-01-4m	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-02-0.07m	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-02-1.8m	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-02B-2.5m	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-04-0-0.5m	-	-	-	Coarse Processed Kimberlite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-04-3.0m	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-05-0m	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-06-0-0.6m	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-09-0-10	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-09-10-20m	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-09B-0-15m	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-10-0-5m	-	-	-	Coarse Processed Kimberlite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-10-0-0.05	-	-	-	Coarse Processed Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-10-DARKm	-	-	-	Coarse Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-13-10-15m	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-14-0-10m	-	-	-	Coarse Processed Kimberlite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TP-SRK-CK-OCT/02	-	-	-	Coarse Processed Kimberlite	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.7	0.1	-	-	-	489	-	-	-	0.20	-	-	-	76	5.0	-	56	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	0.2	-	-	-	512	-	-	-	0.20	-	-	-	78	5.0	-	58	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.6	0.1	-	-	-	401	-	-	-	0.17	-	-	-	60	5.0	-	50	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	0.2	-	-	-	434	-	-	-	0.18	-	-	-	67	5.0	-	48	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.8	0.1	-	-	-	383	-	-	-	0.12	-	-	-	58	5.0	-	38	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.8	0.1	-	-	-	413	-	-	-	0.14	-	-	-	61	5.0	-	42	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.1	-	-	-	393	-	-	-	0.14	-	-	-	61	5.0	-	40	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.8	0.1	-	-	-	471	-	-	-	0.17	-	-	-	73	5.0	-	48	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.2	-	-	-	498	-	-	-	0.20	-	-	-	69	5.0	-	50	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	0.6	-	-	-	367	-	-	-	0.18	-	-	-	80	5.0	-	60	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-																		
					-																		
		From	To	General Rock Type	Paste pH	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U (ICP)	U (XRF)	V	W	Y	Zn	Zr	
			unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
Kimberlite (continued)																							
Coarse Processed Kimberlite (continued)																							
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	0.8	-	-	-	358	-	-	-	0.17	-	-	-	76	5.0	-	66	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	1.2	-	-	-	451	-	-	-	0.18	-	-	-	78	5.0	-	70	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	1.0	-	-	-	469	-	-	-	0.19	-	-	-	76	5.0	-	72	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	1.0	-	-	-	453	-	-	-	0.18	-	-	-	74	5.0	-	66	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	1.0	-	-	-	400	-	-	-	0.16	-	-	-	69	5.0	-	66	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.8	1.0	-	-	-	417	-	-	-	0.17	-	-	-	76	5.0	-	70	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	0.8	-	-	-	381	-	-	-	0.15	-	-	-	67	5.0	-	66	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	0.6	-	-	-	373	-	-	-	0.16	-	-	-	67	5.0	-	66	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	0.6	-	-	-	470	-	-	-	0.19	-	-	-	77	5.0	-	68	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	0.4	-	-	-	507	-	-	-	0.20	-	-	-	79	5.0	-	68	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	0.8	-	-	-	561	-	-	-	0.21	-	-	-	84	5.0	-	72	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	391	-	-	-	0.18	-	-	-	75	5.0	-	68	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	0.8	-	-	-	566	-	-	-	0.21	-	-	-	86	5.0	-	72	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	413	-	-	-	0.18	-	-	-	77	5.0	-	64	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	5.0	-	-	-	345	-	-	-	0.16	-	-	-	70	5.0	-	64	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	2.5	-	-	-	392	-	-	-	0.18	-	-	-	71	5.0	-	62	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	2.5	-	-	-	499	-	-	-	0.22	-	-	-	76	5.0	-	54	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	406	-	-	-	0.18	-	-	-	73	5.0	-	54	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	460	-	-	-	0.21	-	-	-	75	5.0	-	58	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	2.5	-	-	-	460	-	-	-	0.20	-	-	-	80	5.0	-	60	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	2.5	-	-	-	412	-	-	-	0.21	-	-	-	91	5.0	-	70	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	5.0	-	-	-	342	-	-	-	0.17	-	-	-	83	5.0	-	72	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	2.5	-	-	-	382	-	-	-	0.18	-	-	-	68	5.0	-	56	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	243	-	-	-	0.12	-	-	-	55	5.0	-	56	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	2.5	-	-	-	337	-	-	-	0.18	-	-	-	76	5.0	-	76	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	414	-	-	-	0.21	-	-	-	76	5.0	-	74	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	315	-	-	-	0.16	-	-	-	70	5.0	-	62	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	2.5	-	-	-	376	-	-	-	0.16	-	-	-	73	5.0	-	62	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	2.5	-	-	-	423	-	-	-	0.19	-	-	-	71	5.0	-	60	-	
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	5.0	-	-	-	406	-	-	-	0.18	-	-	-	71	5.0	-	62	-	

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																						
Coarse Processed Kimberlite (continued)																						
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	368	-	-	-	0.18	-	-	-	68	5.0	-	56	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	2.5	-	-	-	309	-	-	-	0.16	-	-	-	69	5.0	-	60	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	215	-	-	-	0.10	-	-	-	49	5.0	-	42	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	365	-	-	-	0.15	-	-	-	68	5.0	-	60	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	2.5	-	-	-	360	-	-	-	0.19	-	-	-	77	5.0	-	62	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	362	-	-	-	0.19	-	-	-	74	5.0	-	76	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	364	-	-	-	0.17	-	-	-	62	5.0	-	66	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	2.5	-	-	-	408	-	-	-	0.21	-	-	-	76	5.0	-	74	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	2.5	-	-	-	556	-	-	-	0.22	-	-	-	78	5.0	-	72	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	2.5	-	-	-	431	-	-	-	0.19	-	-	-	64	5.0	-	56	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	2.5	-	-	-	510	-	-	-	0.17	-	-	-	63	5.0	-	57	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	2.5	-	-	-	435	-	-	-	0.20	-	-	-	88	5.0	-	69	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.7	2.5	-	-	-	632	-	-	-	0.25	-	-	-	84	5.0	-	65	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	461	-	-	-	0.17	-	-	-	62	5.0	-	51	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	2.5	-	-	-	465	-	-	-	0.20	-	-	-	80	5.0	-	67	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	2.5	-	-	-	408	-	-	-	0.19	-	-	-	88	5.0	-	62	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	2.5	-	-	-	319	-	-	-	0.12	-	-	-	48	5.0	-	50	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	358	-	-	-	0.12	-	-	-	53	5.0	-	52	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	2.5	-	-	-	618	-	-	-	0.23	-	-	-	67	5.0	-	58	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	2.5	-	-	-	524	-	-	-	0.17	-	-	-	59	5.0	-	52	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	507	-	-	-	0.20	-	-	-	78	5.0	-	70	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	273	-	-	-	0.12	-	-	-	52	5.0	-	52	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.6	2.5	-	-	-	431	-	-	-	0.19	-	-	-	58	10	-	56	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	2.5	-	-	-	433	-	-	-	0.19	-	-	-	60	10	-	57	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	2.5	-	-	-	319	-	-	-	0.12	-	-	-	48	5.0	-	50	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	2.5	-	-	-	510	-	-	-	0.17	-	-	-	63	5.0	-	57	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	422	-	-	-	0.16	-	-	-	54	5.0	-	51	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	486	-	-	-	0.18	-	-	-	61	5.0	-	50	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	474	-	-	-	0.19	-	-	-	73	5.0	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	2.5	-	-	-	417	-	-	-	0.18	-	-	-	66	5.0	-	50	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	492	-	-	-	0.19	-	-	-	62	5.0	-	51	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.2	2.5	-	-	-	502	-	-	-	0.20	-	-	-	74	5.0	-	56	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	379	-	-	-	0.16	-	-	-	62	5.0	-	48	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	405	-	-	-	0.17	-	-	-	55	5.0	-	49	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	375	-	-	-	0.19	-	-	-	76	5.0	-	57	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	379	-	-	-	0.16	-	-	-	60	5.0	-	50	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	372	-	-	-	0.14	-	-	-	47	5.0	-	48	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	382	-	-	-	0.14	-	-	-	47	5.0	-	47	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																						
Coarse Processed Kimberlite (continued)																						
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	456	-	-	-	0.18	-	-	-	63	5.0	-	50	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	376	-	-	-	0.21	-	-	-	84	5.0	-	51	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.6	2.5	-	-	-	357	-	-	-	0.16	-	-	-	63	5.0	-	53	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.7	2.5	-	-	-	408	-	-	-	0.18	-	-	-	60	5.0	-	51	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.4	2.5	-	-	-	398	-	-	-	0.18	-	-	-	64	5.0	-	53	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	2.5	-	-	-	395	-	-	-	0.19	-	-	-	71	5.0	-	56	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.9	2.5	-	-	-	465	-	-	-	0.22	-	-	-	71	5.0	-	59	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	2.5	-	-	-	424	-	-	-	0.19	-	-	-	61	5.0	-	53	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	2.5	-	-	-	388	-	-	-	0.17	-	-	-	61	5.0	-	55	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	2.5	-	-	-	449	-	-	-	0.19	-	-	-	57	5.0	-	52	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.1	2.5	-	-	-	393	-	-	-	0.18	-	-	-	64	10	-	53	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	447	-	-	-	0.19	-	-	-	57	5.0	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	371	-	-	-	0.16	-	-	-	57	5.0	-	52	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	313	-	-	-	0.14	-	-	-	61	10	-	53	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.0	2.5	-	-	-	352	-	-	-	0.16	-	-	-	63	5.0	-	57	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	437	-	-	-	0.14	-	-	-	54	5.0	-	49	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	349	-	-	-	0.15	-	-	-	59	5.0	-	52	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	366	-	-	-	0.17	-	-	-	74	5.0	-	59	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	357	-	-	-	0.13	-	-	-	56	5.0	-	50	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	384	-	-	-	0.15	-	-	-	50	5.0	-	49	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.4	2.5	-	-	-	350	-	-	-	0.16	-	-	-	65	5.0	-	56	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.3	2.5	-	-	-	421	-	-	-	0.17	-	-	-	57	5.0	-	52	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	2.5	-	-	-	607	-	-	-	0.22	-	-	-	73	5.0	-	50	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	2.5	-	-	-	636	-	-	-	0.22	-	-	-	74	5.0	-	52	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	2.5	-	-	-	504	-	-	-	0.20	-	-	-	70	5.0	-	61	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	2.5	-	-	-	488	-	-	-	0.20	-	-	-	72	5.0	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.7	2.5	-	-	-	552	-	-	-	0.22	-	-	-	67	5.0	-	117	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	2.5	-	-	-	549	-	-	-	0.22	-	-	-	67	5.0	-	56	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.4	2.5	-	-	-	532	-	-	-	0.22	-	-	-	77	5.0	-	59	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.8	2.5	-	-	-	519	-	-	-	0.21	-	-	-	71	5.0	-	58	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.0	6.0	-	-	-	487	-	-	-	0.19	-	-	-	63	10	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.2	8.0	-	-	-	487	-	-	-	0.19	-	-	-	65	5.0	-	53	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	7.2	5.0	-	-	-	473	-	-	-	0.18	-	-	-	61	10	-	50	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	6.5	2.5	-	-	-	435	-	-	-	0.19	-	-	-	62	10	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	2.5	-	-	-	467	-	-	-	0.18	-	-	-	66	5.0	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.8	5.0	-	-	-	465	-	-	-	0.18	-	-	-	68	5.0	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	2.5	-	-	-	635	-	-	-	0.24	-	-	-	75	5.0	-	78	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	5.0	-	-	-	630	-	-	-	0.23	-	-	-	74	5.0	-	67	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price	Crustal Abundances																	
					General Rock Type	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70
		From	To	Paste pH	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U (ICP)	U (XRF)	V	W	Y	Zn	Zr	
					unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	
Kimberlite (continued)																						
Coarse Processed Kimberlite (continued)																						
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	2.5	-	-	-	557	-	-	-	0.22	-	-	-	78	5.0	-	72	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	2.5	-	-	-	523	-	-	-	0.21	-	-	-	75	5.0	-	64	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.6	2.5	-	-	-	586	-	-	-	0.22	-	-	-	70	10	-	62	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.7	5.0	-	-	-	596	-	-	-	0.23	-	-	-	73	5.0	-	63	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	2.5	-	-	-	533	-	-	-	0.20	-	-	-	68	5.0	-	57	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	2.5	-	-	-	550	-	-	-	0.20	-	-	-	66	5.0	-	56	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.5	2.5	-	-	-	535	-	-	-	0.20	-	-	-	69	5.0	-	53	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	2.5	-	-	-	544	-	-	-	0.20	-	-	-	67	5.0	-	51	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.5	2.5	-	-	-	543	-	-	-	0.20	-	-	-	66	5.0	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	2.5	-	-	-	581	-	-	-	0.21	-	-	-	71	5.0	-	58	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.4	2.5	-	-	-	589	-	-	-	0.20	-	-	-	66	5.0	-	53	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	2.5	-	-	-	593	-	-	-	0.20	-	-	-	67	5.0	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	0.58	-	-	-	449	-	-	-	0.15	-	-	-	57	0.8	-	55	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	0.31	-	-	-	465	-	-	-	0.15	-	-	-	57	0.6	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.4	2.5	-	-	-	529	-	-	-	0.20	-	-	-	65	5.0	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	2.5	-	-	-	515	-	-	-	0.19	-	-	-	64	5.0	-	53	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.5	2.5	-	-	-	579	-	-	-	0.21	-	-	-	66	5.0	-	58	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	2.5	-	-	-	568	-	-	-	0.21	-	-	-	66	5.0	-	57	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	2.5	-	-	-	622	-	-	-	0.23	-	-	-	74	5.0	-	58	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	2.5	-	-	-	631	-	-	-	0.24	-	-	-	77	5.0	-	57	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	2.5	-	-	-	507	-	-	-	0.24	-	-	-	76	5.0	-	51	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.7	2.5	-	-	-	501	-	-	-	0.24	-	-	-	78	5.0	-	52	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	5.0	-	-	-	614	-	-	-	0.22	-	-	-	71	5.0	-	58	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	5.0	-	-	-	612	-	-	-	0.21	-	-	-	69	5.0	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	2.5	-	-	-	576	-	-	-	0.20	-	-	-	69	5.0	-	62	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.0	2.5	-	-	-	582	-	-	-	0.20	-	-	-	68	5.0	-	61	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	2.5	-	-	-	665	-	-	-	0.22	-	-	-	69	5.0	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.5	2.5	-	-	-	622	-	-	-	0.22	-	-	-	69	5.0	-	52	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.6	2.5	-	-	-	679	-	-	-	0.24	-	-	-	79	5.0	-	57	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.7	2.5	-	-	-	647	-	-	-	0.22	-	-	-	74	5.0	-	54	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	2.5	-	-	-	671	-	-	-	0.23	-	-	-	76	5.0	-	57	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	2.5	-	-	-	630	-	-	-	0.22	-	-	-	73	5.0	-	53	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	2.5	-	-	-	657	-	-	-	0.21	-	-	-	73	5.0	-	52	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.3	2.5	-	-	-	662	-	-	-	0.21	-	-	-	71	5.0	-	51	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.6	2.5	-	-	-	691	-	-	-	0.22	-	-	-	70	5.0	-	56	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	8.9	2.5	-	-	-	580	-	-	20	0.19	5.0	5.0	4.0	61	5.0	-	69	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.1	2.5	-	-	-	638	-	-	10	0.22	5.0	5.0	4.0	69	5.0	-	49	-
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.6	2.5	-	-	-	681	-	-	10	0.23	5.0	5.0	5.0	75	5.0	-	53	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	General Rock Type																		
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-	
		From	To	unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr		
Kimberlite (continued)																							
Coarse Processed Kimberlite (continued)																							
Coarse Processed Kimberlite	-	-	-	Coarse Processed Kimberlite	9.2	2.5	-	-	-	649	-	-	10	0.23	5.0	10	2.0	73	5.0	-	49	-	
CK 00-11-20	-	-	-	Coarse Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
CK 00-11-21	-	-	-	Coarse Processed Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
CK 00-11-24	-	-	-	Coarse Processed Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
CK 00-11-25	-	-	-	Coarse Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
CKC 3SS 11- 26 3	-	-	-	Coarse Processed Kimberlite	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
			Median		8.4	2.5	-	-	-	460	-	-	10	0.19	5.0	5.0	4.0	69	5.0	-	56	-	
			Minimum		6.5	0.1	-	-	-	215	-	-	10	0.10	5.0	5.0	2.0	47	0.6	-	38	-	
			Maximum		9.8	8.0	-	-	-	691	-	-	20	0.25	5.0	10	5.0	91	10	-	117	-	
			Count		189	155	0	0	0	155	0	0	4	155	4	4	4	155	155	0	155	0	
Fine Processed Kimberlite																							
FK 13-SEP-04	-	-	-	Fine Processed Kimberlite	8.1	5.0	-	-	-	275	-	-	-	0.09	-	-	-	39	10	-	48	-	
FK 3-JAN-04	-	-	-	Fine Processed Kimberlite	8.1	5.0	-	-	-	339	-	-	-	0.11	-	-	-	46	10	-	51	-	
FK 7-FEB-04	-	-	-	Fine Processed Kimberlite	8.1	5.0	-	-	-	206	-	-	-	0.07	-	-	-	31	10	-	46	-	
FK 4-APR-04	-	-	-	Fine Processed Kimberlite	8.1	5.0	-	-	-	230	-	-	-	0.08	-	-	-	37	10	-	49	-	
FK 7-JUN-04	-	-	-	Fine Processed Kimberlite	8.1	5.0	-	-	-	266	-	-	-	0.09	-	-	-	37	10	-	47	-	
FK 5-JUL-04	-	-	-	Fine Processed Kimberlite	8.1	5.0	-	-	-	330	-	-	-	0.13	-	-	-	58	10	-	56	-	
FK 6-AUG-04	-	-	-	Fine Processed Kimberlite	7.9	5.0	-	-	-	444	-	-	-	0.20	-	-	-	86	10	-	65	-	
FK 8-AUG-04	-	-	-	Fine Processed Kimberlite	8.2	5.0	-	-	-	374	-	-	-	0.10	-	-	-	44	10	-	47	-	
FK 11-AUG-04	-	-	-	Fine Processed Kimberlite	7.9	5.0	-	-	-	480	-	-	-	0.20	-	-	-	83	10	-	62	-	
FK 12-AUG-04	-	-	-	Fine Processed Kimberlite	8.2	5.0	-	-	-	291	-	-	-	0.12	-	-	-	58	10	-	51	-	
FK 15-AUG-04	-	-	-	Fine Processed Kimberlite	8.0	5.0	-	-	-	445	-	-	-	0.18	-	-	-	76	10	-	65	-	
FK 16-AUG-04	-	-	-	Fine Processed Kimberlite	8.1	5.0	-	-	-	403	-	-	-	0.17	-	-	-	71	10	-	58	-	
FK 23-AUG-04	-	-	-	Fine Processed Kimberlite	8.1	5.0	-	-	-	283	-	-	-	0.12	-	-	-	56	10	-	52	-	
FK 28-AUG-04	-	-	-	Fine Processed Kimberlite	8.2	5.0	-	-	-	347	-	-	-	0.13	-	-	-	60	10	-	56	-	
FK 31-AUG-04	-	-	-	Fine Processed Kimberlite	8.3	5.0	-	-	-	280	-	-	-	0.13	-	-	-	52	10	-	50	-	
FK 12-SEP-04	-	-	-	Fine Processed Kimberlite	8.2	5.0	-	-	-	267	-	-	-	0.09	-	-	-	36	10	-	45	-	
FK 20-SEP-04	-	-	-	Fine Processed Kimberlite	8.3	5.0	-	-	-	252	-	-	-	0.09	-	-	-	39	10	-	48	-	
FK 1-OCT-04	-	-	-	Fine Processed Kimberlite	8.1	5.0	-	-	-	366	-	-	-	0.19	-	-	-	97	10	-	65	-	
FK 18-OCT-04	-	-	-	Fine Processed Kimberlite	8.2	5.0	-	-	-	352	-	-	-	0.16	-	-	-	65	10	-	57	-	
FK 25-OCT-04	-	-	-	Fine Processed Kimberlite	8.1	5.0	-	-	-	352	-	-	-	0.16	-	-	-	63	10	-	59	-	
FINE KIMBERLITE 30-OCT-04	-	-	-	Fine Processed Kimberlite	8.1	5.0	-	-	-	277	-	-	-	0.13	-	-	-	51	10	-	52	-	
FINE KIMBERLITE 25-DEC-04	-	-	-	Fine Processed Kimberlite	8.2	5.0	-	-	-	302	-	-	-	0.15	-	-	-	57	10	-	54	-	
FINE KIMBERLITE 23-JAN-05	-	-	-	Fine Processed Kimberlite	8.2	5.0	-	-	-	345	-	-	-	0.16	-	-	-	58	10	-	53	-	
FINE KIMBERLITE 25-FEB-05	-	-	-	Fine Processed Kimberlite	8.2	5.0	-	-	-	289	-	-	-	0.14	-	-	-	52	10	-	51	-	
FINE KIMBERLITE 24-MAR-05	-	-	-	Fine Processed Kimberlite	8.3	5.0	-	-	-	318	-	-	-	0.16	-	-	-	54	10	-	62	-	
FINE KIMBERLITE 24-APR-05	-	-	-	Fine Processed Kimberlite	7.9	5.0	-	-	-	381	-	-	-	0.16	-	-	-	62	10	-	55	-	
FINE KIMBERLITE 25-MAY-05	-	-	-	Fine Processed Kimberlite	8.2	5.0	-	-	-	288	-	-	-	0.13	-	-	-	49	10	-	51	-	

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval From To		Price Crustal Abundances General Rock Type	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
					Paste pH	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr
					unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Kimberlite (continued)																						
<i>Fine Processed Kimberlite (continued)</i>																						
FINE KIMBERLITE 23-JUN-05	-	-	-	Fine Processed Kimberlite	8.3	5.0	-	-	-	246	-	-	-	0.10	-	-	-	40	10	-	53	-
FINE KIMBERLITE 24-JUL-05	-	-	-	Fine Processed Kimberlite	8.3	5.0	-	-	-	311	-	-	-	0.11	-	-	-	45	10	-	52	-
FINE KIMBERLITE 23-AUG-05	-	-	-	Fine Processed Kimberlite	8.2	5.0	-	-	-	300	-	-	-	0.13	-	-	-	58	10	-	59	-
FINE KIMBERLITE 28-SEP-05A	-	-	-	Fine Processed Kimberlite	8.4	5.0	-	-	-	253	-	-	-	0.13	-	-	-	55	10	-	52	-
FINE KIMBERLITE 28-SEP-05B	-	-	-	Fine Processed Kimberlite	8.5	5.0	-	-	-	282	-	-	-	0.14	-	-	-	60	10	-	58	-
FINE KIMBERLITE 24-OCT-05	-	-	-	Fine Processed Kimberlite	8.0	5.0	-	-	-	324	-	-	-	0.15	-	-	-	53	10	-	52	-
FINE KIMBERLITE 28-NOV-05A	-	-	-	Fine Processed Kimberlite	8.5	5.0	-	-	-	455	-	-	-	0.21	-	-	-	82	10	-	59	-
FINE KIMBERLITE 28-NOV-05B	-	-	-	Fine Processed Kimberlite	8.3	5.0	-	-	-	455	-	-	-	0.20	-	-	-	79	10	-	59	-
FINE KIMBERLITE 23-DEC-05	-	-	-	Fine Processed Kimberlite	8.4	5.0	-	-	-	365	-	-	-	0.16	-	-	-	63	10	-	55	-
FINE KIMBERLITE PPD	-	-	-	Fine Processed Kimberlite	8.2	5.0	-	-	-	246	-	-	-	0.09	-	-	-	34	10	-	46	-
FK 00-11- 09 15	-	-	-	Fine Processed Kimberlite	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FK 00-11- 20 27	-	-	-	Fine Processed Kimberlite	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Median					8.2	5.0	-	-	-	311	-	-	-	0.13	-	-	-	56	10	-	53	-
Minimum					7.9	5.0	-	-	-	206	-	-	-	0.07	-	-	-	31	10	-	45	-
Maximum					8.5	5.0	-	-	-	480	-	-	-	0.21	-	-	-	97	10	-	65	-
Count					39	37	0	0	0	37	0	0	0	37	0	0	0	37	37	0	37	0
Metasediment																						
<i>Beartooth</i>																						
13	BDC-05	48.01	48.44	Metasediment	9.9	2.5	19	-	5.0	19	-	-	-	0.35	-	-	-	136	5.0	6.0	93	-
BDC 2-41.76	BDC 2	41.76	46.16	Metasediment	-	2.5	-	-	-	391	-	-	-	0.54	-	-	-	188	5.0	-	90	-
BDC 2-50.9	BDC 2	50.9	56	Metasediment	-	2.5	-	-	-	585	-	-	-	0.50	-	-	-	164	5.0	-	112	-
BDC 5-41.76	BDC 5	41.76	47.85	Metasediment	-	2.5	-	-	-	398	-	-	-	0.46	-	-	-	166	5.0	-	92	-
BDC 5-49.47	BDC 5	49.47	55.04	Metasediment	-	2.5	-	-	-	493	-	-	-	0.36	-	-	-	113	5.0	-	72	-
BDC 5-55.04	BDC 5	55.04	58.9	Metasediment	-	2.5	-	-	-	574	-	-	-	0.35	-	-	-	122	5.0	-	70	-
Median					9.9	2.5	19	-	5.0	446	-	-	-	0.41	-	-	-	150	5.0	6.0	91	-
Minimum					9.9	2.5	19	-	5.0	19	-	-	-	0.35	-	-	-	113	5.0	6.0	70	-
Maximum					9.9	2.5	19	-	5.0	585	-	-	-	0.54	-	-	-	188	5.0	6.0	112	-
Count					1	6	1	0	1	6	0	0	0	6	0	0	0	6	6	1	6	0
Koala																						
KS 390-25 1a	-	-	-	Metasediment	9.7	2.5	-	-	-	784	-	-	-	0.31	-	-	-	79	5.0	-	68	-
KS 390-25 2a	-	-	-	Metasediment	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-23 1a	-	-	-	Metasediment	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-23 2a	-	-	-	Metasediment	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-24-1a	-	-	-	Metasediment	9.6	2.5	-	-	-	735	-	-	-	0.36	-	-	-	83	5.0	-	76	-
KS-390-24-1a	-	-	-	Metasediment	9.3	2.5	-	-	-	656	-	-	-	0.31	-	-	-	74	5.0	-	70	-
KS-390-24-2a	-	-	-	Metasediment	9.6	2.5	-	-	-	657	-	-	-	0.28	-	-	-	65	5.0	-	64	-
KS-390-24-2a	-	-	-	Metasediment	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-26T-1a	-	-	-	Metasediment	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																						
Koala (continued)																						
KS-390-26T-2a	-	-	-	Metasediment	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-27-1a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-27-2a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-37-1a	-	-	-	Metasediment	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-37-2a	-	-	-	Metasediment	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-38-1a	-	-	-	Metasediment	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-390-38-2a	-	-	-	Metasediment	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS 375-03 1a	-	-	-	Metasediment	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS 375-03 2a	-	-	-	Metasediment	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS 375-05 1a	-	-	-	Metasediment	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS 375-05 2a	-	-	-	Metasediment	9.4	2.5	-	-	-	248	-	-	-	0.16	-	-	-	43	5.0	-	42	-
KS-375-09-1a	-	-	-	Metasediment	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-09-2a	-	-	-	Metasediment	8.8	2.5	-	-	-	401	-	-	-	0.16	-	-	-	39	5.0	-	42	-
KS-375-10-1a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-10-2a	-	-	-	Metasediment	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-11-1a	-	-	-	Metasediment	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-11-2a	-	-	-	Metasediment	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-12-1a	-	-	-	Metasediment	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-12-2a	-	-	-	Metasediment	9.5	2.5	-	-	-	577	-	-	-	0.18	-	-	-	41	5.0	-	50	-
KS-375-14-1a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-14-1a	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-14-2a	-	-	-	Metasediment	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-14-2a	-	-	-	Metasediment	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-20-1A	-	-	-	Metasediment	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-20-2A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-375-22REV1-1A	-	-	-	Metasediment	8.9	2.5	-	-	-	624	-	-	-	0.20	-	-	-	47	5.0	-	48	-
KS-375-22REV1-2A	-	-	-	Metasediment	8.2	2.5	-	-	-	650	-	-	-	0.24	-	-	-	58	5.0	-	52	-
KS-360-05-1A	-	-	-	Metasediment	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KS-360-05-2A	-	-	-	Metasediment	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
				Median	9.5	2.5	-	-	-	650	-	-	-	0.24	-	-	-	58	5.0	-	52	-
				Minimum	8.2	2.5	-	-	-	248	-	-	-	0.16	-	-	-	39	5.0	-	42	-
				Maximum	9.8	2.5	-	-	-	784	-	-	-	0.36	-	-	-	83	5.0	-	76	-
				Count	38	9	0	0	0	9	0	0	0	9	0	0	0	9	9	0	9	0
Misery																						
MGT-66 45-48	-	-	-	Metasediment	9.2	0.05	9.2	0.25	-	8	-	0.1	4.3	0.20	0.4	1.2	-	94	0.3	-	57	-
MGT-66 50-53	-	-	-	Metasediment	9.4	0.05	8.9	0.25	-	13	-	0.1	4.0	0.24	0.5	1.5	-	89	0.1	-	75	-
MGT-66 81.03-82.28	-	-	-	Metasediment	9.4	0.05	5.3	0.25	-	5	-	0.1	6.8	0.19	0.7	3.0	-	67	0.1	-	83	-
MGT-66 100.58-102.04	-	-	-	Metasediment	9.1	0.05	6.5	0.25	-	10	-	0.1	3.5	0.13	0.4	1.0	-	80	0.05	-	64	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																						
Misery (continued)																						
MGT-49 273-276	-	-	-	Metasediment	9.2	0.05	12	0.25	-	6	-	0.1	3.4	0.31	0.8	1.0	-	113	0.1	-	92	-
MDC-4 15.02	-	-	-	Metasediment	7.4	2.5	-	-	-	194	-	-	-	0.39	-	-	-	128	5.0	-	98	-
MDC-4 26.4	-	-	-	Metasediment	8.7	2.5	-	-	-	235	-	-	-	0.39	-	-	-	128	5.0	-	92	-
MDC-4 31.5	-	-	-	Metasediment	9.1	2.5	-	-	-	293	-	-	-	0.35	-	-	-	108	5.0	-	74	-
MDC-4 37.06	-	-	-	Metasediment	8.9	2.5	-	-	-	220	-	-	-	0.40	-	-	-	135	5.0	-	90	-
MDC-4 46.8	-	-	-	Metasediment	8.4	2.5	-	-	-	186	-	-	-	0.41	-	-	-	136	5.0	-	92	-
MDC-4 53.4	-	-	-	Metasediment	8.3	2.5	-	-	-	266	-	-	-	0.31	-	-	-	88	5.0	-	78	-
MDC-4 59.04	-	-	-	Metasediment	8.9	2.5	-	-	-	180	-	-	-	0.39	-	-	-	132	5.0	-	110	-
MDC-4 70.78	-	-	-	Metasediment	9.2	2.5	-	-	-	204	-	-	-	0.36	-	-	-	116	5.0	-	118	-
MDC-6 14.32	-	-	-	Metasediment	9.6	2.5	-	-	-	201	-	-	-	0.33	-	-	-	92	5.0	-	130	-
MDC-6 75.69	-	-	-	Metasediment	9.4	2.5	-	-	-	169	-	-	-	0.26	-	-	-	69	5.0	-	72	-
MDC-6 104.66	-	-	-	Metasediment	9.0	2.5	-	-	-	209	-	-	-	0.25	-	-	-	72	5.0	-	62	-
MDC-6 144.7	-	-	-	Metasediment	9.1	2.5	-	-	-	224	-	-	-	0.32	-	-	-	95	5.0	-	92	-
MDC-6 190	-	-	-	Metasediment	9.1	2.5	-	-	-	182	-	-	-	0.28	-	-	-	102	5.0	-	80	-
MDC-8 18.85	-	-	-	Metasediment	8.3	2.5	-	-	-	174	-	-	-	0.26	-	-	-	85	5.0	-	78	-
MDC-8 46.48	-	-	-	Metasediment	9.3	2.5	-	-	-	251	-	-	-	0.31	-	-	-	90	5.0	-	80	-
MDC-8 157.28	-	-	-	Metasediment	8.8	2.5	-	-	-	262	-	-	-	0.32	-	-	-	107	5.0	-	76	-
MDC-4 25.7	-	-	-	Metasediment	9.1	2.5	-	-	-	165	-	-	-	0.31	-	-	-	80	5.0	-	106	-
MDC-4 87.47	-	-	-	Metasediment	9.3	2.5	-	-	-	260	-	-	-	0.30	-	-	-	96	5.0	-	94	-
MS 450-30 A	-	-	-	Metasediment	9.3	0.1	-	-	-	522	-	-	-	0.09	-	-	-	11	5.0	-	36	-
MS 450-30 B	-	-	-	Metasediment	9.1	0.1	-	-	-	524	-	-	-	0.09	-	-	-	11	5.0	-	34	-
MS 450-34-1A	-	-	-	Metasediment	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 450-34-2A	-	-	-	Metasediment	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 450-35-2A	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS-440-E-01	-	-	-	Metasediment	9.3	2.5	15	-	-	279	-	-	10	0.38	5.0	5.0	-	112	5.0	-	88	-
MS-440-E-02	-	-	-	Metasediment	9.2	2.5	14	-	-	299	-	-	10	0.37	5.0	5.0	-	106	5.0	-	95	-
MS-440-SE-01	-	-	-	Metasediment	8.7	2.5	15	-	-	231	-	-	10	0.38	5.0	10	-	117	5.0	-	98	-
MPS 440-01 A	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A1	-	-	-	Metasediment	8.1	0.1	-	-	-	188	-	-	-	0.33	-	-	-	109	190	-	68	-
MPS 440-01-05 A2	-	-	-	Metasediment	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A3	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A4	-	-	-	Metasediment	8.3	0.1	-	-	-	224	-	-	-	0.31	-	-	-	97	5.0	-	68	-
MPS 440-01-05 A5	-	-	-	Metasediment	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A6	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-01-05 A7	-	-	-	Metasediment	8.6	0.1	-	-	-	304	-	-	-	0.33	-	-	-	108	5.0	-	70	-
MPS 440-01-05 A8	-	-	-	Metasediment	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MPS 440-06 A	-	-	-	Metasediment	8.5	0.1	-	-	-	230	-	-	-	0.29	-	-	-	92	5.0	-	62	-
MPS 440-06 AA	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																						
Misery (continued)																						
MPS 440-06 AAA	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-01 1A	-	-	-	Metasediment	8.4	0.1	-	-	-	205	-	-	-	0.23	-	-	-	67	5.0	-	56	-
MS 440-01 2A	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-01 2AA	-	-	-	Metasediment	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-10 1A	-	-	-	Metasediment	8.5	0.1	-	-	-	266	-	-	-	0.22	-	-	-	60	5.0	-	40	-
MS 440-10 2A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-13 1A	-	-	-	Metasediment	7.8	0.1	-	-	-	196	-	-	-	0.28	-	-	-	91	5.0	-	66	-
MS 440-13 2A	-	-	-	Metasediment	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-16 A	-	-	-	Metasediment	9.3	0.1	-	-	-	236	-	-	-	0.27	-	-	-	77	5.0	-	64	-
MS 440-16 B	-	-	-	Metasediment	8.7	0.1	-	-	-	226	-	-	-	0.33	-	-	-	108	5.0	-	62	-
MS 440-18 1A	-	-	-	Metasediment	8.4	0.1	-	-	-	205	-	-	-	0.34	-	-	-	117	5.0	-	66	-
MS 440-19 1A	-	-	-	Metasediment	7.6	0.1	-	-	-	242	-	-	-	0.33	-	-	-	106	5.0	-	60	-
MS 440-19 2A	-	-	-	Metasediment	7.7	0.1	-	-	-	122	-	-	-	0.30	-	-	-	106	5.0	-	50	-
MS 440-21 1A	-	-	-	Metasediment	7.1	0.1	-	-	-	263	-	-	-	0.26	-	-	-	75	5.0	-	56	-
MS 440-21 2A	-	-	-	Metasediment	7.2	0.1	-	-	-	311	-	-	-	0.24	-	-	-	68	5.0	-	54	-
MS 440-23 1A	-	-	-	Metasediment	8.7	0.2	-	-	-	212	-	-	-	0.32	-	-	-	96	5.0	-	92	-
MS 440-27 28-1A	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-27 28-2A	-	-	-	Metasediment	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-27-1A	-	-	-	Metasediment	7.8	0.1	-	-	-	184	-	-	-	0.22	-	-	-	105	5.0	-	102	-
MS 440-27-2A	-	-	-	Metasediment	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-29-1A	-	-	-	Metasediment	8.2	0.2	-	-	-	226	-	-	-	0.32	-	-	-	113	5.0	-	86	-
MS 440-29-2A	-	-	-	Metasediment	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-30-1A	-	-	-	Metasediment	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-30-2A	-	-	-	Metasediment	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-31-1A	-	-	-	Metasediment	7.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-31-2A	-	-	-	Metasediment	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-33-1A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-33-2A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-35-1A	-	-	-	Metasediment	8.5	0.2	-	-	-	436	-	-	-	0.37	-	-	-	117	5.0	-	64	-
MS 440-36-1A	-	-	-	Metasediment	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 440-36-2A	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 440-38-1A	-	-	-	Metasediment	8.7	0.4	-	-	-	230	-	-	-	0.27	-	-	-	81	10	-	164	-
MS- 440-38-2A	-	-	-	Metasediment	7.7	0.6	-	-	-	178	-	-	-	0.15	-	-	-	25	10	-	52	-
MS- 440-43-1A	-	-	-	Metasediment	8.3	0.2	-	-	-	283	-	-	-	0.39	-	-	-	122	10	-	154	-
MS- 440-43-2A	-	-	-	Metasediment	7.3	0.6	-	-	-	251	-	-	-	0.22	-	-	-	57	10	-	46	-
MS K 440 46 1A	-	-	-	Metasediment	8.2	2.5	-	-	-	257	-	-	-	0.36	-	-	-	108	5.0	-	98	-
MS K 440 46 1B	-	-	-	Metasediment	8.3	2.5	-	-	-	271	-	-	-	0.30	-	-	-	95	20	-	60	-
MS- 440-49-1A	-	-	-	Metasediment	7.3	0.2	-	-	-	195	-	-	-	0.28	-	-	-	86	10	-	102	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																						
Misery (continued)																						
MS- 440-49-2A	-	-	-	Metasediment	7.8	0.2	-	-	-	231	-	-	-	0.31	-	-	-	98	10	-	124	-
MS- 440-52-1A	-	-	-	Metasediment	7.6	0.2	-	-	-	373	-	-	-	0.20	-	-	-	51	10	-	50	-
MS- 440-52-2A	-	-	-	Metasediment	7.8	0.6	-	-	-	393	-	-	-	0.21	-	-	-	55	5.0	-	54	-
MS- 440-64-1A	-	-	-	Metasediment	8.7	2.5	-	-	-	238	-	-	-	0.35	-	-	-	112	10	-	142	-
MS- 440-64-2A	-	-	-	Metasediment	8.6	2.5	-	-	-	165	-	-	-	0.33	-	-	-	107	10	-	80	-
MS- 440-69-1A	-	-	-	Metasediment	8.0	2.5	-	-	-	191	-	-	-	0.35	-	-	-	126	10	-	106	-
MS- 440-69-2A	-	-	-	Metasediment	7.9	2.5	-	-	-	209	-	-	-	0.36	-	-	-	124	10	-	110	-
MS-440-71-1A	-	-	-	Metasediment	8.4	2.5	-	-	-	207	-	-	-	0.36	-	-	-	114	5.0	-	80	-
MS-440-71-2A	-	-	-	Metasediment	8.5	5.0	-	-	-	187	-	-	-	0.34	-	-	-	102	5.0	-	66	-
MS-440-74-1A	-	-	-	Metasediment	8.0	2.5	-	-	-	76	-	-	-	0.26	-	-	-	82	5.0	-	48	-
MS-440-74-2A	-	-	-	Metasediment	7.9	2.5	-	-	-	193	-	-	-	0.30	-	-	-	94	5.0	-	68	-
MS-440-75-1A	-	-	-	Metasediment	7.7	10	-	-	-	303	-	-	-	0.26	-	-	-	69	5.0	-	58	-
MS-440-75-2A	-	-	-	Metasediment	7.5	2.5	-	-	-	246	-	-	-	0.29	-	-	-	93	5.0	-	60	-
MS-430-NW-01	-	-	-	Metasediment	8.3	2.5	14	-	-	189	-	-	10	0.34	5.0	10	-	104	5.0	-	89	-
MS-430-NW-02	-	-	-	Metasediment	8.2	2.5	13	-	-	182	-	-	10	0.33	5.0	10	-	100	5.0	-	84	-
MS-430-NW-03	-	-	-	Metasediment	8.3	2.5	13	-	-	192	-	-	10	0.35	5.0	5.0	-	106	5.0	-	88	-
MS- 430-01-1A	-	-	-	Metasediment	7.7	0.1	-	-	-	64	-	-	-	0.22	-	-	-	74	5.0	-	54	-
MS- 430-01-2A	-	-	-	Metasediment	7.8	0.6	-	-	-	112	-	-	-	0.27	-	-	-	121	5.0	-	76	-
MS- 430-02-1A	-	-	-	Metasediment	7.8	0.6	-	-	-	842	-	-	-	0.19	-	-	-	97	5.0	-	66	-
MS- 430-02-2A	-	-	-	Metasediment	8.2	0.4	-	-	-	232	-	-	-	0.38	-	-	-	134	10	-	98	-
MS- 430-03-1A	-	-	-	Metasediment	8.1	0.4	-	-	-	233	-	-	-	0.35	-	-	-	113	10	-	108	-
MS- 430-03-2A	-	-	-	Metasediment	8.3	0.6	-	-	-	293	-	-	-	0.31	-	-	-	103	10	-	96	-
MS- 430-04-1A	-	-	-	Metasediment	8.3	0.6	-	-	-	616	-	-	-	0.26	-	-	-	89	5.0	-	76	-
MS- 430-04-2A	-	-	-	Metasediment	8.4	0.2	-	-	-	266	-	-	-	0.33	-	-	-	99	10	-	94	-
MS- 430-05-1A	-	-	-	Metasediment	8.3	0.2	-	-	-	494	-	-	-	0.27	-	-	-	93	5.0	-	88	-
MS- 430-05-2A	-	-	-	Metasediment	8.0	0.6	-	-	-	214	-	-	-	0.29	-	-	-	88	5.0	-	84	-
MS- 430-06-1A	-	-	-	Metasediment	8.1	0.6	-	-	-	224	-	-	-	0.36	-	-	-	128	10	-	88	-
MS- 430-06-2A	-	-	-	Metasediment	8.1	1.2	-	-	-	241	-	-	-	0.36	-	-	-	130	10	-	86	-
MS- 430-07-1A	-	-	-	Metasediment	8.6	0.4	-	-	-	321	-	-	-	0.37	-	-	-	118	10	-	104	-
MS- 430-07-2A	-	-	-	Metasediment	8.4	0.8	-	-	-	365	-	-	-	0.34	-	-	-	100	10	-	92	-
MS- 430-08-1A	-	-	-	Metasediment	8.5	0.2	-	-	-	228	-	-	-	0.39	-	-	-	130	10	-	90	-
MS- 430-08-2A	-	-	-	Metasediment	8.6	0.6	-	-	-	268	-	-	-	0.35	-	-	-	113	10	-	88	-
MS- 430-09-1A	-	-	-	Metasediment	8.5	0.2	-	-	-	259	-	-	-	0.33	-	-	-	107	5.0	-	88	-
MS- 430-09-2A	-	-	-	Metasediment	8.6	0.1	-	-	-	286	-	-	-	0.34	-	-	-	107	10	-	92	-
MS 430 10 1A	-	-	-	Metasediment	9.2	10	-	-	-	319	-	-	-	0.24	-	-	-	78	5.0	-	96	-
MS 430 10 2A	-	-	-	Metasediment	9.4	5.0	-	-	-	279	-	-	-	0.30	-	-	-	97	5.0	-	72	-
MS 430 12 1A	-	-	-	Metasediment	9.0	5.0	-	-	-	295	-	-	-	0.31	-	-	-	103	5.0	-	66	-
MS 430 12 2A	-	-	-	Metasediment	9.0	5.0	-	-	-	244	-	-	-	0.33	-	-	-	116	5.0	-	126	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
					Paste pH	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr
					unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																						
Misery (continued)																						
MS 430 14 1A	-	-	-	Metasediment	8.5	2.5	-	-	-	127	-	-	-	0.32	-	-	-	133	5.0	-	120	-
MS 430 14 2A	-	-	-	Metasediment	8.7	2.5	-	-	-	144	-	-	-	0.30	-	-	-	121	5.0	-	78	-
MS 430 16 1A	-	-	-	Metasediment	8.7	2.5	-	-	-	195	-	-	-	0.29	-	-	-	109	5.0	-	62	-
MS 430 16 2A	-	-	-	Metasediment	8.4	5.0	-	-	-	73	-	-	-	0.30	-	-	-	116	5.0	-	58	-
MS 430 17 1A	-	-	-	Metasediment	9.0	2.5	-	-	-	153	-	-	-	0.65	-	-	-	216	5.0	-	96	-
MS 430 17 2A	-	-	-	Metasediment	9.0	2.5	-	-	-	157	-	-	-	0.54	-	-	-	199	5.0	-	88	-
MS 430 22 1A	-	-	-	Metasediment	7.9	5.0	-	-	-	175	-	-	-	0.32	-	-	-	100	5.0	-	86	-
MS 430 22 2A	-	-	-	Metasediment	9.0	2.5	-	-	-	250	-	-	-	0.35	-	-	-	105	5.0	-	96	-
MS 430 24 1A	-	-	-	Metasediment	8.7	5.0	-	-	-	232	-	-	-	0.34	-	-	-	113	5.0	-	88	-
MS 430 24 2A	-	-	-	Metasediment	8.7	2.5	-	-	-	244	-	-	-	0.32	-	-	-	111	5.0	-	82	-
MS 430 26 1A	-	-	-	Metasediment	8.6	2.5	-	-	-	214	-	-	-	0.50	-	-	-	169	5.0	-	92	-
MS 430 26 2A	-	-	-	Metasediment	8.5	2.5	-	-	-	235	-	-	-	0.29	-	-	-	89	5.0	-	64	-
MS 430 32 1A	-	-	-	Metasediment	9.1	5.0	-	-	-	253	-	-	-	0.32	-	-	-	103	5.0	-	84	-
MS 430 32 2A	-	-	-	Metasediment	8.8	5.0	-	-	-	193	-	-	-	0.32	-	-	-	110	5.0	-	88	-
MS- 430-38-1A	-	-	-	Metasediment	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 430-38-2A	-	-	-	Metasediment	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 430-39-1A	-	-	-	Metasediment	7.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 430-39-2A	-	-	-	Metasediment	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 430-40-1A	-	-	-	Metasediment	8.2	2.5	-	-	-	271	-	-	-	0.35	-	-	-	133	5.0	-	130	-
MS- 430-40-2A	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MG/S-430-44-1A	-	-	-	Metasediment	8.7	2.5	-	-	-	213	-	-	-	0.37	-	-	-	112	5.0	-	72	-
MS-430-38-1A	-	-	-	Metasediment	8.8	5.0	-	-	-	145	-	-	-	0.31	-	-	-	100	5.0	-	102	-
MS-430-38-2A	-	-	-	Metasediment	9.0	2.5	-	-	-	223	-	-	-	0.33	-	-	-	122	5.0	-	114	-
MS-430-43-1A	-	-	-	Metasediment	8.8	5.0	-	-	-	291	-	-	-	0.30	-	-	-	87	5.0	-	78	-
MS-430-43-2A	-	-	-	Metasediment	8.6	2.5	-	-	-	131	-	-	-	0.12	-	-	-	30	5.0	-	36	-
MS-430-49-1A	-	-	-	Metasediment	8.2	2.5	-	-	-	300	-	-	-	0.37	-	-	-	115	5.0	-	100	-
MS-430-49-2A	-	-	-	Metasediment	8.4	2.5	-	-	-	262	-	-	-	0.28	-	-	-	86	5.0	-	64	-
MS-430-50-1A	-	-	-	Metasediment	8.6	2.5	-	-	-	355	-	-	-	0.18	-	-	-	52	5.0	-	58	-
MS-430-50-2A	-	-	-	Metasediment	8.5	2.5	-	-	-	221	-	-	-	0.30	-	-	-	102	5.0	-	66	-
MS-430-52-1A	-	-	-	Metasediment	8.8	5.0	-	-	-	173	-	-	-	1.0	-	-	-	373	5.0	-	122	-
MS-430-52-2A	-	-	-	Metasediment	9.4	2.5	-	-	-	111	-	-	-	0.16	-	-	-	48	5.0	-	52	-
MS-430-53-1A	-	-	-	Metasediment	8.8	2.5	-	-	-	274	-	-	-	0.17	-	-	-	45	5.0	-	68	-
MS-430-53-2A	-	-	-	Metasediment	8.5	2.5	-	-	-	283	-	-	-	0.29	-	-	-	87	5.0	-	72	-
MS-430-54-1A	-	-	-	Metasediment	8.3	5.0	-	-	-	197	-	-	-	0.39	-	-	-	115	5.0	-	70	-
MS-430-54-2A	-	-	-	Metasediment	8.2	2.5	-	-	-	103	-	-	-	0.30	-	-	-	92	5.0	-	56	-
MS-430-57-1A	-	-	-	Metasediment	8.4	2.5	-	-	-	216	-	-	-	0.32	-	-	-	107	5.0	-	76	-
MS-430-57-2A	-	-	-	Metasediment	8.5	2.5	-	-	-	228	-	-	-	0.28	-	-	-	89	5.0	-	66	-
MS-430-59-1A	-	-	-	Metasediment	8.7	2.5	-	-	-	211	-	-	-	0.35	-	-	-	107	5.0	-	98	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																						
Misery (continued)																						
MS-430-59-2A	-	-	-	Metasediment	9.1	2.5	-	-	-	325	-	-	-	0.38	-	-	-	121	5.0	-	144	-
MS-420-18-01	-	-	-	Metasediment	9.4	0.025	16	0.5	-	282	-	0.05	6.3	0.36	0.75	2.1	-	119	0.7	-	85	-
MS-420-20-01	-	-	-	Metasediment	9.3	0.025	15	1.0	-	225	-	0.025	6.8	0.36	0.82	3.1	-	114	0.8	-	77	-
MS-420-24-01	-	-	-	Metasediment	8.3	0.025	15	1.0	-	226	-	0.05	6.7	0.35	0.54	2.6	-	110	1.0	-	85	-
MS-420-24-02	-	-	-	Metasediment	8.2	0.025	13	2.0	-	318	-	0.05	7.8	0.31	0.58	3.2	-	92	0.9	-	80	-
MS-420-25-01	-	-	-	Metasediment	8.8	0.025	16	2.0	-	237	-	0.07	7.7	0.37	0.48	2.4	-	115	0.5	-	89	-
MS-420-25-02	-	-	-	Metasediment	8.8	0.025	16	2.0	-	182	-	0.09	10	0.38	0.47	3.2	-	112	0.8	-	85	-
MS- 420-01-1A	-	-	-	Metasediment	8.4	2.5	-	-	-	634	-	-	-	0.17	-	-	-	70	5.0	-	46	-
MS- 420-01-2A	-	-	-	Metasediment	8.4	2.5	-	-	-	206	-	-	-	0.34	-	-	-	106	10	-	90	-
MS- 420-05-1A	-	-	-	Metasediment	8.6	5.0	-	-	-	223	-	-	-	0.31	-	-	-	117	10	-	74	-
MS- 420-05-2A	-	-	-	Metasediment	9.1	2.5	-	-	-	404	-	-	-	0.06	-	-	-	10	10	-	30	-
MS- 420-06-1A	-	-	-	Metasediment	8.5	2.5	-	-	-	194	-	-	-	0.32	-	-	-	105	10	-	82	-
MS- 420-06-2A	-	-	-	Metasediment	8.6	2.5	-	-	-	218	-	-	-	0.28	-	-	-	95	10	-	76	-
MS- 420-08-1A	-	-	-	Metasediment	8.8	2.5	-	-	-	235	-	-	-	0.36	-	-	-	113	10	-	86	-
MS- 420-08-2A	-	-	-	Metasediment	8.9	2.5	-	-	-	272	-	-	-	0.43	-	-	-	141	10	-	78	-
MS- 420-09-1A	-	-	-	Metasediment	8.3	2.5	-	-	-	228	-	-	-	0.26	-	-	-	84	10	-	70	-
MS- 420-09-2A	-	-	-	Metasediment	8.5	2.5	-	-	-	207	-	-	-	0.32	-	-	-	109	10	-	82	-
MS- 420-12-1B	-	-	-	Metasediment	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 420-12-2B	-	-	-	Metasediment	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS- 420-16-1B	-	-	-	Metasediment	8.4	2.5	-	-	-	158	-	-	-	0.37	-	-	-	120	5.0	-	100	-
MS- 420-16-2B	-	-	-	Metasediment	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 420 22 1A	-	-	-	Metasediment	8.4	2.5	-	-	-	266	-	-	-	0.35	-	-	-	111	5.0	-	86	-
MS 420 22 1A	-	-	-	Metasediment	9.1	2.5	-	-	-	138	-	-	-	0.07	-	-	-	13	5.0	-	24	-
MS 420 22 1B	-	-	-	Metasediment	8.7	2.5	-	-	-	277	-	-	-	0.36	-	-	-	109	5.0	-	114	-
MS 420 22 1B	-	-	-	Metasediment	8.3	2.5	-	-	-	489	-	-	-	0.18	-	-	-	57	5.0	-	44	-
MS-420-32-1A	-	-	-	Metasediment	8.2	2.5	-	-	-	211	-	-	-	0.33	-	-	-	99	5.0	-	62	-
MS-420-32-2A	-	-	-	Metasediment	8.3	2.5	-	-	-	192	-	-	-	0.33	-	-	-	102	5.0	-	88	-
MS-420-33-1A	-	-	-	Metasediment	8.7	2.5	-	-	-	265	-	-	-	0.33	-	-	-	103	5.0	-	76	-
MS-420-33-2A	-	-	-	Metasediment	8.6	2.5	-	-	-	229	-	-	-	0.30	-	-	-	97	5.0	-	56	-
MS-420-34-1A	-	-	-	Metasediment	8.6	2.5	-	-	-	203	-	-	-	0.34	-	-	-	111	5.0	-	74	-
MS-420-34-2A	-	-	-	Metasediment	8.8	5.0	-	-	-	222	-	-	-	0.33	-	-	-	107	5.0	-	82	-
MS-420-35-1A	-	-	-	Metasediment	8.5	2.5	-	-	-	250	-	-	-	0.38	-	-	-	118	5.0	-	68	-
MS-420-35-2A	-	-	-	Metasediment	8.7	2.5	-	-	-	249	-	-	-	0.34	-	-	-	117	5.0	-	58	-
MS-420-37-1A	-	-	-	Metasediment	8.5	2.5	-	-	-	241	-	-	-	0.37	-	-	-	113	5.0	-	86	-
MS-420-37-2A	-	-	-	Metasediment	8.5	10	-	-	-	198	-	-	-	0.33	-	-	-	109	5.0	-	82	-
MS-420-39 1A	-	-	-	Metasediment	9.1	2.5	-	-	-	162	-	-	-	0.22	-	-	-	66	5.0	-	54	-
MS-420-39 2A	-	-	-	Metasediment	8.7	5.0	-	-	-	179	-	-	-	0.31	-	-	-	99	5.0	-	62	-
MS-420-40 2A	-	-	-	Metasediment	9.1	2.5	-	-	-	169	-	-	-	0.35	-	-	-	106	5.0	-	92	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																						
Misery (continued)																						
MS-420-40 1A	-	-	-	Metasediment	8.8	2.5	-	-	-	193	-	-	-	0.40	-	-	-	128	5.0	-	100	-
MS-420-40B 1B	-	-	-	Metasediment	9.3	2.5	-	-	-	213	-	-	-	0.41	-	-	-	129	5.0	-	88	-
MS-420-40B 2B	-	-	-	Metasediment	9.3	2.5	-	-	-	230	-	-	-	0.42	-	-	-	127	5.0	-	102	-
MS-420-41 1B	-	-	-	Metasediment	8.1	15	-	-	-	322	-	-	-	0.22	-	-	-	120	10	-	78	-
MS-420-41 2B	-	-	-	Metasediment	9.0	2.5	-	-	-	231	-	-	-	0.27	-	-	-	82	5.0	-	82	-
MS-420-43 1A	-	-	-	Metasediment	9.1	2.5	-	-	-	249	-	-	-	0.34	-	-	-	104	5.0	-	78	-
MS-420-43 2A	-	-	-	Metasediment	9.1	2.5	-	-	-	237	-	-	-	0.32	-	-	-	104	5.0	-	70	-
MS-420-44-1a	-	-	-	Metasediment	9.1	2.5	-	-	-	269	-	-	-	0.37	-	-	-	117	5.0	-	86	-
MS-420-44-2a	-	-	-	Metasediment	8.8	2.5	-	-	-	236	-	-	-	0.31	-	-	-	98	5.0	-	84	-
MS-410-01-01	-	-	-	Metasediment	9.1	0.025	17	1.0	-	144	-	0.025	6.1	0.38	0.94	2.7	-	125	0.8	-	86	-
MS-410-01-02	-	-	-	Metasediment	8.8	0.025	18	1.0	-	145	-	0.025	5.9	0.42	0.84	2.4	-	141	0.8	-	93	-
MS 410 02 1A	-	-	-	Metasediment	8.7	2.5	-	-	-	237	-	-	-	0.32	-	-	-	99	5.0	-	82	-
MS 410 02 1B	-	-	-	Metasediment	8.7	2.5	-	-	-	205	-	-	-	0.30	-	-	-	94	5.0	-	62	-
MS 410 08 1A	-	-	-	Metasediment	8.9	2.5	-	-	-	292	-	-	-	0.20	-	-	-	57	5.0	-	64	-
MS 410 08 1B	-	-	-	Metasediment	8.8	2.5	-	-	-	329	-	-	-	0.16	-	-	-	41	5.0	-	60	-
MS 410 11 1A	-	-	-	Metasediment	8.3	2.5	-	-	-	192	-	-	-	0.30	-	-	-	101	5.0	-	54	-
MS 410 11 1B	-	-	-	Metasediment	8.4	2.5	-	-	-	183	-	-	-	0.34	-	-	-	111	10	-	60	-
MS-410-29 1B	-	-	-	Metasediment	8.7	2.5	-	-	-	216	-	-	-	0.34	-	-	-	118	5.0	-	80	-
MS-410-29 2B	-	-	-	Metasediment	8.2	2.5	-	-	-	334	-	-	-	0.19	-	-	-	91	5.0	-	56	-
MS-410-30B 1B	-	-	-	Metasediment	9.2	2.5	-	-	-	311	-	-	-	0.36	-	-	-	108	5.0	-	100	-
MS-410-30B 2B	-	-	-	Metasediment	8.9	5.0	-	-	-	397	-	-	-	0.37	-	-	-	113	5.0	-	94	-
MS-410-33 1A	-	-	-	Metasediment	8.7	2.5	-	-	-	225	-	-	-	0.32	-	-	-	98	5.0	-	90	-
MS-410-33 2B	-	-	-	Metasediment	8.6	2.5	-	-	-	227	-	-	-	0.28	-	-	-	86	5.0	-	72	-
MS-410-34 1A	-	-	-	Metasediment	8.8	2.5	-	-	-	182	-	-	-	0.28	-	-	-	99	5.0	-	106	-
MS-410-34 2A	-	-	-	Metasediment	8.7	2.5	-	-	-	216	-	-	-	0.32	-	-	-	99	5.0	-	64	-
MS-410-35 1A	-	-	-	Metasediment	8.4	2.5	-	-	-	439	-	-	-	0.20	-	-	-	112	5.0	-	64	-
MS-410-35 2A	-	-	-	Metasediment	8.5	2.5	-	-	-	245	-	-	-	0.32	-	-	-	95	5.0	-	74	-
MS-410-37 1A	-	-	-	Metasediment	9.1	2.5	-	-	-	266	-	-	-	0.34	-	-	-	103	5.0	-	76	-
MS-410-37 2A	-	-	-	Metasediment	9.0	2.5	-	-	-	159	-	-	-	0.38	-	-	-	121	5.0	-	68	-
MS-410-39 1A	-	-	-	Metasediment	9.3	5.0	-	-	-	203	-	-	-	0.32	-	-	-	93	5.0	-	80	-
MS-410-39 2A	-	-	-	Metasediment	9.2	2.5	-	-	-	174	-	-	-	0.22	-	-	-	65	5.0	-	72	-
MS-410-42 1A	-	-	-	Metasediment	9.2	2.5	-	-	-	190	-	-	-	0.33	-	-	-	103	5.0	-	90	-
MS-410-42 2A	-	-	-	Metasediment	9.0	2.5	-	-	-	185	-	-	-	0.92	-	-	-	306	5.0	-	126	-
MS-410-43 1A	-	-	-	Metasediment	9.2	2.5	-	-	-	258	-	-	-	0.32	-	-	-	93	5.0	-	72	-
MS-410-43 2A	-	-	-	Metasediment	9.2	2.5	-	-	-	222	-	-	-	0.30	-	-	-	88	5.0	-	64	-
MS-410-45-1A	-	-	-	Metasediment	9.0	2.5	-	-	-	196	-	-	-	0.31	-	-	-	98	5.0	-	76	-
MS-410-45-2A	-	-	-	Metasediment	9.1	2.5	-	-	-	242	-	-	-	0.55	-	-	-	172	5.0	-	116	-
MS-410-46 1A	-	-	-	Metasediment	9.1	2.5	-	-	-	245	-	-	-	0.32	-	-	-	92	5.0	-	78	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																						
Misery (continued)																						
MS-410-46 2A	-	-	-	Metasediment	9.2	2.5	-	-	-	273	-	-	-	0.34	-	-	-	111	5.0	-	94	-
MS-410-47-1A	-	-	-	Metasediment	9.2	2.5	-	-	-	256	-	-	-	0.33	-	-	-	89	5.0	-	80	-
MS-410-47-1A	-	-	-	Metasediment	9.3	2.5	-	-	-	288	-	-	-	0.36	-	-	-	94	5.0	-	96	-
MS-410-47-2A	-	-	-	Metasediment	8.9	2.5	-	-	-	249	-	-	-	0.35	-	-	-	104	5.0	-	94	-
MS-410-48-1A	-	-	-	Metasediment	8.7	2.5	-	-	-	234	-	-	-	0.38	-	-	-	115	5.0	-	114	-
MS-410-48-2A	-	-	-	Metasediment	8.7	2.5	-	-	-	218	-	-	-	0.38	-	-	-	104	5.0	-	96	-
MS-410-52-1A	-	-	-	Metasediment	8.7	2.5	-	-	-	234	-	-	-	0.37	-	-	-	113	5.0	-	96	-
MS-410-52-2A	-	-	-	Metasediment	8.7	2.5	-	-	-	190	-	-	-	0.31	-	-	-	94	5.0	-	72	-
MS-410-53-1A	-	-	-	Metasediment	8.7	2.5	-	-	-	222	-	-	-	0.35	-	-	-	102	5.0	-	94	-
MS-410-53-2A	-	-	-	Metasediment	8.9	2.5	-	-	-	223	-	-	-	0.31	-	-	-	93	5.0	-	82	-
MS-410-54-1A	-	-	-	Metasediment	9.1	2.5	-	-	-	279	-	-	-	0.38	-	-	-	112	5.0	-	98	-
MS-410-54-2A	-	-	-	Metasediment	9.1	2.5	-	-	-	288	-	-	-	0.35	-	-	-	101	5.0	-	96	-
MS-410-55-1A	-	-	-	Metasediment	9.0	2.5	-	-	-	252	-	-	-	0.32	-	-	-	91	5.0	-	86	-
MS-410-55-2A	-	-	-	Metasediment	8.8	2.5	-	-	-	183	-	-	-	0.35	-	-	-	111	5.0	-	66	-
MS-410-58-1A	-	-	-	Metasediment	8.5	2.5	-	-	-	319	-	-	-	0.41	-	-	-	126	5.0	-	104	-
MS-410-58-2A	-	-	-	Metasediment	8.7	2.5	-	-	-	332	-	-	-	0.37	-	-	-	118	5.0	-	88	-
MS 400-38-1a	-	-	-	Metasediment	9.3	2.5	-	-	-	248	-	-	-	0.35	-	-	-	113	5.0	-	106	-
MS 400-38-2a	-	-	-	Metasediment	9.5	2.5	-	-	-	182	-	-	-	0.31	-	-	-	89	5.0	-	118	-
MS 400-41 2a	-	-	-	Metasediment	9.5	2.5	-	-	-	249	-	-	-	0.31	-	-	-	105	5.0	-	90	-
MS 400-42-2a	-	-	-	Metasediment	9.2	2.5	-	-	-	236	-	-	-	0.62	-	-	-	219	5.0	-	112	-
MS 400-43 1a	-	-	-	Metasediment	9.7	2.5	-	-	-	301	-	-	-	0.34	-	-	-	105	5.0	-	80	-
MS 400-43 2a	-	-	-	Metasediment	9.3	2.5	-	-	-	230	-	-	-	0.35	-	-	-	121	5.0	-	80	-
MS 400-45-1a	-	-	-	Metasediment	8.7	2.5	-	-	-	226	-	-	-	0.23	-	-	-	81	5.0	-	60	-
MS 400-45-2a	-	-	-	Metasediment	9.3	2.5	-	-	-	194	-	-	-	0.29	-	-	-	96	5.0	-	94	-
MS-400-12-1A	-	-	-	Metasediment	8.5	2.5	-	-	-	340	-	-	-	0.27	-	-	-	85	5.0	-	84	-
MS-400-12-2A	-	-	-	Metasediment	8.5	2.5	-	-	-	306	-	-	-	0.28	-	-	-	76	5.0	-	74	-
MS-400-13-1A	-	-	-	Metasediment	8.3	2.5	-	-	-	210	-	-	-	0.34	-	-	-	107	5.0	-	80	-
MS-400-13-2A	-	-	-	Metasediment	8.4	2.5	-	-	-	223	-	-	-	0.36	-	-	-	112	5.0	-	124	-
MS-400-14-1A	-	-	-	Metasediment	8.7	2.5	-	-	-	99	-	-	-	0.27	-	-	-	106	5.0	-	38	-
MS-400-14-2A	-	-	-	Metasediment	8.4	2.5	-	-	-	159	-	-	-	0.34	-	-	-	108	5.0	-	76	-
MS-400-16-1A	-	-	-	Metasediment	8.8	2.5	-	-	-	179	-	-	-	0.38	-	-	-	106	5.0	-	100	-
MS-400-16-2A	-	-	-	Metasediment	8.8	2.5	-	-	-	184	-	-	-	0.33	-	-	-	92	5.0	-	92	-
MS-400-18-1A	-	-	-	Metasediment	8.8	2.5	-	-	-	181	-	-	-	0.33	-	-	-	88	5.0	-	98	-
MS-400-18-2A	-	-	-	Metasediment	9.1	2.5	-	-	-	324	-	-	-	0.29	-	-	-	75	5.0	-	98	-
MS-400-20-1A	-	-	-	Metasediment	9.1	2.5	-	-	-	248	-	-	-	0.34	-	-	-	95	5.0	-	110	-
MS-400-20-2A	-	-	-	Metasediment	8.6	2.5	-	-	-	219	-	-	-	0.30	-	-	-	97	5.0	-	62	-
MS-400-23-1A	-	-	-	Metasediment	8.2	2.5	-	-	-	316	-	-	-	0.28	-	-	-	80	5.0	-	80	-
MS-400-23-2A	-	-	-	Metasediment	8.1	2.5	-	-	-	231	-	-	-	0.33	-	-	-	98	5.0	-	96	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																						
Misery (continued)																						
MS-400-28-1A	-	-	-	Metasediment	9.2	2.5	-	-	-	287	-	-	-	0.3	-	-	-	78	5.0	-	80	-
MS-400-28-2A	-	-	-	Metasediment	9.3	2.5	-	-	-	226	-	-	-	0.34	-	-	-	94	5.0	-	86	-
MS-400-35-1A	-	-	-	Metasediment	8.3	2.5	-	-	-	150	-	-	-	0.32	-	-	-	95	5.0	-	68	-
MS-400-35-2A	-	-	-	Metasediment	8.4	2.5	-	-	-	167	-	-	-	0.35	-	-	-	103	5.0	-	82	-
MS-400-46-1a	-	-	-	Metasediment	9.5	2.5	-	-	-	267	-	-	-	0.31	-	-	-	98	5.0	-	78	-
MS-400-46-2a	-	-	-	Metasediment	9.2	2.5	-	-	-	285	-	-	-	0.36	-	-	-	110	5.0	-	90	-
MS-400-47-2A	-	-	-	Metasediment	9.4	2.5	-	-	-	284	-	-	-	0.37	-	-	-	107	5.0	-	114	-
MS-400-48-1a	-	-	-	Metasediment	9.1	2.5	-	-	-	125	-	-	-	0.44	-	-	-	140	5.0	-	142	-
MS-400-48-2a	-	-	-	Metasediment	9.3	2.5	-	-	-	284	-	-	-	0.37	-	-	-	114	5.0	-	90	-
MS-400-49-1a	-	-	-	Metasediment	9.4	2.5	-	-	-	266	-	-	-	0.34	-	-	-	108	5.0	-	94	-
MS-400-51-1a	-	-	-	Metasediment	9.5	2.5	-	-	-	209	-	-	-	0.19	-	-	-	49	5.0	-	62	-
MS-400-51-2a	-	-	-	Metasediment	8.9	2.5	-	-	-	266	-	-	-	0.35	-	-	-	109	5.0	-	98	-
MS-400-52T-2a	-	-	-	Metasediment	9.3	2.5	-	-	-	178	-	-	-	0.32	-	-	-	108	5.0	-	86	-
MS-400-53-1a	-	-	-	Metasediment	9.2	2.5	-	-	-	210	-	-	-	0.32	-	-	-	100	5.0	-	66	-
MS-400-53-2a	-	-	-	Metasediment	9.1	2.5	-	-	-	187	-	-	-	0.31	-	-	-	96	5.0	-	72	-
MS-400-54-1a	-	-	-	Metasediment	9.4	2.5	-	-	-	354	-	-	-	0.31	-	-	-	95	5.0	-	84	-
MS-400-54-2a	-	-	-	Metasediment	9.3	2.5	-	-	-	274	-	-	-	0.29	-	-	-	83	5.0	-	74	-
MS 390-13-1a	-	-	-	Metasediment	9.1	5.0	-	-	-	264	-	-	-	0.35	-	-	-	107	5.0	-	96	-
MS 390-13-2a	-	-	-	Metasediment	9.0	2.5	-	-	-	262	-	-	-	0.35	-	-	-	118	5.0	-	104	-
MS-390-01-1A	-	-	-	Metasediment	8.4	2.5	-	-	-	210	-	-	-	0.37	-	-	-	116	5.0	-	92	-
MS-390-01-2A	-	-	-	Metasediment	8.3	2.5	-	-	-	234	-	-	-	0.34	-	-	-	98	5.0	-	80	-
MS 390-12T 1a	-	-	-	Metasediment	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS 390-12T 2a	-	-	-	Metasediment	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
MS-390-21-1a	-	-	-	Metasediment	9.4	2.5	-	-	-	199	-	-	-	0.36	-	-	-	119	5.0	-	132	-
MS-390-21-2a	-	-	-	Metasediment	9.3	2.5	-	-	-	228	-	-	-	0.35	-	-	-	107	5.0	-	82	-
MS-390-25-1a	-	-	-	Metasediment	9.7	2.5	-	-	-	465	-	-	-	0.09	-	-	-	16	5.0	-	40	-
MS-390-25-2a	-	-	-	Metasediment	9.0	2.5	-	-	-	245	-	-	-	0.31	-	-	-	100	5.0	-	74	-
MS-390-27-1a	-	-	-	Metasediment	9.1	2.5	-	-	-	267	-	-	-	0.29	-	-	-	98	5.0	-	68	-
MS-390-27-2a	-	-	-	Metasediment	9.0	2.5	-	-	-	183	-	-	-	0.39	-	-	-	136	5.0	-	80	-
MS-390-28-1a	-	-	-	Metasediment	9.0	2.5	-	-	-	284	-	-	-	0.29	-	-	-	94	5.0	-	70	-
MS-390-28-2a	-	-	-	Metasediment	9.7	2.5	-	-	-	460	-	-	-	0.08	-	-	-	10	5.0	-	42	-
MS-390-30-1a	-	-	-	Metasediment	8.2	2.5	-	-	-	225	-	-	-	0.36	-	-	-	117	5.0	-	116	-
MS-390-30-2a	-	-	-	Metasediment	9.4	2.5	-	-	-	328	-	-	-	0.23	-	-	-	70	5.0	-	78	-
MS-390-31-1a	-	-	-	Metasediment	9.2	2.5	-	-	-	214	-	-	-	0.28	-	-	-	82	5.0	-	78	-
MS-390-31-2a	-	-	-	Metasediment	9.5	2.5	-	-	-	265	-	-	-	0.31	-	-	-	90	5.0	-	82	-
MS-390-32-1a	-	-	-	Metasediment	9.3	2.5	-	-	-	254	-	-	-	0.33	-	-	-	109	5.0	-	80	-
MS-390-32-2a	-	-	-	Metasediment	9.2	2.5	-	-	-	262	-	-	-	0.41	-	-	-	138	5.0	-	104	-
MS-390-33-1a	-	-	-	Metasediment	9.3	2.5	-	-	-	288	-	-	-	0.33	-	-	-	96	5.0	-	98	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Metasediment (continued)																						
Misery (continued)																						
MS-390-33-1a	-	-	-	Metasediment	9.2	2.5	-	-	-	327	-	-	-	0.34	-	-	-	99	5.0	-	90	-
MS-390-34-1a	-	-	-	Metasediment	9.2	2.5	-	-	-	236	-	-	-	0.39	-	-	-	121	5.0	-	94	-
MS-390-34-2a	-	-	-	Metasediment	9.7	2.5	-	-	-	273	-	-	-	0.34	-	-	-	101	5.0	-	102	-
MS-390-36-1a	-	-	-	Metasediment	9.2	2.5	-	-	-	200	-	-	-	1.1	-	-	-	380	5.0	-	168	-
MS-390-36-2a	-	-	-	Metasediment	9.2	2.5	-	-	-	259	-	-	-	0.34	-	-	-	101	5.0	-	104	-
MS-390-37-1A	-	-	-	Metasediment	8.9	2.5	-	-	-	261	-	-	-	0.41	-	-	-	120	5.0	-	104	-
MS-390-37-2A	-	-	-	Metasediment	8.7	2.5	-	-	-	257	-	-	-	0.32	-	-	-	98	5.0	-	82	-
MS-390-38-1A	-	-	-	Metasediment	9.3	2.5	-	-	-	217	-	-	-	0.38	-	-	-	133	5.0	-	106	-
MS-390-39-1A	-	-	-	Metasediment	8.8	2.5	-	-	-	248	-	-	-	0.35	-	-	-	109	5.0	-	88	-
MS-390-39-2A	-	-	-	Metasediment	8.9	2.5	-	-	-	265	-	-	-	0.36	-	-	-	115	5.0	-	88	-
MS-390-40-1A	-	-	-	Metasediment	8.6	2.5	-	-	-	218	-	-	-	0.42	-	-	-	132	5.0	-	150	-
MS-390-40-2A	-	-	-	Metasediment	8.7	2.5	-	-	-	141	-	-	-	0.31	-	-	-	96	5.0	-	98	-
MS-380-32-2A	-	-	-	Metasediment	8.8	2.5	-	-	-	220	-	-	-	0.41	-	-	-	150	5.0	-	106	-
MS-380-60-1	-	-	-	Metasediment	8.9	2.5	-	-	-	185	-	-	-	0.35	-	-	-	100	10	-	108	-
MS-380-60-2	-	-	-	Metasediment	8.9	2.5	-	-	-	198	-	-	-	0.34	-	-	-	102	10	-	78	-
MS-380-58-1	-	-	-	Metasediment	8.8	2.5	-	-	-	213	-	-	-	0.31	-	-	-	94	10	-	84	-
MS-380-58-2	-	-	-	Metasediment	8.6	2.5	-	-	-	221	-	-	-	0.31	-	-	-	93	10	-	84	-
MS-370-18-2	-	-	-	Metasediment	8.7	2.5	-	-	-	252	-	-	-	0.38	-	-	-	126	5.0	-	95	-
MS-360-22T-1	-	-	-	Metasediment	8.8	2.5	-	-	-	271	-	-	-	0.35	-	-	-	107	10	-	80	-
MS-360-22T-2	-	-	-	Metasediment	8.5	2.5	-	-	-	100	-	-	-	0.12	-	-	-	15	5.0	-	44	-
MS-360-22T-3	-	-	-	Metasediment	8.7	2.5	-	-	-	163	-	-	-	0.22	-	-	-	64	10	-	58	-
MS-360-22T-4	-	-	-	Metasediment	8.6	2.5	-	-	-	86	-	-	-	0.10	-	-	-	9.0	5.0	-	41	-
MS-360-26-1	-	-	-	Metasediment	8.7	2.5	-	-	-	194	-	-	-	0.34	-	-	-	110	5.0	-	70	-
MS-360-26-2	-	-	-	Metasediment	8.7	2.5	-	-	-	211	-	-	-	0.34	-	-	-	113	5.0	-	73	-
MS-360-26-3	-	-	-	Metasediment	8.7	2.5	-	-	-	256	-	-	-	0.36	-	-	-	117	5.0	-	78	-
MS-360-26-4	-	-	-	Metasediment	8.4	2.5	-	-	-	197	-	-	-	0.37	-	-	-	118	5.0	-	70	-
MS-360-26-5	-	-	-	Metasediment	8.7	2.5	-	-	-	249	-	-	-	0.31	-	-	-	94	5.0	-	61	-
MS-360-26-6	-	-	-	Metasediment	8.7	2.5	-	-	-	303	-	-	-	0.34	-	-	-	100	5.0	-	75	-
MS-320-19-02 14-DEC-04	-	-	-	Metasediment	8.9	2.5	-	-	-	343	-	-	-	0.27	-	-	-	87	5.0	-	66	-
MS-320-19-01 14-DEC-04	-	-	-	Metasediment	8.5	2.5	-	-	-	233	-	-	-	0.32	-	-	-	100	5.0	-	71	-
MS-310-10-02 20-FEB-05	-	-	-	Metasediment	8.1	2.5	-	-	-	469	-	-	-	0.24	-	-	-	97	5.0	-	67	-
MS-310-10-01 20-FEB-05	-	-	-	Metasediment	8.3	5.0	-	-	-	267	-	-	-	0.12	-	-	-	52	5.0	-	52	-
MS-290-12-04- 3-Apr-05	-	-	-	Metasediment	9.3	2.5	-	-	-	343	-	-	-	0.21	-	-	-	69	5.0	-	57	-
MS-290-12-03- 3-Apr-05	-	-	-	Metasediment	9.1	2.5	-	-	-	272	-	-	-	0.24	-	-	-	78	10	-	75	-
MS-290-12-02- 3-Apr-05	-	-	-	Metasediment	9.2	2.5	-	-	-	290	-	-	-	0.27	-	-	-	86	5.0	-	124	-
MS-290-12-01- 3-Apr-05	-	-	-	Metasediment	8.7	2.5	-	-	-	307	-	-	-	0.25	-	-	-	84	5.0	-	57	-
MGT-49 70-73	-	-	-	Metasediment	9.4	0.05	10	0.25	-	42	-	0.1	2.8	0.31	0.4	0.7	-	101	0.2	-	73	-
MGT-49 125-128	-	-	-	Metasediment	9.4	0.05	8.5	0.25	-	17	-	0.1	2.7	0.23	0.4	0.9	-	95	0.2	-	78	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	General Rock Type																	
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr	
Metasediment (continued)																						
Misery (continued)																						
MGT-49 200-203	-	-	-	Metasediment	9.2	0.05	8.6	0.25	-	7	-	0.1	3.6	0.26	0.5	0.8	-	91	0.05	-	80	-
MGT-49 264-267	-	-	-	Metasediment	9.2	0.05	6.4	0.6	-	6	-	0.1	4.8	0.19	0.5	1.6	-	73	0.1	-	90	-
MGT-51 169-172	-	-	-	Metasediment	9.2	0.05	9.1	0.5	-	6	-	0.1	2.5	0.27	0.5	0.6	-	97	0.1	-	78	-
MGT-56 230-233	-	-	-	Metasediment	9.2	0.05	7.4	0.5	-	6	-	0.1	3.1	0.24	0.4	0.9	-	86	0.05	-	64	-
MGT-56 290-293	-	-	-	Metasediment	9.4	0.05	7.9	0.25	-	8	-	0.1	3.3	0.24	0.4	0.9	-	86	0.05	-	69	-
MGT-66 9-12	-	-	-	Metasediment	9.0	0.05	0.9	0.25	-	3	-	0.3	2.0	0.019	0.1	5.8	-	8.0	0.2	-	18	-
MGT-66 21-24	-	-	-	Metasediment	9.6	0.05	8.1	0.25	-	8	-	0.1	3.9	0.24	0.4	1.3	-	85	0.05	-	72	-
MGT-66 33-36	-	-	-	Metasediment	9.4	0.05	12	0.25	-	9	-	0.1	3.4	0.31	0.5	1.0	-	111	0.1	-	84	-
MGT-66 41-44	-	-	-	Metasediment	9.8	0.05	8.7	0.25	-	12	-	0.1	4.5	0.25	0.3	1.2	-	87	0.05	-	87	-
MGT-66 52-65	-	-	-	Metasediment	9.6	0.05	7.2	0.25	-	10	-	0.1	7.0	0.23	0.6	1.5	-	80	0.05	-	79	-
MGT-66 72.47-74.64	-	-	-	Metasediment	10.0	0.05	7.5	0.25	-	5	-	0.1	4.3	0.28	0.7	1.2	-	90	0.05	-	85	-
MGT-66 83-86	-	-	-	Metasediment	9.5	0.05	5.7	0.25	-	5	-	0.1	6.4	0.17	0.5	1.8	-	65	0.05	-	69	-
MGT-66 95-98	-	-	-	Metasediment	9.7	0.05	7.8	0.25	-	6	-	0.1	3.0	0.22	0.3	0.9	-	86	0.2	-	79	-
MGT-44 45-48	-	-	-	Metasediment	8.6	0.05	6.7	0.25	-	6	-	0.1	5.2	0.13	0.2	1.3	-	77	0.05	-	71	-
MGT-44 52-55	-	-	-	Metasediment	8.7	0.05	12	0.25	-	8	-	0.1	3.2	0.28	0.4	1.0	-	103	0.1	-	80	-
MGT-44 70.5-73.5	-	-	-	Metasediment	8.5	0.05	10	0.25	-	6	-	0.1	2.8	0.3	0.8	3.5	-	92	0.2	-	134	-
MGT-51 72-75	-	-	-	Metasediment	9.3	0.05	11	0.25	-	18	-	0.1	4.8	0.29	0.6	2.6	-	96	0.2	-	95	-
MGT-51 79-82	-	-	-	Metasediment	9.1	0.05	9.3	0.25	-	10	-	0.1	4.1	0.24	0.5	5.4	-	85	0.3	-	79	-
MGT-51 220-223	-	-	-	Metasediment	9.3	0.05	1.9	0.25	-	7	-	0.1	16	0.089	0.3	4.8	-	18	0.05	-	47	-
MGT-51 250-253	-	-	-	Metasediment	9.0	0.05	8.3	0.25	-	6	-	0.1	5.7	0.24	0.4	1.4	-	80	12	-	74	-
MGT-51 257-260	-	-	-	Metasediment	9.0	0.05	8.8	0.25	-	7	-	0.1	5.6	0.25	0.4	1.5	-	86	12	-	83	-
MGT-51 328-330	-	-	-	Metasediment	8.7	0.05	4.0	0.5	-	230	-	0.1	3.2	0.026	0.1	1.8	-	45	0.05	-	56	-
MS K 430 45 1A	-	-	-	Metasediment	8.3	2.5	-	-	-	649	-	-	-	0.19	-	-	-	88	5.0	-	66	-
MS K 430 45 1B	-	-	-	Metasediment	8.3	2.5	-	-	-	544	-	-	-	0.20	-	-	-	97	5.0	-	70	-
Median					8.7	2.5	9.2	0.25	-	227	-	0.1	4.8	0.32	0.5	1.8	-	101	5.0	-	80	-
Minimum					7.1	0.025	0.9	0.25	-	3	-	0.025	2.0	0.019	0.1	0.6	-	8.0	0.05	-	18	-
Maximum					10.0	15	18	2.0	-	842	-	0.3	16	1.1	5.0	10	-	380	190	-	168	-
Count					370	333	43	37	0	333	0	37	43	333	43	43	0	333	333	0	333	0
Pigeon																						
97-54	97-54	29.57	30	Metasediment	8.4	5.0	4.0	-	5.0	8	-	-	-	0.005	-	-	-	51	5.0	8.0	6.0	-
94-7 6.71-10	94-7	6.71	10	Metasediment	8.2	2.5	-	-	-	165	-	-	-	0.37	-	-	-	131	10	-	80	-
94-7 10-15	94-7	10	15	Metasediment	-	2.5	-	-	-	153	-	-	-	0.36	-	-	-	130	10	-	78	-
94-7 15-19.3	94-7	15	19.3	Metasediment	-	2.5	-	-	-	224	-	-	-	0.42	-	-	-	148	5.0	-	94	-
94-7 19.3-22	94-7	19.3	22	Metasediment	-	2.5	-	-	-	296	-	-	-	0.38	-	-	-	126	10	-	76	-
94-7 22-27	94-7	22	27	Metasediment	-	2.5	-	-	-	237	-	-	-	0.39	-	-	-	124	10	-	78	-
94-7 27-32	94-7	27	32	Metasediment	8.4	2.5	-	-	-	102	-	-	-	0.40	-	-	-	137	5.0	-	82	-
94-7 32-37	94-7	32	37	Metasediment	-	2.5	-	-	-	140	-	-	-	0.36	-	-	-	132	5.0	-	86	-
94-7 37-42	94-7	37	42	Metasediment	-	2.5	-	-	-	200	-	-	-	0.30	-	-	-	105	5.0	-	72	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	General Rock Type																	
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr	
Metasediment (continued)																						
Pigeon (continued)																						
94-7 42-47	94-7	42	47	Metasediment	-	2.5	-	-	-	145	-	-	-	0.39	-	-	-	141	10	-	84	-
94-7 47-52	94-7	47	52	Metasediment	-	5.0	-	-	-	157	-	-	-	0.32	-	-	-	110	5.0	-	70	-
94-7 52-57	94-7	52	57	Metasediment	8.8	2.5	-	-	-	286	-	-	-	0.38	-	-	-	123	5.0	-	80	-
94-7 57-62	94-7	57	62	Metasediment	-	10	-	-	-	220	-	-	-	0.42	-	-	-	155	10	-	98	-
94-7 62-67	94-7	62	67	Metasediment	-	5.0	-	-	-	249	-	-	-	0.33	-	-	-	115	10	-	70	-
94-7 67-72	94-7	67	72	Metasediment	-	2.5	-	-	-	257	-	-	-	0.31	-	-	-	111	5.0	-	68	-
HC-Pdef-2	-	-	-	Metasediment	8.8	0.07	22	1.0	1.6	88	0.54	0.025	5.5	0.38	0.35	2.9	-	160	2.1	7.4	177	106
HC-Pdef-3	-	-	-	Metasediment	9.5	0.09	22	1.0	1.7	197	0.6	0.05	6.3	0.42	0.79	2.9	-	152	2.6	8.1	105	110
HC-Pdef-4	-	-	-	Metasediment	9.6	0.06	21	1.0	1.1	402	0.46	0.025	4.3	0.46	0.6	1.3	-	161	1.2	9.0	86	103
HC-Pdef-5	-	-	-	Metasediment	9.6	0.06	16	2.0	0.8	449	0.36	0.07	2.3	0.38	0.56	0.9	-	138	0.4	14	88	88
HC-Pdef-8	-	-	-	Metasediment	9.4	0.08	22	1.0	1.1	216	0.69	0.025	7.7	0.47	0.63	2.9	-	167	2.2	7.6	93	131
HC-Pdef-9	-	-	-	Metasediment	9.4	0.08	16	1.0	1.2	198	0.63	0.025	8.5	0.35	0.61	3.2	-	124	0.8	8.3	79	119
HC-Pdef-10	-	-	-	Metasediment	9.7	0.15	30	2.0	3.8	373	0.26	0.07	3.8	0.41	0.95	1.1	-	133	1.0	24	131	101
HC-Pdef-11	-	-	-	Metasediment	9.2	0.05	17	1.0	0.9	171	0.48	0.06	7.2	0.37	0.51	2.4	-	128	2.4	8.8	78	112
HC-Pdef-13	-	-	-	Metasediment	9.5	0.025	18	1.0	1.1	253	0.62	0.025	10	0.39	0.82	4.0	-	135	0.7	11	74	119
HC-Pdef-14	-	-	-	Metasediment	9.5	0.06	16	1.0	0.9	214	0.58	0.025	7.7	0.40	0.57	3.1	-	117	0.8	7.7	64	137
HC-Pdef-15	-	-	-	Metasediment	9.4	0.08	17	1.0	1.0	215	0.48	0.025	7.8	0.41	0.55	2.5	-	129	0.9	6.5	81	136
HC-Pdef-16	-	-	-	Metasediment	8.0	0.07	19	1.0	1.3	133	0.71	0.025	7.1	0.39	0.46	4.1	-	140	1.7	13	74	109
HC-PDef-18	-	-	-	Metasediment	9.2	0.09	15	2.0	1.1	206	0.49	0.025	8.5	0.34	0.42	2.8	-	113	0.8	7.2	74	141
HC-PDef-19	-	-	-	Metasediment	9.8	0.08	18	2.0	1.4	194	0.63	0.025	6.3	0.4	0.71	2.7	-	146	0.8	5.6	96	133
HC-PDef-20	-	-	-	Metasediment	9.3	0.09	20	2.0	1.0	134	0.61	0.025	6.5	0.43	0.62	2.9	-	157	0.7	6.0	94	145
HC-PDef-21	-	-	-	Metasediment	9.6	0.07	25	2.0	1.4	343	0.71	0.025	6.0	0.47	0.69	2.6	-	184	1.6	7.3	107	143
HC-PDef-22	-	-	-	Metasediment	9.8	0.025	13	1.0	1.0	263	0.66	0.025	12	0.26	0.48	4.2	-	85	1.5	10	55	103
HC-PDef-23	-	-	-	Metasediment	9.5	0.06	16	2.0	1.1	203	0.61	0.025	8.4	0.32	0.55	3.7	-	115	1.1	7.2	76	117
HC-PDef-26	-	-	-	Metasediment	9.3	0.05	18	2.0	1.0	137	0.51	0.025	6.5	0.38	0.35	2.5	-	151	1.2	7.3	74	117
HC-PDef-28	-	-	-	Metasediment	9.8	0.05	8.5	1.0	0.7	437	0.54	0.025	4.5	0.18	0.33	2.8	-	47	1.1	7.8	44	83
HC-PDef-31	-	-	-	Metasediment	9.2	0.08	19	1.0	1.1	156	0.63	0.025	6.0	0.35	0.39	3.0	-	126	0.9	7.0	65	113
HC-PDef-32	-	-	-	Metasediment	9.0	0.025	15	1.0	1.0	135	0.89	0.025	11	0.28	0.53	4.3	-	103	2.1	14	59	127
HC-PDef-35	-	-	-	Metasediment	9.4	0.08	13	1.0	0.7	282	0.58	0.025	11	0.24	0.46	3.6	-	84	1.1	9.5	51	109
Median					9.4	0.085	17	1.0	1.1	205	0.6	0.025	7.1	0.38	0.55	2.9	-	130	2.1	7.9	78	117
Minimum					8.0	0.025	4.0	1.0	0.7	8	0.26	0.025	2.3	0.005	0.33	0.9	-	47	0.4	5.6	6.0	83
Maximum					9.8	10	30	2.0	5.0	449	0.89	0.07	12	0.47	0.95	4.3	-	184	10	24	177	145
Count					27	38	24	23	24	38	23	23	23	38	23	23	0	38	38	24	38	23
Jay																						
2014-DD-001	JGT-04	35.58	41.58	Metasediment	8.30	0.025	14	0.5	1.2	8	0.025	0.025	5.2	0.21	0.53	1.96	-	116	0.6	5.18	72	21
2014-DD-002	JGT-04	41.58	48.98	Metasediment	7.94	0.025	16.7	0.5	1.7	8	0.025	0.025	6.1	0.26	0.77	2.02	-	126	0.6	5.25	72	20.5
2014-DD-005	JGT-04	74.58	83.58	Metasediment	9.05	0.025	0.3	0.5	0.15	5	0.025	0.025	0.2	0.005	0.03	1.42	-	1	0.2	1.17	4	2.3
2014-DD-006	JGT-04	86.17	95.58	Metasediment	8.29	0.025	18.3	0.5	1.3	9	0.025	0.025	5.9	0.22	0.6	1.91	-	143	0.4	5.35	84	15.5

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	General Rock Type																	
					Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	unit	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr	
Metasediment (continued)																						
Jay (continued)																						
2014-DD-007	JGT-04	100	107.7	Metasediment	8.58	0.025	17.2	0.5	1.3	24	0.025	0.025	5.5	0.24	0.6	1.37	-	136	2.4	6.9	86	8.2
2014-DD-008	JGT-04	114.12	122.54	Metasediment	8.26	0.025	18.5	0.5	1.1	8	0.025	0.025	5.7	0.22	0.55	2.75	-	143	0.3	4.8	88	20.1
2014-DD-009	JGT-04	125.58	135.9	Metasediment	8.69	0.025	12.3	0.5	3.2	15	0.025	0.025	5.7	0.18	0.77	4.22	-	102	0.3	6.57	81	15.1
2014-DD-010	JGT-04	142.21	147.1	Metasediment	8.24	0.025	18	0.5	1.5	10	0.025	0.025	7.1	0.23	0.99	2.21	-	137	0.3	5.29	91	14.3
2014-DD-011	JGT-04	147.1	152.58	Metasediment	8.01	0.025	18.8	0.5	1.2	8	0.025	0.025	7.3	0.26	0.73	1.74	-	142	0.3	5.06	80	12.7
2014-DD-012	JGT-04	155.58	163.58	Metasediment	8.14	0.025	19.3	0.5	1.2	8	0.025	0.025	6.6	0.25	0.6	1.94	-	144	0.3	4.71	90	18.6
2014-DD-013	JGT-04	163.38	171.69	Metasediment	8.48	0.025	14.3	0.5	0.9	82	0.025	0.025	5.8	0.22	0.54	1.86	-	115	0.3	5.77	81	14.3
2014-DD-014	JGT-04	174.5	180	Metasediment	8.88	0.025	9.7	0.5	1	15	0.025	0.025	4.7	0.25	0.67	1.42	-	85	0.4	6.14	90	13.5
2014-DD-015	JGT-04	188	196.2	Metasediment	8.38	0.025	18.4	0.5	2.3	71	0.025	0.025	6.9	0.25	0.68	2.2	-	139	0.4	5.87	94	17.1
2014-DD-016	JGT-04	199	206.58	Metasediment	8.17	0.025	17.8	0.5	1.2	10	0.025	0.025	7.7	0.24	0.63	2.06	-	135	0.3	5.54	79	15.9
2014-DD-017	JGT-04	221	230	Metasediment	8.57	0.025	11.7	0.5	1.3	8	0.025	0.025	7.3	0.18	0.81	2.64	-	99	0.2	6.26	131	13.1
2014-DD-018	JGT-04	231.28	241	Metasediment	8.64	0.025	9.4	0.5	1.6	7	0.025	0.025	6.5	0.24	1.09	2.96	-	86	0.3	5.15	90	9.6
2014-DD-019	JGT-04	241	251	Metasediment	9.10	0.025	8.9	0.5	1.8	8	0.025	0.025	6.9	0.23	1.17	2.82	-	82	0.3	6.72	105	8.7
2014-DD-020	JGT-04	251	260	Metasediment	9.51	0.025	4.6	0.5	1.8	10	0.025	0.025	4.9	0.09	0.83	6.71	-	43	0.2	5.09	52	10.8
2014-DD-022	JGT-05	15.2	16.44	Metasediment	8.99	0.025	7.9	0.5	8	5	0.025	0.025	5.4	0.21	1.71	6.24	-	65	0.5	3.91	136	16.9
2014-DD-033	JGT-05	281.55	287.77	Metasediment	9.12	0.025	18.9	0.5	2.6	10	0.025	0.025	5.2	0.38	2.57	1.71	-	142	0.5	6.3	121	6.1
2014-DD-034	JGT-05	287.77	292.77	Metasediment	9.48	0.025	15.4	0.5	3.4	7	0.025	0.025	6.1	0.33	2.23	3.14	-	114	0.5	6.14	144	5.9
2014-DD-035	JGT-05	299.18	308.77	Metasediment	9.13	0.025	18.6	0.5	2.4	10	0.025	0.025	6	0.38	1.78	2.17	-	144	0.5	5.86	164	7
2014-DD-036	JGT-05	308.77	317	Metasediment	9.29	0.025	10.4	0.5	2.5	8	0.025	0.025	6.3	0.27	1.67	3.37	-	90	0.3	8.55	154	9.6
2014-DD-037	JGT-05	336	346	Metasediment	9.87	0.025	11.1	0.5	1.7	7	0.025	0.025	7.4	0.3	1.66	2.78	-	89	0.7	5.44	91	15.5
Median					8.6	0.025	14.85	0.5	1.55	8	0.025	0.025	6.05	0.24	0.77	2.185	-	115.5	0.3	5.49	90	13.9
Minimum					7.9	0.025	0.3	0.5	0.15	5	0.025	0.025	0.2	0.005	0.03	1.37	-	1	0.2	1.17	4	2.3
Maximum					9.9	0.025	19.3	0.5	8	82	0.025	0.025	7.7	0.38	2.57	6.71	-	144	2.4	8.55	164	21
Count					24	24	24	24	24	24	24	24	24	24	24	24	0	24	24	24	24	24
Waste Rock																						
Fox																						
SRK FOX 2	SRK FOX 2	0	0.3	Mixed Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SRK FOX 4	SRK FOX 4	0	0.3	Mixed Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SRK FOX 1	SRK FOX 1	0	0.3	Mixed Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SRK FOX 3	SRK FOX 3	0	0.3	Mixed Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SRK FOX 5	SRK FOX 5	0	0.3	Mixed Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Median					9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Minimum					8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Maximum					9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Count					5	0	0	0	0	-	0	0	0	0	0	0	0	0	0	0	0	

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Koala																						
KNW 420 06+07 1A	-	-	-	Waste Rock	8.0	0.2	-	-	-	467	-	-	-	0.15	-	-	-	51	5.0	-	40	-
KNW 420 06+07 2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 465-1 2-1A	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 465-1 2-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-16 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450- 18+21 1	-	-	-	Waste Rock	9.6	0.1	-	-	-	598	-	-	-	0.25	-	-	-	71	5.0	-	52	-
KSW 450- 18+21 2	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-20 1A	-	-	-	Waste Rock	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-20 2A	-	-	-	Waste Rock	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-22 2A	-	-	-	Waste Rock	8.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-22 2AA	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-23 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-23 2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-25-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-25-2A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-28-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-28-2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-29-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-29-2A	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-31-1A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450-31-2A	-	-	-	Waste Rock	9.0	0.2	-	-	-	770	-	-	-	0.35	-	-	-	85	5.0	-	70	-
KSW- 450-34-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 450-34-2A	-	-	-	Waste Rock	9.1	0.6	-	-	-	819	-	-	-	0.30	-	-	-	79	10	-	80	-
KSW- 450-35-1A	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 450-35-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 450-36-1A	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 450-36-2A	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 450-38-1A	-	-	-	Waste Rock	8.5	0.8	-	-	-	595	-	-	-	0.32	-	-	-	81	5.0	-	78	-
KSW- 450-38-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450 39 1A	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 450 39 2A	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-27 1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-27 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-28 1A	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-28 2A	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-32-1A	-	-	-	Waste Rock	9.3	0.2	-	-	-	688	-	-	-	0.32	-	-	-	83	5.0	-	66	-
KSW 443-32-1AA	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-32-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances General Rock Type	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
					Paste pH	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr
					unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Koala (continued)																						
KSW 443-32-2AA	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-33-1A	-	-	-	Waste Rock	9.4	0.2	-	-	-	749	-	-	-	0.29	-	-	-	71	5.0	-	60	-
KSW 443-33-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-34-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-34-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-35-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-35-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-36-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443-36-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-38-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-38-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 445-40-2A	-	-	-	Waste Rock	8.7	0.1	-	-	-	875	-	-	-	0.37	-	-	-	87	10	-	84	-
KSW- 445-40-1A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-41-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-41-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-42-1A	-	-	-	Waste Rock	7.4	0.6	-	-	-	219	-	-	-	0.21	-	-	-	57	10	-	62	-
KSW- 443-42-2A	-	-	-	Waste Rock	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-43-1A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 443-43-2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443+450 2A	-	-	-	Waste Rock	9.6	0.1	-	-	-	682	-	-	-	0.26	-	-	-	76	5.0	-	60	-
KSW 443+450 1A	-	-	-	Waste Rock	9.4	0.1	-	-	-	628	-	-	-	0.26	-	-	-	78	5.0	-	56	-
KSW 443 46 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 443 46 2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-6 1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-6 2A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-7 1A	-	-	-	Waste Rock	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-7 2A	-	-	-	Waste Rock	8.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-10-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-10-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-15-1A	-	-	-	Waste Rock	9.1	0.2	-	-	-	256	-	-	-	0.21	-	-	-	59	5.0	-	40	-
KSW 435-15-2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-16-1A	-	-	-	Waste Rock	8.7	0.8	-	-	-	699	-	-	-	0.19	-	-	-	58	10	-	54	-
KSW- 435-16-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-23-1A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-23-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 24 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 24 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435-25 1A	-	-	-	Waste Rock	9.3	0.1	-	-	-	195	-	-	-	0.19	-	-	-	48	5.0	-	44	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Koala (continued)																						
KSW 435 26 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 26 2A	-	-	-	Waste Rock	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 27 1A	-	-	-	Waste Rock	9.7	5.0	-	-	-	643	-	-	-	0.28	-	-	-	88	5.0	-	66	-
KSW 435 27 2A	-	-	-	Waste Rock	9.6	2.5	-	-	-	593	-	-	-	0.27	-	-	-	91	5.0	-	74	-
KSW 435 30 1A	-	-	-	Waste Rock	8.4	15	-	-	-	213	-	-	-	0.18	-	-	-	50	5.0	-	52	-
KSW 435 30 2A	-	-	-	Waste Rock	9.4	5.0	-	-	-	227	-	-	-	0.34	-	-	-	90	5.0	-	56	-
KSW 435 31 1A	-	-	-	Waste Rock	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 31 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 34 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 34 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 42 1A	-	-	-	Waste Rock	9.2	2.5	-	-	-	401	-	-	-	0.24	-	-	-	63	5.0	-	62	-
KSW 435 42 2A	-	-	-	Waste Rock	9.5	5.0	-	-	-	554	-	-	-	0.32	-	-	-	87	5.0	-	68	-
KSW 435 51 1A	-	-	-	Waste Rock	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 51 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 52 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 52 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 53 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 53 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 54 1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 54 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 55 1A	-	-	-	Waste Rock	9.8	10	-	-	-	599	-	-	-	0.33	-	-	-	69	5.0	-	68	-
KSW 435 55 2A	-	-	-	Waste Rock	9.7	2.5	-	-	-	558	-	-	-	0.43	-	-	-	73	5.0	-	70	-
KSW 435 60 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 60 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 66 1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 435 66 2A	-	-	-	Waste Rock	7.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-59-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-59-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-77-1A	-	-	-	Waste Rock	9.3	2.5	-	-	-	695	-	-	-	0.32	-	-	-	79	10	-	64	-
KSW- 435-77-2A	-	-	-	Waste Rock	9.3	2.5	-	-	-	638	-	-	-	0.30	-	-	-	76	10	-	66	-
KSW- 435-81-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 435-81-2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-07-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-07-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-09-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-09-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-14-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW- 420-14-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval From To		Price Crustal Abundances General Rock Type	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
					Paste pH	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr
					unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Koala (continued)																						
KSW 420 34 1A	-	-	-	Waste Rock	9.0	2.5	-	-	-	749	-	-	-	0.33	-	-	-	81	5.0	-	66	-
KSW 420 34 2A	-	-	-	Waste Rock	9.0	2.5	-	-	-	721	-	-	-	0.32	-	-	-	81	5.0	-	68	-
KSW 420 36 1A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 36 2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 37 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 37 2A	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 39 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 420 39 2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-30-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-30-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-38-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-38-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-38A-1A	-	-	-	Waste Rock	9.7	2.5	-	-	-	737	-	-	-	0.29	-	-	-	77	5.0	-	68	-
KSW-420-38A-2A	-	-	-	Waste Rock	9.5	2.5	-	-	-	407	-	-	-	0.23	-	-	-	58	5.0	-	46	-
KSW-420-40-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-40-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-41-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-41-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-46 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-420-46 2A	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405 04 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405 04 2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405 05 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405 05 2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 405-25 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-06-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-06-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-10-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-10-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-11-1A	-	-	-	Waste Rock	8.8	5.0	-	-	-	518	-	-	-	0.28	-	-	-	66	5.0	-	54	-
KSW-405-11-2A	-	-	-	Waste Rock	8.7	2.5	-	-	-	432	-	-	-	0.24	-	-	-	63	5.0	-	48	-
KSW-405-13-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-13-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-17-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-17-2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-19-1A	-	-	-	Waste Rock	8.9	5.0	-	-	-	622	-	-	-	0.28	-	-	-	68	5.0	-	60	-
KSW-405-19-2A	-	-	-	Waste Rock	8.7	2.5	-	-	-	650	-	-	-	0.27	-	-	-	73	5.0	-	60	-
KSW-405-25 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Koala (continued)																						
KSW-405-38 1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-38 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-40 1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-40 2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-45 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-45 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-49 1A	-	-	-	Waste Rock	9.3	5.0	-	-	-	624	-	-	-	0.29	-	-	-	68	5.0	-	60	-
KSW-405-49 2A	-	-	-	Waste Rock	9.6	5.0	-	-	-	660	-	-	-	0.32	-	-	-	89	10	-	68	-
KSW-405-52-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-52-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-57-1A	-	-	-	Waste Rock	9.2	2.5	-	-	-	745	-	-	-	0.33	-	-	-	78	5.0	-	82	-
KSW-405-57-2A	-	-	-	Waste Rock	9.3	2.5	-	-	-	645	-	-	-	0.29	-	-	-	64	5.0	-	72	-
KSW-405-63-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-405-63-2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 390-21 1a	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 390-21 2a	-	-	-	Waste Rock	9.8	2.5	-	-	-	678	-	-	-	0.26	-	-	-	67	5.0	-	60	-
KSW-390-03-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-03-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-05-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-05-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-06-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-06-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-08-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-08-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-09-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-09-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-10-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-10-2A	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-11-1A	-	-	-	Waste Rock	8.5	2.5	-	-	-	655	-	-	-	0.30	-	-	-	69	5.0	-	74	-
KSW-390-11-2A	-	-	-	Waste Rock	8.8	2.5	-	-	-	709	-	-	-	0.29	-	-	-	65	5.0	-	72	-
KSW-390-12-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-12-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-24-1a	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW-390-24-2a	-	-	-	Waste Rock	8.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 375-03 1a	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 375-03 2a	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
KSW 375-06 1a	-	-	-	Waste Rock	9.6	2.5	-	-	-	607	-	-	-	0.21	-	-	-	49	5.0	-	48	-
KSW 375-06 2a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-																	
					General Rock Type	Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70
		From	To	unit		Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr
Waste Rock (continued)																						
Koala (continued)																						
KSW-375-13-1a	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
KSW-375-13-2a	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
		Median			9.2	2.5	-	-	-	633	-	-	-	0.29	-	-	-	72	5.0	-	63	-
		Minimum			7.2	0.1	-	-	-	195	-	-	-	0.15	-	-	-	48	5.0	-	40	-
		Maximum			10.1	15	-	-	-	875	-	-	-	0.43	-	-	-	91	10	-	84	-
		Count			192	40	0	0	0	40	0	0	0	40	0	0	0	40	40	0	40	0
Panda																						
PPW 360-76 1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-76 2A	-	-	-	Waste Rock	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-76-1B	-	-	-	Waste Rock	9.7	0.1	-	-	-	811	-	-	-	0.31	-	-	-	81	5.0	-	68	-
PPW- 360-76-2B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-77 1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-77 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-77-1B	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-77-2B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-78 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-78 2A	-	-	-	Waste Rock	9.5	0.2	-	-	-	776	-	-	-	0.33	-	-	-	88	5.0	-	64	-
PPW- 360-78-1B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-78-2B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-79 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-79 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-79-1B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-79-2B	-	-	-	Waste Rock	9.8	0.1	-	-	-	708	-	-	-	0.36	-	-	-	91	5.0	-	70	-
PPW 360-80 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-80 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-80-1B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 360-80-2B	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-82 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-82 2A	-	-	-	Waste Rock	9.4	0.1	-	-	-	749	-	-	-	0.33	-	-	-	84	5.0	-	60	-
PPW- 360-82-1B	-	-	-	Waste Rock	9.6	0.1	-	-	-	780	-	-	-	0.34	-	-	-	86	5.0	-	70	-
PPW- 360-82-2B	-	-	-	Waste Rock	9.7	0.1	-	-	-	799	-	-	-	0.33	-	-	-	81	5.0	-	68	-
PPW 360-89 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 360-89 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-29 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-29-1B	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 345-33 1A	-	-	-	Waste Rock	9.5	0.1	-	-	-	754	-	-	-	0.31	-	-	-	86	5.0	-	62	-
PPW 345-33 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 345-33-1B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-																	
					General Rock Type	Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70
		From	To	unit		Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U (ICP)	U (XRF)	V	W	Y	Zn	Zr
Waste Rock (continued)																						
Panda (continued)																						
PPW- 345-33-2B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-34 1A	-	-	-	Waste Rock	12.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-34 2A	-	-	-	Waste Rock	10.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW- 345-34-1B	-	-	-	Waste Rock	11.8	0.2	-	-	-	754	-	-	-	0.31	-	-	-	81	5.0	-	64	
PPW- 345-34-2B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-35 1A	-	-	-	Waste Rock	10.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-35 2A	-	-	-	Waste Rock	10.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW- 345-35-1B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW- 345-35-2B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-36 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-36 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW- 345-36-1B	-	-	-	Waste Rock	9.3	0.1	-	-	-	649	-	-	-	0.28	-	-	-	77	5.0	-	62	
PPW- 345-36-2B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-37 1A	-	-	-	Waste Rock	9.8	0.1	-	-	-	677	-	-	-	0.31	-	-	-	80	5.0	-	58	
PPW 345-37 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW- 345-37-1B	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW- 345-37-2B	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW- 345-41-1	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-42 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-42 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW- 345-42-1	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW- 345-42-2	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-43 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-43 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW- 345-43-1	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW- 345-43-2	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-48 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-49 1A	-	-	-	Waste Rock	9.6	0.1	-	-	-	742	-	-	-	0.29	-	-	-	77	5.0	-	58	
PPW 345-49 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-50-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-50-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-52 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-52 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-55 1A	-	-	-	Waste Rock	9.5	0.1	-	-	-	726	-	-	-	0.31	-	-	-	80	5.0	-	58	
PPW 345-55 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-56 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 345-56 2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
PPW 330-13 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Panda (continued)																						
PPW- 330-13-1B	-	-	-	Waste Rock	9.0	0.1	-	-	-	795	-	-	-	0.31	-	-	-	76	5.0	-	72	-
PPW- 330-16-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-16-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-17 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-17 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-17-1B	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-17-2B	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-18 1A	-	-	-	Waste Rock	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-18 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-18-1B	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-18-2B	-	-	-	Waste Rock	9.5	0.1	-	-	-	709	-	-	-	0.31	-	-	-	81	5.0	-	64	-
PPW 330-20 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-20 2A	-	-	-	Waste Rock	9.4	0.1	-	-	-	637	-	-	-	0.31	-	-	-	79	10	-	56	-
PPW- 330-20-1B	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-20-2B	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-28 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-28 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-28-1B	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-28-2B	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-30 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-30 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-32-1A	-	-	-	Waste Rock	9.3	0.2	-	-	-	718	-	-	-	0.32	-	-	-	83	5.0	-	66	-
PPW 330-32-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-37-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-37-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-38 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-38 2A	-	-	-	Waste Rock	9.6	0.1	-	-	-	804	-	-	-	0.33	-	-	-	89	5.0	-	66	-
PPW 330-41-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-41-1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 330-41-2	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-41-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-44 1A	-	-	-	Waste Rock	9.7	0.1	-	-	-	708	-	-	-	0.32	-	-	-	84	5.0	-	62	-
PPW 330-44 1AA	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-44 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-44 2AA	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-47 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-47 2A	-	-	-	Waste Rock	9.6	0.1	-	-	-	678	-	-	-	0.29	-	-	-	78	5.0	-	58	-
PPW 330-48 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Panda (continued)																						
PPW 330-49 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-49 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-50 1A	-	-	-	Waste Rock	9.5	0.1	-	-	-	732	-	-	-	0.29	-	-	-	74	5.0	-	56	-
PPW 330-50 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-56 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-56 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-59 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-59 2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-61 1A	-	-	-	Waste Rock	9.5	0.1	-	-	-	830	-	-	-	0.32	-	-	-	82	5.0	-	60	-
PPW 330-61 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-62 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-62 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-63 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-63 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-64 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-64 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-65-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-65-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-66-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-66-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-70-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-70-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-71-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-71-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-72-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-72-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-73-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 330-73-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 332-75-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 332-75-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-76-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-77-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-77-2A	-	-	-	Waste Rock	9.2	0.2	-	-	-	729	-	-	-	0.30	-	-	-	79	10	-	72	-
PWP- 330-80-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-80-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 330-82-1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-03 1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-03 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Panda (continued)																						
PPW 315-04 1A	-	-	-	Waste Rock	9.5	0.1	-	-	-	747	-	-	-	0.33	-	-	-	86	5.0	-	60	-
PPW 315-04 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-05 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-05 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-06 1A	-	-	-	Waste Rock	9.8	0.1	-	-	-	683	-	-	-	0.29	-	-	-	71	5.0	-	52	-
PPW 315-06 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-10-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-10-2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-11-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-11-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-13-1A	-	-	-	Waste Rock	9.2	0.2	-	-	-	722	-	-	-	0.30	-	-	-	76	5.0	-	62	-
PPW 315-13-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-14-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-14-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-16-1A	-	-	-	Waste Rock	9.2	0.1	-	-	-	804	-	-	-	0.33	-	-	-	91	5.0	-	68	-
PPW 315-16-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-17-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 317-17-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-18-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-18-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-19-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-19-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-20-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-20-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-22-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-22-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-23-1A	-	-	-	Waste Rock	9.0	0.1	-	-	-	488	-	-	-	0.12	-	-	-	21	5.0	-	34	-
PPW 315-23-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-24-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-24-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-25-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-25-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-28-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315-28-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-26-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-26-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-27-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-27-2A	-	-	-	Waste Rock	9.3	0.4	-	-	-	734	-	-	-	0.29	-	-	-	74	10	-	74	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-																
					General Rock Type	Paste pH	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40
		From	To	unit		Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U (ICP)	U (XRF)	V	W	Y	Zn
Waste Rock (continued)																					
Panda (continued)																					
PWP- 315-28-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-28-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-31-1A	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-31-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-31-2A	-	-	-	Waste Rock	8.4	0.1	-	-	-	55	-	-	-	0.14	-	-	-	70	5.0	-	56
PWP- 315-31-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-33-1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-33-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-34-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-34-2A	-	-	-	Waste Rock	9.1	0.2	-	-	-	941	-	-	-	0.33	-	-	-	85	10	-	78
PWP- 315-35-1A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-35-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-36-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-36-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-42-1A	-	-	-	Waste Rock	9.4	0.1	-	-	-	939	-	-	-	0.35	-	-	-	89	10	-	80
PWP- 315-42-2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-43-1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-43-2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-44-1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-44-2A	-	-	-	Waste Rock	9.7	0.1	-	-	-	782	-	-	-	0.28	-	-	-	76	5.0	-	74
PWP- 315-45-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-45-2A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-46-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-46-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315 48 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 315 48 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 315-76-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-22-1A	-	-	-	Waste Rock	8.8	0.2	-	-	-	863	-	-	-	0.35	-	-	-	91	10	-	82
PWP- 300-22-2A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-24-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-24-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-35-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-35-2A	-	-	-	Waste Rock	9.4	0.1	-	-	-	855	-	-	-	0.34	-	-	-	87	10	-	80
PWP- 300-36-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-36-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-38-1A	-	-	-	Waste Rock	9.8	0.1	-	-	-	855	-	-	-	0.34	-	-	-	90	5.0	-	84
PWP- 300-38-2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-42-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Panda (continued)																						
PWP- 300-42-2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PWP- 300-48-1A	-	-	-	Waste Rock	9.7	0.1	-	-	-	849	-	-	-	0.32	-	-	-	81	10	-	76	-
PWP- 300-48-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 50 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 50 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 53 1A	-	-	-	Waste Rock	8.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 53 1A	-	-	-	Waste Rock	9.6	10	-	-	-	798	-	-	-	0.33	-	-	-	85	5.0	-	78	-
PPW 300 53 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 53 2A	-	-	-	Waste Rock	9.7	2.5	-	-	-	797	-	-	-	0.33	-	-	-	80	5.0	-	74	-
PPW 300 54 1A	-	-	-	Waste Rock	9.7	5.0	-	-	-	750	-	-	-	0.32	-	-	-	86	5.0	-	74	-
PPW 300 54 2A	-	-	-	Waste Rock	9.3	2.5	-	-	-	644	-	-	-	0.27	-	-	-	83	5.0	-	66	-
PPW 300 55 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 55 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 57 1A	-	-	-	Waste Rock	9.5	2.5	-	-	-	743	-	-	-	0.31	-	-	-	88	5.0	-	70	-
PPW 300 57 2A	-	-	-	Waste Rock	9.7	5.0	-	-	-	683	-	-	-	0.28	-	-	-	80	5.0	-	64	-
PPW 300 61 1A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 61 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 63 1A	-	-	-	Waste Rock	9.7	2.5	-	-	-	641	-	-	-	0.32	-	-	-	92	5.0	-	70	-
PPW 300 63 2A	-	-	-	Waste Rock	9.6	10	-	-	-	675	-	-	-	0.27	-	-	-	86	5.0	-	64	-
PPW 300 65 1A	-	-	-	Waste Rock	9.8	5.0	-	-	-	634	-	-	-	0.29	-	-	-	82	5.0	-	72	-
PPW 300 65 2A	-	-	-	Waste Rock	9.8	2.5	-	-	-	613	-	-	-	0.25	-	-	-	79	5.0	-	64	-
PPW 300 66 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 66 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 68 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 68 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 300 69 1A	-	-	-	Waste Rock	8.6	5.0	-	-	-	585	-	-	-	0.25	-	-	-	76	5.0	-	66	-
PPW 300 69 2A	-	-	-	Waste Rock	9.9	2.5	-	-	-	653	-	-	-	0.27	-	-	-	76	5.0	-	68	-
PPW- 300-71-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-71-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-72-1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-72-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-73-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-73-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-75-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 300-75-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 02 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 02 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 03 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Panda (continued)																						
PPW 285 03 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 04 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 04 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 05 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 05 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 06 1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 06 2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 10 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 10 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 23 1	-	-	-	Waste Rock	8.9	2.5	-	-	-	532	-	-	-	0.21	-	-	-	51	5.0	-	52	-
PPW 285 23 1A	-	-	-	Waste Rock	9.3	2.5	-	-	-	522	-	-	-	0.18	-	-	-	41	5.0	-	44	-
PPW 285 27 1	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 27 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 28 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 28 1B	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 30 1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 30 1B	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 32 1	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 32 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 33 1	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 285 33 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-07-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-07-1A	-	-	-	Waste Rock	9.4	2.5	-	-	-	667	-	-	-	0.30	-	-	-	80	10	-	64	-
PPW- 285-07-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-07-2A	-	-	-	Waste Rock	9.2	2.5	-	-	-	729	-	-	-	0.28	-	-	-	74	10	-	60	-
PPW- 285-08-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-08-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-10-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-10-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-12-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-12-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-15-1A	-	-	-	Waste Rock	9.1	2.5	-	-	-	635	-	-	-	0.33	-	-	-	82	10	-	68	-
PPW- 285-15-2A	-	-	-	Waste Rock	9.2	2.5	-	-	-	636	-	-	-	0.29	-	-	-	75	10	-	64	-
PPW- 285-16-1A	-	-	-	Waste Rock	9.3	2.5	-	-	-	521	-	-	-	0.27	-	-	-	79	10	-	54	-
PPW- 285-16-2A	-	-	-	Waste Rock	9.4	2.5	-	-	-	574	-	-	-	0.34	-	-	-	101	10	-	66	-
PPW- 285-19-1A	-	-	-	Waste Rock	9.3	2.5	-	-	-	683	-	-	-	0.30	-	-	-	86	5.0	-	68	-
PPW- 285-19-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 285-24-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Panda (continued)																						
PPW- 285-24-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 270-02-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW- 270-02-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 03 1	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 03 1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 04 1	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 04 1A	-	-	-	Waste Rock	8.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 05 1	-	-	-	Waste Rock	9.3	2.5	-	-	-	684	-	-	-	0.29	-	-	-	71	5.0	-	58	-
PPW 270 05 1A	-	-	-	Waste Rock	9.4	2.5	-	-	-	710	-	-	-	0.33	-	-	-	84	5.0	-	68	-
PPW 270 07 1	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 07 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 10 1	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 10 1A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 13 1	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 13 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 14 1	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW 270 14 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PG-270-27 1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PG-270-27 2A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-07-1A	-	-	-	Waste Rock	9.4	2.5	-	-	-	756	-	-	-	0.28	-	-	-	78	5.0	-	60	-
PPW-270-07-2A	-	-	-	Waste Rock	9.4	5.0	-	-	-	739	-	-	-	0.27	-	-	-	68	5.0	-	56	-
PPW-270-16-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-16-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-17-1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-17-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-18-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-18-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-21-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-21-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-22-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-22-2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-24-1A	-	-	-	Waste Rock	9.6	2.5	-	-	-	667	-	-	-	0.28	-	-	-	73	5.0	-	62	-
PPW-270-24-2A	-	-	-	Waste Rock	9.3	2.5	-	-	-	617	-	-	-	0.26	-	-	-	64	5.0	-	56	-
PPW-270-25-1A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-25-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-270-29 1A	-	-	-	Waste Rock	9.8	5.0	-	-	-	486	-	-	-	0.16	-	-	-	34	5.0	-	44	-
PPW-270-29 2A	-	-	-	Waste Rock	9.5	2.5	-	-	-	680	-	-	-	0.31	-	-	-	79	5.0	-	66	-
PG-255-11 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Panda (continued)																						
PG-255-11 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-03-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-03-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-04-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-04-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-05-1A	-	-	-	Waste Rock	9.4	2.5	-	-	-	578	-	-	-	0.22	-	-	-	59	5.0	-	54	-
PPW-255-05-2A	-	-	-	Waste Rock	9.5	2.5	-	-	-	601	-	-	-	0.27	-	-	-	74	5.0	-	60	-
PPW-255-07 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-07 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-08-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-08-2A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-13 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-13 2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-15 1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-15 2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-17 1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-17 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-19 1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-19 2A	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-21 1A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-21 2A	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-24-1A	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-24-2A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-26-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-26-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-27-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-27-2A	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-29-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-29-2A	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-32-1A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-32-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-33-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-255-33-2A	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-02-240-28-1a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-02-240-28-2a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-02-1A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-02-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-03-1A	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Panda (continued)																						
PPW-240-03-2A	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-15-1A	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-15-2A	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-31-1a	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-31-2a	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-32-1a	-	-	-	Waste Rock	9.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-32-2a	-	-	-	Waste Rock	10.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-38-1a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-38-2a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-39-1a	-	-	-	Waste Rock	9.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-240-39-2a	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PP-225-09-1A	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PP-225-14-1A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PP-225-14-2A	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PPW-225-07-1a	-	-	-	Waste Rock	9.4	2.5	-	-	-	745	-	-	-	0.29	-	-	-	70	5.0	-	72	-
PPW-225-07-2a	-	-	-	Waste Rock	9.6	2.5	-	-	-	703	-	-	-	0.25	-	-	-	63	5.0	-	88	-
SRK-ROAD-18B	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
SRK-PPWR-18B	-	-	-	Waste Rock	9.0	5.0	-	-	-	756	-	-	-	0.30	-	-	-	78	5.0	-	64	-
			Median		9.5	0.3	-	-	-	714	-	-	-	0.30	-	-	-	80	5.0	-	64	-
			Minimum		8.4	0.1	-	-	-	55	-	-	-	0.12	-	-	-	21	5.0	-	34	-
			Maximum		12.1	10	-	-	-	941	-	-	-	0.36	-	-	-	101	10	-	88	-
			Count		391	70	0	0	0	70	0	0	0	70	0	0	0	70	70	0	70	0
Waste Rock Dump																						
BH-00-01 0-2	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 2-4	-	-	-	Waste Rock	8.9	0.2	-	-	-	712	-	-	-	0.28	-	-	-	76	5.0	-	66	-
BH-00-01 4-6	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 6-8	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 8-10	-	-	-	Waste Rock	8.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 10-12	-	-	-	Waste Rock	9.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 12-14	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 14-16	-	-	-	Waste Rock	9.4	2.0	-	-	-	669	-	-	-	0.26	-	-	-	63	5.0	-	82	-
BH-00-01 16-18	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-01 18-19	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 0-2	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 2-4	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 4-6	-	-	-	Waste Rock	9.0	0.2	-	-	-	790	-	-	-	0.30	-	-	-	78	5.0	-	66	-
BH-00-02 6-8	-	-	-	Waste Rock	9.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 8-10	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Waste Rock Dump (continued)																						
BH-00-02 10-12	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 12-14	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 14-16	-	-	-	Waste Rock	9.6	0.6	-	-	-	768	-	-	-	0.35	-	-	-	89	5.0	-	82	-
BH-00-02 16-18	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02 18-19	-	-	-	Waste Rock	7.9	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 0-2	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 2-4	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 4-6	-	-	-	Waste Rock	8.3	0.2	-	-	-	719	-	-	-	0.29	-	-	-	80	5.0	-	72	-
BH-00-02A 6-8	-	-	-	Waste Rock	8.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 8-10	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 10-12	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 12-14	-	-	-	Waste Rock	7.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 16-18	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-02A 18-19	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03 0-2	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03 2-4	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03 4-6	-	-	-	Waste Rock	9.5	0.1	-	-	-	774	-	-	-	0.32	-	-	-	82	5.0	-	68	-
BH-00-03 6-8	-	-	-	Waste Rock	7.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03A 0-2	-	-	-	Waste Rock	8.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03A 2-4	-	-	-	Waste Rock	7.7	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03A 4-6	-	-	-	Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-03A 6-8	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 0-2	-	-	-	Waste Rock	9.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 2-4	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 4-6	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 6-8	-	-	-	Waste Rock	9.2	1.4	-	-	-	773	-	-	-	0.31	-	-	-	81	5.0	-	72	-
BH-00-06 8-10	-	-	-	Waste Rock	9.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 10-12	-	-	-	Waste Rock	9.4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 12-14	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 14-16	-	-	-	Waste Rock	8.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 16-18	-	-	-	Waste Rock	8.9	0.1	-	-	-	777	-	-	-	0.30	-	-	-	77	5.0	-	64	-
BH-00-06 18-20	-	-	-	Waste Rock	8.6	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 20-22	-	-	-	Waste Rock	9.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 22-24	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
BH-00-06 24-26	-	-	-	Waste Rock	9.6	0.6	-	-	-	733	-	-	-	0.33	-	-	-	87	5.0	-	82	-
BH-00-06 26-28	-	-	-	Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

**Table C-1 Metal Contents of Solid Samples
Part C**

Sample No.	Drill Hole No.	Sample Interval		Price Crustal Abundances	-	0.2	22	0.05	2.3	100	-	-	1.2	5.65	2.3	3	3	120	1.25	40	70	-
					Paste pH	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	TI	U (ICP)	U (XRF)	V	W	Y	Zn	Zr
		From	To	General Rock Type	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Waste Rock (continued)																						
Waste Rock Dump (continued)																						
				Waste Rock	9.3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
				Waste Rock	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
				Median	9.2	0.2	-	-	-	768	-	-	-	0.30	-	-	-	80	5.0	-	72	-
				Minimum	7.4	0.1	-	-	-	669	-	-	-	0.26	-	-	-	63	5.0	-	64	-
				Maximum	9.7	2.0	-	-	-	790	-	-	-	0.35	-	-	-	89	5.0	-	82	-
				Count	53	9	0	0	0	9	0	0	0	9	0	0	0	9	9	0	9	0

Note:
a) Typical crustal abundance for continental rocks taken from Price WL. 1997. Draft Guidelines and Recommended Methods for the Prediction of Metal Leaching and Acid Rock Drainage at Mine sites in British Columbia. British Columbia Ministry of Employment and Investment, Energy and Minerals Division: Victoria, BC, Canada.

- >1 x = Concentration greater than typical crustal abundance.
- >5 x = Concentration greater than 5 x the typical crustal abundance.
- >10 x = Concentration greater than 10 x the typical crustal abundance.
- 0.1 = Below detection limit, given half detection limit value
- 15.01 = Above upper detection, given value of detection limit +0.01

No. = number; - = not available; % = percent; pH = potential of hydrogen, provides measure of the acidity or alkalinity of a solution on a scale of 0 to 14; ppm = parts per million; > = greater than.

Table C-2 Whole Rock Analysis of Solid Samples

Sample No.	Drill Hole No.	Sample Interval		General Rock Type	Paste pH	Al ₂ O ₃	Ba	CaO	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	Nb	P ₂ O ₅	SiO ₂	Sr	TiO ₂	Y	Zn	Zr	LOI
		From	To		unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	ppm	%
Diabase																							
<i>Jay</i>																							
2014-DD-040	JGT-03	349.4	356.81	Diabase	9.10	13.5	0.01	9.9	0.03	15.1	0.6	6.35	0.23	2.28	0.003	0.09	50.7	0.013	1.37	0.003	112	0.009	1.1
2014-DD-043	JGT-03	47.22	57.11	Diabase	9.05	13.2	0.013	7.99	0.03	12.4	0.85	5.29	0.19	3.21	0.003	0.15	52.1	0.016	1.09	0.002	96	0.008	1.22
2014-DD-044	JGT-03	57.95	65.48	Diabase	9.05	13.3	0.011	9.79	0.02	15.3	0.86	6.34	0.23	2.4	0.003	0.09	50.6	0.015	1.37	0.002	102	0.009	1.01
2014-DD-049	JGT-02	413.02	421.45	Diabase	9.02	13.3	0.009	9.51	0.03	15.1	0.66	5.73	0.23	2.4	0.003	0.13	50	0.014	1.37	0.002	104	0.009	0.82
Median					9.1	13.3	0.011	9.7	0.03	15.1	0.755	6.035	0.23	2.4	0.003	0.11	51	0.01	1.37	0	103	0.009	1.1
Minimum					9.0	13.2	0.009	8.0	0.02	12.4	0.6	5.29	0.19	2.3	0.003	0.09	50	0.01	1.09	0	96	0.008	0.82
Maximum					9.1	13.5	0.013	9.9	0.03	15.3	0.86	6.35	0.23	3.2	0.003	0.15	52	0.02	1.37	0	112	0.009	1.2
Count					4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Granite																							
<i>Jay</i>																							
2014-DD-003	JGT-04	53	57.25	Granite	8.59	14.8	0.012	0.4	0.04	0.89	4.12	0.44	0.01	2.8	0.001	0.16	79.3	0.002	0.07	0.001	9	0.001	1.26
2014-DD-004	JGT-04	61	71	Granite	8.08	19.2	0.056	0.38	0.04	7.61	4.99	3.67	0.04	0.6	0.002	0.08	58.9	0.004	0.73	0.002	96	0.014	4.76
2014-DD-021	JGT-04	275	285	Granite	9.45	14.9	0.042	0.63	0.04	1.25	5.32	0.35	0.02	3.54	0.001	0.36	73.4	0.009	0.12	0.001	53	0.007	0.54
2014-DD-023	JGT-05	16.44	20.77	Granite	8.49	14.6	0.028	0.53	0.04	1.45	4.72	0.45	0.01	3.4	0.001	0.17	73.3	0.008	0.14	0.001	26	0.003	0.98
2014-DD-024	JGT-05	35.74	44.77	Granite	9.21	15.4	0.041	0.74	0.04	1.76	5.08	0.62	0.02	3.62	0.001	0.31	73.7	0.011	0.19	0.001	49	0.007	0.72
2014-DD-025	JGT-05	71.79	79.86	Granite	9.32	14.6	0.037	0.69	0.04	1.13	4.92	0.32	0.01	3.61	0.001	0.26	72.9	0.009	0.13	0.001	44	0.005	0.59
2014-DD-026	JGT-05	101.77	110.98	Granite	9.30	14.3	0.036	0.61	0.04	1.02	5.21	0.29	0.01	3.43	0.001	0.29	71.1	0.009	0.11	0.001	38	0.005	0.64
2014-DD-027	JGT-05	131	139.1	Granite	9.47	14.2	0.038	0.69	0.04	1.25	4.96	0.35	0.01	3.48	0.001	0.28	71.6	0.008	0.14	0.001	44	0.007	0.57
2014-DD-028	JGT-05	161.34	172.88	Granite	9.49	14.3	0.043	0.77	0.04	1.39	5.15	0.36	0.01	3.29	0.001	0.27	70.7	0.007	0.15	0.001	45	0.008	0.54
2014-DD-029	JGT-05	198.88	206.77	Granite	9.46	14.5	0.038	0.67	0.04	1.11	5.19	0.32	0.01	3.56	0.001	0.16	73.2	0.01	0.13	0.001	37	0.005	0.4
2014-DD-030	JGT-05	233.04	241.73	Granite	9.54	14.1	0.039	0.78	0.04	1.19	4.55	0.34	0.01	3.7	0.001	0.17	71.9	0.009	0.14	0.001	43	0.007	0.46
2014-DD-031	JGT-05	259.49	268.27	Granite	9.51	14.4	0.045	0.79	0.04	1.28	4.81	0.37	0.01	3.44	0.001	0.24	70.5	0.01	0.16	0.001	45	0.008	0.46
2014-DD-032	JGT-05	276.96	281.55	Granite	9.50	17.7	0.043	3.27	0.03	3.2	2.53	1.53	0.04	4.25	0.001	0.25	66.4	0.056	0.32	0.001	90	0.01	0.77
2014-DD-038	JGT-03	433.32	441.89	Granite	9.23	14.6	0.043	0.77	0.03	1.19	4.7	0.4	0.01	3.6	0.001	0.27	74.9	0.012	0.14	0.001	40	0.007	0.66
2014-DD-039	JGT-03	404.73	413.48	Granite	9.08	14.5	0.044	0.71	0.04	1.11	4.7	0.41	0.01	3.87	0.001	0.28	72.1	0.011	0.12	0.001	26	0.006	0.74
2014-DD-041	JGT-03	290.1	298.57	Granite	9.17	14.5	0.044	1.33	0.03	2.2	4.77	0.81	0.03	3.51	0.001	0.29	72.1	0.011	0.22	0.001	48	0.007	0.73
2014-DD-045	JGT-03	89.48	98.08	Granite	9.14	14.9	0.038	0.72	0.03	1.22	4.93	0.38	0.01	3.82	0.001	0.32	75.9	0.01	0.12	0.001	26	0.006	0.73
2014-DD-046	JGT-03	239.48	248.11	Granite	9.19	15	0.041	0.68	0.04	1.25	4.89	0.42	0.01	3.7	0.001	0.32	73.6	0.008	0.14	0.001	29	0.007	0.79
2014-DD-047	JGT-03	205.53	214.19	Granite	9.28	14.6	0.038	0.65	0.04	1.26	5.07	0.39	0.01	3.58	0.001	0.29	73.9	0.01	0.14	0.001	47	0.007	0.69
2014-DD-048	JGT-03	154.51	163.19	Granite	9.36	15.2	0.045	0.74	0.03	1.22	4.75	0.4	0.01	4.06	0.001	0.29	73.8	0.01	0.14	0.001	47	0.007	0.66
2014-DD-050	JGT-02	279	287	Granite	9.20	14.4	0.043	0.81	0.03	1.32	4.91	0.4	0.01	3.53	0.001	0.28	72.4	0.009	0.17	0.001	50	0.008	0.58
2014-DD-051	JGT-02	200	207.55	Granite	8.76	13.8	0.042	0.59	0.04	1.46	4.63	0.47	0.01	3.47	0.001	0.27	73.6	0.009	0.16	0.001	26	0.007	0.76
2014-DD-052	JGT-02	125.42	134.04	Granite	8.54	14.4	0.047	0.69	0.04	1.83	5.67	0.53	0.02	2.91	0.001	0.27	72.6	0.011	0.21	0.001	50	0.009	0.87
2014-DD-053	JGT-02	64.04	74	Granite	8.60	14.3	0.048	0.74	0.04	1.41	5.24	0.38	0.01	3.4	0.001	0.29	72.6	0.011	0.15	0.001	49	0.007	0.71
2014-DD-055	JGT-02	60.16	65.55	Granite	8.44	14.3	0.05	0.69	0.04	1.41	5.2	0.36	0.01	3.22	0.001	0.25	73	0.009	0.14	0.001	42	0.007	0.9
2014-DD-056	JGT-02	29.89	38.2	Granite	9.07	14.5	0.05	0.75	0.03	1.31	5.08	0.35	0.01	3.41	0.001	0.24	71.8	0.011	0.15	0.001	37	0.007	0.58
2014-DD-057	JGT-02	451.14	459.98	Granite	9.50	15	0.044	0.76	0.04	1.49	5.41	0.43	0.02	3.57	0.001	0.35	73.6	0.009	0.18	0.001	59	0.01	0.43

Table C-2 Whole Rock Analysis of Solid Samples

Sample No.	Drill Hole No.	Sample Interval		General Rock Type	Paste pH	Al ₂ O ₃	Ba	CaO	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	Nb	P ₂ O ₅	SiO ₂	Sr	TiO ₂	Y	Zn	Zr	LOI
		From	To		unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	ppm	%
Granite (continued)																							
<i>Jay (continued)</i>																							
2014-DD-058	JGT-02	244.19	252.39	Granite	9.55	14.9	0.033	0.82	0.04	0.96	4.74	0.26	0.01	3.96	0.001	0.21	74.1	0.011	0.1	0.001	31	0.005	0.58
2014-DD-059	JGT-02	377.69	383.33	Granite	9.50	14.6	0.032	0.78	0.03	1.11	4.9	0.31	0.01	3.76	0.001	0.23	74	0.007	0.12	0.001	35	0.005	0.53
2014-DD-060	JGT-02	307	313.09	Granite	9.48	14.1	0.044	0.69	0.03	1.76	5.69	0.55	0.01	3.08	0.001	0.25	69.3	0.008	0.24	0.001	60	0.01	0.54
Median					9.3	14.6	0.04	0.72	0.04	1.3	4.9	0.40	0.01	3.5	0.001	0.27	73	0.009	0.14	0.001	44	0.007	0.66
Minimum					8.1	13.8	0.01	0.38	0.03	0.89	2.5	0.26	0.01	0.60	0.001	0.08	59	0.002	0.07	0.001	9.0	0.001	0.40
Maximum					9.6	19.2	0.06	3.3	0.04	7.6	5.7	3.7	0.04	4.3	0.002	0.36	79	0.06	0.73	0.002	96	0.01	4.8
Count					30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30
Kimberlite																							
<i>Jay</i>																							
2014-DD-042	JGT-03	40.8	47.22	Kimberlite	7.72	6.24	0.072	5.04	0.14	5.73	1.18	20	0.1	0.11	0.008	0.22	41.1	0.035	0.35	0.001	124	0.008	18.5
2014-DD-054	JGT-02	63.4	64.04	Kimberlite	7.81	1.96	0.018	0.38	0.2	7.93	0.61	1.39	0.03	0.07	0.008	0.09	78.7	0.001	0.21	0.001	93	0.003	6.78
Median					7.8	4.1	0.05	2.7	0.17	6.8	0.90	11	0.07	0.09	0.008	0.16	60	0.02	0.28	0.001	109	0.006	13
Minimum					7.7	2.0	0.02	0.38	0.14	5.7	0.61	1.4	0.03	0.07	0.008	0.09	41	0.001	0.21	0.001	93	0.003	6.8
Maximum					7.8	6.2	0.07	5.0	0.20	7.9	1.2	20	0.10	0.11	0.008	0.22	79	0.04	0.35	0.001	124	0.008	19
Count					2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2
Metasediment																							
<i>Jay</i>																							
2014-DD-001	JGT-04	35.58	41.58	Metasediment	8.30	18	0.073	0.63	0.04	6.55	4.53	3.87	0.05	1.29	0.002	0.11	62.6	0.01	0.67	0.001	70	0.014	3.91
2014-DD-002	JGT-04	41.58	48.98	Metasediment	7.94	18.4	0.062	0.4	0.04	6.73	5.11	3.56	0.05	0.7	0.002	0.13	58.9	0.006	0.68	0.002	70	0.013	4.35
2014-DD-005	JGT-04	74.58	83.58	Metasediment	9.05	15	0.038	0.4	0.04	0.58	6	0.19	0.01	3.35	0.001	0.25	74.3	0.009	0.04	0.001	9	0.001	0.54
2014-DD-006	JGT-04	86.17	95.58	Metasediment	8.29	19.4	0.052	0.72	0.05	7.35	3.92	3.78	0.05	1.52	0.002	0.1	56.8	0.009	0.71	0.002	80	0.012	3.89
2014-DD-007	JGT-04	100	107.7	Metasediment	8.58	20.7	0.073	2.49	0.05	6.79	2.9	3.81	0.05	2.48	0.002	0.57	58	0.045	0.52	0.001	82	0.011	2.35
2014-DD-008	JGT-04	114.12	122.54	Metasediment	8.26	18	0.047	0.48	0.05	7.2	4.44	4.22	0.05	1.17	0.002	0.12	59.7	0.007	0.71	0.002	81	0.013	4.22
2014-DD-009	JGT-04	125.58	135.9	Metasediment	8.69	16.4	0.031	1.37	0.05	5.99	2.98	3.34	0.07	2.16	0.002	0.14	58.8	0.013	0.45	0.001	70	0.012	3.02
2014-DD-010	JGT-04	142.21	147.1	Metasediment	8.24	19.5	0.054	0.38	0.04	7.13	4.78	4.19	0.06	0.55	0.002	0.1	55.8	0.002	0.69	0.002	78	0.011	4.79
2014-DD-011	JGT-04	147.1	152.58	Metasediment	8.01	20.5	0.062	0.22	0.04	7.09	4.62	3.87	0.05	0.5	0.002	0.06	53.6	0.002	0.72	0.002	78	0.011	5.36
2014-DD-012	JGT-04	155.58	163.58	Metasediment	8.14	20	0.059	0.31	0.04	7.22	4.52	3.82	0.05	0.61	0.002	0.07	53.2	0.004	0.73	0.002	81	0.013	5.12
2014-DD-013	JGT-04	163.38	171.69	Metasediment	8.48	18.5	0.057	1.51	0.04	6.22	3.86	3.85	0.05	1.65	0.002	0.14	57.4	0.027	0.51	0.001	76	0.012	3.59
2014-DD-014	JGT-04	174.5	180	Metasediment	8.88	18.1	0.058	3.12	0.03	4.77	3.14	2.96	0.06	3.06	0.001	0.12	59.1	0.039	0.44	0.001	83	0.011	2.12
2014-DD-015	JGT-04	188	196.2	Metasediment	8.38	20.4	0.057	0.97	0.03	7.9	4.39	3.88	0.06	0.76	0.002	0.11	55.3	0.011	0.73	0.002	81	0.013	4.96
2014-DD-016	JGT-04	199	206.58	Metasediment	8.17	20.7	0.057	0.28	0.04	7.36	4.76	3.91	0.05	0.61	0.002	0.08	58.4	0.005	0.76	0.002	74	0.013	5.1
2014-DD-017	JGT-04	221	230	Metasediment	8.57	17.7	0.052	0.66	0.05	6.11	3.88	3.33	0.05	1.61	0.002	0.14	65	0.01	0.68	0.002	125	0.016	3.2
2014-DD-018	JGT-04	231.28	241	Metasediment	8.64	17	0.065	0.8	0.05	5.32	3.91	2.91	0.06	2.23	0.002	0.14	64	0.015	0.6	0.001	182	0.013	2.38
2014-DD-019	JGT-04	241	251	Metasediment	9.10	16.9	0.053	1.13	0.05	5.08	3.72	2.68	0.06	2.78	0.002	0.16	65.5	0.018	0.47	0.001	99	0.013	1.98
2014-DD-020	JGT-04	251	260	Metasediment	9.51	17.3	0.024	1.35	0.04	3.84	3.82	1.84	0.08	4.09	0.001	0.15	65.7	0.016	0.38	0.001	54	0.009	1.88
2014-DD-022	JGT-05	15.2	16.44	Metasediment	8.99	14.2	0.018	1.03	0.05	6.21	2.86	1.82	0.04	3.6	0.002	0.08	64.8	0.008	0.44	0.001	115	0.008	0.95
2014-DD-033	JGT-05	281.55	287.77	Metasediment	9.12	19.5	0.057	1.38	0.05	6.51	3.21	3.23	0.07	2.93	0.002	0.15	58	0.028	0.73	0.002	109	0.013	1.62

Table C-2 Whole Rock Analysis of Solid Samples

Sample No.	Drill Hole No.	Sample Interval		General Rock Type	Paste pH	Al ₂ O ₃	Ba	CaO	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	Nb	P ₂ O ₅	SiO ₂	Sr	TiO ₂	Y	Zn	Zr	LOI
		From	To		unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	ppm	%
Metasediment (continued)																							
Jay (continued)																							
2014-DD-034	JGT-05	287.77	292.77	Metasediment	9.48	17.2	0.018	1.12	0.05	5.6	2.94	2.82	0.05	3.02	0.002	0.12	61.1	0.015	0.62	0.001	135	0.014	0.99
2014-DD-035	JGT-05	299.18	308.77	Metasediment	9.13	20.8	0.049	1.61	0.04	6.98	3.42	3.49	0.07	2.62	0.002	0.12	59.9	0.029	0.78	0.002	152	0.017	1.8
2014-DD-036	JGT-05	308.77	317	Metasediment	9.29	16.9	0.027	1.25	0.05	5.42	3.33	2.43	0.05	2.93	0.002	0.25	64.8	0.012	0.47	0.001	154	0.013	1.27
2014-DD-037	JGT-05	336	346	Metasediment	9.87	14.1	0.029	1.63	0.05	4.78	2.38	2.43	0.06	3.76	0.002	0.09	68.8	0.028	0.51	0.001	86	0.018	0.56
Median					8.6	18	0.05	1.0	0.05	6.4	3.9	3.4	0.05	2.2	0.002	0.12	59	0.01	0.65	0.001	81	0.013	2.7
Minimum					7.9	14	0.02	0.22	0.03	0.58	2.4	0.19	0.01	0.50	0.001	0.06	53	0.002	0.04	0.001	9.0	0.001	0.54
Maximum					9.9	21	0.07	3.1	0.05	7.9	6.0	4.2	0.08	4.1	0.002	0.57	74	0.05	0.78	0.002	182	0.018	5.4
Count					24	24	24	24	24	24	24	24	24	24	24	24	24	24	24	24	24	24	24

Note:

0.1 = Below detection limit, given half detection limit value

No. = number; % = percent; pH = potential of hydrogen, provides measure of the acidity or alkalinity of a solution on a scale of 0 to 14; LOI = loss on ignition; ppm = parts per million.